



Designation: D2257 – 20

Standard Test Method for Extractable Matter in Textiles¹

This standard is issued under the fixed designation D2257; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope

1.1 This test method covers a procedure for determining the extractable material on most fibers, yarns, and fabrics. Three options are included. Option 1 uses heat and Soxhlet extraction apparatus. Option 2 uses room temperature and extraction funnels. Option 3 uses either Option 1 or Option 2 extraction but provides for calculation of extractable matter from the loss in mass of the material due to the extraction rather than the extractable matter residue.

NOTE 1—Other standards for the determination of extractable matter in textiles made of specific fibers include: Specification D541, Specification D681, and Test Method D1574.

1.1.1 The solvents for use in this method are any solvents that the party or parties concerned agreed on; such as, Halogenated Hydrocarbon (HH) chloroform, tetrachloroethane, alcohol (isopropyl or methyl).

1.1.2 This test method may not extract cross-linked finishes or resins which may be on the textile.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.* See Sections 6 and 7.

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

¹ This test method is under the jurisdiction of ASTM Committee D13 on Textiles and is the direct responsibility of Subcommittee D13.51 on Conditioning, Chemical and Thermal Properties.

Current edition approved July 1, 2020. Published August 2020. Originally approved in 1989. Last previous edition approved in 2012 as D2257 – 98(2012). DOI: 10.1520/D2257-20.

2. Referenced Documents

2.1 ASTM Standards:²

- D123 Terminology Relating to Textiles
- D541 Specification for Single Jute Yarn (Withdrawn 1996)³
- D681 Specification for Jute Rove and Plyed Yarn for Electrical and Packing Purposes (Withdrawn 2000)³
- D1574 Test Method for Extractable Matter in Wool and Other Animal Fibers
- D1909 Standard Tables of Commercial Moisture Regains and Commercial Allowances for Textile Fibers
- D2258 Practice for Sampling Yarn for Testing
- D3333 Practice for Sampling Manufactured Staple Fibers, Sliver, or Tow for Testing
- D4920 Terminology Relating to Conditioning, Chemical, and Thermal Properties

2.2 Other Documents:

- IWTO 10-62(E) Method for Determination of the Dichloromethane Soluble Matter in Combed Wool Sliver⁴

3. Terminology

3.1 Definitions:

3.1.1 *extractable matter, n*—nonfibrous material in or on a textile not including water, which is removable by a specified solvent or solvents as directed in a specified procedure.

3.1.1.1 *Discussion*—Nonfibrous material is usually oily, waxy, resinous, or polymeric in nature, but may also include other material, such as protein, particularly if ethyl alcohol is used, or in, the extracting solvent.

3.1.2 For definitions of other moisture terms related to textiles, refer to Terminology D4920. For definitions of other textile terms used in this test method refer to Terminology D123.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.

⁴ Available from International Wool Secretariat, Carlton Gardens, London S.W. 1, England.

4. Summary of Test Method

4.1 The specimen is extracted either in Soxhlet apparatus (Option 1), or extraction funnel (Option 2) first with an agreed solvent (Note 2). The solvents are evaporated and the residues and the specimens are dried and weighed separately. The amounts of extracted matter are reported as percentages of either the oven-dried mass or of the oven-dried mass plus commercial moisture regain for the textile.

4.2 Alternatively, in Option 3, the specimen is dried and weighed before and after extraction using Option 1 or Option 2. Extractable matter is calculated as the loss in mass reported as percentages of the extracted oven-dried mass or this mass plus commercial moisture regain for the textile.

5. Significance and Use

5.1 This test method may be used for acceptance testing of commercial shipments.

5.1.1 In case of a dispute arising from differences in reported test results using this test method for acceptance testing of commercial shipments, the purchaser and the supplier should conduct comparative tests to determine if there is a statistical bias between the laboratories. Competent statistical assistance is recommended for the investigation of bias. As a minimum, the two parties should take a group of test specimens which are as homogeneous as possible and which are from a lot of material of the type in question. The test specimens should then be randomly assigned in equal numbers to each laboratory for testing. The average results from the two laboratories should be compared using appropriate statistical analysis and a probability level chosen by the two parties before the testing begins. If a bias is found, either its cause must be found and corrected, or the purchaser and supplier must agree to interpret future test results with consideration to the known bias.

5.2 This test method is used for the determination of the amounts of naturally present oily or waxy impurities that have not been completely removed from textiles made from animal fibers, and for the determination of the amounts of oily or waxy finishing materials applied to raw materials or textiles during manufacture. See 3.1.1, *extractable matter*.

5.3 The test method may be used as a step in the determination of the commercial weight of fiber, yarn, and textile shipments.

5.4 The International Wool Textile Organization specifies the use of a halogenated hydrocarbon, dichloromethane, also called methylene chloride (CH_2Cl_2) instead of the solvent specified in this test method (IWTO-10-62(E)).

5.5 Extractables by mass loss is frequently used for textiles which have a relatively large amount of extractable material to effect a significant mass change.

6. Apparatus and Reagents

6.1 Extraction Apparatus

6.1.1 Soxhlet Extraction Apparatus for Option 1 extraction

6.1.2 Extraction Funnels, wide-mouth, 125 or 150-mL capacity with 145-175 micron filter for Option 2 extraction.

6.2 *Thimbles*, fat-free cellulose or Alundum, for Option 1.

6.3 *Specimen Compressor*, pestle, glass stirring rod or long forceps, for handling specimens in Option 2.

6.4 Containers,

6.4.1 To hold extractables and that will seal to prevent moisture changes, for example weighing bottles, for Option 1.

6.4.2 To collect solvent from extractions, for Option 2.

6.4.3 Containers used for solvent collection must be dry and clean. Use methanol to clean the containers then air-dry before oven drying at 105°C for at least 10 min.

NOTE 2—If metal containers are used, check to ensure that the extractable matter does not react with the metal if the residue is to be weighed.

6.5 Oven

6.5.1 *Ventilated Forced-Draft Drying Oven*, capable of maintaining a temperature of $105 \pm 3^\circ\text{C}$.

6.5.2 *Vacuum Type*, maintained at $65 \pm 2^\circ\text{C}$ for use in Option 3 when low-boiling ingredients are present.

6.6 *Tray*, to contain desiccant, with a screen to prevent specimen or container contact with desiccant, for use in the vacuum oven. If Phosphorus pentoxide (P_2O_5) or sulfuric acid (H_2SO_4) is used, the screen must be acid resistant.

6.7 Dessicator

6.8 *Analytical Balance*—sensitive to 0.0001 g.

6.9 *Nitrogen*, to supply the vacuum oven.

6.10 *Solvent*—as agreed (see 1.1.1). (**Warning**—Various solvents have been used in the past, and are still used to some extent. Many of these solvents are flammable, toxic or have anesthetic effects, or unpleasant odors. As with all volatile solvents, the use of adequate ventilation under a hood is recommended when using this solvent.)

7. Hazards

7.1 Refer to the manufacturer's material safety data sheets for specific information on chemicals used in this test.

7.2 After extraction with alcohol or other flammable or toxic solvents, the specimens must be air-dried under a hood until nearly all of the solvent has evaporated before they are dried in the oven. Otherwise there is a danger of building up a dangerous concentration of explosive vapor in the oven. Oven doors have been blown across the room by the force of an explosion.

7.3 **Warning**—Dichloromethane is toxic, and its use is recommended only when necessary to conform to international specifications, and then with adequate ventilation under a hood.

8. Sampling

8.1 *Lot Sample*—As a lot sample for acceptance testing, take at random the number of shipping containers directed in an applicable material specification or other agreement between the purchaser and the supplier. Consider shipping containers to be the primary sampling unit.

NOTE 3—An adequate specification or other agreement between the purchaser and the supplier requires taking into account the variability between shipping containers, within a shipping container, and between

specimens taken from a single unit within a shipping container, so as to provide a sampling plan with a meaningful producer's risk, consumer's risk, acceptable quality level, and limiting quality level.

8.2 *Laboratory Sample*—As a laboratory sample for acceptance testing, proceed as follows:

8.2.1 *Yarn on Packages*—Take at random from each shipping container in the lot sample the number of packages directed in an applicable material specification or other agreement between the purchaser and the supplier, such as an agreement to use Practice **D2258**. Preferably, the same number of packages should be taken from each shipping case in the lot sample. If differing numbers of packages are to be taken from shipping cases in the lot sample, determine at random which shipping cases are to have each number of packages drawn.

8.2.2 *Yarn on Beams*—Take a laboratory sample from each of the beams in the lot sample as agreed between the purchaser and the supplier.

8.2.3 *Fabrics*—Take a full width swatch 1 m long from the end of each roll of fabric in the lot sample, after first discarding a minimum of 1 m of fabric from the very outside of the roll.

8.2.4 *Staple Fiber*—Systematically take five laboratory sample units from each bale in the lot sample as directed in Practice **D3333**.

8.2.5 *Tow, Sliver, or Top*—Take from the lead end of a strand from each shipping container in the lot sample the first metre of material that has a clean, uniform appearance. If the shipping containers in the lot sample contain multiple packages, take a laboratory sample from one package drawn at random from each container.

8.3 *Test Specimens*—Take a 10 ± 1 -g specimen from each unit in the laboratory sample. If necessary, take an additional specimen from a random unit in the laboratory sample until there is a total of ten specimens.

9. Conditioning

9.1 Neither preconditioning nor conditioning is necessary.

10. Procedure

10.1 *Presence of boiling ingredients* (extractable volatile at low temperatures).

10.1.1 Use the following procedure to determine the presence of low boiling ingredients, that is, extractables that are volatile at low temperatures.

10.1.2 Extract one or more specimens of the material as directed in **10.2** or **10.3**.

10.1.3 Transfer the solvent quantitatively to a tared weighing bottle and evaporate the solvent by blowing with a stream of air at room temperature until there is a mass change of less than 0.001 g in 10 min.

10.1.4 Heat the residue in an oven at $105 \pm 3^\circ\text{C}$ for 30 min, cool, and weigh.

10.1.5 If there is a mass loss greater than 0.001 g in the residue (extractables) due to heating in the oven, the material contains extractable matter which volatilizes at low temperatures, and the specimen solvent extract should not be heated in the oven.

10.1.6 If there is no detectable loss in residue mass (less than 0.001 g) due to heating in the oven, the material does not

contain low boiling ingredients and the extracted residue is dried in the oven before final weighing.

10.2 *Option 1, Soxhlet Extraction,*

10.2.1 Extract fat-free cellulose or Alundum thimbles for each specimen in the solvents to be used, in the Soxhlet chamber. A suitably folded qualitative grade filter paper may be used in place of the thimble. Thimbles are not needed for fabric yarn or thread specimens.

10.2.2 Weigh 10 ± 1 g of each specimen to the nearest 0.010 g.

10.2.3 Place the specimens in the thimbles, if used, and transfer to the Soxhlet apparatus. Thimbles must be long enough to cover the opening of the siphon tube.

10.2.4 Add sufficient solvent to overflow plus about 25 % more to prevent the solvent from boiling dry.

10.2.5 Adjust the heat for 3 to 5 siphonings per hour and extract the specimens for at least 20 siphonings. Maintain the temperature of the solvent in the Soxhlet apparatus at a level low enough to avoid interference with siphoning and in any event, below 50°C . Be certain that the solvent is going through the thimble or filter paper during the extraction, and not overflowing. In case there is evidence that 20 siphonings are not sufficient, the purchaser and supplier should agree upon a suitable number of siphonings.

10.2.6 Remove from the source of heat when the upper chamber of the apparatus is nearly full and ready to siphon again. Pour off the nearly pure solvent from the extraction tube and save for reuse after suitable distillation.

10.2.7 Determine the mass of a weighing bottle to 0.001 g. Transfer the contents of the flask to the tared weighing bottle, rinse with a small quantity of solvent, and add this to the contents of the weighing bottle.

10.2.8 If low boiling ingredients were found (**10.1.5**) evaporate the solvent as directed in **10.1.3** without oven drying the residue.

10.2.9 If low - boiling ingredients were not found, evaporate the solvent and then dry the residue in an oven at $105 \pm 3^\circ\text{C}$ for 30 min. Cool in a desiccator and weigh. Repeat the drying, cooling, and weighing cycle until the difference in intervals of 30 min results in a mass change of less than 0.001 g.

10.2.10 Record the final mass of the residue to the nearest 0.001 g.

NOTE 4—Solvent in weighing bottles may be recovered for subsequent reuse by connecting the effluent stream of solvent and air to a suitable condenser.

10.2.11 Remove the remaining solvent from the Soxhlet apparatus, reinsert the thimble and specimen, and fill with the proper amount of alcohol. Extract through at least 12 siphonings.

10.2.12 Determine the mass of a weighing bottle to 0.001 g. Transfer the alcohol from the flask to the weighing bottle, evaporate the alcohol, dry, and weigh the residue to the nearest 0.001 g.

10.2.13 Remove the specimen from the apparatus and air dry it. Continue as directed in **10.5**.

10.3 *Option 2, room temperature extraction:*

10.3.1 Place the specimen in an extraction funnel.