



Designation: **A297/A297M—19 A297/A297M – 20**

Standard Specification for Steel Castings, Iron-Chromium and Iron-Chromium-Nickel, Heat Resistant, for General Application¹

This standard is issued under the fixed designation A297/A297M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

1. Scope*

1.1 This specification covers iron-chromium and iron-chromium-nickel alloy castings for heat-resistant service. The grades covered by this specification are general purpose alloys and no attempt has been made to include heat-resisting alloys used for special production application.

NOTE 1—For heat-resisting alloys used for special product application, reference should be made to Specifications [A351/A351M](#), [A217/A217M](#), and [A447/A447M](#).

1.2 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in nonconformance with the standard.

1.3 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

[A217/A217M](#) Specification for Steel Castings, Martensitic Stainless and Alloy, for Pressure-Containing Parts, Suitable for High-Temperature Service

[A351/A351M](#) Specification for Castings, Austenitic, for Pressure-Containing Parts

[A370](#) Test Methods and Definitions for Mechanical Testing of Steel Products

[A447/A447M](#) Specification for Steel Castings, Chromium-Nickel-Iron Alloy (25-12 Class), for High-Temperature Service

[A781/A781M](#) Specification for Castings, Steel and Alloy, Common Requirements, for General Industrial Use

[A957/A957M](#) Specification for Investment Castings, Steel and Alloy, Common Requirements, for General Industrial Use

3. General Conditions for Delivery

3.1 Except for investment castings, material furnished to this specification shall conform to the requirements of Specification [A781/A781M](#), including any supplementary requirements that are indicated in the purchase order. Failure to comply with the general requirements of Specification [A781/A781M](#) constitutes nonconformance with this specification. In case of conflict between the requirements of this specification and Specification [A781/A781M](#), this specification shall prevail.

3.2 Investment castings furnished to this specification shall conform to the requirements of Specification [A957/A957M](#), including any supplementary requirements that are indicated in the purchase order. Failure to comply with the general requirements of Specification [A957/A957M](#) constitutes nonconformance with this specification. In case of conflict between the requirements of this specification and Specification [A957/A957M](#), Specification [A957/A957M](#) shall prevail.

4. Ordering Information

4.1 The inquiry and order should include or indicate the following:

¹ This specification is under the jurisdiction of ASTM Committee [A01](#) on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee [A01.18](#) on Castings.

Current edition approved ~~Sept. 1, 2019~~ July 1, 2020. Published ~~September 2019~~ August 2020. Originally approved in 1946. Last previous edition approved in 2017 ~~2019~~ as ~~A297/A297M—17~~ [A297/A297M – 19](#). DOI: ~~10.1520/A0297_A0297M-19~~ [10.1520/A0297_A0297M-20](#).

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard



TABLE 1 Chemical Composition Requirements^{A,B}

Grade/Grade UNS Number(UNS Number)	Type	Composition, % (max, except where range is given)Element, %									
		Carbon	Manganese	Silicon	Phosphorus	Sulfur	Silicon	Chromium	Nickel	Molybdenum ^{6C}	Other ^{6D}
HF J92603	19-Chromium, 9-Nickel	0.20–0.40	2.00	2.00	0.04	0.04	18.0–23.0	8.0–12.0	0.50		
HF (J92603)	19Cr-9Ni	0.20–0.40	2.00	0.04	0.04	2.00	18.0–23.0	8.0–12.0	0.50	...	
HH J93503	25-Chromium, 12-Nickel	0.20–0.50	2.00	2.00	0.04	0.04	24.0–28.0	11.0–14.0	0.50		
HH (J93503)	25Cr-12Ni	0.20–0.50	2.00	0.04	0.04	2.00	24.0–28.0	11.0–14.0	0.50	...	
HI J94003	28-Chromium, 15-Nickel	0.20–0.50	2.00	2.00	0.04	0.04	26.0–30.0	14.0–18.0	0.50		
HI (J94003)	28Cr-15Ni	0.20–0.50	2.00	0.04	0.04	2.00	26.0–30.0	14.0–18.0	0.50	...	
HK J94224	25-Chromium, 20-Nickel	0.20–0.60	2.00	2.00	0.04	0.04	24.0–28.0	18.0–22.0	0.50		
HK (J94224)	25Cr-20Ni	0.20–0.60	2.00	0.04	0.04	2.00	24.0–28.0	18.0–22.0	0.50	...	
HE J93403	29-Chromium, 9-Nickel	0.20–0.50	2.00	2.00	0.04	0.04	26.0–30.0	8.0–11.0	0.50		
HE (J93403)	29Cr-9Ni	0.20–0.50	2.00	0.04	0.04	2.00	26.0–30.0	8.0–11.0	0.50	...	
HT N08605	15-Chromium, 35-Nickel	0.35–0.75	2.00	2.50	0.04	0.04	15.0–19.0	33.0–37.0	0.50		
HT (N08605)	15Cr-35Ni	0.35–0.75	2.00	0.04	0.04	2.50	15.0–19.0	33.0–37.0	0.50	...	
HU N08004	19-Chromium, 39-Nickel	0.35–0.75	2.00	2.50	0.04	0.04	17.0–21.0	37.0–41.0	0.50		
HU (N08004)	19Cr-39Ni	0.35–0.75	2.00	0.04	0.04	2.50	17.0–21.0	37.0–41.0	0.50	...	
HW N08001	12-Chromium, 60-Nickel	0.35–0.75	2.00	2.50	0.04	0.04	10.0–14.0	58.0–62.0	0.50		
HW (N08001)	12Cr-60Ni	0.35–0.75	2.00	0.04	0.04	2.50	10.0–14.0	58.0–62.0	0.50	...	
HX N06006	17-Chromium, 66-Nickel	0.35–0.75	2.00	2.50	0.04	0.04	15.0–19.0	64.0–68.0	0.50		
HX (N06006)	17Cr-66Ni	0.35–0.75	2.00	0.04	0.04	2.50	15.0–19.0	64.0–68.0	0.50	...	
HC J92605	28-Chromium	0.50 max	1.00	2.00	0.04	0.04	26.0–30.0	4.00	0.50		
HC (J92605)	28Cr	0.50	1.00	0.04	0.04	2.00	26.0–30.0	4.00	0.50	...	
HD J93005	28-Chromium, 5-Nickel	0.50 max	1.50	2.00	0.04	0.04	26.0–30.0	4.0–7.0	0.50		
HD (J93005)	28Cr-5Ni	0.50	1.50	0.04	0.04	2.00	26.0–30.0	4.0–7.0	0.50	...	
HL N08604	29-Chromium, 20-Nickel	0.20–0.60	2.00	2.00	0.04	0.04	28.0–32.0	18.0–22.0	0.50		
HL (N08604)	29Cr-20Ni	0.20–0.60	2.00	0.04	0.04	2.00	28.0–32.0	18.0–22.0	0.50	...	
HN J94213	20-Chromium, 25-Nickel	0.20–0.50	2.00	2.00	0.04	0.04	19.0–23.0	23.0–27.0	0.50		
HN (J94213)	20Cr-25Ni	0.20–0.50	2.00	0.04	0.04	2.00	19.0–23.0	23.0–27.0	0.50	...	
HP15Nb	25-Chromium, 35-Nickel	0.05–0.25	0.50–1.60	0.50–1.50	0.030	0.030	24–27	34–38	0.50	Nb 0.5–1.5	
HP15Nb	25Cr-35Ni	0.05–0.25	0.50–1.60	0.030	0.030	0.50–1.50	24–27	34–38	0.50	Nb 0.5–1.5	
HP N08705	26-Chromium, 35-Nickel	0.35–0.75	2.00	2.50	0.04	0.04	24–28	33–37	0.50		
HP (N08705)	26Cr-35Ni	0.35–0.75	2.00	0.04	0.04	2.50	24–28	33–37	0.50	...	



TABLE 1 Continued

Grade/Grade UNS Number(UNS Number)	Type	Composition, % (max, except where range is given)Element, %									
		Carbon	Manganese	Silicon	Phosphorus	Sulfur	Silicon	Chromium	Nickel	Molybdenum ^{a,c}	Other ^{d,e}
HPNb (N28701)	25Cr-35Ni- 1Nb	0.38–0.045	0.50–1.50	0.03	0.03	0.50–1.50	24–27	34–37	0.50	Nb 0.5–1.5	
HPNbS (N28702)	25Cr-35Ni- 1Nb-2Si	0.38–0.045	0.50–1.50	0.03	0.03	1.50–2.50	24–27	34–37	0.50	Nb 0.5–1.5	
HG10 MNN J92604	19-Chromium, 12-Nickel, 4-Manganese	0.07–0.11	3.0–5.0	0.70	0.040	0.03	18.5–20.5	11.5–13.5	0.25–0.45	Cu 0.50 Nb(Cb) ^d N 0.20–0.30	
HG10MNN (J92604)	19Cr-12Ni- 4Mn	0.07–0.11	3.0–5.0	0.040	0.03	0.70	18.5–20.5	11.5–13.5	0.25–0.45	Cu 0.50 Nb ^e N 0.20–0.30	
CT15C N08151	20-Chromium, 33-Nickel, 1-Niobium	0.05–0.15	0.15–1.50	0.15–1.50	0.03	0.03	19.0–21.0	31.0–34.0	...	Nb 0.50–1.50	
CT15C (N08151)	20Cr-33Ni- 1Nb	0.05–0.15	0.15–1.50	0.03	0.03	0.15–1.50	19.0–21.0	31.0–34.0	...	Nb 0.50–1.50	

^a Where ellipses (. . .) appear in this table there is no requirement, and the element need not be analyzed or reported.

^b All values are maximums except where a range is provided.

^c Castings having a specified molybdenum range agreed upon by the manufacturer and the purchaser may also be furnished under these specifications.

^d Niobium (Nb) and Columbium (Cb) both designate element 41.

^e Grade HG10MNN shall have a niobium content of not less than 8× the carbon, but not over 1.00 %.

4.1.1 A description of the casting by pattern number or drawing (dimensional tolerances shall be included on the casting drawing),

4.1.2 Grade of steel,

4.1.3 Options in the specification, and

4.1.4 The supplementary requirements desired, including the standards of acceptance.

5. Process

5.1 Alloys shall be made by the following processes: electric arc, electric induction, or other approved processes.

6. Heat Treatment

6.1 Castings for heat-resistant service may be shipped in the as-cast condition without heat treatment. If heat treatment is required, the treatment shall be established by mutual agreement between the manufacturer and the purchaser and shall be so specified in the inquiry, contract, or order.

7. Chemical Composition

7.1 Alloys shall conform to the requirements as to chemical composition prescribed in Table 1.

8. Repair by Welding

8.1 Except for Grade HG10MNN, the composition of the deposited weld metal shall be similar to the composition of the casting. For Grade HG10MNN, the filler metal to be used shall be established by mutual agreement between the manufacturer and the purchaser. All weld repairs shall be subjected to the same inspection standards as the casting.

8.2 Castings with major weld repairs shall be heat treated in accordance with Section 6.

8.3 Weld repairs shall be considered major when the depth of the cavity after preparation for repair exceeds 20 % of the actual wall thickness, or 1 in. [25 mm], whichever is smaller, or when the extent of the cavity exceeds approximately 10 in.² [65 cm²].

8.3.1 When Supplementary Requirement S7 is specified on the purchase order or inquiry, major weld repairs shall be subject to the prior approval of the purchaser.

8.4 All other weld repairs shall be considered minor and may be made at the discretion of the manufacturer without prior approval of the purchaser.



SUPPLEMENTARY REQUIREMENTS

The following supplementary requirements shall not apply unless specified in the purchase order. A list of standardized supplementary requirements for use at the option of the purchaser is included in Specification [A781/A781M](#) or [A957/A957M](#). Those which are ordinarily considered suitable for use with this specification are given below. Others enumerated in Specification [A781/A781M](#) or [A957/A957M](#) may be used with this specification upon agreement between the manufacturer and purchaser.

S1. Magnetic Particle Examination

S2. Radiographic Examination

S3. Liquid Penetrant Examination

S4. Ultrasonic Examination

S5. Examination of Weld Preparation

S6. Certification

S7. Prior Approval of Major Weld Repairs

S8. Marking

S14. Tension Test

[ASTM A297/A297M-20](#)

S14.1 One tension test shall be made from material representing each heat. The bar from which the test specimen is taken shall be heat treated in production furnaces to the same procedure as the castings it represents. The results shall conform to the requirements specified in [Table S14.1](#).

S14.2 Test bars shall be poured in separately cast keel blocks shown in Specification [A781/A781M](#), unless the purchase order is for investment castings, in which case, test material shall be poured in accordance with the requirements of Specification [A957/A957M](#).

S14.3 Tension test specimens may be cut from heat-treated castings; or from as-cast castings if no heat treatment is specified for the castings, instead of from test bars when agreed upon between the manufacturer and the purchaser or at the option of the producer if suitable separately cast test material is not available.

S14.4 Test specimens shall be the standard round 2-in. [50-mm] gage length specimen shown in Test Methods and Definitions [A370](#), unless the purchase order is for investment castings, in which case, the specimen shall be in accordance with Specification [A957/A957M](#).

S14.5 If the results of the mechanical tests for any heat do not conform to the requirements specified, the castings may be reheat treated and retested, but may not be solution heat treated or re-austenitized more than twice.

S14.6 If any test specimen shows defective machining or develops flaws, it may be discarded and another specimen substituted from the same heat.