



Designation: C1067 – 20

Standard Practice for Conducting a Ruggedness Evaluation or Screening Program for Test Methods for Construction Materials¹

This standard is issued under the fixed designation C1067; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

1. Scope*

1.1 This practice covers a procedure for evaluating the ruggedness of a test method by determining the effects of different experimental factors on the variation of test results. The procedure is intended for use during the development of a test method before the interlaboratory study is executed, such as those described in Practices C802 and E691.

1.2 This practice covers, in general terms, techniques for planning, collecting data, and analyzing results from a few laboratories. Appendix X1 provides the details of the procedure with an example and Appendix X2 provides additional information on the methodology.

1.3 The practice is not intended to give information pertinent to estimating multilaboratory precision.

1.4 The system of units for this practice is not specified. Dimensional quantities in the practice are presented only in illustrations of calculation methods.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.6 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:²

¹ This practice is under the jurisdiction of ASTM Committee C09 on Concrete and Concrete Aggregates and is the direct responsibility of Subcommittee C09.94 on Evaluation of Data (Joint C09 and C01).

Current edition approved April 15, 2020. Published August 2020. Originally approved in 1987. Last previous edition approved in 2012 as C1067 – 12. DOI: 10.1520/C1067-20.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

C670 Practice for Preparing Precision and Bias Statements for Test Methods for Construction Materials

C802 Practice for Conducting an Interlaboratory Test Program to Determine the Precision of Test Methods for Construction Materials

E456 Terminology Relating to Quality and Statistics

E691 Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method

E1169 Practice for Conducting Ruggedness Tests

3. Terminology

3.1 Definitions:

3.1.1 For definitions of statistical terms used in this standard, refer to Terminology E456.

3.2 Definitions of Terms Specific to This Standard:

3.2.1 *determination, n*—numerical value of a characteristic of a test specimen measured in accordance with the given test method.

3.2.2 *effect, n*—of a factor, the difference in the measured characteristics at each level of a factor averaged over all levels of other factors in the experiment.

3.2.3 *factor, n*—a condition or element in the test procedure or laboratory environment that can be controlled and that is a potential source of variation of test results.

3.2.4 *level, n*—the value or setting of a factor associated with a determination.

3.2.5 *replication, n*—the act of obtaining, under specified conditions, two or more determinations on identical specimens.

3.2.5.1 *Discussion*—Replicate determinations are typically required to be obtained by the same operator, using the same apparatus, on specimens that are as similar as possible, and during a short time interval.

3.2.6 *ruggedness, n*—the degree to which a test method is able to produce test results that are not influenced, to a statistically significant degree, by small changes in testing procedure or environment.

3.2.6.1 *Discussion*—Statistical significance is evaluated by comparing the observed variation in test results due to a factor with the expected variation due to chance alone.

3.2.7 *screening, n*—a planned experiment using a low number of determinations to detect among many factors those that

*A Summary of Changes section appears at the end of this standard

have a statistically significant effect on variation of test results compared with chance variation.

3.2.7.1 *Discussion*—In this practice, the influence of seven factors is evaluated using a replicated set of eight determinations, that is, a total of 16 determinations.

4. Summary of Practice

4.1 The practice requires that the user develop, from theoretical or practical knowledge, or both, a list of factors that plausibly would cause statistically significant variation in test results if the factors were not controlled. The technique is limited to the analysis of the effects of seven factors and requires $\frac{1}{16}$ of the determinations that would be required to evaluate seven factors in a full factorial study (see [Appendix X2](#) for additional explanation). Procedures exist for analysis of smaller and larger numbers of factors (see [Guide E1169](#)), but seven is a convenient number for many test methods for construction materials. The seven-factor analysis requires 16 determinations by each laboratory. The procedure can be executed usefully by a single laboratory, but sometimes additional information can be obtained if it is repeated in one or two additional laboratories.

4.2 The procedure requires that two levels of each factor be identified, and 16 determinations be obtained with prescribed combinations of factor levels. The levels assigned to a factor may be quantitative or qualitative (for example, 20°C versus 25°C or brass versus steel).

4.3 After data are acquired, a statistical procedure is applied to establish which of the factors under study have a statistically significant effect on test results.

5. Significance and Use

5.1 The purpose of a ruggedness evaluation, or screening program, is to determine the sensitivity of the test method to changes in levels of pertinent operating factors using a small number of tests. Normally, operating conditions for a test method are defined along with allowable tolerances. A ruggedness analysis determines the effect of “worst-case” variation in operating conditions within the specified tolerances. If the ruggedness evaluation indicates that the factors have a statistically significant effect on test results, the method can be revised with smaller tolerances on operating conditions to reduce variation among test results.

5.2 This practice evaluates the effects of seven factors using eight testing conditions (treatments). The disadvantage of this approach is that it only estimates the main effects of the factors and does not detect the effects of interactions among factors. For this reason, this is a screening program and additional investigation is required to determine whether there are interaction effects.

5.3 A major reason for poor precision in test methods is the lack of adequate control over the sources of variation in testing procedures or testing environments. These sources of variation often are not controlled adequately because they were not identified during the development of the test procedures as having a large effect on test results. This practice provides a

systematic procedure to establish the required degree of control for different testing parameters.

5.4 All new test methods must be subjected to an interlaboratory program to develop a precision and bias statement. These programs can be expensive and time-consuming, and the result may show that the method is too variable and should not be published without further revision. Interlaboratory studies may give the subcommittee an indication that the method is too variable, but they do not usually give a clear picture of the causes of the high variation. Application of this practice using one or two laboratories before finalizing the test method and conducting the interlaboratory study is an economical way to determine these causes.

5.5 Many existing test methods were developed before there was a requirement for precision and bias statements. Since this became a requirement, most of these test methods have developed precision and bias statements, and the result is that many have been found to suffer from relatively large amount of variation. This practice provides a relatively simple and economical way to investigate the causes of variation in test methods, so that a subcommittee will have some guidance as to which parts of the test method need to be revised.

5.6 The procedure can be used for a screening program within a single laboratory, but involvement of at least three laboratories is recommended, particularly if the single laboratory were to be the one that developed the test method. This is particularly important for new test methods. The originating laboratory is so much a part of the development of the test method that it is difficult for it to be objective in spotting any problems in the clarity of the test method instructions. Two additional laboratories will probably contribute fresh critical review of the validity of the test method and provide assistance in clarifying the instructions of the test method if needed. This practice, however, is not intended to provide information on multilaboratory precision, but it does provide some information on single-operator precision, which could be used to develop a temporary repeatability statement until the interlaboratory study is completed.

6. Materials

6.1 The number and types of material shall cover the range of material properties to which the test method is applicable. The test method may not apply to material types or property values outside the range evaluated. Three to five materials with different values of the measured property will usually be sufficient.

6.1.1 Some preliminary testing may help the laboratories involved determine the materials that will be used in the screening program.

7. Procedure

7.1 Determine the number of laboratories that will participate in the screening program and which materials each will use. The maximum amount of information is obtained if all laboratories include all materials in their part of the program, however, cost can be reduced if each laboratory uses a different material. In this case, caution must be exercised in interpreting

the results because laboratory-dependent effects cannot be separated from material-dependent effects.

TABLE 1 Pattern of Assigning Levels^A to Seven Factors

Factor	Determination Number							
	1(9) ^B	2(10)	3(11)	4(12)	5(13)	6(14)	7(15)	8(16)
A	-	-	-	-	+	+	+	+
B	-	-	+	+	-	-	+	+
C	-	+	-	+	-	+	-	+
D	+	+	-	-	-	-	+	+
E	+	-	+	-	-	+	-	+
F	+	-	-	+	+	-	-	+
G	-	+	+	-	+	-	-	+

^A The plus sign (+) indicates one level for the factor and the minus sign (-) indicates the other level.

^B The numbers in parentheses refer to the determinations in replicate set 2.

7.2 Factors that are likely to have the greatest effect on the variability of the test results are selected for study. Levels of these factors are determined by selecting the minimum and maximum levels that would plausibly occur in the execution of the test method if there were no particular efforts to control them. Levels often represent quantitative factors, such as temperature or pressure, but they may also represent qualitative factors, such as old versus new or wet versus dry. Only two levels are allowed for each factor. In this practice, factors are assigned letter designations, A through G, and the two levels of each factor are designated with plus (+) and minus (-) signs, as shown in Table 1.

7.3 Assign combinations of factor levels to each determination according to Table 1. The eight determinations will be replicated; therefore, the full study on each material will require 16 determinations. Run the 16 determinations in random order.

7.4 To analyze the results, construct a 16 row by 16 column matrix composed of ±1 values as shown in Table 2. Each of the 16 columns corresponds to one of the determinations. The values in row 1 are all +1. The +1 and -1 values in rows 2 to 8 for the first replicate set correspond to the high and low settings of the factors A through G as given in Table 1. The

pattern in rows 1 to 8 of the first replicate set is repeated for rows 1 to 8 of the second replicate set and for rows 9 to 16 of the first replicate set. For rows 9 to 16 of the second replicate set, the signs are reversed from those in the first set. The plus and minus signs in Table 2 are applied to the values of the 16 determinations to create a table of signed determinations and various sums of the signed determinations are calculated (see Note 1). For each row of the table of signed determinations, calculate the Z and W statistics using Eq 1 and 2.

$$Z_r = \sum_{i=1}^{16} \alpha_{ri} d_i \tag{1}$$

$$W_r = \frac{Z_r^2}{16} \tag{2}$$

where:

- r = row number as shown in Table 2, where r = 1 to 16,
- i = determination number ranging from 1 to 16,
- α_{ri} = +1 or -1 as defined in Table 2 for each row number and determination number, and
- d_i = measured value of determination number i as defined in Table 1.

NOTE 1—See Table X1.4 for an example of the resulting table of signed determinations after the +1 and -1 values shown in Table 2 are applied to the 16 determinations. Eq 1 represents the sum for each row of the table of signed determinations.

7.5 The Z-statistic for row 1 (Z₁) represents the sum of the 16 determinations and Z₁/16 is the overall average of the 16 determinations. The Z-statistics for rows 2 through 8 (Z₂ through Z₈) are related to the effects of each of the seven factors (see Note 2). These values of Z represent the differences between the sum of the determinations at the high level of the factor and the sum of the determinations at the low level of the factor. The Z-values are divided by eight to obtain the effect of each factor averaged of over the levels of the other factors. For example, Z₃/8 is the average effect of factor B as it is varied from the low level to the high level.

NOTE 2—A positive value for an effect of a factor means that the response increases as the factor level is changed from its low level to its high level. The opposite is the case for a negative effect. Recall that an effect of a factor is the difference between the average of the determinations at the high setting minus the average at the low setting of the factor.

TABLE 2 Matrix of Signs to be Applied to 16 Determinations (d₁ to d₁₆) to Calculate Z- and W-Statistics

Row ^A	Sign Applied to Each Determination in Computing Z _i																Z	W
	Eight Determinations for Replicate Set 1								Eight Determinations for Replicate Set 2									
	1	2	3	4	5	6	7	8	9	10	11	12	13	14	15	16		
1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	Z ₁	W ₁
2	-1	-1	-1	-1	1	1	1	1	-1	-1	-1	-1	1	1	1	1	Z ₂	W ₂
3	-1	-1	1	1	-1	-1	1	1	-1	-1	1	1	-1	-1	1	1	Z ₃	W ₃
4	-1	1	-1	1	-1	1	-1	1	-1	1	-1	1	-1	1	-1	1	Z ₄	W ₄
5	1	1	-1	-1	-1	-1	1	1	1	1	-1	-1	-1	-1	1	1	Z ₅	W ₅
6	1	-1	1	-1	-1	1	-1	1	1	-1	1	-1	-1	1	-1	1	Z ₆	W ₆
7	1	-1	-1	1	1	-1	-1	1	1	-1	-1	1	1	-1	-1	1	Z ₇	W ₇
8	-1	1	1	-1	1	-1	-1	1	-1	1	1	-1	1	-1	-1	1	Z ₈	W ₈
9	1	1	1	1	1	1	1	1	-1	-1	-1	-1	-1	-1	-1	-1	Z ₉	W ₉
10	-1	-1	-1	-1	1	1	1	1	1	1	1	1	-1	-1	-1	-1	Z ₁₀	W ₁₀
11	-1	-1	1	1	-1	-1	1	1	1	1	-1	-1	1	1	-1	-1	Z ₁₁	W ₁₁
12	-1	1	-1	1	-1	1	-1	1	1	-1	1	-1	1	-1	1	-1	Z ₁₂	W ₁₂
13	1	1	-1	-1	-1	-1	1	1	-1	-1	1	1	1	1	-1	-1	Z ₁₃	W ₁₃
14	1	-1	1	-1	-1	1	-1	1	-1	1	-1	1	1	-1	1	-1	Z ₁₄	W ₁₄
15	1	-1	-1	1	1	-1	-1	1	-1	1	1	-1	-1	1	1	-1	Z ₁₅	W ₁₅
16	-1	1	1	-1	1	-1	-1	1	1	-1	-1	1	-1	1	1	-1	Z ₁₆	W ₁₆

^A Rows 2 to 8 and rows 10 to 16 are associated with the levels of the factors A–G.

7.6 The W values are various mean squares. W_1 is the mean of the square of the sum of all determinations and is not used in this analysis. The values W_2 to W_8 are the mean squares for each factor and are compared with the random error (see Note 3). The W values for rows 9 through 16 (W_9 to W_{16}) are used to calculate the error variance (s^2) according to Eq 3 (see Note 4).

$$s^2 = \frac{\sum_{r=9}^{16} W_r}{8} \quad (3)$$

NOTE 3—Appendix X2 provides additional information of the meaning of the term “mean squares.”

NOTE 4—The error variance s^2 is the pooled variance of the two replicate determinations for each of the eight conditions (treatments).

7.7 To establish whether a factor has a statistically significant effect on the results, compute the F statistic for each factor using Eq 4.

$$F_f = \frac{W_r}{s^2} \quad (4)$$

where:

F_f = value of F -statistic for factor f (A through G) for the corresponding row (2 through 8) of Table 2.

Table 3 summarizes the calculations given by Eq 3 and 4.

7.8 An F_f value that is ≥ 5.32 represents a statistically significant effect for factor f at a probability of not greater than 5 % for drawing an erroneous conclusion.

TABLE 3 Summary of Statistics for Seven Factors and Random Error

Factor	W	F
A	W_2	$F_A = W_2/s^2$
B	W_3	$F_B = W_3/s^2$
C	W_4	$F_C = W_4/s^2$
D	W_5	$F_D = W_5/s^2$
E	W_6	$F_E = W_6/s^2$
F	W_7	$F_F = W_7/s^2$
G	W_8	$F_G = W_8/s^2$
	W_9	
	W_{10}	
	W_{11}	
	W_{12}	
	W_{13}	
	W_{14}	
	W_{15}	
	W_{16}	
		$s^2 = \frac{\sum_{r=9}^{16} W_r}{8}$

7.9 An example of an analysis of data representing results on 4 materials from 3 laboratories is presented in Appendix X1.

7.10 If desired, one of the alternative methods discussed in X2.5 of Appendix X2 is permitted for determining which factors have statistically significant effects.

8. Keywords

8.1 analysis of variance; precision; ruggedness; screening; test method; variation

APPENDIXES

(Nonmandatory Information)

X1. EXAMPLE OF A RUGGEDNESS PROGRAM

X1.1 This appendix describes the procedure for conducting a ruggedness evaluation using as an example a proposed test method for measuring the viscosity of asphalt. Three laboratories participated in the program.

X1.2 As the first step in the ruggedness evaluation, each of the laboratories critically examined the procedure in the proposed test method. The objectives of the examination were as follows:

1. To determine if the instructions were clear, concise, and complete,
2. To decide which factors were likely to influence test results and therefore should be included in the study,
3. To select materials that covered the range of the property of interest for the range of physical forms of the materials to be tested, and
4. To determine the proper levels to be evaluated for each of the chosen factors.

X1.3 In this example, representatives of the three laboratories, after familiarizing themselves with the proposed test method, met and tried to improve the instructions for the viscosity measurement. They selected factors and levels that

they believed could affect the measured viscosities. In a preliminary investigation, one of the laboratories measured viscosity at 24°C, 25°C, and 26°C and found that there was about a 10 % variation with a change of 1°C. This was considered too large so 24.6 and 25.4°C were selected as the lower and upper temperature levels for the ruggedness evaluation. In the same manner, the effects of the other factors were examined and the two levels to be used for each factor were selected. The seven factors selected for the program and their levels are shown in Table X1.1. The levels of the factors were assigned to each of the eight determinations in accordance with Table 1 from the body of this practice. Table X1.2 shows the testing conditions (or treatments) for each of the replicated determinations.

X1.4 Four materials were selected to cover the range of viscosities to be measured by the test method. For each testing condition, the viscosities were determined by each of the three laboratories with one replication. Thus each laboratory conducted 16 determinations for each material, for a total of 64 determinations. For each material, the 16 determinations were acquired in random order. This is a critical part of the program to guard against systematic variations in the testing conditions.

TABLE X1.1 Levels Assigned to Seven Factors

Factor	Level
A: Temperature	- = 24.6°C + = 25.4°C
B: Age of viscometer tube	- = New + = Old
C: Applied vacuum	- = 310 mmHg + = 290 mmHg
D: Stirring sample before charging viscometer	- = No stirring + = Stir for 1 minute
E: Angle of viscometer	- = 87° from horizontal + = 90° from horizontal
F: Height of filling	- = 6 mm (1 mm above line) + = 4 mm (1 mm below line)
G: Time viscometer held in bath	- = 40 min (10 min more than specified) + = 20 min (10 min less than specified)

TABLE X1.2 Conditions for Each Determination

Factor	Determination Number							
	1(9)	2(10)	3(11)	4(12)	5(13)	6(14)	7(15)	8(16)
A-Temperature	24.6 °C	24.6 °C	24.6 °C	24.6 °C	25.4 °C	25.4 °C	25.4 °C	25.4 °C
B-Viscometer	New	New	Old	Old	New	New	Old	Old
C-Vacuum	310 mmHg	290 mmHg	310 mmHg	290 mmHg	310 mmHg	290 mmHg	310 mmHg	290 mmHg
D-Stirring	1 min	1 min	No	No	No	No	1 min	1 min
E-Angle	90°	87°	90°	87°	87°	90°	87°	90°
F-Fill Height	4 mm	6 mm	6 mm	4 mm	4 mm	6 mm	6 mm	4 mm
G-Time in Bath	40 min	20 min	20 min	40 min	20 min	40 min	40 min	20 min

The tests results, grouped by laboratory, are shown in Table X1.3.

X1.5 After the data were obtained, the results for each laboratory-material combination were analyzed independently. Thus in this program, there are 12 analyses corresponding to each row of data in Table X1.3. To proceed with each analysis, the relevant row of data from Table X1.3 is copied into 16 rows to create a 16 by 16 matrix. Each column corresponds to a determination and the value of that determination is repeated 16 times. The numbers in the matrix are multiplied by the corresponding values of +1 or -1 given in Table 2 in the body of this practice. Table X1.4 is an example of the resulting matrix of signed determinations derived from the data for Material 1 and Laboratory 1 in Table X1.3.

X1.6 After the 16 by 16 matrix with the proper signs applied to each determination has been created, the next step is to calculate the sum of each row to obtain 16 Z-values, which are identified as Z₁ to Z₁₆. Table X1.5 shows the resulting sums for Laboratory 1 and Material 1. The value Z₁ represents the sum of all viscosities and Z₁/16 is the overall average viscosity for the laboratory-material combination. The value Z₂ represents the difference between the results at the high level of factor A and at the low level. In this case factor A is temperature, so Z₂ measures the effect of temperature. In the same manner, Z₃ measures the effect of the factor B, the age of the viscometer. The value Z₄ measures the effect of factor C, the vacuum level. The value Z₅ measures the effect of factor D, whether or not the sample is stirred before filling the viscometer. The value Z₆

TABLE X1.3 Viscosity Data

Material	Viscosity															
	First Replicate Determination Number								Second Replicate Determination Number							
	1	2	3	4	5	6	7	8	9	10	11	12	13	14	15	16
	Laboratory 1															
1	2370	2258	2355	2185	1825	1845	1820	1830	2320	2275	2350	2380	1840	1850	1825	1820
2	520	495	519	480	401	404	398	402	492	516	490	522	390	408	402	395
3	4205	4006	4191	3846	3212	3284	3185	3221	4200	4160	4130	4020	3218	3180	3280	3280
4	1075	1061	1060	961	803	793	801	805	1050	1070	1015	1000	808	790	795	805
	Laboratory 2															
1	2350	2240	2335	2165	1805	1825	1800	1810	2280	2310	2400	2120	1825	1806	1809	1812
2	540	515	539	500	421	424	418	422	518	545	524	492	410	425	430	420
3	4235	4036	4121	3876	3242	3314	3117	3250	4250	4142	3960	4205	3310	3112	3240	3117
4	1102	1040	1085	980	820	811	824	828	1110	1125	1040	1050	825	804	816	835
	Laboratory 3															
1	2390	2278	2375	2205	1845	1865	1840	1850	2400	2268	2350	2250	1860	1850	1870	1845
2	510	485	509	470	391	394	388	392	505	482	510	480	395	390	385	392
3	4200	3975	4160	3816	3190	3246	3150	3200	4180	3990	4140	3890	3200	3180	3220	3195
4	1050	990	1035	930	786	766	775	780	1040	980	1050	970	780	760	785	782

TABLE X1.4 Analysis Matrix Based on Applying Signs in Table 1 to Data for Laboratory 1 and Material 1

NOTE 1—The data in Tables X1.5-X1.16 are derived from matrices constructed, as illustrated by this table, from the data for each of the remaining eleven laboratory-material combinations shown in Table X1.3.

Row	Replicate 1								Replicate 2							
	d_1	d_2	d_3	d_4	d_5	d_6	d_7	d_8	d_9	d_{10}	d_{11}	d_{12}	d_{13}	d_{14}	d_{15}	d_{16}
1	2370	2258	2355	2185	1825	1845	1820	1830	2320	2275	2350	2380	1840	1850	1825	1820
2	-2370	-2258	-2355	-2185	1825	1845	1820	1830	-2320	-2275	-2350	-2380	1840	1850	1825	1820
3	-2370	-2258	2355	2185	-1825	-1845	1820	1830	-2320	-2275	2350	2380	-1840	-1850	1825	1820
4	-2370	2258	-2355	2185	-1825	1845	-1820	1830	-2320	2275	-2350	2380	-1840	1850	-1825	1820
5	2370	2258	-2355	-2185	-1825	-1845	1820	1830	2320	2275	-2350	-2380	-1840	-1850	1825	1820
6	2370	-2258	2355	-2185	-1825	1845	-1820	1830	2320	-2275	2350	-2380	-1840	1850	-1825	1820
7	2370	-2258	-2355	2185	1825	-1845	-1820	1830	2320	-2275	-2350	2380	1840	-1850	-1825	1820
8	-2370	-2258	2355	-2185	1825	-1845	-1820	1830	-2320	2275	2350	-2380	1840	-1850	-1825	1820
9	2370	2258	2355	2185	1825	1845	1820	1830	-2320	-2275	-2350	-2380	-1840	-1850	-1825	-1820
10	-2370	-2258	-2355	-2185	1825	1845	1820	1830	2320	2275	2350	2380	-1840	-1850	-1825	-1820
11	-2370	-2258	2355	2185	-1825	-1845	1820	1830	2320	2275	-2350	-2380	1840	1850	-1825	-1820
12	-2370	2258	-2355	2185	-1825	1845	-1820	1830	2320	-2275	2350	-2380	1840	-1850	1825	-1820
13	2370	2258	-2355	-2185	-1825	-1845	1820	1830	-2320	-2275	2350	2380	1840	1850	-1825	-1820
14	2370	-2258	2355	-2185	-1825	1845	-1820	1830	-2320	2275	-2350	2380	1840	-1850	1825	-1820
15	2370	-2258	-2355	2185	1825	-1845	-1820	1830	-2320	2275	2350	-2380	-1840	1850	1825	-1820
16	-2370	2258	2355	-2185	1825	-1845	-1820	1830	2320	-2275	-2350	2380	-1840	1850	1825	-1820

TABLE X1.5 Results of Calculations for Laboratory 1 and Material 1

$Z_1 = 33148$	$W_1 = 68,674,369.00$	Avg. = 2071.8
$Z_2 = -3838$	$W_2 = 920,640.25$	$F_A = 357.41^A$
$Z_3 = -18$	$W_3 = 20.25$	$F_B = 0.01$
$Z_4 = -262$	$W_4 = 4,290.25$	$F_C = 1.67$
$Z_5 = -112$	$W_5 = 784.00$	$F_D = 0.30$
$Z_6 = 332$	$W_6 = 6,889.00$	$F_E = 2.67$
$Z_7 = -8$	$W_7 = 4.00$	$F_F = 0.00$
$Z_8 = -42$	$W_8 = 110.25$	$F_G = 0.04$
$Z_9 = -172$	$W_9 = 1,849.00$	
$Z_{10} = 142$	$W_{10} = 1,260.25$	$s^2 = 2575.88$
$Z_{11} = -198$	$W_{11} = 2,450.25$	$s = 50.75$
$Z_{12} = -242$	$W_{12} = 3,660.25$	
$Z_{13} = 248$	$W_{13} = 3,844.00$	
$Z_{14} = 292$	$W_{14} = 5,329.00$	
$Z_{15} = -128$	$W_{15} = 1,024.00$	
$Z_{16} = 138$	$W_{16} = 1,190.25$	

^A Bold numbers in Tables X1.5-X1.16 indicate statistically significant values.

is the single-operator variance calculated from the replicate determinations for each of the eight conditions and it indicates the random error associated with the test method. The error variance is obtained by calculating the sum of W_9 to W_{16} and dividing by 8 as indicated by Eq 3 in the body of this practice. The calculated values of s^2 for each laboratory-material combination are shown in Tables X1.5-X1.16. If there are duplicate determinations, as is the case in this program, the error variance can also be determined as follows:

$$s^2 = \frac{\sum_1^k \Delta^2}{2k} \tag{X1.1}$$

where:

- s^2 = error variance or the pooled single-operator variance,
- Δ = the difference between duplicate determinations, and
- k = number of pairs of determinations ($k=8$ in this program).

measures the effect of factor E , whether the viscometer is vertical or slanted slightly. The value Z_7 measures the effect of factor F , the variation of the height of the asphalt when the viscometer is filled. The value Z_8 measures the effect of factor G , the time that the viscometer is kept in the water bath before testing. Each of these Z -values comprises eight determinations at one level of the factor and eight determinations at the other level. Therefore, the effect of a factor is obtained by dividing the corresponding Z -value by eight.

X1.7 The next step in the analysis is to square the Z -values and divide the squares by 16. The resulting values, which are denoted W_1 to W_{16} are various kinds of “mean sum of squares.” As far as the ruggedness evaluation is concerned, the values W_2 to W_8 are measures of the variance of the means associated with each factor level. For example W_2 is the variance associated with the average values of the determinations obtained at the high and low temperatures. See Appendix X2 for more discussion on the meaning of the W -values.

X1.8 To determine if a factor has a statistically significant effect, the values of W_2 to W_8 are compared with the error variance (also called the mean square error). The error variance

X1.9 The final step in the analysis is to compute the F -values for each of the factors by dividing W_2 to W_8 by s^2 as indicated by Eq 4 in the body of the practice. The calculated F -values for each laboratory-material combination are shown in Tables X1.5-X1.16. These values are compared with the

TABLE X1.6 Results of Calculations for Laboratory 1 and Material 2

$Z_1 = 7234$	$W_1 = 3,270,672.25$	Avg. = 452.1
$Z_2 = -834$	$W_2 = 43,472.25$	$F_A = 172.51$
$Z_3 = -18$	$W_3 = 20.25$	$F_B = 0.08$
$Z_4 = 10$	$W_4 = 6.25$	$F_C = 0.02$
$Z_5 = 6$	$W_5 = 2.25$	$F_D = 0.01$
$Z_6 = 26$	$W_6 = 42.25$	$F_E = 0.17$
$Z_7 = -30$	$W_7 = 56.25$	$F_F = 0.22$
$Z_8 = -18$	$W_8 = 20.25$	$F_G = 0.08$
$Z_9 = 4$	$W_9 = 1.00$	
$Z_{10} = 16$	$W_{10} = 16.00$	$s^2 = 252.00$
$Z_{11} = -24$	$W_{11} = 36.00$	$s = 15.87$
$Z_{12} = -124$	$W_{12} = 961.00$	
$Z_{13} = 16$	$W_{13} = 16.00$	
$Z_{14} = 116$	$W_{14} = 841.00$	
$Z_{15} = 4$	$W_{15} = 1.00$	
$Z_{16} = 48$	$W_{16} = 144.00$	

TABLE X1.7 Results of Calculations for Laboratory 1 and Material 3

Z ₁ = 58618	W ₁ = 214,754,370.25	Avg. = 3663.6
Z ₂ = -6898	W ₂ = 2,973,900.25	F _A = 586.74
Z ₃ = -312	W ₃ = 6,084.00	F _B = 1.20
Z ₄ = -624	W ₄ = 24,336.00	F _C = 4.80
Z ₅ = 456	W ₅ = 12,996.00	F _D = 2.56
Z ₆ = 764	W ₆ = 36,481.00	F _E = 7.20
Z ₇ = -214	W ₇ = 2,862.25	F _F = 0.56
Z ₈ = 218	W ₈ = 2,970.25	F _G = 0.59
Z ₉ = -318	W ₉ = 6,320.25	
Z ₁₀ = 206	W ₁₀ = 2,652.25	s ² = 5068.50
Z ₁₁ = -216	W ₁₁ = 2,916.00	s = 71.19
Z ₁₂ = -248	W ₁₂ = 3,844.00	
Z ₁₃ = -288	W ₁₃ = 5,184.00	
Z ₁₄ = 540	W ₁₄ = 18,225.00	
Z ₁₅ = -150	W ₁₅ = 1,406.25	
Z ₁₆ = 2	W ₁₆ = 0.25	

TABLE X1.10 Results of Calculations for Laboratory 2 and Material 2

Z ₁ = 7543	W ₁ = 3,556,053.06	Avg. = 471.4
Z ₂ = -803	W ₂ = 40,300.56	F _A = 331.86
Z ₃ = -53	W ₃ = 175.56	F _B = 1.45
Z ₄ = -57	W ₄ = 203.06	F _C = 1.67
Z ₅ = 73	W ₅ = 333.06	F _D = 2.74
Z ₆ = 81	W ₆ = 410.06	F _E = 3.38
Z ₇ = -97	W ₇ = 588.06	F _F = 4.84
Z ₈ = 49	W ₈ = 150.06	F _G = 1.24
Z ₉ = 15	W ₉ = 14.06	
Z ₁₀ = -15	W ₁₀ = 14.06	s ² = 121.44
Z ₁₁ = 11	W ₁₁ = 7.56	s = 11.02
Z ₁₂ = -57	W ₁₂ = 203.06	
Z ₁₃ = -51	W ₁₃ = 162.56	
Z ₁₄ = 61	W ₁₄ = 232.56	
Z ₁₅ = 71	W ₁₅ = 315.06	
Z ₁₆ = -19	W ₁₆ = 22.56	

TABLE X1.8 Results of Calculations for Laboratory 1 and Material 4

Z ₁ = 14692	W ₁ = 13,490,929.00	Avg. = 918.3
Z ₂ = -1892	W ₂ = 223,729.00	F _A = 828.24
Z ₃ = -208	W ₃ = 2,704.00	F _B = 10.01
Z ₄ = -122	W ₄ = 930.25	F _C = 3.44
Z ₅ = 232	W ₅ = 3,364.00	F _D = 12.45
Z ₆ = 94	W ₆ = 552.25	F _E = 2.04
Z ₇ = -78	W ₇ = 380.25	F _F = 1.41
Z ₈ = 162	W ₈ = 1,640.25	F _G = 6.07
Z ₉ = 26	W ₉ = 42.25	
Z ₁₀ = -18	W ₁₀ = 20.25	s ² = 270.13
Z ₁₁ = -2	W ₁₁ = 0.25	s = 16.44
Z ₁₂ = -116	W ₁₂ = 841.00	
Z ₁₃ = 18	W ₁₃ = 20.25	
Z ₁₄ = 120	W ₁₄ = 900.00	
Z ₁₅ = -64	W ₁₅ = 256.00	
Z ₁₆ = 36	W ₁₆ = 81.00	

TABLE X1.11 Results of Calculations for Laboratory 2 and Material 3

Z ₁ = 58527.00	W ₁ = 214,088,108.06	Avg. = 3657.9
Z ₂ = -7123.00	W ₂ = 3,171,070.56	F _A = 226.64
Z ₃ = -755.00	W ₃ = 35,626.56	F _B = 2.55
Z ₄ = -423.00	W ₄ = 11,183.06	F _C = 0.80
Z ₅ = 247.00	W ₅ = 3,813.06	F _D = 0.27
Z ₆ = 191.00	W ₆ = 2,280.06	F _E = 0.16
Z ₇ = 443.00	W ₇ = 12,265.56	F _F = 0.88
Z ₈ = -171.00	W ₈ = 1,827.56	F _G = 0.13
Z ₉ = -145.00	W ₉ = 1,314.06	
Z ₁₀ = 433.00	W ₁₀ = 11,718.06	s ² = 13991.81
Z ₁₁ = -171.00	W ₁₁ = 1,827.56	s = 118.29
Z ₁₂ = -55.00	W ₁₂ = 189.06	
Z ₁₃ = -77.00	W ₁₃ = 370.56	
Z ₁₄ = 1107.00	W ₁₄ = 76,590.56	
Z ₁₅ = -413.00	W ₁₅ = 10,660.56	
Z ₁₆ = 385.00	W ₁₆ = 9,264.06	

TABLE X1.9 Results of Calculations for Laboratory 2 and Material 1

Z ₁ = 32692	W ₁ = 66,797,929.00	Avg. = 2043.3
Z ₂ = -3708	W ₂ = 859,329.00	F _A = 813.76
Z ₃ = -190	W ₃ = 2,256.25	F _B = 2.14
Z ₄ = -516	W ₄ = 16,641.00	F _C = 15.76
Z ₅ = 130	W ₅ = 1,056.25	F _D = 1.00
Z ₆ = 544	W ₆ = 18,496.00	F _E = 17.52
Z ₇ = -358	W ₇ = 8,010.25	F _F = 7.59
Z ₈ = 382	W ₈ = 9,120.25	F _G = 8.64
Z ₉ = -32	W ₉ = 64.00	
Z ₁₀ = 8	W ₁₀ = 4.00	s ² = 1056.00
Z ₁₁ = -30	W ₁₁ = 56.25	s = 32.50
Z ₁₂ = 16	W ₁₂ = 16.00	
Z ₁₃ = 10	W ₁₃ = 6.25	
Z ₁₄ = 76	W ₁₄ = 361.00	
Z ₁₅ = 218	W ₁₅ = 2,970.25	
Z ₁₆ = -282	W ₁₆ = 4,970.25	

TABLE X1.12 Results of Calculations for Laboratory 2 and Material 4

Z ₁ = 15095	W ₁ = 14,241,189.06	Avg. = 943.4
Z ₂ = -1969	W ₂ = 242,310.06	F _A = 269.21
Z ₃ = -179	W ₃ = 2,002.56	F _B = 2.22
Z ₄ = -149	W ₄ = 1,387.56	F _C = 1.54
Z ₅ = 265	W ₅ = 4,389.06	F _D = 4.88
Z ₆ = 135	W ₆ = 1,139.06	F _E = 1.27
Z ₇ = 5	W ₇ = 1.56	F _F = 0.00
Z ₈ = 101	W ₈ = 637.56	F _G = 0.71
Z ₉ = -115	W ₉ = 826.56	
Z ₁₀ = 121	W ₁₀ = 915.06	s ² = 900.06
Z ₁₁ = 67	W ₁₁ = 280.56	s = 30.00
Z ₁₂ = -195	W ₁₂ = 2,376.56	
Z ₁₃ = -69	W ₁₃ = 297.56	
Z ₁₄ = 189	W ₁₄ = 2,232.56	
Z ₁₅ = -65	W ₁₅ = 264.06	
Z ₁₆ = 11	W ₁₆ = 7.56	

critical *F*-value at a significance level of 0.05 for 1 degree of freedom for the numerator and 8 degrees of freedom for the denominator. The critical value is 5.32. If the calculated *F*-value for a factor is ≥ 5.32 , the factor has a statistically significant effect with no more than a 5% probability of making the incorrect inference.

X1.10 The calculated *F*-values that exceed the critical value are shown as bold numbers in Tables X1.5-X1.16. Table X1.17 summarizes the calculated *F*-values for all factors and all laboratory-material combinations. All *F*-values that are less

than 5.32 are indicated in the table as NS to show that they are not statistically significant, and the corresponding factor does not have a statistically significant effect on the results. The effect of temperature (factor A) was found to be highly significant for every material and every laboratory indicating the importance of tight control of temperature. The effect of variation in the level of vacuum (factor C) showed five statistically significant *F*-values indicating a need for tight tolerance on the applied vacuum. The effect of the viscometer deviating from the vertical position (factor E) was statistically significant in six of the laboratory-material combinations