



Designation: C147 – 86 (Reapproved 2020)

Standard Test Methods for Internal Pressure Strength of Glass Containers¹

This standard is issued under the fixed designation C147; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 These test methods cover the determination of the breaking strength of glass containers when subjected to internal pressure. These test methods are intended to determine the pressure strength of containers manufactured to contain products reasonably expected to develop a sustained pressure of 138 kPa (20 psi) or greater, after processing. Two test methods are covered as follows:

| | Sections |
|--|----------|
| Test Method A—Application of Uniform Internal Pressure for a Predetermined Period | 5 – 7 |
| Test Method B—Application of Internal Pressure Increasing at a Predetermined Constant Rate | 8 – 10 |

1.2 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

- 2.1 *ASTM Standard*:²
[C224 Practice for Sampling Glass Containers](#)

¹ These test methods are under the jurisdiction of ASTM Committee C14 on Glass and Glass Products and are the direct responsibility of Subcommittee C14.07 on Glass Containers.

Current edition approved Aug. 1, 2020. Published August 2020. Originally approved in 1939. Last previous edition approved in 2015 as C147 – 86 (2015). DOI: 10.1520/C0147-86R20.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

2.2 *ASTM Adjunct*:³

Single-head Hydraulic Testing Machine (8 Blueprints)

3. Sampling

3.1 Methods of sampling a minimum lot from a group of containers of a given type are given in Practice C224, for the various situations to which it may apply.

4. Precision and Bias

4.1 Statements regarding either precision or bias of the internal pressure test results are not possible because suitable internal pressure reference test materials are not available.

4.2 *Test Method A*—The pressure test precision is within one half the incremental step size used at failure. Pressure test bias is generally within $\pm 1\%$ of full scale.

4.3 *Test Method B*—The pressure test precision is within ± 1 psi (7 kPa). Pressure test bias is generally within \pm % of full scale.

TEST METHOD A—APPLICATION OF UNIFORM INTERNAL PRESSURE FOR PREDETERMINED PERIOD

5. Apparatus

5.1 The apparatus³ shall embody the following principles:

5.1.1 The bottles to be tested shall be held in such a manner that the bottle is not clamped, but is suspended from the *bead of the finish*.

5.1.2 There shall be a resilient sealing member that shall act with the sealing surface of the container to retain the pressurizing medium during the period of the test.

5.1.3 There shall be a means of applying fluid pressure to a predetermined level at a minimum rate of 69 MPa (10 000 psi)/min and of maintaining that pressure constant during the period

³ Single-head automatic sustained pressure testing machine developed by American Glass Research, Inc., Butler, PA, meets these requirements for durations greater than 15 s. Detailed working drawings of this machine are available from ASTM Headquarters. An increment pressure tester developed by the same laboratory is suitable for shorter durations. Available from ASTM International Headquarters. Order Adjunct No. [ADJC0147](#).

of test. Applied incremental fluid pressure levels shall be provided extending over the range from 0.18 MPa (25 psi) to at least 2.41 MPa (350 psi). The applied fluid pressure level shall be reproducible to within $\pm 1\%$ of full scale.

5.1.4 An automatically controlled timing mechanism shall be built into the apparatus so that the container will be subject to uniform internal pressure for a predetermined period which shall be not less than 3 s nor more than 1 min (Note 1). The period of test shall be reproducible within $\pm 2\%$.

NOTE 1—For test durations between 3 s and 1 min, the actual pressure (P_t) can be converted to the 1-min pressure (P_{60}) calculated as follows:

$$P_{60} = \left(\frac{7.97 + 1.53 \log t}{10.69} \right) P_t \quad (1)$$

where:

t = the duration of the test in s. For instance, the actual pressure in a 3-s test would be multiplied by 0.81 in order to be equivalent to the pressure at a test period of 1 min.

6. Procedure

6.1 Fill the containers with water or other low-density liquid, if such is used as the medium for applying pressure.

6.2 Use one of the following test procedures, depending upon the purpose of the test:

6.2.1 *Pass Test*—Apply the internal test pressure and hold it constant for the predetermined time of test. This pass test, usually at a pressure 50 % greater than that reasonably expected under actual conditions of use of the containers, is sufficient for routine testing of samples from continuous production in a manufacturer's plant.

6.2.2 *Progressive Test (to Predetermined Percent of Breakage)*—Where it may be desirable to conduct the test as a measurement test, repeat or continue the test described in 6.2.1, increasing the pressure stepwise by uniform increments (usually 172 or 335 kPa (25 or 50 psi) each step), until the predetermined percent of containers is broken.

6.2.3 *Progressive Test (Total)*—As an alternative to the progressive test described in 6.2.2, continue the progressive test until all of the containers break.

7. Report

7.1 Report the following information:

7.1.1 Report of method of sampling (see Practice C224),

7.1.2 Number of containers from each mold included in the sample,

7.1.3 Duration of the test, and

7.1.4 Results of the test. Use one of the following depending on the kind of test:

7.1.4.1 For the pass test in accordance with 6.2.1:

(1) Pressure used, and

(2) Number of containers that failed in the test.

7.1.4.2 For the progressive test in accordance with 6.2.2:

(1) Pressure at which first failure occurred and number of containers that failed at that pressure, and

(2) Pressure required to break the predetermined percent of the sample, interpolated to the nearest 34 kPa (5 psi).

7.1.4.3 For the progressive test in accordance with 6.2.3:

(1) Pressures used in the test and number of containers that failed at each pressure, and

(2) Average breaking pressure (corrected for the size of the pressure increment by subtracting one half of the increment; for example, 86 kPa (12.5 psi) for 172 kPa (25-psi) steps or increments).

TEST METHOD B—APPLICATION OF INTERNAL PRESSURE INCREASING AT PREDETERMINED CONSTANT RATE

8. Apparatus

8.1 The apparatus⁴ shall embody the following principles:

8.1.1 The bottles to be tested shall be held in such a manner that the bottle is not clamped, but is suspended from the bead of the finish.

8.1.2 There shall be a resilient sealing member which shall act with the sealing surface of the container to retain the pressurizing medium during the period of the test.

8.1.3 There shall be a means of applying fluid pressure increasing at a predetermined constant rate until the container fails or a predetermined level is reached. The rate of increase of pressure shall be reproducible to $\pm 2\%$. Applied fluid pressure levels shall be provided over the range from 0.34 MPa (50 psi) to at least 4.07 MPa (590 psi), determinable to the nearest 0.01 MPa (or nearest integral psi unit). The applied fluid pressure level shall be reproducible to within $\pm 1\%$ of full scale.

8.1.4 The apparatus shall include a means of indicating the pressure level at which the container failed or the maximum pressure reached during the test.

8.1.5 If desired, the apparatus may be equipped to read out the equivalent pressure values for an appropriate fixed-duration test rather than actual pressures reached in the constant rate tests. When this is done, the conversion factor to be incorporated in the apparatus shall be determined from actual pressure tests on appropriate samples of glass containers, and the apparatus shall clearly indicate that an equivalent pressure value is being used.

NOTE 2—For the apparatus mentioned in footnote 4, the relationship between the actual pressure (P_R) and the 1-min pressure (P_{60}) is as follows:

$$P_R = 1.38 P_{60} + 25.9 \quad (2)$$

9. Procedure

9.1 Fill the containers with water or other low-density liquid, if such is used as the medium for applying pressure.

9.2 Use one of the following test procedures, depending upon the purpose of the test:

9.2.1 *Pass Test*—Increase the internal test pressure at the predetermined constant rate until a predetermined level of pressure has been reached or exceeded. This pass test level, usually at a pressure 50 % greater than that reasonably expected under actual conditions of use of the containers, is sufficient for routine testing of samples from continuous production in a manufacturer's plant.

⁴ The Ramp Pressure Tester developed by American Glass Research, Inc., Butler, PA meets the requirements for this test method.