



Designation: **D3955—13** **D3955 – 20**

Standard Specification for Electrical Insulating Varnishes¹

This standard is issued under the fixed designation D3955; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification covers the tests and values for electrical insulating varnishes, as supplied, which are suitable for the impregnation and treatment of electrical coils and windings applied by dip process.

1.2 Varnishes, flexible or rigid, included in this specification are:

Grade DA—Air-dry

Grade DO—Organic solvent containing, baking,

Grade DM—Reactive diluent containing,

Grade DS—Silicone,

Grade DW—Water containing, and

Grade DT—Thixotropic.

1.3 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

NOTE 1—This specification resembles IEC 60455 in title only. The content is significantly different.

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

D93 Test Methods for Flash Point by Pensky-Martens Closed Cup Tester

D115 Test Methods for Testing Solvent Containing Varnishes Used for Electrical Insulation

D1711 Terminology Relating to Electrical Insulation

D2519 Test Method for Bond Strength of Electrical Insulating Varnishes by the Helical Coil Test

D3056 Test Method for Gel Time of Solventless Varnishes

D3145 Test Method for Thermal Endurance of Electrical Insulating Varnishes by Helical Coil Method

D3251 Test Method for Thermal Endurance Characteristics of Electrical Insulating Varnishes Applied Over Film-Insulated Magnet Wire

¹ This specification is under the jurisdiction of ASTM Committee D09 on Electrical and Electronic Insulating Materials and is the direct responsibility of Subcommittee D09.01 on Electrical Insulating Varnishes, Powders and Encapsulating Compounds Products.

Current edition approved April 1, 2013; Aug. 1, 2020. Published April 2013; September 2020. Originally approved in 1980. Last previous edition approved in 2009 as D3955-04 (2009) – 13. DOI: 10.1520/D3955-13; 10.1520/D3955-20.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard

[D3278 Test Methods for Flash Point of Liquids by Small Scale Closed-Cup Apparatus](#)
[D4733 Test Methods for Solventless Electrical Insulating Varnishes](#)
[D4880 Test Method for Salt Water Proofness of Insulating Varnishes Over Enamelled Magnet Wire](#)
[D5637 Test Method for Moisture Resistance of Electrical Insulating Varnishes](#)
[D5638 Test Method for Chemical Resistance of Electrical Insulating Varnishes](#)

2.2 *Military Specifications:*³

[MIL-PRF-17672 Hydraulic Fluid, Petroleum, Inhibited](#)
[MIL-PRF-17331 Lubricating Oil, Synthetic Base P-D-680, Dry Cleaning Solvent](#)
[MIL-D-16791 Detergent, General Purpose, \(Liquid, Non-Ionic\)](#)

2.3 *Other Standards:*³

[NEMA MW1000 Magnet Wire](#)
[IEC 60455 Resin Based Reactive Compounds Used for Electrical Insulation](#)

3. Terminology

3.1 *Definitions*—For definitions of terms used in this specification refer to Terminology [D1711](#).

3.1 *Definitions:*

3.1.1 For definitions of terms used in this specification refer to Terminology [D1711](#).

3.1.2 *varnish, electrical insulating, n*—a liquid resin system that is applied to and cured on electrical components providing electrical, mechanical, and environmental protection.

3.1.2.1 *Discussion*—

There are two types of electrical insulating varnish: solvent-containing and solventless. The solvent-containing varnish is a solution, dispersion, or emulsion of a polymer or mixture of polymers in a volatile, nonreactable liquid. The solventless type is a liquid resin system free of volatile, nonreactable solvents.

4. Flexible or Rigid Classification

4.1 This specification covers both flexible and rigid, solvent (including water) and solventless insulating varnishes.

5. Thermal Classification

5.1 The thermal classification of insulating varnishes covered by this specification is determined by using Test Methods [D3145](#) and [D3251](#) in conjunction with 18 AWG magnet wire conforming to MW 35-C and MW 16-C in accordance with NEMA MW1000. Determine the temperature index at ~~20 000 h~~ 20 000 h.

5.2 The thermal class is determined from the temperature index range as follows:

Thermal Class	Temperature Index Range
130	130.0 to 154.9
155	155.0 to 179.9
180	180.0 to 199.9
200	200.0 to 219.9
220	220.0 and above

6. General Specifications and Qualification Requirements

6.1 All varnishes supplied under this specification must conform to the limits outlined in [Table 1](#), and must meet, or exceed, all specification requirements.

6.2 A varnish supplied under this specification is to be manufactured from one specific formula and one specific process at one or more plants of the same company.

6.3 Changes involved solely with percent nonvolatile content or compatible solvent system, do not require requalification, if agreed upon between supplier and user.

³ Available from Global Engineering Documents, 15 Inverness Way, East Englewood, CO 80112-5704, <http://www.global.ihs.com>.

TABLE 1 Specification Requirements

Class	Grade Type of Magnet Wire Over which Varnish is Applied	ASTM Test Method	Minimum Thermal Class					
			DA	DO	DM	DS	DW	DT
130	MW 35-C and MW 16-C	D3251 and D3145	Class 130 for both wire types and both test methods					
155	MW 35-C and MW 16-C	D3251 and D3145	Class 155 for both wire types and both test methods					
180	MW 35-C and MW 16-C	D3251 and D3145	Class 180 for both wire types and both test methods					
200	MW 35-C and MW 16-C	D3251 and D3145	Class 200 for both wire types and both test methods					
220	MW 35-C and MW 16-C	D3251 and D3145	Class 220 for both wire types and both test methods					
Dielectric strength, V/mil, min, on metal panels		D115/D4733						
	Conditioned 24 h at 23°C and 50 % RH		1500	2000	1500	1800	2000	1500
	Conditioned 24 h at 23°C and 96 % RH		975	1500	1125	1350	1500	1125
	Conditioned 24 h at 23°C in deionized water		900	1500	1125	1350	1500	1125
Bond strength (minimum pounds) over 18 AWG MW 16-C or MW 35-C		D2519						
	Flexible at 77°F/300°F (25°C/150°C)		5/0	10/1	10/1	6/0.5	20/1	15/2
	Rigid at 77°F/300°F (25°C/150°C)		NA ^A	20/3	25/4	NA	25/3	30/5
Salt water proofness over MW 35-C or MW 16-C		D4880						
	Moisture resistance		100 ^B	100 ^B	100 ^B	100 ^B	100 ^B	100 ^B
	percent retained, min	D5637	50	50	50	50	50	50
Chemical resistance		D5638						
	minimum percent retained after 168 h at 73°F (23°C)							
	Hydraulic fluid ^C		50	50	50	50	50	50
	Lubricating oil ^D		50	50	50	50	50	50
	Cleaning fluid ^E		50	50	50	50	50	50
	Distilled water		50	50	50	50	50	50
	Detergent solution ^F		50	50	50	50	50	50
	Storage life, months min ^G		12	12	6	6	6	6
Viscosity (cps at 77°F (25°C))		D115/D4733	80–1200	100–1200	100–1300	80–240	100–1300	15 000 ^H 5000 ^I
Thixotropic index, min		D4733	NA	NA	NA	NA	NA	1.1
% Nonvolatile matter, min		D115	30	40	NA	40	35	NA
Variation in specific gravity/density (% of reported value)		D115/D4733	±1.0	±1.0	±1.0	±1.0	±1.0	±1.0
Build as received (mils, min)		D115/D4733	0.9	0.9	0.3	0.5	0.8	1.1
Flash point (°F (°C), min)		D93/D3278	73 (23) ^J	73 (23) ^J	200 (93) ^J	73 (23) ^J	194 (90) ^J	200 (93) ^J
Drying time (h at °F (°C)) max		D115	3 at 230 (110)	2 at 300 (150)	NA	6 at 390 (200)	2 at 300 (150)	NA
Variation in gel time (% of reported value)		D3056	NA	NA	±10.0	NA	NA	±10.0

^A Not applicable.

^B Passing is defined as 7 of 9 specimens still passing at specified time.

^C In accordance with MIL-PRF-17672.

^D In accordance with MIL-PRF-17331.

^E In accordance with P-D-680[1,1,2-trichloro-1,2,2-trifluoroethane]-Mil-PRF-680, Degreasing Solvent.

^F Detergent per MIL-D-16791, non-ionic detergent (1 lb per 2¼ gal water).

^G As warranted by the manufacturer.

^H Maximum at 2 r/min.

^I Maximum at 20 r/min.

^J Or as agreed to by supplier and user.

6.4 If any formula or process changes are desired after qualification approval has been granted, conduct the tests in **Table 1**, except for thermal class.

6.5 If varnishes from different suppliers are to be mixed or used in a common tank or container, determine their compatibility by Test Methods **D115**. They must be compatible, both in the liquid and solid state, with the varnish currently being used in the system.

6.6 Varnishes containing silicone in any portion, must not be mixed with non-silicone varnishes.

6.7 The qualification requirements of the varnish shall be as mutually agreed upon between supplier and user, with tests to be performed in accordance with the appropriate methods, and limits as shown in **Table 1**.