



Designation: ~~D2680–01 (Reapproved 2014)~~ D2680 – 20

Standard Specification for Acrylonitrile-Butadiene-Styrene (ABS) and Poly(Vinyl Chloride) (PVC) Composite Sewer Piping¹

This standard is issued under the fixed designation D2680; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. ~~Scope~~ Scope*

1.1 This specification covers thermoplastic composite pipe, fittings and a joining system for use in gravity flow, nonpressure sanitary sewer, and storm drain installations. The pipe and fittings are made of ABS or PVC plastic material. Recommended installation practices are referenced in [Appendix X1](#).

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 The following safety hazards caveat pertains only to the test method portion, Section ~~10.4.2~~₂ of this specification: *This standard does not purport to address all of the safety ~~problems, concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and health~~environmental practices and determine the applicability of regulatory limitations prior to use. ~~Specific precautionary information is given in 7.2.4.~~*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

[ASTM D2680-20](#)

<https://standards.iteh.ai/catalog/standards/sist/7a1a2b7-4add-4f0d-80ba-7f2f595417c5/astm-d2680-20>

2.1 *ASTM Standards*:²

[D618 Practice for Conditioning Plastics for Testing](#)

[D1084 Test Methods for Viscosity of Adhesives](#)

[D1600 Terminology for Abbreviated Terms Relating to Plastics](#)

[D1784 Classification System and Basis for Specification for Rigid Poly\(Vinyl Chloride\) \(PVC\) Compounds and Chlorinated Poly\(Vinyl Chloride\) \(CPVC\) Compounds](#)

[D2122 Test Method for Determining Dimensions of Thermoplastic Pipe and Fittings](#)

[D2152 Test Method for Adequacy of Fusion of Extruded Poly\(Vinyl Chloride\) \(PVC\) Pipe and Molded Fittings by Acetone Immersion](#)

[D2235 Specification for Solvent Cement for Acrylonitrile-Butadiene-Styrene \(ABS\) Plastic Pipe and Fittings](#)

[D2321 Practice for Underground Installation of Thermoplastic Pipe for Sewers and Other Gravity-Flow Applications](#)

[D2412 Test Method for Determination of External Loading Characteristics of Plastic Pipe by Parallel-Plate Loading](#)

[D2564 Specification for Solvent Cements for Poly\(Vinyl Chloride\) \(PVC\) Plastic Piping Systems](#)

[D3138 Specification for Solvent Cements for Transition Joints Between Acrylonitrile-Butadiene-Styrene \(ABS\) and Poly\(Vinyl](#)

¹ This specification is under the jurisdiction of ASTM Committee F17 on Plastic Piping Systems and is the direct responsibility of Subcommittee F17.62 on Sewer. Current edition approved Aug. 1, 2014; Aug. 1, 2020. Published November 2014; September 2020. Originally published as D2680 – 68 T. Last previous edition approved in 2009 as D2680–01(2009); –01(2014). DOI: ~~10.1520/D2680-01R14~~ 10.1520/D2680-20.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard

Chloride) (PVC) Non-Pressure Piping Components

D3212 Specification for Joints for Drain and Sewer Plastic Pipes Using Flexible Elastomeric Seals

D3965 Classification System and Basis for Specifications for Rigid Acrylonitrile-Butadiene-Styrene (ABS) Materials for Pipe and Fittings

D4396 Specification for Rigid Poly(Vinyl Chloride) (PVC) and Chlorinated Poly(Vinyl Chloride) (CPVC) Compounds for Plastic Pipe and Fittings Used in Nonpressure Applications

F402 Practice for Safe Handling of Solvent Cements, Primers, and Cleaners Used for Joining Thermoplastic Pipe and Fittings

F412 Terminology Relating to Plastic Piping Systems

F477 Specification for Elastomeric Seals (Gaskets) for Joining Plastic Pipe

F913 Specification for Thermoplastic Elastomeric Seals (Gaskets) for Joining Plastic Pipe

2.2 *Federal Standard:*

Fed. Std. No. 123 Marking for Shipment (Civil Agencies)³

2.3 *Military Standard:*

MIL-STD-129 Marking for Shipment and Storage³

3. Terminology

3.1 *Definitions:*

3.1.1 *General*—Definitions are in accordance with Terminology **F412** and abbreviations are in accordance with Terminology **D1600**, unless otherwise specified. The abbreviation for acrylonitrile-butadiene-styrene is ABS and the abbreviation for poly(vinyl chloride) is PVC.

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *acrylonitrile-butadiene-styrene (ABS)*—plastics containing polymers or blends of polymers, or both, in which the minimum butadiene content is 6 %; the minimum acrylonitrile content is 15 %; the minimum styrene or substituted styrene content, or both, is 15 %; and the maximum content of all other monomers is not more than 5 %, plus lubricants, stabilizers, and colorants.

3.2.2 *poly (vinyl chloride) (PVC)*—plastic compounds containing poly(vinyl chloride) homopolymer, and such additives as stabilizers, lubricants, processing aids, impact improvers, and colorants as needed to provide the required processing and toughness characteristics.

4. Classification

4.1 Pipe produced in accordance with this specification shall be classified as ABS composite pipe or PVC composite pipe based on plastic materials used in manufacture.

5. Materials and Manufacture

5.1 ABS composite pipe or PVC composite pipe shall consist of two concentric thermoplastic tubes integrally braced across the annulus. The resultant annular space is filled to provide continuous support between the inner and outer tubes.

5.2 *Compounds*—The ABS and PVC composite pipe and fittings shall be produced from the following compounds:

5.2.1 *ABS*—The pipe shall be made from a rigid ABS plastic and shall meet or exceed the requirements of Specification **D3965** for a minimum cell classification of 1-0-2-2-3. The fittings shall be made from ABS plastic and shall meet or exceed the requirements of Specification **D3965** for cell classifications of 1-0-2-2-3 or 4-2-2-2-2. Clean rework ABS, generated from the manufacturer's own pipe extrusion and fittings produced before filling the annulus as described in 5.3 may be used by the same manufacturer, provided that the pipe and fittings produced meet all the requirements of this specification.

5.2.2 *PVC*—The thermoplastic material shall be a rigid PVC plastic and shall meet or exceed the requirements of Specification **D1784**, for a minimum cell classification of 12454 or of Specification **D4396**, for a minimum cell classification of 11432. Homopolymer PVC compounds that have higher cell classifications, because one or more properties are superior to those of the specified compounds, are also acceptable. Clean rework PVC, generated from the manufacturer's own pipe and fittings production

³ Available from Standardization Documents Order Desk, DODSSP, Bldg. 4, Section D, DLA Document Services, Building 4/D, 700 Robbins Ave., Philadelphia, PA 19111-5098, <http://www.dodssp.daps.mil>—19111-5094, <http://quicksearch.dla.mil>.

produced before filling the annulus as described in 5.3 may be used by the same manufacturer provided that the pipe and fittings produced meet all the requirements of this specification.

5.3 The other component shall be portland cement-perlite concrete or other inert filler material exhibiting the same degree of performance, that essentially fills the truss annulus to form a composite pipe that meets the requirements of this specification.

5.4 *Gaskets*—Elastomeric seals (gaskets) shall comply with requirements described in Specifications F477 and F913.

NOTE 1—Gasket joints manufactured for PVC composite pipe only.

5.5 *Lubricants*—The lubricant used for the assembly of gasket joints shall have no detrimental effect on the gasket or on the pipe.

6. Performance Requirements

6.1 *Pipe Stiffness*—Pipe tested in accordance with 10.2 shall have a minimum pipe stiffness of 200 lb/in./in. (1380 kPa) at 5 % deflection.

6.2 *Pipe Deflection*—Pipe tested in accordance with 10.2 shall deflect a minimum of 7.5 % without rupture of inner or outer wall.

NOTE 2—The purpose of the quality control tests in 6.1 and 6.2 is to furnish test results for a consumer only upon his request at the time of order and prior to shipment from the point of manufacture.

6.3 *Acid Conditioning*—Pipe tested in accordance with 10.3 shall meet the requirements of 6.1 and 6.2.

NOTE 3—This test is intended only for use as a qualification test, not for use as a simulated service test nor a quality control test.

6.4 *Joint Tightness:*

6.4.1 *Solvent Cement Joints*—Pipe and fittings attached to the pipe shall show no signs of leakage when tested in accordance with 10.4.1 (See Note 3).

6.4.2 *Gasket Joints for PVC Composite Pipe*—Joints shall show no signs of leakage when tested in accordance with 10.4.2 (See Note 3).

6.5 *Extrusion Quality*—When tested in accordance with 10.5, PVC extruded pipe tubes shall not flake or disintegrate.

NOTE 4—This test is intended for use as a quality control test, not for use as a simulated service test.

7. Other Requirements

7.1 *Joints and Fittings* as shown in Fig. 1 and Fig. 2, shall be molded or fabricated from materials described in Section 5. Joints and fittings may be factory-attached to the pipe or furnished loose, at the option of the purchaser.




FIG. 1 Assembly of Joints




FIG. 2 Fittings (see Tables 5 and 6 for dimensions)

7.2 Solvent Cement Joints:

7.2.1 Solvent Cement Joint—In the solvent cement joint, the pipe spigot wedges into the tapered socket and the surfaces fuse together.

7.2.2 ABS Solvent Cement Joints—Primer for priming solvent cemented joints shall be MEK (methyl ethyl ketone) and the cement shall be MEK containing a minimum of 20 % by weight of dissolved ABS as described in 5.2.1. The cement viscosity when measured in accordance with Method D of Test Method D1084 at 70 to 75° F (21 to 23°C) with a No. 5 Zahn Cup, shall fall within a range of 60 to 80 s. The solids content of the cement shall be measured in accordance with Specification D2235.

7.2.3 *PVC Solvent Cement Joints*—The cement shall comply with Specification **D2564**, with the exception that the minimum resin content shall be 16 % and minimum viscosity shall be 3500 cP (3500 mPa·s).

7.2.4 *Transition Joints (ABS to PVC)*— Whenever a transition joint is to be assembled, the cement shall comply with Specification **D3138**. (**Warning**—Solvent cements for plastic pipe are made from flammable liquids and should be kept away from all sources of ignition. Good ventilation should be maintained to reduce fire hazard and to minimize breathing of solvent vapors. Avoid contact of cement with skin and eyes. Refer to Practice **F402** for additional information.)

NOTE 5—Unless otherwise specified, it is permissible to use transition joints in accordance with this specification and Specification **D3138**.

7.3 *Elastomeric (Gasket) Joints for PVC Composite Pipe:*

7.3.1 Elastomeric joints shall be designed so that when assembled, the gasket will be compressed in the joint to form a positive seal.

7.3.2 The joint shall be designed to avoid displacement of the gasket when assembled in accordance with the manufacturers’ recommendation.

7.3.3 The assembly of joints shall be in accordance with the manufacturers’ recommendation.

8. Dimensions

8.1 *Diameters and Thickness*—The pipe shall conform to the dimensions and tolerances shown in **Table 1** for ABS composite pipe, and **Table 2** for PVC composite pipe, when measured in accordance with **10.6.1** and **10.6.2**.

8.2 *Laying Length*—Pipe shall be furnished in standard 12½ ft (3.82 m) lengths with a tolerance of –1 in. (–25 mm) when measured in accordance **10.6.1**. There is no limit for plus variation. Other lengths may be provided, if agreed upon by the purchaser and the seller.

8.3 *Straightness*—Pipe intended to be straight shall have a maximum deviation from straightness of ¼ in./ft (4.85 mm/m) of length, when measured in accordance with **10.6.1**.

8.4 *End Squareness*—Pipe ends shall be cut square to the longitudinal axis as provided in **Table 3**, when measured in accordance with **10.6.3**.

TABLE 1 Pipe Dimensions for ABS Composite Pipe

Nominal Size, in.	Outside Diameter			Average Inside Diameter		Average Concentric Tube Thickness	
	Average	Tolerance	max	min	max	Inner, min	Outer, min
Inches							
8	9.41	+0.04 –0.03	9.51	7.75	7.90	0.060	0.035
10	11.75	+0.04 –0.04	11.87	9.75	9.88	0.068	0.038
12	14.07	+0.06 –0.05	14.22	11.75	11.83	0.079	0.048
15	17.62	+0.07 –0.07	17.80	14.75	14.80	0.096	0.059
Millimetres							
8	239	+1.0 –0.8	242	197	201	1.52	0.90
10	298	+1.2 –1.0	302	248	251	1.73	0.96
12	357	+1.5 –1.2	361	298	301	2.01	1.22
15	447	+1.8 –1.5	452	375	376	2.44	1.50

TABLE 2 Pipe Dimensions for PVC Composite Pipe

Nominal Size, in.	Outside Diameter			Average Inside Diameter			Average Concentric Tube Thickness	
	Average	Tolerance	max	min	max	Inner, min	Outer, min	
Inches								
8	9.41	+0.04 -0.03	9.51	7.75	7.90	0.050	0.030	
10	11.75	+0.04 -0.04	11.87	9.75	9.88	0.058	0.035	
12	14.07	+0.06 -0.05	14.22	11.75	11.83	0.067	0.041	
15	17.62	+0.07 -0.07	17.80	14.75	14.80	0.080	0.050	
Millimetres								
8	239	+1.0 -0.8	242	197	201	1.27	0.76	
10	298	+1.2 -1.0	302	248	251	1.47	0.89	
12	357	+1.5 -1.2	361	298	301	1.70	1.04	
15	447	+1.8 -1.5	452	375	376	2.03	1.27	

TABLE 3 End Squareness

Nominal Size, in.	Max Allowable Gap	
	in.	mm
8	0.25	6.4
10	0.33	8.4
12	0.41	10.4
15	0.50	12.8

8.5 *Joint Couplings*, shall conform to the dimensions shown in **Table 4**, when measured in accordance with **10.6.1**.

<https://standards.iteh.ai/catalog/standards/sist/7a1af2b7-4add-4f0d-80ba-7f2f595417c5/astm-d2680-20>

8.6 *Fittings*:

8.6.1 *Molded Fittings*—The wall thickness of the water way shall be no less than the respective minimum thickness listed in **Table 5**. The socket dimensions and respective wall thickness shall conform to **Table 4**. The dimensions and wall thicknesses shall be determined in accordance with **10.6.1**.

8.6.2 *Fabricated Fittings*—Fabricated fittings shall be considered satisfactory if made from pipe and molded fittings meeting the requirements of this specification.

8.6.3 The spur (lateral) socket shall be suitable for attaching the respective ABS or PVC solid wall pipe or adapters shall be furnished for attaching other types of pipes.

TABLE 4 Coupling and Fitting Socket Dimensions

Nominal Size, in.	Nominal Length		Min Inside Socket Diameter		Min Thickness at Socket Stop	
	in.	(mm)	in.	(mm)	in.	(mm)
4 ^A	1¼	(44)	4.20	(107)	0.165	(4.19)
6 ^A	2½	(64)	6.26	(159)	0.195	(4.95)
8	5½	(140)	9.36	(238)	0.180	(4.57)
10	6	(152)	11.69	(297)	0.190	(4.83)
12	6¾	(172)	14.00	(356)	0.220	(5.59)
15	8	(200)	17.54	(446)	0.225	(6.48)

^ASaddle stubs.

TABLE 5 Wall Thickness of Molded Fittings^A

Wall Thickness ^B	Min Wall Thickness, in. (mm) ^C			
	8 (203)	10 (254)	12 (305)	15 (381)
t_1	0.160 (4.06)	0.160 (4.06)	0.160 (4.06)	0.160 (4.06)
t_2	0.270 (6.86)	D	D	D
t_3	...	D	D	D
t_4	0.180 (4.57)	D	D	D

^ASocket dimensions of fittings are in Table 4.

^BSee Fig. 2.

^CThe wall thickness is a minimum value except that a $\pm 10\%$ variation resulting from core shift is allowable. In such a case, the average of two opposite wall thicknesses shall equal or exceed the value shown in the table.

^DFittings are fabricated.

9. Workmanship

9.1 The inner and outer surfaces of the pipe, joints, and fittings shall be homogeneous throughout and free from visible cracks, holes, foreign inclusions, and other injurious defects. The pipe, joints, and fittings shall be as uniform as commercially practicable in other physical properties.

10. Test Methods

10.1 Conditioning:

10.1.1 *Referee Testing*—When conditioning is required for referee tests, condition the specimens in accordance with Procedure A of Methods **D618** at $73.473 \pm 3.6^\circ\text{F}$ ($23 \pm 2^\circ\text{C}$) and $50 \pm 5\%$ relative humidity for not less than 40 h prior to test. Conduct tests under the same conditions of temperature and humidity, unless otherwise specified.

10.1.2 *Quality Control Testing*—Condition specimens for a minimum of 4 h in air or 1 h in water at $73.473 \pm 3^\circ\text{F}$ ($23 \pm 2^\circ\text{C}$). Test the specimens at $73.473 \pm 3^\circ\text{F}$ without regard to relative humidity.

10.1.3 *Test Conditions*—Conduct tests in the Standard Laboratory Atmosphere of $73.473 \pm 3.6^\circ\text{F}$ ($23 \pm 2^\circ\text{C}$) and $50 \pm 5\%$ relative humidity, unless otherwise specified in the test methods or in this specification. In cases of disagreement, the tolerances shall be $\pm 1.8^\circ\text{F}$ ($\pm 1^\circ\text{C}$) $\pm 2^\circ\text{F}$ ($\pm 1^\circ\text{C}$) and $\pm 2\%$ relative humidity.

<https://standards.iteh.ai/catalog/standards/sist/7a1a2b7-4add-4f0d-80ba-72f595417c5/astm-d2680-20>

TABLE 6 Minimum Laying Length Dimensions, in. (mm)

		Minimum Laying Length Dimensions, in. (mm)				
in.		deg	8 in. (203 mm)	10 in. (254 mm)	12 in. (305 mm)	15 in. (381 mm)
G ₁	4 stub	90	4 ⁷ / ₈ (123)	5 ⁷ / ₈ (149)	6 ⁹ / ₁₆ (167)	8 ⁷ / ₈ (225)
G ₁	6 stub	90	4 ⁹ / ₁₆ (106)	5 ⁹ / ₈ (142)	6 ⁵ / ₁₆ (160)	8 ⁵ / ₁₆ (211)
G ₂	4 stub	45	9 ⁵ / ₈ (244)	11 ¹⁹ / ₁₆ (303)	13 ³ / ₈ (346)	16 ³ / ₁₆ (411)
G ₂	6 stub	45	8 ⁷ / ₈ (225)	11 ¹¹ / ₁₆ (296)	13 ³ / ₈ (339)	15 ¹⁵ / ₁₆ (404)
G ₃		3	3 ⁵ / ₈ (9)	1 ¹ / ₈ (3)	3 ¹ / ₁₆ (4)	1 ¹ / ₄ (6)
G ₃		45	2 ¹ / ₄ (57)	12 (304)	12 (304)	12 (304)
G ₃		90	...	16 ¹ / ₄ (412)	16 ¹ / ₄ (412)	20 ⁷ / ₁₆ (519)
G ₄		90	6 ¹ / ₈ (155)	13 (330)	14 (355)	16 (406)
G ₄	6 stub	90	4 ⁷ / ₈ (123)
G ₅		90	4 ¹ / ₁₆ (103)	13 (330)	14 (355)	16 (406)
G ₅	6 stub	90	3 ⁷ / ₈ (79)
G ₆		45	11 ¹ / ₂ (292)	21 (533)	22 ⁷ / ₈ (581)	23 ¹ / ₂ (596)
G ₆	6 stub	45	8 ⁷ / ₈ (225)
G ₇		45	11 ¹ / ₂ (292)	21 (533)	22 ⁷ / ₈ (581)	28 ¹ / ₂ (723)
G ₇	6 stub	45	10 ³ / ₈ (263)
G ₈		45	1 ¹ / ₄ (31)
G ₈	6 stub	45	3 ⁵ / ₈ (9)
H ₁		45	9 (228)	12 (304)	12 (304)	12 (304)
H ₁		90	13 ¹ / ₄ (336)	16 ¹ / ₄ (412)	16 ¹ / ₄ (412)	20 ⁷ / ₁₆ (519)
H ₂		90	...	13 (330)	14 (355)	16 (406)
H ₃		45	...	9 (228)	10 ⁷ / ₈ (276)	12 ¹ / ₂ (318)
N ₁	6 stub ^A	...	1 ¹ / ₄ (6)
N ₁	4 stub ^A

^AReducing bushing is for 8 to 6 in. (203 to 152 mm) or 6 to 4 in. (152 to 102 mm). Reducers for other reductions are from 10 in. (254 mm), 12 in. (305 mm), or 15 in. (381 mm).