



Designation: **D8032—16** **D8032 – 20**

Standard Test Method for Acid Number of Terephthalic Acid by Color-Indicator Titration¹

This standard is issued under the fixed designation D8032; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

1. ~~Scope~~ Scope*

1.1 This test method covers the determination of acid number of terephthalic acid (TA) by color-indicator titration. Acid number of TA product is usually within 674 to 676 mg KOH/g.

1.2 In determining the conformance of the test results using this method, results shall be rounded off in accordance with the rounding-off method of Practice **E29**.

1.3 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate ~~safety~~ safety, health, and health ~~environmental~~ environmental practices and determine the applicability of regulatory limitations prior to use.*

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

D974 Test Method for Acid and Base Number by Color-Indicator Titration

D1193 Specification for Reagent Water

D4790 Terminology of Aromatic Hydrocarbons and Related Chemicals

D6809 Guide for Quality Control and Quality Assurance Procedures for Aromatic Hydrocarbons and Related Materials

E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

E177 Practice for Use of the Terms Precision and Bias in ASTM Test Methods

E300 Practice for Sampling Industrial Chemicals

E691 Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method

2.2 *Other Document:*³

OSHA Regulations, 29 CFR paragraphs 1910.1000 and 1910.1200

¹ This test method is under the jurisdiction of ASTM Committee **D16** on Aromatic Hydrocarbons-Aromatic, Industrial, Specialty and Related Chemicals and is the direct responsibility of Subcommittee **D16.02** on Oxygenated Aromatics.

Current edition approved ~~March 1, 2016~~ Aug. 1, 2020. Published ~~June 2016~~ September 2020. Originally approved in 2016. Last previous edition approved in 2016 as D8032 – 16. DOI: ~~10.1520/D8032-16.10.1520/D8032-20.~~

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from U.S. Government Printing Office, Superintendent of Documents, 732 N. Capitol St., NW, Washington, DC 20401-0001, <http://www.access.gpo.gov>.

*A Summary of Changes section appears at the end of this standard

3. Terminology

3.1 Definitions:

3.1.1 *acid number, n*—the quantity of base, expressed in milligrams of potassium hydroxide per gram of sample that is required to titrate a sample in a specified solvent to a specified end point.

4. Summary of Test Method

4.1 A TA sample is dissolved in dimethyl sulfoxide and titrated with standard sodium hydroxide solution to the end point indicated by the color change of the added phenolphthalein solution (colorless in acid and pink in base). The acid number is calculated as milligrams of KOH per gram of TA sample. Its theoretical value of TA sample is 675.5 mg KOH/g.

5. Significance and Use

5.1 An estimate of TA purity can be determined by titrating with KOH. As an index of TA purity, the acid number can be used as a guide in the quality control of TA production.

6. Apparatus

6.1 *Analytical Balance*, capable of weighing ± 0.0001 g.

6.2 *Burets*, 50-mL with 0.1-mL graduations.

7. Reagents

7.1 *Purity of Reagents*—Unless otherwise indicated, it is intended that all reagents shall conform to the reagent grade specification of the Analytical Reagents of the American Chemical Society,⁴ where such specifications are available. Other grades may be used, provided it is first ascertained that the reagent is of sufficient high purity to permit its use without lessening the performance or accuracy of the determination. Reagent chemicals shall be used for all tests.

7.2 *Purity of Water*—Unless otherwise indicated, references to water shall be understood to mean Type III of Specification **D1193**. Boil the water gently for 5 to 10 min to remove any CO₂ and cool the water to room temperature.

7.3 *Dimethyl Sulfoxide*—(~~Warning—Warning~~~~Flammable—Flammable~~ and harmful if inhaled, swallowed or absorbed through the skin.).

7.4 *Sodium Hydroxide Solution (0.5 M)*—Weigh 20 g of sodium hydroxide (NaOH) (~~Warning—Warning~~~~Highly—Highly~~ corrosive to all body tissue.) in a beaker. Add 100 mL water (boiling gently for 5 to 10 min and cooling to room temperature, free of CO₂) to dissolve and cool the solution. Then quantitatively transfer the solution into a 1000 mL volumetric flask and dilute to volume with the above water. The NaOH solution should be stored in a plastic bottle and stopper must be stressed.

NOTE 1—After standardization, the NaOH solution should not be stored in a glass container because it will be slowly neutralized from exposure to a glass container. It will also “cement” a glass stopper into a glass container.

7.5 *Ethanol*.

7.6 *Phenolphthalein Indicator Solution (1 g/L)*—Dissolve 0.1 g solid phenolphthalein in 100 mL ethanol.

7.7 *Potassium Hydrogen Phthalate*.

⁴ *Reagent Chemicals, American Chemical Society Specifications, ACS Reagent Chemicals, Specifications and Procedures for Reagents and Standard-Grade Reference Materials*, American Chemical Society, Washington, DC. For suggestions on the testing of reagents not listed by the American Chemical Society, see *Analar Standards for Laboratory Chemicals*, BDH Ltd., Poole, Dorset, U.K., and the *United States Pharmacopeia and National Formulary*, U.S. Pharmacopeial Convention, Inc. (USPC), Rockville, MD.

8. Hazards

8.1 Consult current federal regulations, supplier's Safety Data Sheets, and local regulations for all materials used in this test method.

9. Sampling, Test Specimens, and Test Units

9.1 Use only representative samples obtained as described in Practice E300, unless otherwise specified.

10. Standardization of Titrant

10.1 Place 10 to 20 g of primary standard potassium hydrogen phthalate in a weighing bottle and dry at 120°C for 2 h. Close the weighing bottle and cool in a desiccator.

10.2 Weigh, to the nearest 0.0001 g, 4.5 to 5.0 g of the dried potassium hydrogen phthalate and transfer to a 250-mL Erlenmeyer flask. Add 100 mL of CO₂-free water and stir gently to dissolve the sample.

10.3 Add 3 drops of phenolphthalein indicator solution and titrate with 0.5 M NaOH solution (7.4) until one drop of NaOH changes the color of the solution from colorless to pink.

10.4 Perform a blank titration by repeating the above steps without adding potassium hydrogen phthalate.

10.5 Calculate the molarity of the NaOH solution as follows:

$$C = \frac{m \times 1000}{M \times (V - V_0)} \quad (1)$$

where:

C = molarity of NaOH solution, mol/L,

V = NaOH solution required for titration of the potassium hydrogen phthalate (10.3), mL,

V_0 = NaOH solution required for titration of the potassium hydrogen phthalate (10.4), mL,

M = 204.23 g/mol, molar mass of the potassium hydrogen phthalate (7.7), and

m = mass of potassium hydrogen phthalate titrated, g.

11. Procedure

11.1 Weigh, to the nearest 0.0001 g, 0.8 to 1.5 g of TA sample, into a 250-mL flask, and add 20 mL of dimethyl sulfoxide with swirling to dissolve TA completely.

11.2 Add 20 mL of CO₂-free water, and 0.1 mL of the phenolphthalein indicator solution into the flask.

11.3 Titrate using the standard NaOH solution and swirl flask contents gently during titration to a 15-s pink end point. Record the amount of titrant required.

11.4 Perform a blank titration by repeating the above steps without adding the TA sample.

12. Calculation

12.1 Calculate the acid number as follows:

$$\text{Acid number, mg of KOH / g} = [(A - B) \times C \times M] / W \quad (2)$$

where:

A = NaOH solution required for titration of the TA sample (11.3), mL,

B = NaOH solution required for titration of the blank (11.4), mL,