



Designation: **B344 – 14 B344 – 20**

Standard Specification for Drawn or Rolled Nickel-Chromium and Nickel-Chromium- Iron Alloys for Electrical Heating Elements¹

This standard is issued under the fixed designation B344; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope

1.1 This specification covers annealed, drawn, or rolled shapes for electrical heating purposes, of alloys having the nominal compositions of 80 % nickel and 20 % chromium; 60 % nickel, 16 % chromium, and remainder iron; and 35 % nickel, 20 % chromium, and remainder iron; 38 % nickel, 21 % chromium, and remainder iron; and 35 % nickel, 20 % chromium remainder iron.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to become familiar with all hazards including those identified in the appropriate Safety Data Sheet (SDS) for this product/material as provided by the manufacturer, to establish appropriate safety, health, and environmental practices, and determine the applicability of regulatory limitations prior to use.

1.4 This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.

2. Referenced Documents

2.1 *ASTM Standards:*²

[A751 Test Methods, Practices, and Terminology for Chemical Analysis of Steel Products](#)

[B63 Test Method for Resistivity of Metallically Conducting Resistance and Contact Materials](#)

[B70 Test Method for Change of Resistance With Temperature of Metallic Materials for Electrical Heating](#)

[B76 Test Method for Accelerated Life of Nickel-Chromium and Nickel-Chromium-Iron Alloys for Electrical Heating](#)

3. Significance and Use

3.1 This specification on nickel-chromium and nickel-chromium-iron alloys contains the requirements for chemistry, electrical resistance, mechanical properties, and packaging.

¹ This specification is under the jurisdiction of ASTM Committee B02 on Nonferrous Metals and Alloys and is the direct responsibility of Subcommittee B02.10 on Thermostat Metals and Electrical Resistance Heating Materials.

Current edition approved Oct. 1, 2014; Oct. 1, 2020. Published October 2014; October 2020. Originally approved in 1959. Last previous edition approved in 2014 as B344B344 – 14. —11— DOI: 10.1520/B0344-14.10.1520/B0344-20.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

4. Requirements

4.1 The alloys shall conform to the requirements as to chemical composition prescribed in **Table 1**.

4.2 *Samples for Chemical Analysis*—Specimens for chemical analysis may be taken from either the melt or from a sample of finished wire that is representative of the lot.

4.2.1 The lot size for determining compliance with the requirements of this specification shall be one heat.

4.3 *Chemical Analysis*—The chemical analysis shall be made in accordance with Test Methods **A751**, or by other analytical methods approved by the purchaser.

4.4 Actual chemical analysis is not required for routine acceptance.

5. Physical Requirements

5.1 The material shall be thoroughly and uniformly annealed.

5.2 Wire shall conform to the following elongation requirements:

Size	Elongation in 10 in., min, %
0.0035 in. (0.0889 mm) (No. 39 Awg) and larger	20
0.0031 in. (0.0787 mm) to 0.002 in. (0.0508 mm) (Nos. 40 to 44 Awg)	10

5.3 Determination is not required for routine acceptance.

6. Nominal Resistivity

6.1 The nominal resistivity (**Note 1**) shall be the resistivity of the wire as quenched from a temperature above 1450°F (788°C). The numerical value of the nominal resistivity shall be as shown in **Table 2**.

<https://standards.iteh.ai/catalog/standards/sist/022fe941-07a2-4552-8e7c-40dad7706de5/astm-b344-20>

6.2 Determination is not required for routine acceptance.

NOTE 1—The characteristics of these alloys are such that the actual resistivity of annealed wire may be as much as 6 % higher than the nominal, depending on its method of manufacture.

7. Test for Resistivity

7.1 The resistivity shall be determined in accordance with Test Method **B63**.

TABLE 1 Chemical Requirements

Element	Composition, %			
	80 Nickel-20 Chromium Alloy UNS N06023	60 Nickel-16 Chromium Alloy UNS N06024	38 Nickel-21 Chromium Alloy UNS S35021	35 Nickel-20 Chromium Alloy UNS S35020
Nickel ^A	remainder	57 min	36 to 39	34 to 37
Chromium	19 to 21	14 to 18	20 to 23	18 to 21
Manganese	1.0 max	1.0 max	1.0 max	1.0 max
Carbon	0.15 max	0.15 max	0.12 max	0.15 max
Silicon	0.75 to 1.75	0.75 to 1.75	1.3 to 2.2	1.0 to 3.0
Sulfur	0.01 max	0.01 max	0.03 max	0.01 max
Iron	1.0 max	remainder	remainder	remainder
Phosphorus			0.03 max	
Copper			0.5 max	
Lanthanum			0.03 to 0.20	

^AQuantities of less than 1 % cobalt included shall be reported as nickel.

TABLE 2 Specific Resistance

Alloy	Specific Resistance	
80 Nickel-20 Chromium	650 Ω-cm/ft	1.081 μΩ-M
	510 Ω-mil ² /ft	1.081 μΩ-M
60 Nickel-16 Chromium	675 Ω-cm/ft	1.122 μΩ-M
	530 Ω-mil ² /ft	1.122 μΩ-M
38 Nickel-21 Chromium	638 Ω-cm ² /ft	1.06 μΩ-M
	500 Ω-mil ² /ft	1.06 μΩ-M
35 Nickel-20 Chromium	610 Ω-cm/ft	1.014 μΩ-M
	479 Ω-mil ² /ft	1.014 μΩ-M

TABLE 2 Specific Resistance

Alloy	Specific Resistance	
80 Nickel-20 Chromium (UNS N06023)	650 Ω-cm/ft	1.081 μΩ-M
	510 Ω-mil ² /ft	1.081 μΩ-M
60 Nickel-16 Chromium (UNS N06024)	675 Ω-cm/ft	1.122 μΩ-M
	530 Ω-mil ² /ft	1.122 μΩ-M
38 Nickel-21 Chromium (UNS S35021)	638 Ω-cm ² /ft	1.06 μΩ-M
	500 Ω-mil ² /ft	1.06 μΩ-M
35 Nickel-20 Chromium (UNS S35020)	610 Ω-cm/ft	1.014 μΩ-M
	479 Ω-mil ² /ft	1.014 μΩ-M

7.2 Determination is not required for routine acceptance.

8. Nominal Electrical Resistance for Unit Length

8.1 The nominal resistance per unit length for round wire shall be calculated from the nominal resistivity and the nominal cross-sectional area.

NOTE 2—When ribbon or flat wire is produced by rolling from round wire, the cross section departs from that of a true rectangle by an amount depending on the width-to-thickness ratio and the specific manufacturing practice. The conventional formula for computing ohms per foot and feet per pound is to consider the cross section as 17 % less than a true rectangle when width is more than 15 times the thickness and 6 % less than a true rectangle in other cases. This is not valid in view of modern rolling equipment and practices, but still is widely used as a basis of description. Ribbon actually is made to a specified resistance per foot, and no tolerance is specified for thickness. An alternative and a closer approximation would be that for ribbon rolled from round wire, the electrical resistance would be calculated on a cross 6 % less than a true rectangle.

9. Tolerance on Electrical Resistance per Unit Length

9.1 The actual resistance per unit length shall not vary from the nominal resistance by more than the amounts shown in **Table 3**.

NOTE 3—*Dimensional Tolerances*—Tolerances on dimensions are not specified since the material is used for resistance purposes in which the resistivity and the electrical resistance per unit length rather than the dimensions are of prime importance. The electrical resistance per unit length can be determined more accurately than the dimensions of very small sizes of wire or strip.

10. Resistance Change with Temperature

10.1 Nominal values for resistance change with temperature are contained in **Appendix X1**.

10.2 The change in resistance with change in temperature shall be measured in accordance with Test Method **B70**.

TABLE 3 Electrical Resistance Tolerance

	Tolerance, %
Round Wire:	
0.005-in. (0.127-mm) diameter and larger	±5
Finer than 0.005 in. to 0.002-in. (0.014-mm) diameter, incl	±8
Finer than 0.002-in. diameter	±10
Strip:	
Cold rolled	±5
Hot rolled	±8

11. Durability

11.1 When it is desired to determine the durability of the material at high temperatures, life tests shall be made in accordance with Test Method **B76**. Test results may be reported either in hours or in percentage of an accepted standard. The temperature of the life tests for the four alloys shall be as follows:

80 Nickel-20 Chromium Alloy (UNS N06023)	2175°F (1190°C)
60 Nickel-16 Chromium Alloy (UNS N06024)	2100°F (1150°C)
38 Nickel-21 Chromium Alloy (UNS S35021)	2050°F (1120°C)
35 Nickel-20 Chromium Alloy (UNS S35020)	2025°F (1105°C)

11.2 The life or durability value shall be the average of at least three simultaneous determinations each, on wire specimens of the material and on the reference standard. If any test result varies more than 10 % from the average of the three determinations, that group shall be discarded and the test repeated.

11.3 Determination is not required for routine acceptance.

12. Finish

12.1 The material shall be as uniform and free from surface defects such as splits, kinks, laminations, scale, and other irregularities as the best commercial practice will permit. The finish shall be either bright annealed or oxidized, as specified.

13. Packaging and Marking

13.1 Packaging shall be subject to agreement between the manufacturer and the purchaser.

13.2 The material as furnished under this specification shall be identified by the name or symbol and color code of the manufacturer and by melt number.

14. Precision and Bias

14.1 Precision and bias on chemistry, electrical resistance, and resistance change with temperature are contained in Test Methods **A751**, **B63**, and **B70**. The precision and bias on the test method for durability is contained in Test Method **B76**.

15. Keywords

15.1 flat wire; heating element; nickel chrome alloys; resistance alloy

APPENDIX

(Nonmandatory Information)

X1. BASIS FOR ESTABLISHMENT OF PERCENT CHANGE IN RESISTANCE WITH TEMPERATURE

X1.1 The conditions of test, wire or strip size, chemistry of heats, and the environment are so varied it is not possible to accurately specify the resistance change versus temperature for nickel-chromium and nickel-chromium-iron alloys.

X1.2 Since this information is of general value to those designing appliances, furnaces, or other apparatus, the data in **Table X1.1** is included for general guidance only. See also **Fig. X1.1**. The change in resistance values in this table were obtained using free coils of wire tested in accordance with Test Method **B70**.