



Designation: D2875 – 00 (Reapproved 2020)

# Standard Test Method for Insoluble Ash of Vegetable-Tanned Leather<sup>1</sup>

This standard is issued under the fixed designation D2875; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This test method covers the determination of the insoluble ash in all types of vegetable-tanned leathers. This test method does not apply to wet blue.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

## 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

D2617 Test Method for Total Ash in Leather

D2876 Test Method for Water-Soluble Matter of Vegetable-Tanned Leather

## 3. Summary of Test Method

3.1 The specimen from which the water-soluble matter has been removed is heated at  $600 \pm 25^\circ\text{C}$  until carbon is removed

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee D31 on Leather and is the direct responsibility of Subcommittee D31.01 on Vegetable Leather. This test method was developed in cooperation with the American Leather Chemists Assn.

Current edition approved Dec. 1, 2020. Published December 2020. Originally approved in 1970. Last previous edition approved in 2016 as D2875 – 00 (2016). DOI: 10.1520/D2875-00R20.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

and constant weight is attained. The weighed residual matter is termed "insoluble ash" and is calculated as a percentage of the original sample.

## 4. Significance and Use

4.1 This test method gives the amount of ash remaining in the specimen after water extraction to remove water solubles from the leather in accordance with Test Method D2876. The insoluble ash is used in calculating the combined tannin because it is part of the tanned fiber structure that does not leach from the leather during water extraction.

## 5. Apparatus

5.1 *Crucible*, porcelain or platinum, large enough to hold the leather specimen.

5.2 *Electric Muffle Furnace*, with temperature controller and pyrometer, capable of maintaining a temperature of  $600 \pm 25^\circ\text{C}$ .

## 6. Test Specimen

6.1 The specimen shall consist of the 5-g leather sample remaining after water extraction as directed in Test Method D2876. Any deviation from this sample size should be included with the analytical results.

## 7. Procedure

7.1 Remove the specimen quantitatively from the extraction tube, dry at room temperature, transfer to the crucible, place in a cold muffle furnace, and ash at  $600 \pm 25^\circ\text{C}$  until the crucible and contents have reached constant weight as directed in Test Method D2617. Remove the crucible to a desiccator, cool, and weigh.

## 8. Calculation

8.1 Calculate the percentage of insoluble ash in the leather as follows:

$$\text{Insoluble ash, \%} = [(W_3 - W_2)/W_1] \times 100 \quad (1)$$

where:

$W_1$  = weight of specimen (15 g),

$W_2$  = weight of the crucible, and  
 $W_3$  = weight of the crucible plus ash.

## 9. Precision and Bias<sup>3</sup>

9.1 The precision of this test method is limited by the lack of homogeneity of the sample in a complex material such as leather. It will also vary with the insoluble ash content.

9.1.1 At the 95 % confidence level, duplicate determinations by the same operator should not differ by more than 0.1 % insoluble ash.

---

<sup>3</sup> Supporting data have been filed at ASTM International Headquarters and may be obtained by requesting Research Report RR:D31-1000.

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/*

9.1.2 At the 95 % confidence level, the average of duplicate determinations in each of two laboratories by different operators should not differ by more than 0.1 % insoluble ash.

9.2 Inasmuch as all leathers contain an unknown amount of natural or inherent ash, no meaningful statement can be made with respect to bias.

## 10. Keywords

10.1 ash content; insoluble ash; leather; vegetable tanned leather

iteh Standards  
(<https://standards.iteh.ai>)  
Document Preview

[ASTM D2875-00\(2020\)](https://standards.iteh.ai/catalog/standards/sist/b954d0ac-50e9-4161-8d69-dd92d4172d49/astm-d2875-002020)

<https://standards.iteh.ai/catalog/standards/sist/b954d0ac-50e9-4161-8d69-dd92d4172d49/astm-d2875-002020>