



Designation: B 434 – 00

Standard Specification for Nickel-Molybdenum-Chromium-Iron Alloys (UNS N10003, UNS N10242)* Plate, Sheet, and Strip¹

This standard is issued under the fixed designation B 434; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification² covers nickel-molybdenum-chromium-iron alloys (UNS N10003 and UNS N10242)* plate, sheet, and strip for use in general corrosive service.

1.2 The following products are covered under this specification:

1.2.1 *Sheet and Strip*—Hot or cold rolled, annealed, and descaled unless annealing is performed in an atmosphere yielding a bright finish.

1.2.2 *Plate*—Hot rolled, annealed, and descaled.

1.3 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are for information only.

2. Referenced Documents

2.1 *ASTM Standards*:

B 880 Specification for General Requirements for Chemical Check Analysis Limits for Nickel, Nickel Alloys and Cobalt Alloys³

E 8 Test Methods for Tension Testing of Metallic Materials⁴

E 29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications⁵

E 112 Test Methods for Determining the Average Grain Size⁴

E 1473 Test Methods for Chemical Analysis of Nickel, Cobalt, and High-Temperature Alloys⁶

3. Terminology

3.1 *Definitions of Terms Specific to This Standard*:

¹ This specification is under the jurisdiction of ASTM Committee B02 on Nonferrous Metals and Alloys and is the direct responsibility of Subcommittee B02.07 on Refined Nickel and Cobalt and Their Alloys.

Current edition approved May 10, 2000. Published June 2000. Originally published as B 434 – 66 T. Last previous edition B 434 – 95a.

² For ASME Boiler and Pressure Vessel Code applications see related Specification SB-434 in section II of that Code.

* New designation established in accordance with ASTM E527 and SAE J1086, Recommended Practice for Numbering Metals and Alloys (UNS).

³ *Annual Book of ASTM Standards*, Vol 02.04.

⁴ *Annual Book of ASTM Standards*, Vol 03.01.

⁵ *Annual Book of ASTM Standards*, Vol 14.02.

⁶ *Annual Book of ASTM Standards*, Vol 03.06.

3.1.1 *plate*—material $\frac{3}{16}$ in. (4.76 mm) and over in thickness.

3.1.2 *sheet and strip*—material under $\frac{3}{16}$ in. (4.76 mm) in thickness.

4. Ordering Information

4.1 It is the responsibility of the purchaser to specify all requirements that are necessary for the safe and satisfactory performance of material ordered under this specification. Examples of such requirements include but are not limited to the following:

4.1.1 *Dimensions*—Thickness (in decimals of an inch), width, and length (inch or fraction of an inch),

4.1.2 *Certification*—State if certification or a report of test results is required (Section 15),

4.1.3 *Purchase Inspection*—State which tests or inspections are to be witnessed (Section 13), and

4.1.4 *Samples for Product (Check) Analysis*—State whether samples shall be furnished (9.2.2).

5. Chemical Composition

5.1 The material shall conform to the requirements as to chemical composition prescribed in Table 1.

5.2 If a product (check) analysis is made by the purchaser, the material shall conform to the requirements specified in Table 1 subject to the permissible tolerances in B 880.

6. Mechanical Properties and Other Requirements

6.1 *Tensile Properties*—The material shall conform to the room temperature tensile properties prescribed in Table 2.

6.2 *Grain Size for Sheet and Strip*—Sheet and strip shall conform to the grain size requirements given in Table 3.

7. Dimensions and Permissible Variations

7.1 *Weight*—For calculation of mass or weight, the following densities shall be used:

Alloy	lb/in ³	g/cm ³
N10003	0.317	8.78
N10242	0.327	9.05

7.2 *Thickness*:

7.2.1 *Plate*—The permissible variations in thickness of plate shall be as prescribed in Table 4.

TABLE 1 Chemical Requirements

Element	Composition, %	
	UNS N10242	UNS N10003
Chromium	7.0-9.0	6.0-8.0
Iron, max	2.0	5.0
Carbon	0.03 max	0.04-0.08
Silicon, max	0.80	1.00
Cobalt, max	1.00	0.20
Manganese, max	0.80	1.00
Tungsten, max	...	0.50
Vanadium, max	...	0.50
Molybdenum	24.0-26.0	15.0-18.0
Phosphorus, max	0.030	0.015
Sulfur, max	0.015	0.020
Aluminum plus titanium, max	...	0.50
Copper, max	0.50	0.35
Boron, max	0.006	0.010
Nickel	remainder	remainder
Aluminum, max	0.50	...

TABLE 2 Mechanical Properties for Plate and Sheet

UNS	Tensile Strength, min, ksi (MPa)	Yield Strength (0.2 % Offset), min, ksi (MPa)	Elongation in 2 in. (50.8 mm) or 4D ^A min, %
N10003	100 (690)	40 (280)	40
N10242	105 (725)	45 (310)	40

^AD refers to the diameter of the tension specimen.

TABLE 3 Grain Size for Annealed Sheets

Thickness, in. (mm)	ASTM Micrograin Size Number, max	Average Grain Diameter, max, in (mm)
0.125 (3.175) and under	3.0	0.0050 (0.127)
Over 0.125 (3.175)	1.5	0.0084 (0.214)

TABLE 4 Permissible Variations in Thickness of Plate^A

Specified Thickness, in. (mm)	Permissible Variations in Thickness, in. (mm) ^{BC}	
	Plus	Minus
3/16 to 7/32 (4.762 to 5.556), incl	0.021 (0.53)	0.010 (0.25)
Over 7/32 to 1/4 (5.556 to 6.350), incl	0.024 (0.61)	0.010 (0.25)
Over 1/4 to 3/8 (6.350 to 9.525), incl	0.027 (0.69)	0.010 (0.25)
Over 3/8 to 1/2 (9.525 to 12.70), incl	0.030 (0.76)	0.010 (0.25)
Over 1/2 to 5/8 (12.70 to 15.88), incl	0.035 (0.89)	0.010 (0.25)
Over 5/8 to 3/4 (15.88 to 19.05), incl	0.040 (1.02)	0.010 (0.25)
Over 3/4 to 7/8 (19.05 to 22.25), incl	0.045 (1.14)	0.010 (0.25)
Over 7/8 to 1 (22.25 to 25.4), incl	0.050 (1.27)	0.010 (0.25)
Over 1 to 2 1/2 (25.4 to 63.5), incl	5 ^D	0.010 (0.25)

^AApplicable to plate 48 in. (1.22 m) and under in width.

^BMeasured 3/16 in. (9.525 mm) or more from any edge.

^CBuffing or grinding for removal of light surface imperfections shall be permitted. The depth of such buffed or ground areas shall not exceed the minimum tolerance thickness.

^DExpressed as percentage of thickness.

7.2.2 Sheet and Strip—The permissible variations in thickness of sheet and strip shall be as prescribed in Table 5. The thickness shall be measured with the micrometer spindle 3/8 in. (9.525 mm) or more from any edge for material 1 in. (25.4 mm) or over in width and at any place on material under 1 in. in width.

7.3 Width:

7.3.1 Plate—The permissible variations in width of rectangular plates shall be as prescribed in Table 6.

7.3.2 Sheet and Strip—The permissible variations in width for sheet and strip shall be as prescribed in Table 7.

TABLE 5 Permissible Variations in Thickness of Sheet^A and Strip

Specified Thickness, in. (mm)	Permissible Variations in Thickness, in ^{BC} (mm) (All Widths)	
	Plus	Minus
0.020 to 0.034 (0.51 to 0.86), incl	0.004 (0.10)	0.004 (0.10)
Over 0.034 to 0.056 (0.86 to 1.42), incl	0.005 (0.13)	0.005 (0.13)
Over 0.056 to 0.070 (1.42 to 1.78), incl	0.006 (0.15)	0.006 (0.15)
Over 0.070 to 0.078 (1.78 to 1.98), incl	0.007 (0.18)	0.007 (0.18)
Over 0.078 to 0.093 (1.98 to 2.36), incl	0.008 (0.20)	0.008 (0.20)
Over 0.093 to 0.109 (2.36 to 2.77), incl	0.009 (0.23)	0.009 (0.23)
Over 0.109 to 0.125 (2.77 to 3.18), incl	0.010 (0.25)	0.010 (0.25)
Over 0.125 to 0.140 (3.18 to 3.56), incl	0.013 (0.33)	0.010 (0.25)
Over 0.140 to 0.171 (3.56 to 4.34), incl	0.016 (0.41)	0.010 (0.25)
Over 0.171 to 0.187 (4.34 to 4.5), incl	0.018 (0.46)	0.010 (0.25)

^AApplicable to sheet 48 in. (1.22 m) and under in width.

^BMeasured 3/16 in. (9.525 mm) or more from any edge.

^CBuffing for removal of light surface imperfections shall be permitted. The depth of such buffed areas shall not exceed the permissible minus variation.

TABLE 6 Permissible Variations in Width and Length of Sheared or Abrasive Cut Rectangular Plate

Specified Thickness	Permissible Variations in Widths and Lengths for Dimensions Given, in. (mm)			
	Up to 30 (760), incl		Over 30 (760)	
	Plus	Minus	Plus	Minus
	Inches			
<i>Sheared</i>				
3/16 to 5/16, excl	3/16	1/8	1/4	1/8
5/16 to 1/2, incl	1/4	1/8	3/8	1/8
<i>Abrasive cut</i>				
3/16 to 1 1/2, incl	1/16	1/16	1/16	1/16
Over 1 1/2 to 2 1/2, incl	1/8	1/8	1/8	1/8
	Millimetres			
<i>Sheared</i>				
4.76 to 7.94, excl	4.76	3.18	6.35	3.18
7.94 to 12.70, incl	6.35	3.18	9.52	3.18
<i>Abrasive cut</i>				
4.76 to 38.1, incl	1.59	1.59	1.59	1.59
Over 38.1 to 63.5, incl	3.18	3.18	3.18	3.18

7.4 Length:

7.4.1 Plate—Permissible variations in the length of rectangular plate shall be as prescribed in Table 6.

7.4.2 Sheet and Strip—Sheet and strip may be ordered to cut lengths, in which case a variation of 1/8 in. (3.175 mm) over the specified length shall be permitted, with a 0 minus tolerance.

7.5 Straightness:

7.5.1 The edgewise curvature (depth of chord) of flat sheet, strip, and plate shall not exceed the product of 0.05 in. multiplied by the length in feet (0.04 mm) multiplied by the length in centimetres.

7.5.2 Straightness for coiled strip is subject to agreement between the manufacturer and the purchaser.

7.6 Squareness (Sheet)—For sheets of all thicknesses and widths of 6 in. (152.4 mm) or more, the angle between adjacent sides shall be 90 ± 0.15 deg (1/16 in. in 24 in. or 2.6 mm/m).