



Edition 2.0 2023-09 REDLINE VERSION

INTERNATIONAL STANDARD



Electrolyte and water for vented lead acid accumulators – Part 1: Requirements for electrolyte

Document Preview

IEC 62877-1:2023

https://standards.iteh.ai/catalog/standards/iec/4d26b99c-fd19-4e28-857d-e12bb30785ff/iec-62877-1-2023





THIS PUBLICATION IS COPYRIGHT PROTECTED Copyright © 2023 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

IEC Secretariat 3, rue de Varembé CH-1211 Geneva 20 Switzerland

Tel.: +41 22 919 02 11 info@iec.ch www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigendum or an amendment might have been published.

IEC publications search - webstore.iec.ch/advsearchform

The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee, ...). It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - webstore.iec.ch/justpublished Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and once a month by email.

IEC Customer Service Centre - webstore.iec.ch/csc If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: sales@iec.ch.

IEC Products & Services Portal - products.iec.ch

Discover our powerful search engine and read freely all the publications previews. With a subscription you will always have access to up to date content tailored to your needs.

Electropedia - www.electropedia.org

The world's leading online dictionary on electrotechnology, containing more than 22 300 terminological entries in English and French, with equivalent terms in 19 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.







Edition 2.0 2023-09 REDLINE VERSION

INTERNATIONAL STANDARD



Electrolyte and water for vented lead acid accumulators – Part 1: Requirements for electrolyte Document Preview

IEC 62877-1:2023

https://standards.iteh.ai/catalog/standards/iec/4d26b99c-fd19-4e28-857d-e12bb30785ff/iec-62877-1-2023

INTERNATIONAL ELECTROTECHNICAL COMMISSION

ICS 29.220.20

ISBN 978-2-8322-7550-4

Warning! Make sure that you obtained this publication from an authorized distributor.

CONTENTS

F	OREWO)RD	3		
1	Scop	be	5		
2	2 Normative references				
3	3 Terms and definitions				
4	4 Preparation of electrolyte for lead acid-accumulators batteries				
5	Phys	sical properties of diluted sulphuric acid as electrolyte	8		
	5.1	Dependence of sulphuric acid electrolyte density on temperature	8		
	5.2	Relationship of acid electrolyte density on at 25 °C with the content of sulphuric acid at 25 °C	9		
	5.3	Electrolyte density compared in relation to the state of discharge	10		
6	Req	uirements for sulphuric acid used as electrolyte	10		
	6.1	Impurities of sulphuric acid-of higher at high concentration-degrees	10		
	6.2	Impurities-of limits of sulphuric acid electrolyte for first filling-acid	10		
	6.3	Impurities of operating limits for sulphuric acid electrolyte in operation	11		
7	7 Storage of electrolyte				
8 Remedy in the event of damage due to the electrolyte					
Bi	Bibliography				

Table 1 – Correction of density from measuring temperature to reference/specified temperature factor to convert the acid electrolyte density found at the measuring temperature to that at the specified reference temperature 9
Table 2 – Acid electrolyte density at 25 °C versus percentage of sulphuric acid at 25 °C
Table 3 – Maximum allowed impurities of in diluted sulphuric acid in the density range $d_n \le 1,30$ kg/l when used as filling electrolyte for lead acid batteries in the density
range ≤ 1,30 kg/l catalog/standards/iec/4d26b99c-fd19-4e28-857d-e12bb30785fl/iec-62877-11102 Table 4 – Maximum allowed impurity of diluted acid as operating electrolyte for lead- acid batteries in the density range ≤ 1,30 kg/l impurities in diluted sulphuric acid in the
density range $d_n \le 1,30$ kg/l when this acid is acting as the operating electrolyte in lead acid batteries

INTERNATIONAL ELECTROTECHNICAL COMMISSION

ELECTROLYTE AND WATER FOR VENTED LEAD ACID ACCUMULATORS –

Part 1: Requirements for electrolyte

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
 - 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
 - Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

This redline version of the official IEC Standard allows the user to identify the changes made to the previous edition IEC 62877-1:2016. A vertical bar appears in the margin wherever a change has been made. Additions are in green text, deletions are in strikethrough red text.

IEC 62877-1 has been prepared by IEC technical committee 21: Secondary cells and batteries. It is an International Standard.

This second edition cancels and replaces the first edition published in 2016. This edition constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

a) Addition of the concentration values of halogens in Table 4.

The text of this International Standard is based on the following documents:

Draft	Report on voting
21/1169/FDIS	21/1172/RVD

Full information on the voting for its approval can be found in the report on voting indicated in the above table.

The language used for the development of this International Standard is English.

This document was drafted in accordance with ISO/IEC Directives, Part 2, and developed in accordance with ISO/IEC Directives, Part 1 and ISO/IEC Directives, IEC Supplement, available at www.iec.ch/members_experts/refdocs. The main document types developed by IEC are described in greater detail at www.iec.ch/publications.

A list of all parts of the IEC 62877 series can be found, under the general title *Electrolyte and* water for vented lead acid accumulators, on the IEC website.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under webstore.iec.ch in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

ELECTROLYTE AND WATER FOR VENTED LEAD ACID ACCUMULATORS –

Part 1: Requirements for electrolyte

1 Scope

This part of IEC 62877 applies to electrolytes and their components used for filling vented lead acid batteries, for example with dry-charged cells or batteries, and for electrolyte replenishment, replacement or electrolyte density adjustment of batteries in operation. This document defines the composition, purity and properties of electrolyte, for application where specific instructions from the battery manufacturer are not available.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 62877-2, Electrolyte and water for vented lead acid accumulators – Part 2: Requirements for water

3 Terms and definitions OCUMENT Preview

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- IEC Electropedia: available at https://www.electropedia.org/
- ISO Online browsing platform: available at https://www.iso.org/obp

3.1

lead dioxide lead battery

lead acid battery

secondary battery with an aqueous electrolyte based on dilute sulphuric acid, a positive electrode of lead dioxide and a negative electrode of lead

[SOURCE: IEC 60050-482:2004, 482-05-01, modified – Note 1 deleted and the term "lead acid battery" added.]

3.2 electrolyte diluted sulfuric acid (H₂SO₄) for lead-acid accumulators

<of a lead dioxide lead battery> dilute solution of sulphuric acid (H_2SO_4) in purified water

Note 1 to entry: The electrolyte is prepared by mixing concentrated sulphuric acid or sulphuric acid with high density of d > 1,30 kg/l and purified water to achieve the density values specified by the battery manufacturer or specified in standards related to the type and battery design in question for a defined state of charge. Its purity meets the requirements laid down in Table 3.

Note 2 to entry: Concentrated sulphuric acid is a colourless and highly corrosive and etching liquid with a density $\frac{1,84 \text{ kg/l}}{1,82 \text{ kg/l}}$ d > 1,82 kg/l.

3.3

water

<for a lead dioxide lead battery> purified water (H_2O) used for the preparation of electrolyte for batteries and for the replacement (topping up) of water loss in the operating electrolyte due to decomposition of water by overcharge and evaporation

Note 1 to entry: The requirements for purified water are specified in IEC 62877-2.

3.4

filling electrolyte

<of a lead dioxide lead battery> diluted sulphuric acid used for the first filling of dry-charged
batteries or for the replenishment, density adjustment or replacement of contaminated operating
electrolyte

3.5

first filling

<of a lead dioxide lead battery> original filling of a dry-charged battery carried out by the battery manufacturer or the user in accordance with the applicable manufacturer's instructions

3.6

operating electrolyte

<of a lead dioxide lead battery> electrolyte present in the battery following-the first electrolyte
filling and first use in the application

Note 1 to entry: The density values and the degree of purity of the operating electrolyte may can deviate from the values of the filling electrolyte due to impurity input from replenishment by water and to elution electrolysis, evaporation, introduction of impurities with the replacement water and leaching from e.g. separators, active material and electrode grids.

3.7

electrolyte density density

IEC 62877-1:2023

<of a battery electrolyte> value for the mass per unit volume expressed in kg/l

Note 1 to entry: The density varies with the battery's state of charge, the electrolyte volume variation due to water loss and the temperature.

Note 2 to entry: The density value is not to be confounded with that of specific gravity (SG). Specific gravity or relative density is the ratio of the density of a substance e.g., the electrolyte, to the density of a given reference material e.g., water, and is dimensionless.

3.8

specified density

density of the battery to be stated by the battery manufacturer valid at the maximum electrolyte level (see 3.10) at full state of charge of the battery at the reference temperature

Note 1 to entry: It is related to the application and design of the battery.

<of a battery electrolyte> density of the electrolyte of the battery declared by the manufacturer when being at the maximum upper electrolyte level, at a state of full charge and at the reference temperature

Note 1 to entry: The value is related to the design and application of the battery.

3.9

reference temperature for analytical results

reference temperature for analytical results of electrolyte impurities which is 25 °C ± 1 °C

Note 1 to entry: Density values measured at temperatures deviating from this reference temperature are adjusted accordingly.

IEC 62877-1:2023 RLV © IEC 2023 - 7 -

reference temperature

<for analytical results> temperature of the substance for which the analysis results are applicable

Note 1 to entry: Electrolyte density values measured at temperatures deviating from the reference temperature of 25 °C, are adjusted accordingly.

3.10

measurement of the electrolyte density

measurement is carried out by densimeters, in which areometers (hydrometers) are used, or by electronic devices based on e.g. on ultrasonic measurements

Note 1 to entry: The accuracy of the instrument is better than ± 0,001 kg/l.

density measurement

<of the electrolyte> determination of the mass per unit volume of the electrolyte with appropriate tools such as aerometers, hydrometers, diffractometers or vibration-type densitometers

Note 1 to entry: The accuracy of such instruments is typically ± 0,001 kg/l.

3.11

electrolyte level

position of the electrolyte surface in the cell/battery, where the recommended tidal movements are indicated by maximum and minimum electrolyte level marks to assist in water replenishment

Note 1 to entry: Water replenishment should take place in a fully charged state to the upper limit, to avoid over topping and electrolyte loss.

position of the electrolyte surface in the cell during operation

Note 1 to entry: The recommended level heights are indicated by the maximum and minimum electrolyte level marks on the cell or filling plug.

Note 2 to entry: Level adjustments such as water replenishment are carried out only when the cell reaches, under charge current flow and gas evolution, a fully charged state so as to avoid spillage due to overflowing electrolyte. IFC 62877-12023

ttp 3.12 ndards iteh ai/catalog/standards/iec/4d26b99c-fd19-4e28-857d-e12bb30785ff/iec-62877-1-2023 reference temperature

value specified by the battery manufacturer for the indication of properties, such as the nominal electrolyte density, the maximum electrolyte level and the nominal capacity of the battery

Note 1 to entry: The value of the nominal temperature for the indication of parameters may differ depending on the battery type and application.

<for specified values> temperature at which properties, such as the electrolyte density, the maximum electrolyte level and the capacity of the battery are specified by the battery manufacturer

Note 1 to entry: The value of the reference temperature for the indication of parameters can differ depending on battery type and application.

3.13

electrolyte additives

compounds which, added to the electrolyte, improve certain properties of the accumulator

Note 1 to entry: They shall be specified by the manufacturer. Other additives, not specified or not approved by the battery manufacturer, should not be used as they may cause damage to the battery and thus endanger the functional reliability.

Note 2 to entry: Examples of electrolyte additives are alkaline metal sulfates.

additive

<to the electrolyte> compound which, added deliberately to the electrolyte, modifies certain properties of the cell

Note 1 to entry: Additives and their level are specified by the battery manufacturer. Non-specified additives can result in damages to the cell and voiding the terms of warranty.

Note 2 to entry: Examples of electrolyte additives are alkaline metal sulphates or phosphoric acid.

3.14

impurity impurities from the electrolyte in practical use may cause damage to the battery and reduce its performance

Note 1 to entry: The type and maximum permissible quantity of impurities are specified in Tables 3 and 4. constituent in the electrolyte impairing the performance and life of a cell

Note 1 to entry: The type and maximum permissible quantity of impurities are specified in Table 3 and Table 4.

4 Preparation of electrolyte for lead acid accumulators batteries

The electrolyte is prepared from sulfuric acid of high concentration by pouring it into purified water.

As concentrated and diluted sulfuric acid has a highly etching effect on human skin and corrosive effect on clothes and many materials, and therefore the electrolyte shall be prepared by the battery manufacturer or skilled personnel only.

NOTE The mixing of sulphuric acid of high concentrations with water releases a high amount of heat. To avoid sudden splashing of hot acid, always pour acid into water, never the opposite. Pay attention to the safety data sheets.

The electrolyte shall be prepared from sulphuric acid of high concentration by pouring it into purified water and not the reverse. Purified water as specified in IEC 62877-2 shall be used.

Concentrated and diluted sulphuric acid has a highly irritating and burning effect on skin and a corrosive effect on clothes and many materials. The electrolyte shall be prepared by the battery manufacturer or by skilled personnel only. Adequate personal protection equipment such as goggles, face shields, rubber gloves, aprons and similar shall be used.

http

The mixing of sulphuric acid of high concentrations with water releases a great amount of heat. To avoid splashing of hot acid, sulphuric acid shall be always poured into water and not the reverse. The relevant material safety data sheets (MSDS) shall be consulted.

The density measurement of the electrolyte can be carried out with appropriate tools such as aerometers, hydrometers, diffractometers or vibration-type densitometers. The obtained values shall be normalized to the specified reference temperature.

5 Physical properties of diluted sulphuric acid as electrolyte

5.1 Dependence of sulphuric acid electrolyte density on temperature

The value of sulphuric acid densities electrolyte density obtained at the measuring temperature shall be converted to the value of sulphuric acid electrolyte density at the reference temperature of 25 °C-by with the following equation:

$$d_{\mathsf{n}} = d_{\mathsf{T}} + f_{\mathsf{d}} \left(T - T_{\mathsf{n}} \right)$$

where

 d_n is the acid electrolyte density at 25 °C;

 d_{T} is the acid electrolyte density at measuring temperature *T*;

- $f_{\rm d}$ is the correction factor according to Table 1;
- *T* is the measuring temperature;
- T_n is the reference temperature of 25 °C.

Table 1 – Correction of density from measuring temperature to reference/specified temperature factor to convert the acid electrolyte density found at the measuring temperature to that at the specified reference temperature

Acid electrolyte density d _n	Correction factor f_d^a
kg/l	kg/l per K
1,10	0,000 50
1,15	0,000 60
1,20	0,000 70
1,30	0,000 75
^a The correction factor refers to the to 55 °C.	pplicable for a temperature range from 0 °C

5.2 Relationship of acid electrolyte density-on at 25 °C with the content of sulphuric acid-at 25 °C

Table 2 presents the relationship between the density and the content of sulphuric acid in the electrolyte.

Table 2 – Acid electrolyte density at 25 °C versus percentage of sulphuric acid at 25 °C

Sulphuric acid content (H ₂ SO ₄)					
Acid electrolyte density	Mass ratio fraction	Amount of	Concentration		
at 25 °C	H ₂ SO ₄₆₂₈₇₇ -	:2023 H ₂ SO ₄	H ₂ SO ₄		
://standards.ice/ai/catalog/sta	n lards/jec <mark>% w/w</mark> 6b99c-f	119-4e28mol/l7d-e12bb	30785ff/je.g/l62877		
1,100	15,18	1,704	166,98		
1,110	16,45	1,863	182,60		
1,120	17,80	2,034	199,36		
1,130	19,15	2,208	216,40		
1,140	20,47	2,381	233,36		
1,150	21,81	2,558	250,70		
1,160	23,11	2,735	268,07		
1,170	24,39	2,911	285,36		
1,180	25,63	3,086	302,43		
1,190	26,90	3,266	320,11		
1,200	28,12	3,443	337,44		
1,210	29,34	3,622	355,01		
1,220	30,55	3,803	372,71		
1,230	31,78	3,989	390,89		
1,240	32,98	4,173	408,95		
1,250	34,18	4,360	427,25		
1,260	35,40	4,551	446,04		
1,270	36,60	4,743	464,82		
1,280	37,81	4,938	483,97		

Sulphuric acid content (H ₂ SO ₄)					
Acid electrolyte density	Mass ratio fraction	Amount of	Concentration		
at 25 °C	H ₂ SO ₄	H ₂ SO ₄	H ₂ SO ₄		
kg/l	%- w/w	mol/l	g/l		
1,290	38,93	5,124	502,20		
1,300	40,10	5,319	521,30		

Similar tabulations of concentration vs. density values can be found in:

H. Bode, Lead-Acid Batteries, Translated by R.J. Brodd, K. Kordesch, The Electrochemical Society Series, John Wiley & Sons, New York, 1977, p. 42.

D. Berndt, Maintenance-Free Batteries, 3rd Edition, Research Studies Press Ltd., Baldock, England, 2003, p.109

When additives are present in the sulphuric acid electrolyte, the density measurement value will not reveal the true content of sulphuric acid (H_2SO_4) therein.

5.3 Electrolyte density-compared in relation to the state of discharge

The electrolyte density decreases during discharge of a battery. Therefore the specified electrolyte densities relate to a fully charged state. The permissible limit values shall be specified by the battery manufacturer for the various battery types and applications. Therefore, the specified density of the electrolyte relates to that in a fully charged battery.

The permissible limit values of the densities in operation are specified by the battery manufacturer for each of the various battery types, applications and specific reference temperatures.

Document Preview

6 Requirements for sulphuric acid used as electrolyte

EC 62877-1:2023

6.1 Impurities of sulphuric acid of higher at high concentration degrees

The purity of sulphuric acid-of higher at high concentration-degrees shall be such that after the following subsequent dilution with water to values of $\leq d_n \leq 1,30$ kg/l and use as filling electrolyte, the values given in Table 3 are by no means not exceeded.

6.2 Impurities of sulphuric acid electrolyte for first filling acid

The sulphuric acid used for filling lead acid batteries shall be clear and colourless.

The appropriate electrolyte filling levels shall be observed in order to avoid electrolyte spillage and associated corrosion damages and hazards.

The impurities included present in the acid filling electrolyte shall not exceed any value in Table 3.

This level of purity is required also for acid used for an electrolyte with density higher than 1,30 kg/l, e.g., for adjustment of the electrolyte density in batteries where an electrolyte loss has occurred.