



Designation: D3283 – 98 (Reapproved 2020)

Standard Specification for Air as an Electrical Insulating Material¹

This standard is issued under the fixed designation D3283; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification applies to air used as an electrical insulating material in electrical equipment.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.3 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

D2029 Test Methods for Water Vapor Content of Electrical Insulating Gases by Measurement of Dew Point

E105 Practice for Probability Sampling of Materials

E260 Practice for Packed Column Gas Chromatography

2.2 *Other Documents:*

Specification G-7.1 Commodity Specification for Air³

3. Classification

3.1 This specification shall apply to Type I, gaseous air.

¹ This specification is under the jurisdiction of ASTM Committee D27 on Electrical Insulating Liquids and Gases and is the direct responsibility of Subcommittee D27.02 on Gases and Non-Mineral Oil Liquids.

Current edition approved Dec. 1, 2020. Published December 2020. Originally approved in 1973. Last previous edition approved in 2012 as D3283 – 98(2012). DOI: 10.1520/D3283-98R20.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from the Compressed Gas Assn., Inc., 500 Fifth Ave., New York, NY 10036.

4. Manufacture

4.1 This specification applies to both atmospheric air and to air synthesized by blending oxygen and nitrogen in proper proportions.

5. Composition and Properties

5.1 The material shall conform to the chemical requirements specified in **Table 1**.

6. Sampling

6.1 *Gaseous Air in High Pressure Metal Containers*—Extract samples from the container or containers with an appropriate pressure reducing regulator. Screw the pressure regulator inlet connection on to the container valve outlet. Connect the regulator outlet connection to the gas sampling pipe or to the gas analyzing equipment by means of metal or glass tubing except that rubber tubing may be used to secure butt joints in metal-to-glass or glass-to-glass tubing. Take care to ensure that all tubing is clean and dry and the sampling apparatus is thoroughly purged of atmospheric air before the sample is taken. Where a multiplicity of containers are to be sampled, follow Practice **E105** if it is considered satisfactory to sample less than the total number of containers.

7. Test Methods

7.1 The components enumerated in this specification shall be determined in accordance with the following:

7.1.1 *Carbon Monoxide and Carbon Dioxide*— Practice **E260**.

7.1.2 *Oxygen*—Practice **E260**.

7.1.3 *Dew Point*—Test Methods **D2029**.

8. Shipping

8.1 Air for shipment shall be packaged in metal containers that comply with the requirements of and be approved by the Interstate Commerce Commission. The inside of the cylinders shall be dry and free from oil and corrosive chemicals.

9. Keywords

9.1 dielectric; dielectric air; dielectric gas; electrical insulating gas; gaseous air; insulating air



D3283 – 98 (Reapproved 2020)

TABLE 1 Composition and Properties for Air^A

	Type I
Oxygen, volume %	19.5 to 23.5
Carbon monoxide, max, volume %	0.0020
Carbon dioxide, max, volume %	0.10
Nitrogen	predominantly balance
Dew point, max, °C	-58

^A By agreement between purchaser and manufacturer, analysis may be required and limits established for elements or compounds not specified in the table of chemical composition.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>

iTeh Standards (<https://standards.iteh.ai>) Document Preview

[ASTM D3283-98\(2020\)](#)

<https://standards.iteh.ai/catalog/standards/sist/fl39ddaa-d520-40ce-9b6f-57c4d951bd00/astm-d3283-982020>