



Designation: D4904 – 99 (Reapproved 2020)

Standard Practice for Cooling of Analytical Solutions¹

This standard is issued under the fixed designation D4904; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This practice covers a standard procedure for the cooling of analytical solutions such as those prepared in Practices **D4901**, **D4905**, or **D6405**. The tannin analysis results for an analytical solution are to some extent dependent on the conditions of the cooling of that solution.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:²

D4901 Practice for Preparation of Solution of Liquid Vegetable Tannin Extracts

D4905 Practice for Preparation of Solution of Solid, Pasty and Powdered Vegetable Tannin Extracts

D6405 Practice for Extraction of Tannins from Raw and Spent Materials

¹ This practice is under the jurisdiction of ASTM Committee **D31** on Leather and is the direct responsibility of Subcommittee **D31.01** on Vegetable Leather. This practice has been adapted from, and is a replacement for, Method **A12** of the Official Methods of the American Leather Chemists Association.

Current edition approved Dec. 1, 2020. Published December 2020. Originally approved in 1989. Last previous edition approved in 2016 as D4904 – 99 (2016). DOI: 10.1520/D4904-99R20.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

2.2 ALCA Methods:

A12 Cooling of Analytical Solutions³

3. Summary of Practice

3.1 This practice specifies a procedure to follow in cooling to standard or room temperature the hot analytical solutions prepared from tanning materials for Practices **D4901**, **D4905**, or **D6405**.

4. Significance and Use

4.1 The solubility of extracts is influenced by temperature. The analytical solutions prepared from tanning extracts are dissolved or diluted in hot water. It is necessary to exercise caution in cooling these solutions, and to do so in such a way as to avoid chilling, under-cooling, or uneven cooling of the solutions.

5. Specimen

5.1 The specimen shall be the 1-L or 2-L solutions prepared under Practices **D4901**, **D4905**, or **D6405**.


6. Procedure

6.1 The prepared solutions shall be protected from drafts, and shall be allowed to stand overnight in an ambient temperature of not less than 23 °C, nor more than 28 °C. After their temperature has been adjusted, the solutions shall be made up to the mark with distilled water at 23°C. Where a constant temperature room is available, the solutions, suitably protected from drafts, may be cooled therein with advantage. In this case, the room shall be so controlled that solutions in flasks, exposed therein, shall remain at 24 °C.

7. Keywords

7.1 analytical solutions; cooling; tannin analysis; vegetable tannin analysis

³ Official Methods of the American Leather Chemists Association. Available from the American Leather Chemists Association, University of Cincinnati, P.O. Box 210014, Cincinnati, OH 45221-0014.

 **D4904 – 99 (2020)**

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>

iTeh Standards
(<https://standards.itih.ai>)
Document Preview

[ASTM D4904-99\(2020\)](#)

<https://standards.itih.ai/catalog/standards/sist/d74f28d5-d032-485f-a0ff-6676c48d4290/astm-d4904-992020>