



Designation: **D350—13 D350 – 21**

# Standard Test Methods for Flexible Treated Sleeving Used for Electrical Insulation<sup>1</sup>

This standard is issued under the fixed designation D350; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the U.S. Department of Defense.*

## 1. Scope\*Scope

1.1 These test methods cover procedures for testing electrical insulating sleeving comprising a flexible tubular product made from a woven textile fibre base, such as cotton, rayon, nylon, or glass, thereafter impregnated, or coated, or impregnated and coated, with a suitable dielectric material.

1.2 The procedures appear in the following sections:

<u>Procedures</u>	<u>Section(s)</u>
Selection of Test Material	5
Conditioning	6
Dimensions	7 to 11
Dielectric Breakdown Voltage	12 to 17
Brittleness Temperature	18 to 21
Flammability (See Test Methods D8355)	22 to 23
Dielectric Breakdown Voltage After Short-Time Aging	24 to 28
Oil Resistance	29 to 32
Thermal Endurance	33 to 39
Compatibility of Sleeving with Magnet Wire Insulation	40 to 54
Solvent Resistance	55 to 60
Hydrolytic Stability	61 to 67
Effect of Push-Back After Heat Aging	68 to 73

<u>Procedures</u>	<u>Sections</u>
Brittleness Temperature	18 to 21
Compatibility of Sleeving with Magnet Wire Insulation	45 to 59
Conditioning	-6
Dielectric Breakdown Voltage	12 to 17
Dielectric Breakdown Voltage After Short-Time Aging	29 to 33
Dimensions	-7 to 11
Effect of Push-Back After Heat Aging	73 to 78
Flammability	22 to 28
Hydrolytic Stability	66 to 72
Oil Resistance	34 to 37
Selection of Test Material	5
Solvent Resistance	60 to 65
Thermal Endurance	38 to 44

1.3 The values stated in inch-pound units, except for °C, are to be regarded as the standard. The values in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

<sup>1</sup> These test methods are under the jurisdiction of ASTM Committee D09 on Electrical and Electronic Insulating Materials and are the direct responsibility of Subcommittee D09.07 on Flexible and Rigid Electrical Insulating Materials.

Current edition approved Nov. 1, 2013 Jan. 1, 2021. Published December 2013 February 2021. Originally approved in 1932. Last previous edition approved in 2009 2013 as D350—09 D350—13. DOI: 10.1520/D0350-13.10.1520/D0350-21.

\*A Summary of Changes section appears at the end of this standard

1.4 This is a fire-test-response standard. See Sections ~~Test 22~~ through ~~Methods D835528~~, which ~~are the~~ contains procedures for flammability tests.

1.5 This standard measures and describes the response of materials, products, or assemblies to heat and flame under controlled conditions, but does not by itself incorporate all factors required for fire hazard or fire risk assessment of the materials, products or assemblies under actual fire conditions.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate ~~safety~~ safety, health, and health ~~environmental~~ environmental practices and determine the applicability of regulatory limitations prior to use.* For specific hazard statements, see 45.240.2 and 63.1.158.1.1.

NOTE 1—This standard resembles IEC 60684-2, Specification for Flexible Insulating Sleeving—Part 2 Methods of Test, in a number of ways, but is not consistently similar throughout. The data obtained using either standard are not necessarily technically equivalent.

1.7 *Fire testing is inherently hazardous. Adequate safeguards for personnel and property shall be employed in conducting these tests.*

1.6 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

## 2. Referenced Documents

### 2.1 ASTM Standards:<sup>2</sup>

[D149 Test Method for Dielectric Breakdown Voltage and Dielectric Strength of Solid Electrical Insulating Materials at Commercial Power Frequencies](#)

[D374 Test Methods for Thickness of Solid Electrical Insulation \(Metric\) D0374\\_D0374M](#)

[D471 Test Method for Rubber Property—Effect of Liquids](#)

[D746 Test Method for Brittleness Temperature of Plastics and Elastomers by Impact](#)

[D876 Test Methods for Nonrigid Vinyl Chloride Polymer Tubing Used for Electrical Insulation](#)

[D1711 Terminology Relating to Electrical Insulation](#)

[D2307 Test Method for Thermal Endurance of Film-Insulated Round Magnet Wire](#)

[D3487 Specification for Mineral Insulating Oil Used in Electrical Apparatus](#)

[D3636 Practice for Sampling and Judging Quality of Solid Electrical Insulating Materials](#)

[D5423 Specification for Forced-Convection Laboratory Ovens for Evaluation of Electrical Insulation](#)

[D6054 Practice for Conditioning Electrical Insulating Materials for Testing \(Withdrawn 2012\)<sup>3</sup>](#)

[D8355 Test Methods for Flammability of Electrical Insulating Materials Used for Sleeving or Tubing](#)

[E145 Specification for Gravity-Convection and Forced-Ventilation Ovens](#)

[E176 Terminology of Fire Standards](#)

### 2.2 IEEE Standard:<sup>4</sup>

[IEEE 101 Guide for the Statistical Analysis of Thermal Life Test Data](#)

### 2.3 IEC Standard:<sup>5</sup>

[IEC 60684-2 Specification for Flexible Insulating Sleeving—Part 2 Methods of Test](#)

### 2.4 ISO Standard:<sup>6</sup>

[ISO 13943 Fire Safety—Vocabulary](#)

## 3. Terminology

### 3.1 Definitions:

3.1.1 Use Terminology [E176](#) and ISO 13943 for definitions of terms used in this test method and associated with fire issues. Where

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> The last approved version of this historical standard is referenced on [www.astm.org](http://www.astm.org).

<sup>4</sup> Available from Institute of Electrical and Electronics Engineers, Inc. (IEEE), 445 Hoes Ln., P.O. Box 1331, Piscataway, NJ 08854-1331, 08854-4141, <http://www.ieee.org>.

<sup>5</sup> Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

<sup>6</sup> Available from International Organization for Standardization (ISO), ISO Central Secretariat, Chemin de Blandonnet 8, CP 401, 1214 Vernier, Geneva, Switzerland, <https://www.iso.org>.

differences exist in definitions, those contained in Terminology **E176** shall be used. Use Terminology **D1711** for definitions of terms used in this test method and associated with electrical insulation materials.

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *size, n*—a numerical designation which indicates that the inside diameter of the sleeving lies within the limits prescribed in **Table 1**.

3.2.2 *wall thickness, n*—one half the difference between the outside diameter of the sleeving mounted on a loosely fitting gagegauge rod and the diameter of the gagegauge rod when measured in accordance with **9.2**.

**4. Apparatus and Materials**

4.1 Ovens used in these test methods shall meet the requirements of Specification **D5423**.

**5. Selection of Test Material**

5.1 In the case of sleeving on spools or in coils, not less than three turns of the product shall be removed before the selection of material from which test specimens are to be prepared.

5.2 In the case of sleeving offered in cut lengths, test specimens shall not be prepared from material closer than 1 in. (25 mm) from each end.

5.3 Specimens for test shall not show obvious defects unless the purpose of the test is to determine the effect of such defects.

5.4 Specimens shall be prepared from samples selected in accordance with Practice **D3636**. The sampling plan and acceptance quality level shall be as agreed upon between the user and the producer.

**TABLE 1 ASTM Standard Sizes for Flexible Sleeving**

Size	Inside Diameter, in. (mm)	
	Max	Min
1 in.	1.036 (26.3)	1.000 (25.4)
7/8 in.	0.911 (23.1)	0.875 (22.2)
3/4 in.	0.786 (20.0)	0.750 (19.1)
5/8 in.	0.655 (16.6)	0.625 (15.9)
1/2 in.	0.524 (13.3)	0.500 (12.7)
7/16 in.	0.462 (11.7)	0.438 (11.1)
3/8 in.	0.399 (10.1)	0.375 (9.5)
No. 0	0.347 (8.8)	0.325 (8.3)
No. 1	0.311 (7.9)	0.289 (7.3)
No. 2	0.278 (7.1)	0.258 (6.6)
No. 3	0.249 (6.3)	0.229 (5.8)
No. 4	0.224 (5.7)	0.204 (5.2)
No. 5	0.198 (5.0)	0.182 (4.6)
No. 6	0.178 (4.5)	0.162 (4.1)
No. 7	0.158 (4.0)	0.144 (3.7)
No. 8	0.141 (3.6)	0.129 (3.3)
No. 9	0.124 (3.1)	0.114 (2.9)
No. 10	0.112 (2.8)	0.102 (2.6)
No. 11	0.101 (2.6)	0.091 (2.31)
No. 12	0.091 (2.31)	0.081 (2.06)
No. 13	0.082 (2.08)	0.072 (1.83)
No. 14	0.074 (1.88)	0.064 (1.63)
No. 15	0.067 (1.70)	0.057 (1.45)
No. 16	0.061 (1.55)	0.051 (1.30)
No. 17	0.054 (1.37)	0.045 (1.14)
No. 18	0.049 (1.24)	0.040 (1.02)
No. 20	0.039 (0.99)	0.032 (0.81)
No. 22	0.032 (0.81)	0.025 (0.64)
No. 24	0.027 (0.69)	0.020 (0.51)

## 6. Conditioning

6.1 Unless otherwise specified, a standard laboratory atmosphere of  $50 \pm 5\%$  relative humidity and  $23 \pm 2\text{ }^\circ\text{C}$  ( $73.4 \pm 3.6\text{ }^\circ\text{F}$ ) shall be used in conducting all tests and for conditioning specimens for a period of at least 18 h prior to testing.

6.2 In the case of dielectric breakdown voltage tests after humidity conditioning, specimens shall be conditioned for 96 h in an atmosphere of  $93 \pm 3\%$  relative humidity and  $23 \pm 2\text{ }^\circ\text{C}$  ( $73.4 \pm 3.6\text{ }^\circ\text{F}$ ) before testing. If a conditioning cabinet is used, specimens shall be tested for dielectric breakdown voltage within 1 min after removal from the cabinet.

6.3 For details regarding conditioning, refer to Practice [D6054](#).

## DIMENSIONS

### 7. Apparatus

7.1 *Gage Gauge Rods*—Standard gagegauge rods shall be made of steel and shall have smooth surfaces and rounded edges. One rod is required for each of the maximum and minimum diameters shown in [Table 1](#) for each size. Each rod shall be within  $\pm 0.005$  in. ( $\pm 0.127$  mm) of the values shown in [Table 1](#).

### 8. Test Specimens

8.1 Five test specimens of at least 7 in. (180 mm) in length shall be cut from material obtained in accordance with [Section 5](#).

### 9. Procedure

9.1 *Inside Diameter*—Pass the minimum gagegauge rod for the size sleeving under test into the specimen for a distance of 5 in. (127 mm) without expanding the wall of the sleeving. If the rod has a snug fit, then consider the specimen as having an inside diameter equal to the diameter of the rod. If the minimum gagegauge rod fits loosely, insert the maximum gagegauge rod into the specimen. If the maximum gagegauge rod passes freely into the specimen for a distance of 5 in. with a snug fit, or if it expands the wall of the specimen, then consider the sleeving to be of that size which falls within the limits of the maximum and minimum inside diameters as represented by the gagegauge rods. [ASTM D350-21](#)

<https://standards.iteh.ai/catalog/standards/sist/54d6e358-11eb-4c22-9115-2366d03a77d3/astm-d350-21>

9.2 *Wall Thickness*—Insert in the specimen the largest standard gagegauge rod that will pass freely into the sleeving. Apply a micrometer over the specimen and make thickness measurements as specified in Method C of Test Methods [D374](#) except that the force on the pressor foot shall be 3 oz (85 g). Obtain the average of five thickness readings taking the micrometer readings at approximately  $90^\circ$  intervals about the circumference of the specimen and spaced lineally approximately 0.25 in. (6 mm). Methods A and B of Test Methods [D374](#) can be used as alternative methods where agreed upon between the manufacturer and purchaser. Compute wall thickness as half the distance between the outside diameter of the mounted sleeving and the diameter of the gagegauge rod.

### 10. Report

10.1 Report the following information:

10.1.1 Identification of the sleeving,

10.1.2 Method of measurement if other than Method C,

10.1.3 Size of sleeving, and

10.1.4 Wall thickness.

### 11. Precision and Bias

11.1 *Precision*—The overall estimates of the precision within laboratories ( $S_r$ ) and the precision between laboratories ( $S_R$ ) for

**TABLE 2 Estimated Precision of Wall Thickness Measurement**

Sleeving Type	Nominal Value,		$(S_r)_p$ ,		$(SR)_p$ ,	
	in. (mm)		in. (mm)		in. (mm)	
Acrylic	0.0213	(0.54)	0.0007	(0.018)	0.0017	(0.043)
PVC	0.0237	(0.60)	0.0007	(0.018)	0.0021	(0.053)
Silicone Rubber	0.0331	(0.84)	0.0012	(0.030)	0.0019	(0.048)

the determination of wall thickness are given in **Table 2** for three selected materials. These estimates are based on a round robin of the three materials with six laboratories participating.<sup>7</sup>

11.2 *Bias*—This test method has no bias because the value for wall thickness is determined solely in terms of this test method itself.

## DIELECTRIC BREAKDOWN VOLTAGE

### 12. Significance and Use

12.1 The dielectric breakdown voltage of the sleeving is of importance as a measure of its ability to withstand electrical stress without failure. This value does not correspond to the dielectric breakdown voltage expected in service, but is of value in comparing different materials or different lots, in controlling manufacturing processes or, when coupled with experience, for a limited degree of design work. The comparison of dielectric breakdown voltage of the same sleeving before and after environmental conditioning (moisture, heat, and the like) gives a measure of its ability to resist these effects. For a more detailed discussion, refer to Test Method **D149**.

### 13. Apparatus

13.1 *Inner Electrode*—A straight suitable metallic conductor which fits snugly into the sleeving, without stretching the wall, in such a manner that one end of the wire is exposed and can be used to support the specimen.

13.1.1 For specimens having an inside diameter greater than about size 8, the use of stranded conductors or of a bundle of wires of smaller size, is recommended, instead of using a solid conductor.

13.2 *Outer Electrode*—Strips of soft metal foil 1-in. (25 mm) wide and not more than 0.001 in. (0.03 mm) in thickness.

### 14. Procedure A—Straight Specimens

14.1 *Test Specimens*—Ten specimens 7 in. (180 mm) long shall be prepared for each conditioning test (see Section 6) from material selected in accordance with Section 5.

14.2 *Procedure:*

14.2.1 After conditioning in accordance with 6.1, determine the dielectric breakdown voltage in accordance with Test Method **D149** except as specified in 14.2.2 and 14.2.3.

14.2.2 Mount a sleeving specimen on the inner electrode. Wrap the outer electrode tightly on the outside of the sleeving at a distance of not less than 1 in. (25 mm) from the ends of the specimens. Snugly wrap the foil over the sleeving. Wind two more turns of foil over the first turn, leaving a free end of about 0.5 in. (13 mm) to which an electrical contact can be made.

14.2.3 Determine the breakdown voltage, in accordance with Test Method **D149** by the short time method, increasing the voltage from zero at a rate of 0.5 kV/s. Calculate the average breakdown voltage for the ten tests.

<sup>7</sup> Supporting data have been filed at ASTM International Headquarters and may be obtained by requesting Research Report **RR-RR:D09-1024**. Contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org).

## 15. Procedure B—90° Bent Specimens

15.1 *Test Specimens*—Ten specimens 4 in. (100 mm) long shall be prepared for each conditioning test (see Section 6) from material selected in accordance with Section 5.

15.2 *Procedure:*

15.2.1 Mount a sleeving specimen on the inner electrode.

15.2.2 Bend the specimen through an angle of  $90 \pm 2^\circ$  over a smooth mandrel having a diameter of ten times the nominal inside diameter of the specimen. Arrange the bend so that it is centrally located on the specimen.

15.2.3 Condition the samples as specified in 6.1.

15.2.4 Determine the dielectric breakdown voltage of the bent specimen using the following procedure:

15.2.4.1 Carefully wrap a strip of metal foil as in 14.2.2 snugly over the specimens at the bend. In accordance with Test Method D149 apply a voltage starting at zero and increasing at a constant rate of 0.5 kV/s until breakdown. Calculate the average breakdown voltage of the ten specimens.

15.2.4.2 Apply the foil electrode after exposure to conditioning.

## 16. Report

16.1 Report the following information:

16.1.1 Identification of the sleeving,

16.1.2 Conditioning before test,

16.1.3 Voltage breakdown for each puncture,

16.1.4 Average, minimum, and maximum voltage breakdown, D350-21

16.1.5 Procedure used (Method A or B), and

16.1.6 Temperature and relative humidity of test, if different from 6.1.

## 17. Precision and Bias

17.1 *Precision*—The overall estimates of the precision within laboratories ( $Sr$ )<sub>i</sub> and the precision between laboratories ( $SR$ )<sub>i</sub> for the determination of Dielectric Breakdown Voltage by Procedure A are given in Table 3 for three selected materials. These estimates are based on a round robin of the three materials with six laboratories participating.<sup>7</sup>

17.2 *Bias*—This test method has no bias because the value for dielectric breakdown voltage is determined solely in terms of this test method.

**TABLE 3 Estimated Precision of Dielectric Breakdown Voltage Measurement**

Sleeving Type	Nominal Value, Volts-volts	( $Sr$ ) <sub>i</sub> , Volts-volts	( $SR$ ) <sub>i</sub> , Volts-volts
Conditioned 18 h/23 °C/50 % RH			
Acrylic	8480	802	1126
PVC	10980	983	1528
Silicone Rubber	10770	904	1616
Conditioned 96 h/23 °C/93 % RH			
Acrylic	2048	197	828
PVC	8100	1003	2137
Silicone Rubber	8540	1367	2550

## BRITTLENESS TEMPERATURE

### 18. Significance and Use

18.1 This test method serves to measure the brittleness temperature of the sleeving. It is useful for comparative and quality control purposes.

18.2 Results of this test have not been found to correlate with those obtained by bending or flexing around mandrels at low temperatures. Brittleness temperatures determined for sleeving materials by this test are affected by differences in cross-sectional dimensions and in specimen configuration, even if the materials have the same composition.

### 19. Procedure

19.1 Determine the brittleness temperature in accordance with Test Method [D746](#), except as specified in [19.1.1 – 19.1.4](#).

19.1.1 For sleeving sizes 20 through 8, cut specimens in full section and 1.5 in. (38 mm) long.

19.1.2 For sleeving sizes 7 through 1 in. inside diameter, cut specimens 0.25 in. (6.4 mm) wide and 1.5 in. (38 mm) long with the longer dimension parallel to the axis of the sleeving. Take care to avoid cutting the specimens from the edges of sleeving that has been flattened during manufacture or storage.

19.1.3 Use only motor-driven or gravity-fall apparatus, such as described in Test Methods [D876](#). Mount specimens so that the striking edge of the apparatus contacts the film and not the braid.

19.1.4 Failure of a specimen is indicated by cracking of the film completely through to the braid, as determined by visual examination.

### 20. Report

20.1 Report the following information:

20.1.1 Identification of the sleeving,

[ASTM D350-21](#)

<https://standards.iteh.ai/catalog/standards/sist/54d6e358-11eb-4c22-9115-2366d03a77d3/astm-d350-21>

20.1.2 Brittleness temperature to the nearest °C,

20.1.3 Method of calculation (see Test Method [D746](#)),

20.1.4 Type of apparatus used, and

20.1.5 Number of specimens tested.

### 21. Precision and Bias

21.1 *Precision*—This test method has been in use for many years, but no information has been presented to ASTM upon which to base a statement of precision. No activity has been planned to develop such information.

21.2 *Bias*—This test method has no bias because the value for brittleness temperature is determined solely in terms of this test method.

## FLAMMABILITY—METHOD A

**22. Procedure**—Determine the flammability in accordance with test method A in Test Methods [D8355](#).

~~22.1 Determine the flammability in accordance with Test Methods [D876](#). The results of this test give an indication of the tendency of the material to burn in case of fire.~~