



Designation: D5200 – 03 (Reapproved 2021)

Standard Test Method for Determination of Weight Percent Volatile Content of Solvent-Borne Paints in Aerosol Cans¹

This standard is issued under the fixed designation D5200; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method is for the determination of the weight percent volatile organic compounds of solvent-borne paints in aerosol cans. It offers a unique way to obtain paint specimens from aerosol cans.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use. A specific hazard statement is given in 6.7.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

E145 Specification for Gravity-Convection and Forced-Ventilation Ovens

E180 Practice for Determining the Precision of ASTM Methods for Analysis and Testing of Industrial and Specialty Chemicals (Withdrawn 2009)³

¹ This test method is under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.21 on Chemical Analysis of Paints and Paint Materials.

Current edition approved Feb. 1, 2021. Published February 2021. Originally approved in 1991. Last previous edition approved in 2014 as D5200 – 03 (2014). DOI: 10.1520/D5200-03R21.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.

2.2 *Other Standard:*

Method 35 Determination of Percent Volatile Organic Compounds (VOC) in Solvent Based Aerosol Paints⁴

3. Summary of Test Method

3.1 A designated quantity from an aerosol coating is sprayed into an adapter glass tube assembly and heated in an oven at $110 \pm 5^\circ\text{C}$ for 60 min. The percent volatile is calculated from the loss in weight.

4. Significance and Use

4.1 This test method is the procedure of choice for determining the volatile content in aerosol coatings under specified test conditions modeled after Method 35.⁴ The inverse value, nonvolatile, is used to determine the weight percent solids content. This information is useful to the paint producer, user, and to environmental interests for determining the grams of volatile organic compounds per gram of solids emitted from aerosol cans.

5. Apparatus

5.1 *Adapter Glass Tube Assembly, (Fig. 1).*

5.1.1 *Sample Adapter Tube*, straight connecting with 35/25 spherical joints. Loosely fill with glass wool and precondition for 30 min in an oven at $110 \pm 5^\circ\text{C}$ and store in a desiccator prior to use.^{5,6}

5.1.2 *Charcoal Adapter Tube*, straight connecting with 35/25 spherical joints. Fill with activated charcoal and plug both ends with glass wool. This tube is used to prevent the solvent vapors from contaminating the vacuum pump.^{6,7}

5.1.3 *Adapters*, connecting hose with 35/25 socket joints.^{6,8}

⁴ Bay Area Air Quality Management District, (BAAQMD) *Manual of Procedures*, Vol III, 939 Ellis St., San Francisco, CA 94109.

⁵ The sole source of supply of the adapter tube, No. 5035-35 known to the committee at this time is Ace Glass Inc., P.O. Box 688, 1430 Northwest Blvd., Vineland, NJ 08360.

⁶ If you are aware of alternative suppliers, please provide this information to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee,¹ which you may attend.

⁷ The sole source of supply of the charcoal adapter tube, No. 5035-3 known to the committee at this time is Ace Glass Inc.

⁸ The sole source of supply of the adapters (socket joints) No. 5217-35 known to the committee at this time is Ace Glass Inc.




FIG. 1 Adapter Glass Tube Assembly




FIG. 2 Aerosol Can on Eberbach Shaker

- 5.1.4 Adapter,^{6,9} connecting hose with 35/25 ball joint.
- 5.1.5 Clamps, pinch type, with screw-locking device.^{6,10}
- 5.1.6 Glass Wool, medium-fine silk.
- 5.1.7 Activated Charcoal, coconut, 8 to 12 mesh.
- 5.1.8 Tygon Tubing.
- 5.1.9 Iron Stands.
- 5.1.10 Utility Clamps.

5.2 Vacuum Pump.

5.3 Forced Draft Oven, Type II A or Type II B as specified in Specification E145.

5.4 Actuators (Valves), with extension tubes.

5.5 Top-Loading Balance, capable of weighing to 0.01 g.

⁹ The sole source of supply of the adapter (ball joint) No. 5216-35 known to the committee at this time is Ace Glass Inc.

¹⁰ The sole source of supply of the clamps, No. 7669-14 known to the committee at this time is Ace Glass Inc.

5.6 Shaker, similar to the Eberbach shaker in Fig. 2.

6. Procedure

6.1 Mix the aerosol can thoroughly using a shaker, similar to the Eberbach shaker in Fig. 2, for 15 min at the low-speed setting. It is essential that the samples be well mixed to obtain valid results.

6.2 Weigh accurately to 0.01 g, a preconditioned sample adapter tube. Use a pair of gloves at all times when handling the adapter glass tube.

6.3 Remove the cap and actuator from the mixed can. Replace the actuator with one having an extension tube.

6.4 Test actuator and extension tube fit by spraying some contents out for about 5 s. This step also clears the dip tube in case a separation has occurred. If a leak is observed, replace with a better fitting actuator or extension tube.

6.5 Weigh the aerosol can with the actuator to the nearest 0.01 g. Spray 3 to 5 g of aerosol into the adapter tube assembly, spreading out the coating by moving the extension tube around the wall of the adapter tube. The spraying is done with the vacuum on.

6.6 Obtain the specimen weight by difference by weighing the aerosol can again to 0.01 g after spraying out the specimen.

6.7 Place the sample adapter tube in the drying oven for 60 min at $110 \pm 5^\circ\text{C}$. (**Warning**—Provide adequate ventilation, consistent with accepted laboratory practice, to prevent solvent vapors from accumulating to a dangerous level.)

6.8 Remove the adapter tubes from the oven, place immediately in a dessicator, cool to ambient temperature, and weigh to 0.01 g.

7. Calculations

7.1 Calculate the weight percent nonvolatile content (NV), in the aerosol can as follows:

$$NV, \% = (W_2/W_1) \times 100 \quad (1)$$

where:

W_1 = weight of aerosol can before spraying sample minus weight of aerosol can after spraying sample, g, and

W_2 = weight of sample adapter tube with solids minus weight of sample adapter tube, g.

7.2 The weight percent organic volatiles (WO), in the aerosol can may be calculated by the difference as follows:

$$WO, \% = 100 - NV \quad (2)$$

where grams of organic volatiles/grams of solid equal WO/NV.

8. Precision and Bias

8.1 Precision—Estimates are based on an interlaboratory study in which 1 operator in each of 3 laboratories analyzed in duplicate on two different days 3 samples of solvent-borne aerosol coatings containing 63.04 to 77.53 % organic volatiles. The coatings were commercially supplied. The results were analyzed statistically in accordance with Practice E180. The within laboratory coefficient of variation was found to be