



Standard Test Method for Acid-Insoluble Lignin in Wood^{1,2}

This standard is issued under the fixed designation D1106; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method³ covers the determination of the acid-insoluble lignin content of wood.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.* Specific precautionary statements are given in 6.1.

1.3 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*⁴

D1107 Test Method for Ethanol-Toluene Solubility of Wood

3. Principle of Method

3.1 When wood is treated with strong acids the carbohydrates are hydrolyzed, leaving an insoluble residue which is determined as acid-insoluble lignin. Since some of the wood extractives (oils, resins, fats, waxes, tannins, gums, and starch) would remain insoluble with the lignin, these are first removed by proper extraction with suitable solvents. The 72 % sulfuric acid method for lignin contains two and sometimes three preliminary extractive treatments, treatments of the wood, namely: (1) with alcohol-ethanol, to remove the catechol tannins; (2) with alcohol-benzene-ethanol-toluene solution, to remove the resins, oils, fats and waxes; and (3) with hot water, to remove the remaining water-soluble materials.

3.2 The alcohol-ethanol extraction is necessary in analysis of woods high in tannin; that is, oak, chestnut, redwood, etc. It has not been shown necessary in the more common pulpwoods, such as the various species of spruce, pine, fir, hemlock, poplar, birch, beech, and maple. It is recommended that for these woods the alcohol extraction be omitted unless it is desirable for a special

¹ This test method is under the jurisdiction of ASTM Committee D07 on Wood and is the direct responsibility of Subcommittee D07.01 on Fundamental Test Methods and Properties.

Current edition approved Aug. 1, 2013; Feb. 1, 2021. Published September 2013; March 2021. Originally approved in 1950. Last previous edition approved in 2007; 2013 as D1106 – 96 (2007); (2013). DOI: 10.1520/D1106-96R13.10.1520/D1106-21.

² This standard was originally based upon TAPPI standard Method T222-om-83, which has been replaced by T 222 om-15.

³ For further information on this test method the following references may be consulted:

Bray, M. W., "Methods Used at the Forest Products Laboratory for the Chemical Analysis of Pulps and Pulpwoods," *Paper Trade Journal*, Vol 87, No. 25, December 20, 1928, p. 29.

Ritter, G. J., Seborg, R. M., Mitchell, R. L., *Industrial and Engineering Chemistry*, Analytical Edition, Vol 4, 1932, p. 202.

Ritter, G. J., and Barbour, J. H., *Industrial and Engineering Chemistry*, Analytical Edition, Vol 7, 1935, p. 238.

⁴ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

purpose. In analysis of woods not listed, the desirability of the alcohol extraction depends upon the purpose of the analysis and the report should state whether or not ~~alcohol~~ethanol extraction was used.

4. Significance and Use

4.1 Wood contains approximately 20 to 30 % lignin. Removal of the lignin is the primary objective of pulping and bleaching procedures. Determination of the lignin content provides information for the evaluation and application of these processes.

5. Apparatus

5.1 *Extraction Apparatus*—A compact form of Soxhlet extraction apparatus, with ground-glass joints, is preferable. The apparatus shall consist of the following items:

5.1.1 *Soxhlet Extraction Flask*, having a capacity of 250 mL.

5.1.2 *Soxhlet Extraction Tube*, 45 to 50 mm in inside diameter, having a capacity to the top of the siphon of approximately 100 mL and a siphon tube approximately 55 mm in height. Extraction tubes of these dimensions siphon more rapidly than extractors with higher siphon tubes.

5.1.3 *Condenser*, of the Hopkins inner-cooled type.

5.1.4 *Extraction Crucibles*, of Alundum or fritted glass and of medium or fine porosity.

5.2 *Filtering Crucibles*—Alundum, porous porcelain, or fritted-glass crucibles (all of fine porosity), or Gooch crucibles with a glass-fiber mat, are recommended for filtering the separated lignin. Glass crucibles cannot be used if the lignin is to be ashed.

6. Reagents

6.1 *Ethylene-Toluene-Ethanol-Toluene Solution*—Mix 1.0 L absolute ethanol and 427 mL toluene. (**Warning**—Avoid inhalation of vapors and contact with skin.)

6.2 *Sulfuric Acid (72 %)*—Carefully pour 665 mL of H₂SO₄ (sp gr 1.84) into about 300 mL of water, with vigorous stirring, and after cooling, dilute to 1 L. Standardize against standard NaOH solution, using a methyl orange indicator. Adjust the H₂SO₄ to a strength of 72 ± 0.1 % by addition of water or H₂SO₄ (sp gr 1.84) as may be found necessary. If desired, the solution may be standardized by an accurate determination of its specific gravity. For 72 % H₂SO₄ the specific gravity at 20/4°C is 1.6338; for use of this specific gravity method appropriate tables should be consulted.

7. Test Specimen

7.1 The test specimen shall consist of 1 g of wood that has been groundmilled to pass a 425- μ m (40 mesh) sieve and thoroughly air-dried.

8. Procedure

8.1 Weigh two 1-g test specimens in tared glass-stoppered weighing bottles. Dry in an oven for 2 h at 100 to 105°C, replace and stopper, and cool in a desiccator. Loosen the stopper to equalize the pressure and weigh. Continue the drying for 1-h periods until the weight is constant. Calculate the percentage of moisture-free wood.

8.2 Weigh in the extraction crucibles two additional 1-g test specimens for the lignin determination in duplicate. Place the extraction crucible containing the specimen in a Soxhlet extraction apparatus. Extract with 95 % ~~alcohol~~ethanol for 4 h, unless the wood is known not to contain catechol tannins, in which case this extraction with alcohol will not be required. Then extract the test specimen with ethanol-toluene solution as described in Test Method **D1107**. Remove as much of the solvent by suction as possible and wash by suction with 50 mL of ethanol to remove the toluene. Remove the excess ethanol, transfer to a beaker, and digest-extract successively with three 400 mL of hot water in a steam or portions of distilled water, heating the flask with each change of water for 1 h in a hot-water bath at approximately 100°C for 3 h, 100°C. Filter, wash with 100 mL of hot water, and finally with 50 mL of ethanol to facilitate the removal of the test specimen from the crucible. After these preliminary extractions, let the specimen dry in the air.