



Designation: A1081/A1081M – 21

## Standard Test Method for Evaluating Bond of Seven-Wire Steel Prestressing Strand<sup>1</sup>

This standard is issued under the fixed designation A1081/A1081M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### 1. Scope\*

1.1 This test method describes procedures for determining the bond of seven-wire steel prestressing strand. The bond determined by this test method is stated as the tensile force required to pull the strand through the cured mortar in a cylindrical steel casing. The result of the test is the tensile force measured on the loaded-end of the strand corresponding to a movement of 0.1 in. [2.5 mm] at the free-end of the strand.

1.2 This test method is applicable either in inch-pound units (as Test Method A1081) or SI units (as Test Method A1081M).

1.3 The values stated in either inch-pound units or in SI units are to be regarded separately as standard. Within the text, SI units are shown in brackets. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the test method.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

### 2. Referenced Documents

#### 2.1 ASTM Standards:<sup>2</sup>

[A416/A416M Specification for Low-Relaxation, Seven-Wire Steel Strand for Prestressed Concrete](#)

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.05 on Steel Reinforcement.

Current edition approved March 1, 2021. Published March 2021. Originally approved in 2013. Last previous edition approved in 2015 as A1081/A1081M – 15. DOI: 10.1520/A1081\_A1081M-21.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

[C33/C33M Specification for Concrete Aggregates](#)  
[C109/C109M Test Method for Compressive Strength of Hydraulic Cement Mortars \(Using 2-in. or \[50 mm\] Cube Specimens\)](#)  
[C150/C150M Specification for Portland Cement](#)  
[C192/C192M Practice for Making and Curing Concrete Test Specimens in the Laboratory](#)  
[C670 Practice for Preparing Precision and Bias Statements for Test Methods for Construction Materials](#)  
[C1437 Test Method for Flow of Hydraulic Cement Mortar](#)

### 3. Terminology

#### 3.1 Definitions of Terms Specific to This Test Method:

3.1.1 *bond, n*—the adhesion of strand to concrete or mortar.

3.1.2 *bond breaker, n*—a product wrapped around strand to prevent strand-to-concrete bond over the installed length. Extruded polystyrene foam pipe insulation is commonly used for this purpose.

3.1.3 *manufactured length, n*—a length of strand that is manufactured in one continuous length.

3.1.4 *mortar, n*—a mixture of cement, fine aggregate (that is, sand) and water.

3.1.5 *strand, n*—all references to strand in this test method shall be interpreted to be Specification [A416/A416M](#) seven-wire prestressing steel strand with nominal diameters of 0.500 in. [12.70 mm] or 0.600 in. [15.24 mm].

3.1.6 *test specimen, n*—an assembly consisting of one steel casing, one sample of strand and mortar.

### 4. Summary of Test Method

4.1 Six samples of seven-wire steel prestressing strand with nominal diameters of 0.500 in. [12.7 mm] or 0.600 in. [15.24 mm] are selected from a single continuous length. Each of the six strand samples are individually cast in a steel cylinder casing with a specified cement mortar. The strand is exposed on both ends of the cylinder with a designated loaded-end and free-end. Once the mortar reaches a specified compressive strength, the cylinder with the embedded steel strand is loaded into a tensile testing machine. The designated loaded-end of the steel strand is gripped by the tensile testing machine and pulled away from the cylinder at a specified displacement rate. The tensile force on the loaded-end of the strand is measured along with the corresponding displacement of the free-end. The

\*A Summary of Changes section appears at the end of this standard

result of the test is the tensile force measured at the loaded-end of the strand corresponding to a movement of 0.1 in. [2.5 mm] at the free-end of the strand. The results of each sample test in the set of six are reported individually and as an average.

## 5. Significance and Use

5.1 Prestressing steel strand is used in pre-tensioned and post-tensioned concrete construction.

5.2 In pre-tensioned concrete applications, the prestressing steel strand is expected to transfer prestressing forces to the structural member by means of the adhesion (that is, bond) of the exposed wire strand surfaces to the surrounding cementitious material.

5.3 Manufacturing processes, subsequent handling, and storage conditions can influence the strand bond.

5.4 Prestressing steel strand is used in construction applications with a variety of concrete mixtures. Developing tests and threshold values for the performance of the strand in each of these unique mixtures is impractical.

## 6. Apparatus

6.1 A dial gauge or position transducer with a minimum precision of 0.001 in. [0.025 mm].

6.2 A tensile testing machine with the following functionality:

6.2.1 Controlled loading rate based on cross-head displacement.

6.2.2 Gripping device without torsional restraint. The lack of torsion restraint and satisfaction of this requirement shall be verified by demonstrating the ability to twist the actuator or the test specimen by hand or by manual lever (Note 1).

NOTE 1—In testing to develop the test method, hydraulic actuators were employed to apply tension force to the strand. The nature of the hydraulic actuators generally allows the piston to rotate with minimal resistance (since the piston floats on hydraulic fluid). Neither a roller bearing nor a ball bearing is required though one may be necessary if the pull-out force is applied through a mechanism where twist is restrained.

## 7. Sampling of Strand

7.1 Six samples of prestressing steel strand are needed for this test. Each sample shall be at least 32 in. [800 mm] long.

7.2 Samples shall be collected from the same reel or reelless pack of strand (typically 3.5 tons [3 tonnes]) or the same manufactured length of strand (typically 20–28 tons [18–25 tonnes]).

7.3 The surface condition of the strand samples shall be representative of the strand intended for use in bonded applications. Care shall be taken to prevent the introduction of surface contaminants which may alter the bond performance of the strand. For qualification of a manufacturing process, the sample surface shall be in the as-manufactured condition.

## 8. Mortar Requirements

### 8.1 Materials:

8.1.1 *Sand*—The sand shall conform to Specification C33/C33M requirements for fine aggregate. The sand shall come from natural sources. Manufactured sand shall not be permitted.

8.1.2 *Cement*—The cement shall conform to Specification C150/C150M requirements for Type III cement.

8.1.3 *Water*—The water shall be potable.

8.2 *Mortar Preparation*—The preparation of the materials and procedure used to mix the mortar shall be performed in conformance with Practice C192/C192M (Note 2) with the following exceptions:

8.2.1 Aggregates, other than sand, shall not be used.

8.2.2 Admixtures shall not be used.

8.3 *Mortar Performance Requirements*—The mortar shall be tested in conformance with Practice C192/C192M with the following exceptions and additional requirements.

8.3.1 *Slump*—No measurements required.

8.3.2 *Air Content*—No measurements required.

8.3.3 *Flow*—Mortar flow shall be measured in accordance with the procedures in Test Method C1437. The flow rate shall be greater than or equal to 100 % but shall not exceed 125 %.

8.3.4 *Strength*—Mortar strength shall be evaluated in conformance with Test Method C109/C109M using 2 in. [50 mm] mortar cubes. Before starting the test and after a minimum of 22 hours curing time, mean mortar cube strength shall not be less than 4 500 psi [31 MPa]. During performance of the strand bond test and within 24 hours  $\pm$  2 hours of mortar mixing, mean mortar cube strengths shall be between 4 500 psi [31 MPa] and 5 000 psi [34.5 MPa] (Note 3).

NOTE 2—Practice C192/C192M is described as a standard practice to be used for concrete test specimens. As outlined in 8.1, only fine aggregates (that is, sand) are included in the mixture along with cement and water. Because coarse aggregates are not included, this mixture is defined as “mortar” and not “concrete.” Aside from this difference and a few other exceptions noted in Section 8, the practices documented in Practice C192/C192M are to be applied when making the mortar used in this test method.

NOTE 3—The ability to consistently achieve the specified mortar strengths can be a challenge for testing facilities with limited mortar experience or limited mixing and curing facilities, or both, and multiple trial batches may be required to develop appropriate mixes. If mean mortar strengths are less than the 4 500 psi [31 MPa] when the strand bond test is performed, the strand bond test results will be biased to provide lower bond test values than if the mortar was within the specified range. For the purpose of comparing the bond test results of this test method against a minimum threshold value, a bond test result that exceeds a minimum threshold value with a mean mortar strength less than 4 500 psi [31 MPa] should be accepted as meeting a specified minimum threshold value.

If mortar strengths are greater than the 5 000 psi [34.5 MPa] when the strand bond test is performed, the strand bond test results will be biased to provide higher bond test values than if the mortar was within the specified range. For the purpose of comparing the bond test results of this test method against a minimum threshold value, a bond test result that is below a minimum threshold value with a mean mortar strength greater than 5 000 psi [34.5 MPa] should be considered as failing to meet the specified minimum threshold value.

9. Preparation of Test Specimens

9.1 Materials:


9.1.1 Strand Samples—Strand sample requirements are defined in Section 7.

9.1.2 Mortar—Mortar requirements are defined in Section 8.

9.1.3 Bond Breaker—A 1 in. ± 0.25 in. [25 mm ± 6 mm] outside diameter × 2 in. ± 0.08 in. [50 mm ± 2 mm] length section of pipe insulation or equivalent material shall be used

as a bond breaker. The position of the bond breaker shall be as defined in Fig. 1 (Note 4).

9.1.4 Steel Casing—Each individual test specimen of strand shall be cast in a 5 in. [130 mm] outside diameter × 18 in. [450 mm] long cylindrical steel casing as defined in Fig. 1. The thickness of the cylindrical walls of the steel casing shall not be less than 11 gauge or 0.119 in. [3.0 mm]. A 6 in. × 6 in. × 0.25 in. [150 mm × 150 mm × 6 mm] square plate with a hole located at the center of the plate sufficient to accommodate the



Note—The “Electronic End Slip Measurement” apparatus shown here is an example of one type of measurement set-up. Other configurations and devices can be used.

A mold release agent may be sprayed onto the canister ID walls before pouring mortar.

<sup>A</sup> SI equivalent: 50 mm ± 2.0 mm

<sup>B</sup> SI equivalent: 64 mm ± 13 mm

<sup>C</sup> SI equivalent: 450 mm ± 6.4 mm

<sup>D</sup> SI equivalent: 800 mm +250 mm -0 mm

<sup>E</sup> SI equivalent: 130 mm ± 3 mm (OD) × 3 mm min (wall thickness)

FIG. 1 Longitudinal Cross-Section of Strand Test Specimen in a Mortar-Filled Cylinder