



Designation: ~~A307-14~~^{ε1} A307-21

Standard Specification for Carbon Steel Bolts, Studs, and Threaded Rod 60 000 PSI Tensile Strength¹

This standard is issued under the fixed designation A307; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ε) indicates an editorial change since the last revision or reappraisal.

This standard has been approved for use by agencies of the U.S. Department of Defense.

^{ε1} NOTE—Section 7.3 was editorially corrected in May 2017.

1. Scope*

1.1 This specification² covers the chemical and mechanical requirements of two grades of carbon steel bolts and studs in sizes ¼ in. through 4 in. The fasteners are designated by “Grade” denoting tensile strength and intended use, as follows:

Grade	Description
Grade A	Bolts, studs, and threaded rod having a minimum tensile strength of 60 ksi and intended for general applications.
Grade B	Bolts, studs, and threaded rod ^A having a tensile strength of 60 to 100 ksi and intended for flanged joints in piping systems with cast iron flanges, and
Grade C	Replaced by Specification F1554 Gr.36

^A Threaded rod is not usually produced to Grade B, but can be when specified by the purchaser.

1.2 This specification does not cover requirements for machine screws, thread cutting/forming screws, mechanical expansion anchors or similar externally threaded fasteners.

1.3 Suitable nuts are covered in Specification A563. Unless otherwise specified, the grade and style of nut for each grade of fastener, of all surface finishes, shall be as follows:

Fastener Grade and Size	Nut Grade and Style ^A
A ¼ to 1½ in.	A, hex
A over 1½ to 4 in.	A, heavy hex
B, ¼ to 4 in.	A, heavy hex

¹ This specification is under the jurisdiction of ASTM Committee F16 on Fasteners and is the direct responsibility of Subcommittee F16.02 on Steel Bolts, Nuts, Rivets and Washers.

Current edition approved Oct. 1, 2014; Feb. 15, 2021. Published October 2014; April 2021. Originally approved in 1947. Last previous edition approved in 2012 as A307-12, -14^{ε1}. DOI: 10.1520/A0307-14E01-10.1520/A0307-21.

² For ASME Boiler and Pressure Vessel Code applications see related Specification SA-307 in Section II of that Code.

*A Summary of Changes section appears at the end of this standard

^A Nuts of other grades and styles having specified proof load stresses (Specification **A563**, Table 3) greater than the specified grade and style of nut are also suitable.

iTeh Standards
(<https://standards.itih.ai>)
Document Preview

[ASTMA307-21](#)

<https://standards.itih.ai/catalog/standards/sist/c94a5d63-aa6a-4368-92d9-86bd94cdcdd1/astm-a307-21>

1.4 The values stated in inch-pound units are to be regarded as standard. No other units of measurement are included in this standard.

1.5 Supplementary Requirement S1 of an optional nature is provided, which describes additional restrictions to be applied when bolts are to be welded. It shall apply only when specified in the inquiry, order, and contract.

1.6 Terms used in this specification are defined in Terminology **F1789** unless otherwise defined herein.

1.7 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:³

A563 Specification for Carbon and Alloy Steel Nuts

A706/A706M Specification for Deformed and Plain Low-Alloy Steel Bars for Concrete Reinforcement

A751 Test Methods and Practices for Chemical Analysis of Steel Products

B695 Specification for Coatings of Zinc Mechanically Deposited on Iron and Steel

F606/F606M Test Methods for Determining the Mechanical Properties of Externally and Internally Threaded Fasteners, Washers, and Rivets (Metric) ~~F0606–F0606M~~ **F606M** Direct Tension Indicators, and Rivets

F788/F788M ~~F788~~ **F788M** Specification for Surface Discontinuities of Bolts, Screws, Studs, and Rivets, Inch and Metric Series

F1470 Practice for Fastener Sampling for Specified Mechanical Properties and Performance Inspection

F1554 Specification for Anchor Bolts, Steel, 36, 55, and 105-ksi Yield Strength

F1789 Terminology for F16 Mechanical Fasteners

F2329 ~~F2329~~ **F2329M** Specification for Zinc Coating, Hot-Dip, Requirements for Application to Carbon and Alloy Steel Bolts, Screws, Washers, Nuts, and Special Threaded Fasteners

2.2 ASME Standards:⁴

B 1.1 Unified Screw Threads

B 18.2.1 Square and Hex Bolts and Screws

B 18.24 Part Identifying Number (PIN) Code System

B 18.5 Round Head Bolts (Inch Series)

B18.31.3 Threaded Rods (Inch Series)

3. Ordering Information

3.1 Orders for externally threaded fasteners (including nuts and accessories) under this specification shall include the following:

3.1.1 ASTM designation and year of issue,

3.1.2 Name of product, bolts or studs; and bolt head style, that is, hex or heavy hex, or threaded rod,

3.1.3 Grade, that is, A, or B. If no grade is specified, Grade A is furnished.

3.1.4 Quantities (number of pieces by size including nuts),

3.1.5 Fastener size and length,

3.1.6 *Washers*—Quantity and size (separate from bolts),

3.1.7 *Zinc Coating*—Specify the zinc-coating process required, for example, hot-dip, mechanically deposited, or no preference (see 4.5).

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

⁴ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

⁴ Available from American Society of Mechanical Engineers (ASME), ASME International Headquarters, Three Two Park Ave., New York, NY 10016-5990, <http://www.asme.org>.

- 3.1.8 *Other Finishes*—Specify other protective finish, if required.
- 3.1.9 Specify if inspection at point of manufacture is required,
- 3.1.10 Specify if certified test report is required (see 9.2), and
- 3.1.11 Specify additional testing (9.3) or special requirements.
- 3.1.12 For establishment of a part identifying system, see ASME B18.24.

4. Materials and Manufacture

- 4.1 Steel for bolts, studs, and threaded rod shall be made by the open-hearth, basic-oxygen, or electric-furnace process.
- 4.2 Bolts shall be produced by hot or cold forging of the heads or machining from bar stock.
- 4.3 *Heat Treatment:*

4.3.1 Cold headed fasteners with head configurations other than hex having a specified minimum head height less than or equal to $-.50.5$ D (D is nominal diameter) shall be stress relief annealed at a minimum temperature of 875°F : 875°F . This would include cold headed Round Head and Round Head Square Neck Bolts in accordance with ASME B18.5. When specified by the purchaser, cold headed hex head bolts and screws shall be stress relieved at 875°F minimum.

4.3.2 Stress relieving of hex head fasteners and those with minimum head heights greater than $-.50.5$ D shall be at the manufacturer's option.

4.4 Bolt and stud threads shall be rolled or cut.

4.5 *Zinc Coatings, Hot-Dip and Mechanically Deposited:*

4.5.1 When zinc-coated fasteners are required, the purchaser shall specify the zinc-coating process, for example hot dip, mechanically deposited, or no preference.

4.5.2 When hot-dip is specified, the fasteners shall be zinc-coated by the hot-dip process in accordance with the requirements of Specification ~~F2329~~F2329/F2329M.

4.5.3 When mechanically deposited is specified, the fasteners shall be zinc-coated by the mechanical-deposition process in accordance with the requirements of Class 55 of Specification **B695**.

4.5.4 When no preference is specified, the supplier may furnish either a hot-dip zinc coating in accordance with Specification ~~F2329~~F2329/F2329M, or a mechanically deposited zinc coating in accordance with Specification **B695**, Class 55. Threaded components (bolts and nuts) shall be coated by the same zinc-coating process and the supplier's option is limited to one process per item with no mixed processes in a lot.

5. Chemical Composition

- 5.1 Grade A and B bolts, studs, and threaded rod shall have a heat analysis conforming to the requirements specified in **Table 1** based on the steel producer's heat analysis.
- 5.2 The purchaser shall have the option of conducting product analyses on finished bolts in each lot, which shall conform to the product analysis specified in **Table 1**.
- 5.3 In case of conflict or for referee purposes, the product analysis shall take precedence.
- 5.4 Bolts and studs are customarily furnished from stock, in which case individual heats of steel cannot be identified.

TABLE 1 Chemical Requirements for Grades A and B Bolts, Studs, and Threaded Rod

	Heat Analysis	Product Analysis
-	Heat Analysis	Product Analysis
Carbon, max	0.29	0.33
Manganese, max	1.20	1.25
Phosphorus, max	0.04	0.041
Sulfur, max		^A
Grade A	0.15	
Grade B	0.05	0.051

^A Resulfurized steel is not subject to rejection based on product analysis for sulfur.

5.5 Application of heats of steel to which bismuth, selenium, tellurium, or lead has been intentionally added shall not be permitted for Grade B bolts and studs.

5.6 Chemical analyses shall be performed in accordance with Test Methods, Practices, and Terminology [A751](#).

6. Mechanical Properties

6.1 Grades A and B bolts, studs, and threaded rod shall conform to the hardness specified in [Table 2](#).

6.2 Grade A and B bolts, studs, and threaded rod $\frac{1}{2}$ in. in diameter or less, other than those excepted in [6.4](#), shall be tested full size and shall conform to the requirements for tensile strength specified in [Table 3](#). Threaded rod is permitted to be cut to a length suitable for tensile testing and shall be treated using the same method specified for studs.

6.3 Grade A and B bolts, studs, and threaded rod larger than $1\frac{1}{2}$ in. in diameter, other than those excepted in [6.4](#), shall preferably be tested full size and when equipment of sufficient capacity is available and shall conform to the requirements for tensile strength specified in [Table 3](#). When equipment of sufficient capacity for full-size testing is not available, or when the length of the bolt or stud makes full-size testing impractical, machined specimens shall be tested and shall conform to the requirements specified in [Table 4](#).

6.4 Grades A and B bolts and studs less than three diameters in nominal length or bolts with drilled or undersize heads are not subject to tensile tests.

6.5 In the event that bolts, studs, and threaded rod are tested by both full size and by machine test specimen methods, the full-size test shall govern if a controversy between the two methods exists.

6.6 For bolts, studs, and threaded rod on which both hardness and tension tests are performed, acceptance based on tensile requirements shall take precedence in the event that there is controversy over low readings of hardness tests.

TABLE 2 Hardness Requirements for Bolts, Studs, and Threaded Rod

Grade	Nominal Length, in.	Hardness ^A			
		Brinell		Rockwell B	
		min	max	min	max
A	Less than 3 × dia ^B	121	241	69	100
	3 × dia and longer	...	241	...	100
B	Less than 3 × dia ^B	121	212	69	95
	3 × dia and longer	...	212	...	95

^A As measured anywhere on the surface or through the cross section.

^B Also bolts with drilled or undersize heads. These sizes and bolts with modified heads shall meet the minimum and maximum hardness as hardness is the only requirement.

TABLE 3 Tensile Requirements for Full-Size Bolts, Studs, and Threaded Rod

Bolt Size, in.	Threads per inch	Stress Area, ^A in. ²	Tensile Strength, lbf ^B		
			Grade A, min ^C	Grade B	
				min ^D	max ^D
1/4	20	0.0318	1 900	1 900	3 180
5/16	18	0.0524	3 100	3 100	5 240
3/8	16	0.0775	4 650	4 650	7 750
7/16	14	0.1063	6 350	6 350	10 630
1/2	13	0.1419	8 500	8 500	14 190
9/16	12	0.182	11 000	11 000	18 200
5/8	11	0.226	13 550	13 550	22 600
3/4	10	0.334	20 050	20 050	33 400
7/8	9	0.462	27 700	27 700	46 200
1	8	0.606	36 350	36 350	60 600
1 1/8	7	0.763	45 800	45 800	76 300
1 1/4	7	0.969	58 150	58 150	96 900
1 3/8	6	1.155	69 300	69 300	115 500
1 1/2	6	1.405	84 300	84 300	140 500
1 3/4	5	1.90	114 000	114 000	190 000
2	4 1/2	2.50	150 000	150 000	250 000
2 1/4	4 1/2	3.25	195 000	195 000	325 000
2 1/2	4	4.00	240 000	240 000	400 000
2 3/4	4	4.93	295 800	295 800	493 000
3	4	5.97	358 200	358 200	597 000
3 1/4	4	7.10	426 000	426 000	710 000
3 1/2	4	8.33	499 800	499 800	833 000
3 3/4	4	9.66	579 600	579 600	966 000
4	4	11.08	664 800	664 800	1 108 000

^A Area calculated from the equation:

$$A_s = 0.7854 [D - (0.9743/n)]^2$$

where:

- A_s = stress area,
- D = nominal diameter of bolt, and
- n = threads per inch.

ASTMA307-21

<https://standards.iteh.ai/catalog/standards/sist/c94a5d63-aa6a-4368-92d9-86bd94cdcdd1/astm-a307-21>
^B 1 lbf = 4.448 N.

^C Based on 60 ksi (414 MPa).

^D Based on 60–100 ksi (414–690 MPa).

TABLE 4 Tensile Requirements for Machined Specimens

	Grade A	Grade B
Tensile strength, ksi	60 min	60–100
Yield point, min ksi
Elongation in 2 in., min, %	18	18

7. Dimensions

7.1 Unless otherwise specified, threads on bolts and studs shall be the Coarse Thread Series as specified in the latest issue of ASME B1.1, and shall have a Class 2A tolerance. Unless otherwise specified, threads on threaded rod shall be per the requirements of the latest issue of ASME B18.31.3.

7.2 Unless otherwise specified, Grade A bolts shall be hex bolts with dimensions as given in the latest issue of ASME B18.2.1. Unless otherwise specified, Grade B bolts shall be heavy hex bolts with dimensions as given in the latest issue of ASME B18.2.1. Unless otherwise specified, threads on threaded rod shall be per the requirements of the latest issue of ASME B18.31.3.

7.3 Unless otherwise specified, bolts, studs, and threaded rod to be used with nuts or tapped holes which have been tapped oversize, in accordance with Specification A563, shall have threads as specified in 7.1 before hot-dip or mechanically deposited

zinc coating.

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[ASTMA307-21](#)

<https://standards.iteh.ai/catalog/standards/sist/c94a5d63-aa6a-4368-92d9-86bd94cdcdd1/astm-a307-21>