



Designation: B983 – 21

Standard Specification for Precipitation Hardened or Cold Worked, Seamless Nickel Alloy Pipe and Tube¹

This standard is issued under the fixed designation B983; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification covers high strength, seamless pipe and tube of nickel alloys (UNS N07022, UNS N07725, UNS N07740, UNS N09945, UNS N09925, UNS N07718, UNS N10276, UNS N06985)² as shown in [Table 1](#).

1.2 Pipe and tube shall be supplied in the cold worked or cold worked and precipitations hardened or solution annealed plus precipitation hardened and descaled conditions. When atmosphere control is used, descaling is not necessary.

1.3 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to become familiar with all hazards including those identified in the appropriate Safety Data Sheet (SDS) for this product/material as provided by the manufacturer, to establish appropriate safety, health, and environmental practices, and determine the applicability of regulatory limitations prior to use.*

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*³

¹ This specification is under the jurisdiction of ASTM Committee B02 on Nonferrous Metals and Alloys and is the direct responsibility of Subcommittee B02.07 on Refined Nickel and Cobalt and Their Alloys.

Current edition approved April 1, 2021. Published April 2021. Originally approved in 2012. Last previous edition approved in 2016 as B983 – 16^ε. DOI: 10.1520/B0983-21.

² New designation established in accordance with Practice E527 and SAE J1086, Practice for Numbering Metals and Alloys (UNS).

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

[B829 Specification for General Requirements for Nickel and Nickel Alloys Seamless Pipe and Tube](#)

[B899 Terminology Relating to Non-ferrous Metals and Alloys](#)

[E8 Test Methods for Tension Testing of Metallic Materials \[Metric\] E0008_E0008M](#)

[E527 Practice for Numbering Metals and Alloys in the Unified Numbering System \(UNS\)](#)

3. Terminology

3.1 Terms shall be defined in accordance with Terminology [B899](#).

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *average diameter, n*—See Terminology [B899](#).

3.2.2 *pipe, n*—See Terminology [B899](#) and Specification [B829](#).

3.2.3 *tube, n*—See Terminology [B899](#).

4. General Requirements

4.1 Material furnished under this specification shall conform to the applicable requirements of Specification [B829](#) unless otherwise provided herein.

5. Ordering Information

5.1 It is the responsibility of the purchaser to specify all requirements that are necessary for the material ordered under this specification. Examples of such requirements include, but are not limited to the following:

5.1.1 *Alloy*—See [Table 1](#).

5.1.1.1 *Heat Treatment or Cold Work or Type*—See [Table 2](#) and [Table 3](#).

5.1.2 *Dimensions:*

5.1.2.1 *Tube*—Outside diameter, minimum or average wall thickness, and length.

5.1.2.2 *Pipe*—Standard pipe size and schedule (Specification [B829](#)).

5.1.3 *Ends*—Plain ends cut and deburred will be furnished.

5.1.4 *Certification*—State if certification or a report of test results is required (Section [16](#)).

5.1.5 *Samples for Check Analysis*—State whether samples for check analysis should be furnished.

*A Summary of Changes section appears at the end of this standard

TABLE 1 Chemical Requirements

Element	UNS N07022	UNS N07725	UNS N07740	UNS N09945	UNS N09925	UNS N07718	UNS N10276	UNS N06985
Carbon	0.010 max	0.03 max	0.005-0.08	0.005-0.04	0.03 max	0.08 max	0.02 max	0.015 max
Manganese	0.5 max	0.35 max	1.0 max	1.0 max	1.00 max	0.35 max	1.0 max	1.0 max
Silicon	0.08 max	0.20 max	1.0 max	0.5 max	0.50 max	0.35 max	0.08 max	1.0 max
Phosphorous	0.025 max	0.015 max	0.030 max	0.03 max	...	0.015 max	0.030 max	0.04 max
Sulfur	0.015 max	0.010 max	0.030 max	0.03 max	0.030 max	0.015 max	0.030 max	0.03 max
Chromium	20.0-21.4	19.0-22.5	23.5-25.5	19.5-23.0	19.5-23.5	17.0-21.0	14.5-16.5	21.0-23.5
Cobalt	1.0 max	...	15.0-22.0	1.0 max	2.5 max	5.0 max
Molybdenum	15.5-17.4	7.00-9.50	2.0 max	3.0-4.0	2.50-3.50	2.80-3.30	15.0-17.0	6.0-8.0
Columbium	...	2.75-4.00	...	2.4-4.5	0.50 max	4.75-5.50
Titanium	...	1.00-1.70	0.5-2.5	0.5-2.5	1.90-2.40	0.65-1.15
Aluminum	0.5 max	0.35 max	0.2-2.0	0.01-0.7	0.10-0.50	0.20-0.80
Zirconium
Boron	0.006 max	...	0.0006–0.006	0.006 max
Iron	1.8 max	Remainder ^B	3.0 max	Remainder ^B	22.0 min ^A	Remainder ^B	4.0-7.0	18.0-21.0
Copper	0.5 max	...	0.50 max	1.5-3.0	1.50-3.00	0.30 max	...	1.5-2.5
Nickel	Remainder ^B	55.0–59.0	Remainder ^B	45.0-55.0	38.0-46.0	50.0-55.0	Remainder ^B	Remainder ^B
Tantalum	0.2 max
Tungsten	0.8 max	3.0-4.5	1.5 max
Columbium + Tantalum	0.50–2.5	0.50 max
Vanadium	0.35 max	...

^A Minimum: The element may be determined arithmetically by difference.
^B Remainder: The element may be determined arithmetically by difference.

5.1.6 *Purchaser Inspection*—If the purchaser wishes to witness tests or inspection of material at the place of manufacture, the purchase order must so state, indicating which tests or inspections are to be witnessed (Section 15).

6. Chemical Composition

6.1 The material shall conform to the composition limits specified in Table 1.

6.2 If a product (check) analysis is made by the purchaser, the material shall conform to the requirements specified in Table 1 subject to the permissible tolerances per Specification B829.

7. Mechanical Properties

7.1 Unless otherwise specified, the material shall be supplied in the cold worked (cw), or cold worked and precipitation hardened (prec hard), or solution annealed plus precipitation hardened condition as described in Table 2 and Table 3.

7.2 The mechanical properties of the material at room temperature shall conform to those shown in Table 3.

8. Hydrostatic Test or Non-Destructive Electric Test

8.1 Each pipe or tube shall be tested by the manufacturer by either hydrostatic or a non-destructive electric test in accordance with Specification B829. Hydrostatic testing at a pressure greater than 1000 psi may be performed upon agreement between the purchaser and manufacturer or at the option of the manufacturer provided that the allowable fiber stress per Specification B829 is not exceeded.

9. Weight

9.1 For calculation of mass or weight, the following densities shall be tested:

Alloy	Density	
	lb/in. ³	g/cm ³
UNS N07022	0.311	8.60
UNS N07725	0.300	8.31
UNS N07740	0.291	8.05
UNS N09945	0.296	8.2
UNS N09925	0.292	8.08
UNS N07718	0.296	8.19
UNS N10276	0.321	8.89
UNS N06985	0.294	8.14

10. Sampling

10.1 *Lots for Chemical Analysis and Mechanical Testing are as defined in Specification B829.*

10.2 *Sampling of Chemical Analysis:*

10.2.1 A representative sample shall be taken from each lot during pouring or subsequent processing.

10.2.2 Product (check) analysis shall be wholly the responsibility of the purchaser.

10.3 *Sampling for Mechanical Testing:*

10.3.1 A representative sample shall be taken from each lot of finished material.

11. Number of Tests and Retests

11.1 *Chemical Analysis*—One test per lot.

11.2 *Tension Test*—One test per lot.

11.3 *Retests*—If the specimen used in the mechanical test of any lot fails to meet the specified requirements, two additional specimens shall be taken from different sample pieces and tested. The results of the tests on both of these specimens shall meet the specified requirements.

12. Specimen Preparation

12.1 Tension test specimens shall be taken from material after final heat treatment and tested in the direction of fabrication.

TABLE 2 Heat Treatments

Alloy	Recommended Solution Annealing Treatment	Recommended Precipitation Hardening Treatment
UNS N07022 Type 1A or 1B	1800–2100°F (982–1149°C), hold ½ h/in., 5 min. minimum, rapid air cool or water quench	none
UNS N07022 Type 2	1800–2100°F (982–1149°C), hold ½ h/in., 5 min. minimum, rapid air cool or water quench	1075–1150°F (579–621°C), hold 10 h, air cool
UNS N07725 Type 1	1900 ± 25°F (1040 ± 14°C), hold 1 h per in. of thickness, water quench or rapid air/gas cool	1350 ± 25°F (730 ± 14°C), hold 8 h, furnace cool at 100°F (56°C) per min. to 1150 ± 25°F (620 ± 14°C), hold for 8 h, air cool
UNS N07725 Type 2	1900 ± 25°F (1040 ± 14°C), hold 1 h per in. of thickness, water quench or rapid air/gas cool	1350 ± 25°F (730 ± 14°C), hold 8 h, furnace cool at 100°F (56°C) per min. to 1150 ± 25°F (620 ± 14°C), hold for 8 h, air cool
UNS N07740	2012–2192°F (1100–1200°C), hold ½ h/in., 5 min. minimum, water quench or rapid air/gas cool	1400–1500°F (760–815°C), hold 4 h minimum for up to 2 in. thickness + additional ½ h per each additional in. of thickness, air cool
UNS N09945 Type 1	1850–1950°F (1010–1066°C) hold 0.5 to 4 h, water quench	1300–1350°F (704–732°C), for 6 to 8 h, furnace cool at 50–100°F (26–56°C)/h to 1125–1175°F (607–635°C) hold 6 to 8 h, air cool
UNS N09945 Type 2	1850–1950°F (1010–1066°C) hold 0.5 to 4 h, water quench	1300–1350°F (704–732°C), for 6 to 8 h, furnace cool at 50–100°F (26–56°C)/h to 1125–1175°F (607–635°C) hold 6 to 8 h, air cool
UNS N09925	Batch Anneal 1825–1875°F (996–1024°C) hold 0.5 to 4 h, air cool or faster	1365–15°F (740–9°C) hold 6 to 9 h, furnace cool to 1150°F (621°C) for total aging time of 18 min., air cool
UNS N07718	1875 ± 25°F (1024 ± 14°C) for 1 to 2 h, water quench	1425–1475°F (774–802°C) hold 6 to 8 h, air cool
UNS N10276	2050°F (1121°C) minimum for time commensurate with thickness	none
UNS N06985	2050°F (1121°C) minimum for time commensurate with thickness	none

TABLE 3 Mechanical Properties

Alloy	Condition ^A	Tensile Strength, min., ksi (MPa)	Yield Strength min., ksi (MPa)	Elongation in 2 in., (50 mm) or 4D ^B , min, %	Hardness Rc max
UNS N07022 Type 1A	Solution Ann + cw	160 (1103)	150 (1034)	17	42
UNS N07022 Type 1B	Solution Ann + cw	185 (1276)	180 (1240)	13	46
UNS N07022 Type 2	Solution Ann + cw + prec hard	178 (1227)	160 (1103)	15	50
UNS N07725 Type 1	Solution Ann + prec hard	150 (1035)	120 (827)	20	43
UNS N07725 Type 2	Solution Ann + cw + prec hard	150 (1035)	120 (827)	20	...
UNS N07740	Solution Ann + prec hard	150 (1035)	90 (620)	20	...
UNS N09945 Type 1	Solution Ann + prec hard	150 (1035)	130 (896)	18	42
UNS N09945 Type 2	Solution Ann + prec hard	165 (1138)	140 (965)	18	42
UNS N09925	Solution Ann + prec hard	140 (965)	110 (758)	18	38
UNS N07718	Solution Ann + prec hard	150 (1034)	125 (862)	20	40
UNS N10276 Type 1	Solution Ann + cw	115 (793)	110 (758)	11	40
UNS N10276 Type 2	Solution Ann + cw	130 (896)	125 (862)	10	40
UNS N06985 Type 1	Solution Ann + cw	115 (793)	110 (758)	11	40
UNS N06985 Type 2	Solution Ann + cw	130 (896)	125 (862)	10	40

^A See Table 2.

^B D refers to the diameter of the tension specimen.