



Designation: **E2206–11 (Reapproved 2015) E2206 – 21**

## Standard Test Method for Force Calibration of Thermomechanical Analyzers<sup>1</sup>

This standard is issued under the fixed designation E2206; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### 1. Scope

1.1 This test method describes the calibration or performance confirmation of the electronically applied force signal for thermomechanical analyzers over the range of 0 N to 1 N.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

~~1.3 There is no ISO method equivalent to this standard.~~

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

### 2. Referenced Documents

- 2.1 *ASTM Standards:*<sup>2</sup>
- [E4 Practices for Force Verification of Testing Machines](#)
  - [E473 Terminology Relating to Thermal Analysis and Rheology](#)
  - [E617 Specification for Laboratory Weights and Precision Mass Standards](#)
  - [E831 Test Method for Linear Thermal Expansion of Solid Materials by Thermomechanical Analysis](#)
  - [E1142 Terminology Relating to Thermophysical Properties](#)
  - [E1363 Test Method for Temperature Calibration of Thermomechanical Analyzers](#)
  - [E2113 Test Method for Length Change Calibration of Thermomechanical Analyzers](#)
  - [E2161 Terminology Relating to Performance Validation in Thermal Analysis and Rheology](#)

### 3. Terminology

3.1 The technical terms used in this standard are defined in Terminologies [E473](#), [E1142](#), and [E2161](#) including *calibration*, *conformance*, *precision*, *relative standard deviation*, *repeatability*, *reproducibility*, and *thermomechanical analyzer*.

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee [E37](#) on Thermal Measurements and is the direct responsibility of Subcommittee [E37.10](#) on Fundamental, Statistical and Mechanical Properties.

Current edition approved ~~Oct. 1, 2015~~ March 1, 2021. Published ~~October 2015~~ April 2021. Originally approved in 2002. Last previous edition approved in ~~2014~~ 2015 as [E2206–11](#):[E2206 – 11 \(2015\)](#). DOI: ~~10.1520/E2206-11R15~~ 10.1520/E2206-21.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

#### 4. Summary of Test Method

4.1 The electronic force signal generated by a thermomechanical analyzer is compared to that exerted by gravity on a known mass. The thermomechanical analyzer may be said to be in conformance if the performance is within established limits, typically 1 %. Alternatively, the force signal may be calibrated using a two-point calibration method.

#### 5. Significance and Use

5.1 Most thermomechanical analysis experiments are carried out with some force applied to the test specimen. This force is often created electronically. It may be constant or changed during the experiment.

5.2 This method demonstrates conformance or calibrates the electronically applied force signal.

5.3 This method may be used for research and development, quality control, manufacturing or regulatory applications.

5.4 Other thermomechanical analyzer calibration functions include temperature by Test Method **E1363** and length change by Test Method **E2113**.

#### 6. Apparatus

6.1 *Thermomechanical Analyzer*—The essential instrumentation required to provide a minimum thermomechanical analysis or thermodilatometric capability for this method includes:

6.1.1 *Rigid Specimen Holder*, inert, low expansivity material [typically  $<0.6 \mu\text{m}/(\text{m} \cdot \text{K})$ ] to center the specimen in the furnace and to fix the specimen to mechanical ground.

NOTE 1—Amorphous silica (quartz) is a commonly used material of construction. Materials of construction with greater expansivity may be used but shall be reported.

6.1.2 *Rigid (Expansion or Compression) Probe*, inert, low expansivity material [typically  $<0.6 \mu\text{m}/(\text{m} \cdot \text{K})$ ] which contacts the specimen with an applied compressive force (see **Note 1**).

6.1.3 *Sensing Element*, linear over a minimum range of 2 mm to measure the displacement of the rigid probe readable to  $\pm 1 \mu\text{m}$  resulting from changes in length of the specimen.

6.1.4 *Programmable Force Transducer*, to generate a constant force ( $\pm 1.0 \%$ ) of up to 1.0 N that is applied through the rigid probe to the specimen.

NOTE 2—Other force ranges may be used but shall be reported.

6.1.5 *Furnace*, capable of providing uniform controlled heating (cooling) of the specimen to a constant temperature or at a constant rate within the temperature range of  $-100 \text{ }^\circ\text{C}$  to  $600 \text{ }^\circ\text{C}$ .

NOTE 3—Other temperature ranges may be used but shall be reported.

6.1.6 *Temperature Controller*, capable of executing a specific temperature program by operating the furnace between selected temperature limits at a rate of change of up to  $10 \text{ }^\circ\text{C}/\text{min}$  constant to  $0.1 \text{ }^\circ\text{C}/\text{min}$  or at an isothermal temperature constant to  $\pm 0.5 \text{ }^\circ\text{C}$ .

NOTE 4—Other heating rates may be used but shall be reported.

6.1.7 *Temperature Sensor*, that can be attached to, in contact with, or reproducibly positioned in close proximity to the specimen to provide an indication of the specimen temperature to  $\pm 0.1 \text{ }^\circ\text{C}$ .

6.1.8 A means of sustaining an environment around the specimen of inert purge gas with a purge gas rate of 10 to  $100 \pm 5$  mL/min  $\pm 5$  mL/min.

NOTE 5—Typically, 99.9+ % pure nitrogen, argon, or helium is employed when oxidation in air is a concern. Unless effects of moisture are to be studied, use of dry purge gas is recommended and is essential for operation at subambient temperatures.

6.1.9 *Data Collection Device*, to provide a means of acquiring, storing, and displaying measured or calculated signals, or both. The minimum output signals required for thermomechanical analysis are a change in linear dimension, temperature, and time.

6.2 50 g to 100 g  $\pm 0.002$  % Class 4 or better *mass* (traceable to a national reference laboratory) in compliance with Specification E617.

## 7. Calibration

7.1 Prepare the thermomechanical analyzer for operation according to procedures recommended by the manufacturer of the thermomechanical analyzer as described in the Operations Manual.

7.2 Other calibration procedures which may be used, but which are not required in this standard include Test Methods E1363, E831, and E2113.

## 8. Procedure

8.1 With no specimen present, lower the probe so that it contacts the specimen holder. Zero the device so that no force (load) is applied by the probe to the specimen holder.

NOTE 6—The means for determining “no load” condition is specific to the instrument used. The user of this method should check the Instrument Operations Manual for this information.)

8.2 Apply a Class 4 or better (that is, Class 1, 2, 3, or 4) mass standard of 50 g to 100 g to the probe. Record the (traceable) mass of the standard as  $M_1$  in g. Apply a countering force to the force transducer so that no force is applied by the probe to the specimen holder. Record this force as  $F_2$  in mN.

NOTE 7—Other masses may be used but shall be reported.

8.3 Calculate the force calibration constant ( $S$ ) and conformity ( $C$ ) using the equations of Section 9.

## 9. Calculations

9.1 For the purpose of this test method, it is assumed that the relationship between observed force ( $F_2$ ) and the actual force ( $F_1$ ) is linear and is governed by Eq 1:

$$F_1 = F_2 \cdot S \quad (1)$$

where:

$S$  = force calibration constant (nominal value of 1.00000).

9.2 Calculate the force exerted by the standard mass in air using Eq 2:

$$F_1 = M a f \quad (2)$$

where:

$M$  = mass of the weight, g,

$a$  = standard acceleration due to gravity, (= 9.8065 m s<sup>-2</sup>),

$f$  = correction factor for local values of gravity and air buoyancy taken from Table 1, dimensionless, and

$F_1$  = force exerted by the standard mass, mN.

**TABLE 1 Unit Force Exerted by a Unit Mass in Air at Various Latitudes<sup>A</sup>**

Latitude, (°)	Elevation Above Sea Level, m (ft)					
	-30.5 to 152 (-100 to 500)	152 to 457 (500 to 1500)	457 to 762 (1500 to 2500)	762 to 1067 (2500 to 3500)	1067 to 1372 (3500 to 4500)	1372 to 1676 (4500 to 5500)
20	0.9978	0.9977	0.9976	0.9975	0.9975	0.9974
25	0.9981	0.9980	0.9979	0.9979	0.9978	0.9977
30	0.9985	0.9984	0.9983	0.9982	0.9982	0.9981
35	0.9989	0.9988	0.9987	0.9987	0.9986	0.9985
40	0.9993	0.9993	0.9992	0.9991	0.9990	0.9989
45	0.9998	0.9997	0.9996	0.9996	0.9995	0.9994
50	1.0003	1.0002	1.0001	1.0000	0.9999	0.9999
55	1.0007	1.0006	1.0005	1.0005	1.0004	1.0003

<sup>A</sup> Taken from Practice E4.

9.3 Calculate the calibration constant ( $S$ ) using the values from 8.2 and 9.2 and Eq 2.

$$S = \frac{F_1}{F_2} \quad (3)$$

iTeh Standards  
(<https://standards.iteh.ai>)  
Document Preview

[ASTM E2206-21](https://standards.iteh.ai/catalog/standards/sist/7c67d745-3ca1-4805-bc61-4aa0ed5817b5/astm-e2206-21)

<https://standards.iteh.ai/catalog/standards/sist/7c67d745-3ca1-4805-bc61-4aa0ed5817b5/astm-e2206-21>