



Designation: D7149 – 05 (Reapproved 2021)

Standard Practice for Determining the Freeze Thaw Stability of Adhesives¹

This standard is issued under the fixed designation D7149; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This practice determines the ability of an adhesive to withstand repeated freezing and thawing cycles at specific temperatures without any significant change in physical properties.

1.2 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

- [D907 Terminology of Adhesives](#)
- [D1084 Test Methods for Viscosity of Adhesives](#)
- [D1293 Test Methods for pH of Water](#)
- [D2556 Test Method for Apparent Viscosity of Adhesives Having Shear-Rate-Dependent Flow Properties Using Rotational Viscometry](#)

3. Terminology

3.1 *Definitions:*

3.1.1 Many of the terms utilized in this practice are defined in Terminology [D907](#).

¹ This practice is under the jurisdiction of ASTM Committee [D14](#) on Adhesives and is the direct responsibility of Subcommittee [D14.10](#) on Working Properties.

Current edition approved April 1, 2021. Published April 2021. Originally approved in 2005. Last previous edition approved in 2016 as D7149 – 05 (2016). DOI: 10.1520/D7149-05R21.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

4. Significance and Use

4.1 This practice will provide a procedure for determining the stability of an adhesive to withstand five repeated cycles, or as otherwise specified, of freezing and thawing at a specific temperature.

4.2 This practice will allow the user to determine whether or not the adhesive can be appropriately applied after cycling of freezing and thawing.

4.3 This practice will identify any significant changes in the manufactured viscosity of the product after five cycles, or as otherwise specified, of freezing and thawing at a specific temperature.

4.4 This practice will help determine if the pH of adhesive has changed significantly due to the freezing and thawing cycles.

5. Apparatus

5.1 A 1.0 L (1 qt) container, or larger, with lid. Other container sizes may be applicable for some adhesives.

5.2 Freezer capable of maintaining $-18 \pm -2^{\circ}\text{C}$ ($0.0 \pm -5^{\circ}\text{F}$) to $-7 \pm -2^{\circ}\text{C}$ ($20 \pm -5^{\circ}\text{F}$).

5.3 Brookfield RVT Viscometer 1-spindle TC at 5 – 20 rpm, Heliopath stand.

NOTE 1—Other viscometer models, their speed and spindle size, may be utilized as long as they comply to Test Methods [D1084](#) or [D2556](#) and are recommended by the manufacturer for such use.

5.4 pH meter.

5.5 Tongue depressor or similar.

6. Conditioning

6.1 Condition the adhesive to be tested 24 h at $23 \pm -2^{\circ}\text{C}$ ($73 \pm -4^{\circ}\text{F}$) with a relative humidity of $50 \pm -5\%$ prior to testing.

7. Procedure

7.1 Fill the container with adhesive to be tested.

7.2 Check the viscosity of the adhesive after it is transferred into the container, as defined in Test Methods [D1084](#) (Method B) or Test Method [D2556](#).

7.3 Check the pH of the adhesive after it is transferred into the container, as defined in Test Method [D1293](#).

7.4 Close the container with lid and place it into the freezer at the specified temperature to be tested for a period of not less than 16 h.

7.5 Remove container from freezer after the appropriate time limit and allow to thaw until the adhesive reaches room temperature as defined in 6.1. It is recommended that a constant temperature oven with a temperature set at $24 \pm -2^{\circ}\text{C}$ ($75 \pm -4^{\circ}\text{F}$) be used for the thawing procedure. This constitutes one freeze / thaw cycle. Remove container lid by appropriate means; if the adhesive forms a surface film remove with the tongue depressor without stirring contents.

7.6 Insert clean tongue depressor about one inch into the adhesive and remove slowly.

7.7 If the adhesive “strings” from the tongue depressor or appears gelled, the sample has failed the test. Report which particular cycle displayed a change in the physical properties or that had failed.

7.8 If adhesive appears to be of normal consistency, measure viscosity and pH and record.

7.9 Repeat steps 7.3 – 7.8 for a total of five cycles or until a change in physical properties or failure is noted.

8. Reporting

8.1 Report the following information:

8.1.1 Type of adhesive.

8.1.2 Temperature at which product was frozen and tested.

8.1.3 Initial viscosity and pH of adhesive.

8.1.4 Viscosity and pH of the individual freeze thaw cycles or if applicable after which cycle product was no longer classified as usable.

9. Precision and Bias

9.1 The precision and bias of this practice for measuring viscosity is essentially as specified in Test Method D1084. Other results produced from this practice are non-quantitative.

10. Keywords

10.1 freeze; stability; thaw

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/

[ASTM D7149-05\(2021\)](https://standards.iteh.ai/ASTM-D7149-05(2021))

<https://standards.iteh.ai/catalog/standards/sist/1e0736b7-09fc-4055-a933-1762f6f51ea0/astm-d7149-052021>