



Designation: D3808 – 01 (Reapproved 2021)

Standard Test Method for Qualitative Determination of Adhesion of Adhesives to Substrates by Spot Adhesion¹

This standard is issued under the fixed designation D3808; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers a simple qualitative procedure for quickly screening whether an adhesive will, under recommended application conditions, bond to a given substrate without actually making bonded assemblies.

1.2 The values stated in SI units are to be regarded as the standard. The values in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

[D907 Terminology of Adhesives](#)

[E171 Practice for Conditioning and Testing Flexible Barrier Packaging](#)

3. Terminology

3.1 *Definitions*—Many of the terms used in this test method are defined in Terminology [D907](#).

3.1.1 *spot adhesion, n*—a qualitative method of determining adhesion by attempting to pry a “spot” of cured adhesive from a substrate.

¹ This test method is under the jurisdiction of ASTM Committee [D14](#) on Adhesives and is the direct responsibility of Subcommittee [D14.40](#) on Adhesives for Plastics.

Current edition approved April 1, 2021. Published April 2021. Originally approved in 1979. Last previous edition approved in 2013 as D3808 – 01 (2013). DOI: 10.1520/D3808-01R21.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.

4. Summary of Test Method

4.1 Spots of adhesive (size can vary, but generally about 6 mm ($\frac{1}{4}$ in.) in diameter) are placed onto a substrate using the application procedure and curing conditions acceptable to both user and supplier of the adhesive.

4.2 The substrate preparation and environmental exposure of the spot of adhesive after cure or setting can be varied as desired.

4.3 The determination of whether an adhesive bonds to the substrate is made by simply trying to pry the spot of adhesive from the substrate.

4.4 The mode of failure is readily evident by examining whether the bond separated adhesively or cohesively, either in the adhesive or substrate.

5. Significance and Use

5.1 This is a quick, simple, and inexpensive test method for qualitatively determining, without the need to prepare bonded test specimens, whether the adhesive under consideration will bond to a particular substrate. If the results are acceptable, then standard quantitative adhesive test procedures can be used to obtain quantitative measurements of the adhesive’s performance.

5.2 This test method can also be used to compare relative adhesion of several adhesives to given substrates.

5.3 It can be used to determine whether an adhesive will continue to adhere to the substrate under specified environmental conditions.

5.4 It can be used to evaluate adhesion of a particular adhesive to a variety of substrates.

5.5 It can be used to obtain “subjective” comparative data between several adhesives on a given substrate by noting the relative ease of inducing failure between the adhesives tested.

5.6 It should be most applicable to adhesives that cure or set when exposed to “air” (ambient, heated, etc.) and could be used for anaerobic adhesives if testing is carried out in an oxygen-free atmosphere.

6. Apparatus

6.1 No special equipment is needed for application of the adhesive to the test substrate(s). When using hot-melt

adhesives, for example, it would be desirable to have a hand-gun applicator or equivalent apparatus to allow deposition of the hot-melt at a recommended application temperature. The use of such equipment is not mandatory as a hot plate can be used to melt a quantity of the hot melt to the application temperature in a deformable container such as an aluminum weighing dish. Upon reaching proper temperature, the hot melt can be poured onto the substrate after forming a pouring spout in the container.

6.2 For some applications it is desirable to preheat the substrate. For this reason an oven or other heat source would be useful.

6.3 To test adhesion of the adhesive spot, a thin stainless steel spatula or similar probe is needed to pry or lift the spot from the substrate.

7. Test Specimen

7.1 Any form or shape of the substrate is acceptable. It is advisable to place several spots of the same adhesive onto the substrate.

7.2 In most cases, it is most efficient to test several adhesives on the same substrate sample.

8. Conditioning

8.1 Store the test specimens at the test conditions for 24 h, unless other test time is described. Note this when recording data. If other conditions are not specified, the storage and test conditions shall be $23 \pm 2^\circ\text{C}$ and $50 \pm 5\%$ relative humidity. Specification E171 details these and other test conditions.

9. Failure

9.1 Failure is a visible separation of the adhesive spot either adhesively from the substrate or cohesively in the adhesive or substrate.

9.2 The ease of separation of the adhesive spot can be used to compare the relative performance of the adhesives.

10. Procedure

10.1 Run the tests in the same environment used to condition the test specimens and test apparatus.

10.2 Using a thin-bladed stainless steel spatula or probe, try to separate the adhesive spot from the substrate.

10.3 Note the type and ease of failure as described in Section 9.

11. Report

11.1 Report the following information:

11.1.1 Method of specimen preparation, that is, adhesive used, method of cure, substrate preparation, preheating of substrate, if hot-melt was used, application temperature, and any other relevant information.

11.1.2 Conditioning exposure.

11.1.3 Mode of failure, that is, *adhesive* to substrate or *cohesive* in adhesive or substrate, or both; relative ease of failure and any visible change in substrate due to adhesive attack, for example, discoloration, crazing, softening, etc.

12. Precision and Bias

12.1 No information is presented about either precision or bias of this test method, since the test result is nonquantitative.

13. Keywords

13.1 hot melt adhesive; spot adhesion; structural adhesive

<https://standards.iteh.ai/catalog/standards/sist/09d0174f-cf30-48fe-9a76-3be2a6dbe4f1/astm-d3808-012021>

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/