



Designation: ~~F1515--15~~ F1515 - 21

Standard Test Method for Measuring Light Stability of Resilient Flooring by Color Change¹

This standard is issued under the fixed designation F1515; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

1. Scope

1.1 This test method covers a procedure for determining the resistance of resilient floor covering to color change from exposure to light over a specified period of time.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.3 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:²

[D2244 Practice for Calculation of Color Tolerances and Color Differences from Instrumentally Measured Color Coordinates](#)

[D4459 Practice for Xenon-Arc Exposure of Plastics Intended for Indoor Applications](#)

[E177 Practice for Use of the Terms Precision and Bias in ASTM Test Methods](#)

[E691 Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method](#)

[G151 Practice for Exposing Nonmetallic Materials in Accelerated Test Devices that Use Laboratory Light Sources](#)

[G155 Practice for Operating Xenon Arc Light Apparatus for Exposure of Non-Metallic Materials](#)

[G177 Tables for Reference Solar Ultraviolet Spectral Distributions: Hemispherical on 37° Tilted Surface](#)

3. Summary of Practice

3.1 Specimens are exposed continuously at a controlled temperature and humidity to a properly filtered xenon-arc radiant-energy source. The filters selected are to simulate indoor exposure conditions behind window glass. See Practice [D4459](#).

3.2 To ensure uniform exposure, periodic specimen repositioning is a good practice to reduce the variability in exposure stresses experienced during the test interval.

NOTE 1—See Practice [G151](#) for guidance on repositioning of specimens.

¹ This test method is under the jurisdiction of ASTM Committee [F06](#) on Resilient Floor Coverings and is the direct responsibility of Subcommittee [F06.20](#) on Test Methods. Current edition approved ~~Dec. 15, 2015~~ April 1, 2021. Published ~~January 2016~~ April 2021. Originally approved in 1995. Last previous edition approved in ~~2008~~ 2015 as ~~F1515-03 (2008)~~ F1515 - 15. DOI: ~~10.1520/F1515-15~~ 10.1520/F1515-21.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

3.3 The effect of radiation (actinic and thermal) on the specimen shall be the color difference between the specimen before and after exposure.

4. Significance and Use

4.1 Resilient floor covering is made by fusing polymer materials under heat or pressure, or both, in various manufacturing and decorating processes. The polymer material may be compounded with plasticizers, stabilizers, fillers, and other ingredients for processability and product performance characteristics. The formulation of the compound can be varied considerably depending on the desired performance characteristics and methods of processing.

4.2 Light stability, which is resistance to discoloration from light, is a basic requirement for functional use.

4.3 This test method provides a means of measuring the amount of color change in flooring products when subjected to accelerated light exposure over a period of time (functional use of the flooring product).

4.4 This test method specifies that a sample is measured by a spectrophotometer and expressed in ΔE^* units before and after accelerated light exposure.

NOTE 2—It is the intent that this test method be used for testing light stability performance properties to be referenced in resilient flooring specifications.

5. Apparatus

5.1 The apparatus employed shall utilize either a water-cooled or air-cooled xenon-arc lamp as the source of radiation as described in Practices **D4459** or **G155**.

5.2 *Xenon Light Source*—The xenon light source consists of a quartz-jacketed burner tube charged with xenon gas.

5.3 *Glass Filters*—**Table 1** shows the relative spectral power distribution limits of xenon-arcs filtered for simulating a behind window-glass exposure.

5.4 *Light Monitor*—The light monitor shall be capable of measuring spectral irradiance at either 340 nm or at 300 to 400 nm incident to the specimen.

5.5 *Black Panel Temperature (BPT) Sensor*—A black-coated stainless steel panel, as specified in Practice **G155**, should be used as the standard reference to control test temperature. (Alternative devices such as the Black Standard Thermometer (BST) described in Practice **G151** may be used. The BST equivalent to the BPT = 145°F (63°C) has been found to be approximately 153°F (67°C)).

TABLE 1 Sunlight Behind Window Glass Simulation Relative Spectral Irradiance for Xenon-Arc Output as Percentage of Irradiance at 300–400 nm^A

Bandpass (nm)	Minimum Percent ^A	Window Glass Filtered Solar Radiation Percent ^B	Maximum Percent ^A
$\lambda < 300$		0.0	0.29
$300 \leq \lambda \leq 320$	0.1	≤ 0.5	2.8
$320 \leq \lambda \leq 360$	23.8	34.2	35.5
$360 \leq \lambda \leq 400$	62.5	65.3	76.1

^A Table 1 is copied from Practice **G155**.

^B The window glass filtered solar data is for a solar spectrum with atmospheric conditions and altitude chosen to maximize the fraction of short wavelength solar UV (defined in Practice **G177**) that has been filtered by window glass. The glass transmission is the average for a series of single strength window glasses tested as part of a research study for ASTM Subcommittee G3.02.9. While this data is provided for comparison purposes only, it is desirable for a xenon-arc with window glass filters to provide a spectrum that is a close match to this window glass filtered solar spectrum.

5.6 A suitable spectrophotometer or colorimeter with a minimum 0.25-in. (6.35-mm) diameter opening having both cool white fluorescent (CWF) and daylight (D-65) light sources that measure color in CIE L^* , a^* , b^* using CIE 10° Standard Observer and specular included. When an individual color cannot be totally covered within the 0.25 in. spectrophotometer opening, then the largest spectrophotometer opening shall be used. See Test Method [D2244](#).

6. Hazards

6.1 Check to be sure the apparatus is operating properly at the start of each test. Check the lamp condition at weekly intervals to be sure that the burner tube and optical filters are clean and that they have not exceeded the maximum recommended period of use.

6.2 Be sure specimens are held flat when measuring color.

7. Procedure

7.1 The test specimens shall be flat and of uniform thickness. Dimensions are not critical. However, the specimens should be capable of fitting the exposure rack and covering the aperture (usually 2.0 in. by 2.0 in. (50.8 mm by 50.8 mm) of the color-measuring apparatus used.

7.2 For each exposure time cut three specimens or cut one specimen and mark three test areas from each sample. All specimens shall be of similar color, pattern and texture.

NOTE 3—White, monochromatic, flat material is preferred for testing.

7.3 Obtain and record initial L^* , a^* , and b^* readings on each of the three specimens or areas with the color measuring equipment before placing in the xenon-arc test apparatus. Mark the exact area of the measurement for future location in the color measurement equipment.

7.4 Program the instrument to operate in the continuous light-on mode without water spray at an irradiance equivalent to 0.30 W/m^2 at 340 nm (that is, 37 W/m^2 at 300 nm to 400 nm). Place the black panel sensor and specimens on the specimen rack in accordance with manufacturer's recommendations and fill the remaining vacancies with non-UV reflecting blanks, for example, gray card stock.

7.4.1 Control black-panel temperature at $145^\circ F \pm 4^\circ F$ ($63^\circ C \pm 2^\circ C$) or BST at $153^\circ F \pm 4^\circ F$ ($67^\circ C \pm 2^\circ C$).

7.4.2 Control the relative humidity at $50 \pm 10 \%$.

7.5 Expose the specimens to be tested for a total of 400 h, with specimens removed for color measurements at 100 h, 200 h, 300 h, and 400 h.

7.6 Remove the specimens from the test apparatus and recondition at $73.4^\circ F$ ($23^\circ C$) for a minimum of 1 h.

7.7 Within 24 h after reconditioning, obtain final L^* , a^* , b^* and calculate ΔE^* readings on each specimen at the marked position using the color measuring equipment. Use either the cool white fluorescent (CWF) or daylight (D-65) light source. If during testing localized spotting is noted, additional sample testing is advised. However, judgment of color change will still be based upon ΔE^* value.

8. Reporting

8.1 Record the light source used for color change measurement.

8.2 Record initial and final L^* , a^* , b^* and ΔE^* values for each specimen and report the individual and average ΔE^* values.