



Designation: C1263 – 95 (Reapproved 2021)

Standard Test Method for Thermal Integrity of Flexible Water Vapor Retarders¹

This standard is issued under the fixed designation C1263; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the visual determination of the thermal integrity of flexible water vapor retarders for those materials classified under Specification C1136, including plastic, foil, or paper and composites of two or more of these materials to temperatures listed in the specification or purchase contract. The vapor retarders are intended for use at temperatures of -20 to 150°F (-29 to 66°C). This test method does not cover mastics or barrier coatings applied in liquid form or materials intended for use as weather barriers.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

C168 Terminology Relating to Thermal Insulation

C1136 Specification for Flexible, Low Permeance Vapor Retarders for Thermal Insulation

3. Terminology

3.1 *Definitions*—Definitions of terms used in this test method will be found in Terminology C168.

¹ This test method is under the jurisdiction of ASTM Committee C16 on Thermal Insulation and is the direct responsibility of Subcommittee C16.33

Current edition approved March 1, 2021. Published April 2021. Originally approved in 1994. Last previous edition approved in 2015 as C1263 – 95 (2015). DOI: 10.1520/C1263-95R21.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

4. Significance and Use

4.1 In many applications, the vapor retarders used on a thermal insulation will be exposed to the temperatures listed in 7.2. Cracking or delamination of the retarder under these conditions would, in most cases, cause it to lose its effectiveness as a vapor retarder material.

5. Apparatus

5.1 *1 in. (25 mm) Outside Diameter Solid, Mild Steel Mandrel.*

5.2 *Laboratory Oven*, capable of maintaining $\pm 3^{\circ}\text{F}$ (2°C) up to a temperature of 150°F (66°C).

5.3 *Laboratory Freezer*, capable of maintaining $\pm 3^{\circ}\text{F}$ (2°C) down to a temperature of -20°F (-29°C).

5.4 *Room or Cabinet*, capable of maintaining $73.4 \pm 3^{\circ}\text{F}$ ($23 \pm 2^{\circ}\text{C}$) and $50 \pm 2\%$ relative humidity.

5.5 *Insulated Gloves.*

6. Test Specimen

6.1 From each sampled vapor retarder, test three 1 ft (305 mm) square specimens for each temperature extreme specified.

7. Procedure

7.1 Condition test specimen at a temperature of $73.4 \pm 3^{\circ}\text{F}$ ($23 \pm 2^{\circ}\text{C}$) and a relative humidity of $50 \pm 2\%$ for a period of 24 h.

7.2 Expose the specimen and the mandrel to the test temperatures of -20 and 150°F (-29 and 66°C) for a period of 4 h.

7.3 At the end of the exposure period, with specimen and mandrel at test temperatures, bend each specimen around the mandrel once through an angle of 180° in 3 ± 2 s so that the opposing sides are parallel. If the two surfaces of the test specimen are materially different, six specimens shall be tested with three specimens of each surface tested on the outside of the bend.

NOTE 1—When test conditions specify both low temperature and high temperature exposure conditions on the same vapor retarder, it is satisfactory to use the same specimen or to select separate specimens for each of the exposed temperatures, unless the specification or contract explicitly states that exposure tests must be conducted on the same specimen. If the latter is so, the test specimen must be reconditioned before submitting it

to the next test temperature.

7.4 Immediately examine each specimen, while in the bent condition, for any cracks or delamination.

NOTE 2—Where multiple specimens are being examined, it is permissible to remove the tested specimen, while still in the bent condition, from the mandrel to allow for rapid reuse of the mandrel. The specimen must be restrained in the bent condition with paper clips or other suitable means until it returns to room temperature and is then examined.

7.5 To inspect for delamination, let each specimen return to room temperature, open to a flat condition and examine.

7.6 Any visible evidence of cracking or delamination on any of the three specimens shall constitute failure.

8. Report

8.1 Report the following information:

8.1.1 Identification of the material tested, including its composition and date of manufacture, if available.

8.1.2 Test temperature(s).

8.1.3 Date of testing.

8.1.4 Pass or fail and description of the failure, if any.

9. Precision and Bias

9.1 No precision measurement is necessary as this test method reports only a pass-fail condition of the test specimen.

10. Keywords

10.1 cracking; delamination; thermal integrity; vapor retarders

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/

<https://standards.iteh.ai>

Document Preview

[ASTM C1263-95\(2021\)](#)

<https://standards.iteh.ai/catalog/standards/sist/af2b5133-4142-4fad-b3ff-b6e7b3fcf27a/astm-c1263-952021>