



## Standard Test Method for Using Reflectance Spectra to Produce an Index of Temperature Rise in Polymeric Siding<sup>1</sup>

This standard is issued under the fixed designation D7990; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reappraisal.

### 1. ~~Scope~~ Scope\*

1.1 This test method uses reflectance spectra from the ultraviolet, visible, and near infrared region to produce an index of the temperature rise of polymeric siding above ambient temperature that occurs due to absorption of the sun's energy.

1.2 The test method determines the intensity factor of a sample color. The intensity factor is a function of the sample's reflectance spectra and the energy output of the heat lamp used in the test method Test Method **D4803**.

1.3 **Appendix X1** provides a method for using the intensity factor to determine the maximum temperature rise of a sample under severe solar exposure.

1.3.1 A correlation between intensity factor and heat buildup (temperature rise) as predicted by Test Method **D4803** exists.

1.3.2 The heat buildup (temperature rise) for a polymeric building product specimen is determined from its reflectance spectra and the correlation's regression equation.

1.4 *Units*—The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.6 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

### 2. Referenced Documents

#### 2.1 ASTM Standards:

D2244 Practice for Calculation of Color Tolerances and Color Differences from Instrumentally Measured Color Coordinates

**D4803** Test Method for Predicting Heat Buildup in PVC Building Products

**E903** Test Method for Solar Absorptance, Reflectance, and Transmittance of Materials Using Integrating Spheres

**E1331** Test Method for Reflectance Factor and Color by Spectrophotometry Using Hemispherical Geometry

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee **D20** on Plastics and is the direct responsibility of Subcommittee **D20.24** on Plastic Building Products. Current edition approved Dec. 1, 2015/April 1, 2021. Published December 2015/April 2021. Originally approved in 2015. Last previous edition approved in 2015 as D7990 – 15. DOI: ~~10.1520/D7990-15~~10.1520/D7990-21.

\*A Summary of Changes section appears at the end of this standard

### 3. Terminology

#### 3.1 Definitions of Terms Specific to This Standard:

3.1.1 *fractional absorptance*—one minus Fractional Reflectance,  $1 - R$ .

3.1.2 *fractional reflectance*—the percentage of energy reflected by a sample at a given wavelength, divided by 100.

3.1.3 *intensity factor*—an indicator of a specimen's heat buildup based on its reflectance spectrum and the energy output of the IR lamp used in Test Method **D4803**.

##### 3.1.3.1 Discussion—

The intensity factor is a summation product of the heat lamp's relative intensity and the specimen's fractional absorptance at 20 nm intervals between 200 and 2,500 nm.

3.1.4 *heat buildup*—the temperature rise above that of ambient air due to the amount of energy absorbed from the sun by a specimen.

3.1.5 *relative intensity (of heat lamp)*—the lamp's spectral output across the range of 200 nm to 2500 nm, normalized to a value of 100 at the lamp's maximum output.

### 4. Summary of Test Method

4.1 The specimen's size must cover the spectrophotometer's measurement port, typically 25.4 mm in diameter. Typical sample dimensions are 102 by 102 by 1.3 mm.

4.2 A black backer card or plaque is used directly behind the specimen to absorb any radiant energy transmitted through the specimen.

4.3 The spectral reflectance curve of the test specimen is measured to determine the amount of energy the specimen absorbs at each wavelength.

4.4 The intensity factor of the test specimen is the result of a series summation for the specimen's spectral absorptance and the relative intensity of the IR lamp used in Test Method **D4803**. The product of the specimen's spectral absorptance and relative intensity is determined for the spectral region of 200 – 2,500 nm at an interval of 20 nm

4.5 **Appendix X1** provides a method for using the intensity factor to determine the maximum temperature rise of a sample under severe solar exposure.

4.5.1 A correlation of intensity factors and heat buildup (temperature rise) results from Test Method **D4803** for a number of specimens was determined to derive an equation expressing a specimen's temperature rise as a function of its reflectance.

4.5.2 A specimen's heat buildup is determined by measuring its reflectance in the UV, VIS, and NIR spectral region and the correlation's regression equation.

### 5. Significance and Use

5.1 Heat buildup of polymeric building products due to absorption of energy from the sun may lead to distortion problems. Test Method Test Method **D4803** was developed to predict a building product's heat buildup (temperature rise). It compares the relative temperature changes of a pigmented PVC product and a PVC panel containing carbon black when exposed to an infrared heat lamp. Based on experimental results that determined the maximum temperature for this black panel under both solar exposure and in the laboratory test, a method for determining the exterior temperature rise and heat buildup for a test panel was developed. This test has shown to be useful and reliable but is time consuming and requires controlled conditions to minimize sources of variation.

5.2 This test method uses a spectrophotometer to measure a specimen's reflectance in the ultraviolet, visible, and near infrared region and uses the spectral power distribution of the heat lamp specified in Test Method **D4803** to determine an intensity factor, which is an index of the relative spectral energy absorption by the specimen.

5.2.1 The temperature rise that would occur under an Test Method **D4803** test is proportional to this intensity factor. An equation has been derived from the correlation of the intensity factor and temperature rise data obtained from Test Method **D4803** testing of samples with a wide range of color and lightness. A total of 99 samples were studied and represent samples with the lowest to highest temperature rise. Linear regression analysis yields a R<sup>2</sup> correlation coefficient of 0.98.

5.2.2 The procedure in **Appendix X1** allows prediction of temperature rise that would result from testing of the same sample under Test Method **D4803**.

5.2.3 As this procedure is a correlation to results obtained by Test Method **D4803**, it is a method that yields a relative temperature rise compared to black under certain defined severe conditions, but does not predict actual field application temperatures of the product. These product temperatures are influenced by incident angle of the sun, clouds, wind speed, insulation, installation behind glass, etc.

5.3 The intensity factor itself is a dimensionless index of the relative energy absorption of the specimen, without conversion to a temperature rise. It can be used to compare the heat buildup characteristics of different colors, or different candidate formulations for the same color. It can also be used to categorize color into ranges of intensity factor, to be used as a basis for testing of full siding products for resistance to thermal distortion.

## 6. Apparatus

6.1 *UV/VIS/NIR Spectrophotometer*—The spectral reflectance data are obtained using a spectrophotometer equipped with a PTFE-coated integrating sphere detector, capable of reading spectral reflectance across the range of 200 nm to 2500 nm.

## 7. Sampling and Test Specimens

7.1 Samples shall be representative of the color or pigment system under study.

7.2 Test specimens shall consist of the actual product or material in which the color is used, in a thickness typical of the actual product.

7.3 An opaque black backing material is placed behind the specimen. The backer shall be a card, plaque or other rigid or semi-rigid material. The black color shall cover the entire surface.

7.3.1 Measure the color of the backer in accordance with Test Method **E1331**. ~~Calculate the CIE 1976 L\*a\*b\* units in accordance with the “CIE 1976 L\*a\*b\* Uniform Color Space and Color-Difference Equation” in Practice Report~~ Report the color values as CIE L\*, a\*, b\* and save them in a ~~D2244~~ permanent record.

7.3.2 The backer shall have L\* not greater than 30.0, and both a\* and b\* shall not exceed  $\pm 3.0$ .

7.4 The specimen and backer shall be large enough to cover the instrument’s sample port and fit inside the instrument’s measurement compartment.

## 8. Procedure

8.1 Allow the spectrophotometer instrument to warm up and stabilize according to manufacturer’s instructions.

8.2 Acquire a baseline correction according to manufacturer’s instructions.

8.3 Acquire spectral data between 200 and 2,500 nm.

8.4 Check the spectrophotometer’s readiness by testing a known standard.

8.5 Once the instrument’s readiness is confirmed, proceed with the analysis.

8.6 Place the test specimen and black backer on the measurement port with the side to be tested facing and covering the instrument's measurement port.

8.7 Acquire the test specimen's spectral reflectance data 200 – 2,500 nm following the procedures in Test Method **E903**.

**iTeh Standards**  
**(<https://standards.itih.ai>)**  
**Document Preview**

[ASTM D7990-21](#)

<https://standards.itih.ai/catalog/standards/sist/7123fe5d-0bf5-4f84-b333-4ccf638d4187/astm-d7990-21>