



Designation: D6929 – 21

Standard Practice for Evaluating the Effect of Freezing on Emulsified Asphalts¹

This standard is issued under the fixed designation D6929; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 Emulsified asphalt is normally damaged by freezing temperatures, but specially formulated materials are expected to pass this practice.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 The text of this standard references notes and footnotes which provide explanatory material. These notes and footnotes (excluding those in tables and figures) shall not be considered as requirements of the standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

D3666 Specification for Minimum Requirements for Agencies Testing and Inspecting Road and Paving Materials

3. Significance and Use

3.1 Certain agencies who desire to use, store, or transport emulsified asphalt under less than ideal weather conditions may require that the product remain homogeneous (unbroken) after being subjected to a temperature of $-18\text{ }^{\circ}\text{C}$.

¹ This practice is under the jurisdiction of ASTM Committee D04 on Road and Paving Materials and is the direct responsibility of Subcommittee D04.42 on Emulsified Asphalt Test.

Current edition approved May 1, 2021. Published May 2021. Originally approved in 2004. Last previous edition approved in 2016 as D6929 – 16. DOI: 10.1520/D6929-21.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

NOTE 1—The quality of the results produced by this standard are dependent on the competence of the personnel performing the procedure and the capability, calibration, and maintenance of the equipment used. Agencies that meet the criteria of Specification D3666 are generally considered capable of competent and objective testing, sampling, inspection, etc. Users of this standard are cautioned that compliance with Specification D3666 alone does not completely ensure reliable results. Reliable results depend on many factors; following the suggestions of Specification D3666 or some similar acceptable guideline provides a means of evaluating and controlling some of those factors.

4. Sample Conditioning

4.1 All emulsified asphalts shall be properly stirred to achieve homogeneity.

4.2 All emulsified asphalts with viscosity testing requirements of $50\text{ }^{\circ}\text{C}$ shall be heated to $50 \pm 3\text{ }^{\circ}\text{C}$ in the original sample container in a water bath or oven. The container should be vented to relieve pressure. After the sample reaches $50 \pm 3\text{ }^{\circ}\text{C}$, stir the sample to achieve homogeneity.

4.3 Emulsified asphalts with viscosity testing requirements of $25\text{ }^{\circ}\text{C}$ should be mixed or stirred at $25 \pm 3\text{ }^{\circ}\text{C}$ in the original sample container to achieve homogeneity.

NOTE 2—Emulsified asphalts with viscosity testing requirements of $25\text{ }^{\circ}\text{C}$ may be heated and stirred as specified in 4.2, if necessary. In the event the 4.2 method is used, the sample should be cooled to $25 \pm 3\text{ }^{\circ}\text{C}$.

5. Apparatus

5.1 *Freezer*—Capable of maintaining a test temperature of $-18 \pm 5\text{ }^{\circ}\text{C}$.

5.2 *Metal Container*, such as a 500-mL press-top can.

5.3 *Glass Stirring Rod*, of optional size.

6. Procedure

6.1 Place approximately 400 g of the emulsified asphalt in a clean metal container.

6.2 Expose the emulsified asphalt in the closed container to an air temperature of $-18 \pm 5\text{ }^{\circ}\text{C}$ for 12 to 18 consecutive hours.

6.3 At the expiration of the freezing period, permit the emulsified asphalt to thaw by exposure of the container to ambient temperature.

6.4 Repeat the freezing and thawing periods until the emulsified asphalt has been subjected to three cycles of freezing and thawing.

6.5 After the third cycle, the emulsified asphalt may be homogeneous or broken.

NOTE 3—An emulsified asphalt is considered broken when it may have separated into distinct layers which cannot be rendered homogeneous by stirring at laboratory conditions.

7. Report

7.1 Report the result of this practice as either “homogeneous” or “broken.”

8. Keywords

8.1 asphalt; broken; cationic emulsified asphalt; emulsified asphalt; freezing

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>

iTeh Standards (<https://standards.iteh.ai>) Document Preview

[ASTM D6929-21](#)

<https://standards.iteh.ai/catalog/standards/sist/f12f98e6-3785-4d88-8c65-b9b228e777fe/astm-d6929-21>