



SLOVENSKI STANDARD
SIST EN 14227-5:2005
01-januar-2005

<]XfUj`] bc`j YnUbY`na Yg]`È`GdYWZ_ UW`Y`È) "XY.`G`]XfUj`] b]a]`j Yn]j]`j YnUbY`na Yg]

Hydraulically bound mixtures - Specifications - Part 5: Hydraulic road binder bound mixtures

Hydraulisch gebundene Gemische - Anforderungen - Teil 5: Tragschichtbinderbundene Gemische für den Straßenbau

Mélanges traités aux liants hydrauliques - Spécifications - Partie 5 : Mélanges traités au liant hydraulique routier

[SIST EN 14227-5:2005](https://standards.iteh.ai/catalog/standards/sist/333d013f-c156-4b02-89f1-d0d0cfe674e/sist-en-14227-5-2005)

[https://standards.iteh.ai/catalog/standards/sist/333d013f-c156-4b02-89f1-](https://standards.iteh.ai/catalog/standards/sist/333d013f-c156-4b02-89f1-d0d0cfe674e/sist-en-14227-5-2005)

[d0d0cfe674e/sist-en-14227-5-2005](https://standards.iteh.ai/catalog/standards/sist/333d013f-c156-4b02-89f1-d0d0cfe674e/sist-en-14227-5-2005)

Ta slovenski standard je istoveten z: EN 14227-5:2004

ICS:

93.080.20 Materiali za gradnjo cest Road construction materials

SIST EN 14227-5:2005

en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 14227-5:2005

<https://standards.iteh.ai/catalog/standards/sist/333d013f-c156-4b02-89fd-d0d0cefe674e/sist-en-14227-5-2005>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN 14227-5

July 2004

ICS 93.080.20

English version

Hydraulically bound mixtures - Specifications - Part 5: Hydraulic road binder bound mixtures

Mélanges traités aux liants hydrauliques - Spécifications -
Partie 5 : Mélanges traités au liant hydraulique routier

Hydraulisch gebundene Gemische - Anforderungen - Teil
5: Tragschichtbinderbundene Gemische für den
Straßenbau

This European Standard was approved by CEN on 16 April 2004.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

[SIST EN 14227-5:2005](https://standards.iteh.ai/catalog/standards/sist/333d013f-c156-4b02-89f1-d0d0cefe674e/sist-en-14227-5-2005)

<https://standards.iteh.ai/catalog/standards/sist/333d013f-c156-4b02-89f1-d0d0cefe674e/sist-en-14227-5-2005>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

	page
Foreword.....	4
1 Scope	5
2 Normative references	5
3 Terms and definitions	6
4 Symbols and abbreviations	6
5 Constituents	7
5.1 Hydraulic road binder.....	7
5.2 Aggregates	7
5.3 Water	7
5.4 Retarders	7
6 Hydraulic road binder bound mixtures.....	7
6.1 Types.....	7
6.2 Water content.....	7
6.3 Proportioning of the constituents, grading and dry density.....	7
6.4 Laboratory mechanical performance.....	8
6.5 Hydraulic road binder bound mixtures 1.....	8
6.6 Hydraulic road binder bound mixture 2.....	8
6.6.1 Description	8
6.6.2 Grading of the mixture.....	8
6.6.3 Compacity.....	8
6.6.4 Immediate bearing index of the mixture.....	8
6.7 Hydraulic road binder bound mixture 3.....	8
6.7.1 Description	8
6.7.2 Grading of the mixture	9
6.7.3 Immediate bearing index of the mixture.....	9
6.8 Hydraulic road binder bound mixture 4.....	9
7 Laboratory mechanical performance classification.....	9
7.1 General.....	9
7.2 Classification by compressive strength.....	9
7.3 Classification by R_b , E	10
7.3.1 General.....	10
7.3.2 Method by direct tensile testing.....	11
7.3.3 Method by indirect tensile testing.....	11
7.3.4 Method by indirect tensile and compression testing.....	11
8 Workability period.....	11
9 Other characteristics	12
10 Production control.....	12
11 Designation and description	12
11.1 Designation	12
11.2 Description	12
12 Marking and labelling	13
Annex A (normative) Compacity of a hydraulic road binder bound mixture 2.....	18
Annex B (informative) Production control for hydraulic road binder bound mixtures	19

B.1	General	19
B.2	Quality manual	19
B.3	Organization.....	19
B.3.1	Responsibility and authority	19
B.3.2	Management representative.....	19
B.3.3	Internal audits	19
B.3.4	Management review	20
B.3.5	Sub-contract services	20
B.3.6	Records	20
B.3.7	Training	20
B.4	Control procedures	20
B.4.1	Production management	20
B.4.2	Composition of the mixture.....	21
B.4.3	Constituents.....	21
B.4.4	Process control	21
B.4.5	Inspection, calibration and control of process equipment.....	21
B.4.6	Handling and delivery	22
B.5	Inspection and testing of constituents and mixtures during production.....	22
B.5.1	General	22
B.5.2	Characteristics that require control during production	22
B.5.3	Frequency of sampling the mixture.....	23
B.6	Inspection and testing equipment.....	23
B.6.1	General	23
B.6.2	Measuring and testing equipment.....	23
B.6.3	Measuring and testing equipment in the process	23
B.6.4	Measuring and testing equipment in laboratory	23
B.7	Non-conformity.....	24
B.7.1	General	24
B.7.2	Non-conformity of constituents.....	24
B.7.3	Non-conformity of the mixture	24
Bibliography	25

SIST EN 14227-5:2005
<https://standards.iteh.ai/catalog/standards/sist/333d013f-c156-4b02-89f1-d0d0cfe674e/sist-en-14227-5-2005>

EN 14227-5:2004 (E)

Foreword

This document (EN 14227-5:2004) has been prepared by Technical Committee CEN/TC 227 "Road materials", the secretariat of which is held by DIN.

This document shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by January 2005, and conflicting national standards shall be withdrawn at the latest by January 2005.

This document is one of a series of standards for hydraulically bound mixtures:

prEN 14227-1, *Unbound and hydraulically bound mixtures — Specifications — Part 1: Cement bound granular mixtures*

prEN 14227-2, *Hydraulically bound mixtures — Specifications — Part 2: Slag bound mixtures*

EN 14227-3, *Hydraulically bound mixtures — Specifications — Part 3: Fly ash bound mixtures*

EN 14227-4, *Hydraulically bound mixtures — Specifications — Part 4: Fly ash for hydraulically bound mixtures*

EN 14227-5, *Hydraulically bound mixtures — Specifications — Part 5: Hydraulic road binder bound mixtures*

prEN 14227-10, *Hydraulically bound mixtures — Specifications — Part 10: Soil treated by cement*

prEN 14227-11, *Hydraulically bound mixtures — Specifications — Part 11: Soil treated by lime*

prEN 14227-12, *Hydraulically bound mixtures — Specifications — Part 12: Soil treated by slag*

prEN 14227-13, *Hydraulically bound mixtures — Specifications — Part 13: Soil treated by hydraulic road binder*

prEN 14227-14, *Hydraulically bound mixtures — Specifications — Part 14: Soil treated by fly ash*

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

1 Scope

This document specifies hydraulic road binder bound mixtures for roads, airfields and other trafficked areas and specifies the requirements for their constituents, composition and laboratory performance classification.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 933-1, *Tests for geometrical properties of aggregates — Part 1: Determination of particle size distribution — Sieving method*

EN 1097-6:2000, *Tests for mechanical and physical properties of aggregates – Part 6: Determination of particle density and water absorption*

EN 1097-7, *Tests for mechanical and physical properties of aggregates – Part 7: Determination of the particle density of filler – Pycnometer method*

EN 13242, *Aggregates for unbound and hydraulically bound materials for use in civil engineering work and road construction*

ENV 13282, *Hydraulic road binders — Composition, specifications and conformity criteria*

EN 13286-1, *Unbound and hydraulically bound mixtures — Part 1: Test methods for laboratory reference density and water content – Introduction, general requirements and sampling*

EN 13286-2, *Unbound and hydraulically bound mixtures — Part 2: Test methods for the determination of the laboratory reference density and water content — Proctor compaction*

EN 13286-3, *Unbound and hydraulically bound mixtures — Part 3: Test methods for laboratory reference density and water content — Vibrocompression with controlled parameters*

EN 13286-4, *Unbound and hydraulically bound mixtures — Part 4: Test methods for laboratory reference density and water content — Vibrating hammer*

EN 13286-5, *Unbound and hydraulically bound mixtures — Part 5: Test methods for laboratory reference density and water content — Vibrating table*

EN 13286-40, *Unbound and hydraulically bound mixtures — Part 40: Test method for the determination of the direct tensile strength of hydraulically bound mixtures*

EN 13286-41, *Unbound and hydraulically bound mixtures — Part 41: Test method for the determination of the compressive strength of hydraulically bound mixtures*

EN 13286-42, *Unbound and hydraulically bound mixtures — Part 42: Test method for the determination of the indirect tensile strength of hydraulically bound mixtures*

EN 13286-43, *Unbound and hydraulically bound mixtures — Part 43: Test method for the determination of the modulus of elasticity of hydraulically bound mixtures*

EN 14227-5:2004 (E)

EN 13286-45, *Unbound and hydraulically bound mixtures — Part 45: Test method for the determination of the workability period of hydraulically bound mixtures*

EN 13286-47, *Unbound and hydraulically bound mixtures — Part 47: Test methods for the determination of California bearing ratio, immediate bearing index and linear swelling*

prEN 13286-50, *Unbound and hydraulically bound mixtures — Part 50: Methods for the manufacture of test specimens of hydraulically bound mixtures using Proctor equipment or vibrating table compaction*

prEN 13286-51, *Unbound and hydraulically bound mixtures — Part 51: Method for the manufacture of test specimens of hydraulically bound mixtures by vibrating hammer compaction*

prEN 13286-52, *Unbound and hydraulically bound mixtures — Part 52: Method for the manufacture of test specimens of hydraulically bound mixtures by vibrocompression*

prEN 13286-53, *Unbound and hydraulically bound mixtures — Part 53: Method for the manufacture of test specimens of hydraulically bound mixtures by axial compression*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1**hydraulically bound mixture**

mixture which sets and hardens by hydraulic reaction

3.2**hydraulic road binder bound mixture**

hydraulically bound mixture where hydraulic road binder is the binder

3.3**slenderness ratio**

height to diameter ratio of the specimen

3.4**compacity**

ratio of the absolute volume of the solid to the apparent volume of the mixture (see annex A)

4 Symbols and abbreviations

For the purpose of this document, the following symbols and abbreviations apply.

- R_c is the compressive strength, expressed in megapascals (MPa);
- R_t is the direct tensile strength, expressed in megapascals (MPa);
- R_{it} is the indirect tensile strength, expressed in megapascals (MPa);
- E is the modulus of elasticity, expressed in megapascals (MPa);
- E_c is the E determined by compression, expressed in megapascals (MPa);
- E_t is the E determined in direct tension, expressed in megapascals (MPa);
- E_{it} is the E determined in indirect tension, expressed in megapascals (MPa).

5 Constituents

5.1 Hydraulic road binder

Hydraulic road binder shall comply with ENV 13282 or with an European approval or equivalent or with the provisions valid in the place of use.

5.2 Aggregates

Aggregates shall be selected from EN 13242.

The properties and the appropriate categories of the aggregates shall be specified depending on the position of the hydraulic road binder bound mixture in the pavement structure and the traffic to be carried.

NOTE Siliceous fly ash conforming to EN 14227-4 may be used as an addition to the aggregates.

Aggregates shall be volumetrically stable. When this is not the case, the use of the mixture shall be permitted provided there is a satisfactory performance record or a thorough laboratory evaluation of the mixture has been carried out in accordance with provisions valid at the place of use.

5.3 Water

Water shall not contain components which adversely affect the hardening and the performance of the hydraulic road binder bound mixtures.

5.4 Retarders

Retarders shall comply with provisions valid in the place of use.

NOTE Generally retarders are not necessary.

6 Hydraulic road binder bound mixtures

6.1 Types

Hydraulic road binder bound mixture shall be made from the constituents specified in 5.

The mixture shall be selected from the 4 types described below and shall conform to the specified requirements for the selected mixture.

6.2 Water content

The water content shall be selected to permit compaction on site by rolling and to optimize the mechanical performance of the mixture. The water content shall be determined by the Proctor test or other method in accordance with EN 13286-1 to 5 and limits set to give a workable range of water content on site compatible with the compaction and the desired mechanical performance of the mixture.

6.3 Proportioning of the constituents, grading and dry density

The proportioning of the constituents, expressed as a percentage by dry mass of the total dry mass of the mixture, the grading and the dry density of the mixture, shall be declared. The declared proportions shall be based on the laboratory mixture design and/or practical experiences with mixtures produced with the same constituents and under the same conditions in a way that the mixture complies with the requirements of this document.

EN 14227-5:2004 (E)

NOTE Irrespective of the binder content necessary to fulfil the strength requirements of this document, the binder content should normally not be less than a minimum value fixed by provisions valid at the place of use to ensure adequate distribution of the binder through out the mixture.

6.4 Laboratory mechanical performance

The laboratory mechanical performance characterization and class shall be selected from clause 7.

6.5 Hydraulic road binder bound mixtures 1

Hydraulic road binder bound mixture 1 shall be a 0/31,5 mm mixture with a grading, determined in accordance with EN 933-1, complying with the requirements in Figure 1.

6.6 Hydraulic road binder bound mixture 2**6.6.1 Description**

Hydraulic road binder bound mixture 2 shall be a granular mixture with compacity requirement. There are 3 sub-types depending on the aggregate size.

6.6.2 Grading of the mixture

The grading of the selected sub-type, determined in accordance with EN 933-1, shall comply with Table 1. According to the use of the mixture, either category G1 or category G2 of the grading envelopes in Figures 2 to 4 shall be specified.

Table 1 — Grading of hydraulic road binder bound mixture 2

Column	1	2	3
Line	Hydraulic road binder bound mixture	Grading category	Grading envelopes
1	2-0/20	G1 or G2	Figure 2
2	2-0/14	G1 or G2	Figure 3
3	2-0/10	G1 or G2	Figure 4

6.6.3 Compacity

The minimum compacity of the mixture at the maximum modified Proctor dry density shall be 0,80 calculated in accordance with annex A.

6.6.4 Immediate bearing index of the mixture

In the case of hydraulic road binder bound mixture 2 – 0/10, the immediate bearing index, determined in accordance with EN 13286-47 using modified Proctor compaction, shall not be less than 50.

6.7 Hydraulic road binder bound mixture 3**6.7.1 Description**

Hydraulic road binder bound mixture 3 shall be a 'fine aggregate' mixture with an immediate bearing index requirement.

6.7.2 Grading of the mixture

The grading of the mixture, determined in accordance with EN 933-1, shall comply with Table 2.

Table 2 — Grading of hydraulic road binder bound mixture 3

Column	1	2	3	4
Line	Sieve mm	12,5	6,3	0,063
1	Percentage passing by mass	100	≥85	≤35

6.7.3 Immediate bearing index of the mixture

In order to facilitate site compaction and depending on trafficking, the immediate bearing index of the mixture, determined in accordance with EN 13286-47 using modified Proctor compaction, shall be selected from Table 3.

Table 3 — Immediate bearing index categories for hydraulic road binder bound mixture 3

Column	1	2
Line	Immediate bearing index requirement	Immediate bearing index category
1	≥40	IPI ₄₀
2	≥25	IPI ₂₅
3	No requirement	IPI _{NR}

NOTE Mixtures with an immediate bearing index less than 40 may not support immediate trafficking and should be used with care. The addition of another aggregate can be necessary to achieve the immediate bearing index required for immediate use.

6.8 Hydraulic road binder bound mixture 4

Hydraulic road binder bound mixture 4 shall be a mixture where the grading, determined in accordance with EN 933-1, is declared by the supplier.

NOTE If appropriate, other properties, such as immediate bearing index, may be declared.

7 Laboratory mechanical performance classification

7.1 General

Laboratory mechanical performance shall be characterized and classified by one of the following methods:

- compressive strength R_c ;
- the combination R_t , E of tensile strength R_t and modulus of elasticity E .

NOTE No correlation is intended nor should be assumed between the two methods.

7.2 Classification by compressive strength

Mixtures shall be classified by compressive strength determined in accordance with EN 13286-41 carried out on specimens manufactured in accordance with prEN 13286-50 to prEN 13286-53.