



Designation: D2902 – 21

Standard Specification for Fluoropolymer Resin Heat-Shrinkable Tubing for Electrical Insulation¹

This standard is issued under the fixed designation D2902; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification applies to flexible heat-shrinkable extruded tubing made from tetrafluoroethylene resin, copolymer of tetrafluoroethylene and hexafluoropropylene, and from perfluoroalkoxy resin for use as electrical insulation. This specification excludes crosslinked poly(vinylidene fluoride) and poly(vinylidene fluoride) copolymer which are covered under Specification D3144.

NOTE 1—This standard is similar but not identical to IEC 60684-3-240.

1.2 The values stated in inch-pound units are to be regarded as standard, except temperature, which shall be stated in degrees Celsius. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.

ASTM D2902

2. Referenced Documents

2.1 ASTM Standards:²

- C618 Specification for Coal Fly Ash and Raw or Calcined Natural Pozzolan for Use in Concrete
- D638 Test Method for Tensile Properties of Plastics
- D1711 Terminology Relating to Electrical Insulation
- D2116 Specification for FEP Resin Molding and Extrusion Materials
- D2671 Test Methods for Heat-Shrinkable Tubing for Electrical Use

¹ This specification is under the jurisdiction of ASTM Committee D09 on Electrical and Electronic Insulating Materials and is the direct responsibility of Subcommittee D09.07 on Electrical Insulating Materials.

Current edition approved March 1, 2021. Published May 2021. Originally approved in 1970. Last previous edition approved in 2013 as D2902 – 00 (2013)^{e1}. DOI: 10.1520/D2902-21.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard's Document Summary page on the ASTM website.

D3144 Specification for Crosslinked Poly(Vinylidene Fluoride) Heat-Shrinkable Tubing for Electrical Insulation

D3307 Specification for Perfluoroalkoxy (PFA) Resin Molding and Extrusion Materials

D3636 Practice for Sampling and Judging Quality of Solid Electrical Insulating Materials

D4895 Specification for Polytetrafluoroethylene (PTFE) Resin Produced From Dispersion

E176 Terminology of Fire Standards

2.2 IEC Standards:³

IEC 60684-3-240 Flexible insulating sleeving - Part 3: Specifications for individual types of sleeving - Sheets 240 to 243: Heat-shrinkable PTFE sleeving

3. Terminology

3.1 Definitions:

3.1.1 For definitions pertaining to electrical insulation, refer to Terminology D1711.

3.1.2 For definitions pertaining to fire standards, refer to Terminology E176.

4. Classification

4.1 Type I—Tubing made from tetrafluoroethylene polymer (TFE) and capable of being heat shrunk at a temperature of 327 °C (621 °F).

4.2 Type II—Tubing made from a copolymer of tetrafluoroethylene and hexafluoropropylene (FEP) and capable of being heat shrunk at a temperature of 150 °C (302 °F).

4.3 Type III—Tubing made from perfluoroalkoxy resin (PFA) and capable of being heat shrunk at a temperature of 175 °C (347 °F).

5. Ordering Information

5.1 When ordering to this specification, the purchaser must state the size, and type of the required tubing.

³ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.



6. Materials and Manufacture

6.1 The compound used in the manufacture of this tubing shall be modified fluoropolymer resin, and the finished compound shall be free of all foreign matter other than intended formulation additives as appropriate.

6.2 Type I tubing is normally made by paste extrusion. Type II and Type III tubings are normally made by melt extrusion. All types are expanded by mechanical means.

7. Chemical and Physical Property Requirements

7.1 The material shall conform to the chemical and physical property requirements specified in **Table 1**.

7.2 Every lot of material manufactured should be tested for dimensional requirements and restricted shrinkage. Other requirements shall be permitted to be tested less frequently or with a frequency agreed upon between seller and purchaser.

8. Dimensional Requirements

8.1 Type I material shall conform to the requirements specified in **Table 3**.

8.2 Type II and Type III materials shall conform to the requirements specified in **Table 4**.

8.3 Tubing with non-standard dimensions shall be permitted to be supplied when agreed upon between purchaser and seller. Tubing with non-standard dimensions shall be considered to comply with this specification if the requirements of **Table 1**

TABLE 2 Mandrel Sizes for Low-temperature Flexibility Testing

Nominal Tubing Inside Diameter (Max After Unrestricted Shrinkage)		Mandrel Diameter	
in.	(mm)	in.	(mm)
0.015 to 0.125	(0.38 to 3.2)	0.3125 ± 0.002	(7.95 ± 0.06)
0.126 to 0.250	(3.3 to 6.3)	0.375 ± 0.003	(8.06 ± 0.07)
0.251 to 1.000	(6.4 to 26)	0.437 ± 0.004	(11.10 ± 0.10)
1.001 to 2.000	(27 to 50)	0.875 ± 0.005	(16.13 ± 0.13)
2.001 to 3.000	(51 to 75)	1.000 ± 0.005	(25.40 ± 0.13)
3.001 to 4.000	(76 to 101)	1.125 ± 0.005	(28.58 ± 0.13)

are satisfied and the minimum recovered wall thickness equals or exceeds that of the identical or next largest as supplied size. The wall for sizes greater than the largest specified size shall be at least as thick as that of the largest specified size.

9. Workmanship

9.1 The heat-shrinkable tubing shall be homogeneous and free from flaws and defects and from foreign matter that have the potential to compromise its performance.

9.2 Type I tubing shall be furnished in clear (transparent milk white to tan) or in a color as agreed between purchaser and seller.

9.3 Type II tubing shall be furnished in clear (water white to transparent light blue) or in a color as agreed between purchaser and seller.

TABLE 1 Chemical and Physical Property Requirements

Property	Requirement		
	Type I	Type II	Type III
Restricted shrinkage, ^A procedure B, 2000 V, 10 min	no cracking	no cracking	no cracking
Specific gravity	2.13 to 2.18	2.12 to 2.20	2.13 to 2.20
Longitudinal change, max, %	+20	±15	±15
Tensile modulus at 200 % elongation, min, psi (MPa) Test Method D638 2 in./min (50 mm/min)	2000 (13.8)	1500 (10.3)	2500 (17.3)
Volume resistivity, ^B Ω-cm, at standard laboratory atmosphere, min	10 ¹⁶	10 ¹⁶	10 ¹⁶
Dielectric breakdown voltage, min kV:			
Wall thickness:			
0.004 to 0.006 in.	8	8	8
0.007 to 0.008 in.	10	10	10
0.009 in.	11.5	11.5	11.5
0.010 to 0.011 in.	12.5	12.5	12.5
0.012 to 0.014 in.	14.6	14.6	14.6
0.015 in.	15	15	15
0.016 to 0.019 in.	16.3	16.3	16.3
0.020 in. and larger	17	17	17
Heat resistance for 96 h followed by tests for tensile modulus at 200 % elongation, min, psi (MPa)			
Type I—350 ± 4 °C (662 ± 7 °F)	2000 (13.8)		
Type II—250 ± 3 °C (482 ± 6 °F)		1500 (10.3)	
Type III—275 ± 4 °C (527 ± 7 °F)			2500 (17.3)
Low-temperature flexibility, -55 ± 2 °C (-67 ± °F)	no cracking	no cracking	no cracking
Melting point:			
Specification D4895	327 ± 10 °C (621 ± 20 °F)		
Specification D2116		270 ± 20 °C (518 ± 40 °F)	
Specification D3307 endotherm peak, min			300 ± 2 °C (572 ± 7 °F)
Specification D3307			305 ± 3 °C (581 ± 5 °F)

^A For over-expanded sleeving, use a mandrel equal to the enclosable diameters $(D + d)/2$.

^B See Specification **C618**.

TABLE 3 Dimensions, Type I—Lengths for Type I

As Supplied	After Unrestrictive Shrinkage		Stock Lengths, ft	Packaging
Inside Diameter, min, in. (mm)	Inside Diameter, max, in. (mm)	Wall Thickness, in. (mm)		
Heavy Wall				
0.166 (4.22)	0.130 (3.30)	0.030 ± 0.005 (0.76 ± 0.13)	3 to 1, min	straight lengths
0.250 (6.35)	0.193 (4.90)	0.030 ± 0.005 (0.76 ± 0.13)	3 to 1, min	straight lengths
0.333 (8.46)	0.257 (6.53)	0.030 ± 0.005 (0.76 ± 0.13)	3 to 1, min	straight lengths
0.415 (10.54)	0.320 (8.13)	0.030 ± 0.005 (0.76 ± 0.13)	3 to 1, min	straight lengths
0.498 (12.65)	0.383 (9.73)	0.030 ± 0.005 (0.76 ± 0.13)	3 to 1, min	straight lengths
0.580 (14.73)	0.448 (11.38)	0.030 ± 0.005 (0.76 ± 0.13)	3 to 1, min	straight lengths
0.666 (16.92)	0.510 (12.95)	0.030 ± 0.005 (0.76 ± 0.13)	3 to 1, min	straight lengths
0.748 (19.00)	0.572 (14.53)	0.030 ± 0.005 (0.76 ± 0.13)	3 to 1, min	straight lengths
0.830 (21.1)	0.637 (16.18)	0.030 ± 0.005 (0.76 ± 0.13)	3 to 1, min	straight lengths
0.915 (23.2)	0.700 (17.78)	0.032 ± 0.006 (0.81 ± 0.15)	3 to 1, min	straight lengths
1.000 (25.4)	0.764 (19.41)	0.040 ± 0.007 (1.02 ± 0.18)	3 to 1, min	straight lengths
1.170 (29.7)	0.891 (22.6)	0.045 ± 0.007 (1.14 ± 0.18)	3 to 1, min	straight lengths
1.330 (33.8)	1.020 (25.9)	0.050 ± 0.008 (1.27 ± 0.20)	3 to 1, min	straight lengths
Standard Wall				
0.045 (1.14)	0.027 (0.69)	0.012 ± 0.002 (0.30 ± 0.05)		
0.050 (1.27)	0.032 (0.81)	0.012 ± 0.002 (0.30 ± 0.05)	3, min	spools
0.055 (1.40)	0.039 (0.99)	0.016 ± 0.003 (0.41 ± 0.08)	3, min	spools
0.060 (1.52)	0.043 (1.09)	0.016 ± 0.003 (0.41 ± 0.08)	3, min	spools
0.065 (1.65)	0.049 (1.24)	0.016 ± 0.003 (0.41 ± 0.08)	3, min	spools
0.076 (1.93)	0.054 (1.37)	0.016 ± 0.003 (0.41 ± 0.08)	3, min	spools
0.085 (2.16)	0.061 (1.55)	0.016 ± 0.003 (0.41 ± 0.08)	3, min	spools
0.093 (2.36)	0.067 (1.70)	0.016 ± 0.003 (0.41 ± 0.08)	3, min	spools
0.110 (2.79)	0.072 (1.83)	0.016 ± 0.003 (0.41 ± 0.08)	3, min	spools
0.120 (3.05)	0.080 (2.03)	0.016 ± 0.003 (0.41 ± 0.08)	3, 2, 1	straight lengths
0.140 (3.56)	0.089 (2.26)	0.016 ± 0.003 (0.41 ± 0.08)	3, 2, 1	straight lengths
0.160 (4.06)	0.101 (2.56)	0.016 ± 0.003 (0.41 ± 0.08)	3, 2, 1	straight lengths
0.180 (4.57)	0.112 (2.84)	0.016 ± 0.003 (0.41 ± 0.08)	3, 2, 1	straight lengths
0.200 (5.08)	0.124 (3.15)	0.020 ± 0.004 (0.51 ± 0.10)	3, 2, 1	straight lengths
0.210 (5.33)	0.130 (3.30)	0.020 ± 0.004 (0.51 ± 0.10)	3, 2, 1	straight lengths
0.230 (5.84)	0.141 (3.58)	0.020 ± 0.004 (0.51 ± 0.10)	3, 2, 1	straight lengths
0.240 (6.10)	0.158 (4.01)	0.020 ± 0.004 (0.51 ± 0.10)	3, 2, 1	straight lengths
0.290 (7.37)	0.178 (4.52)	0.020 ± 0.004 (0.51 ± 0.10)	3, 2, 1	straight lengths
0.310 (7.87)	0.198 (5.03)	0.020 ± 0.004 (0.51 ± 0.10)	3, 2, 1	straight lengths
0.370 (9.40)	0.224 (5.69)	0.020 ± 0.004 (0.51 ± 0.10)	3, 2, 1	straight lengths
0.390 (9.91)	0.249 (6.32)	0.020 ± 0.004 (0.51 ± 0.10)	3, 2, 1	straight lengths
0.410 (10.41)	0.260 (6.60)	0.020 ± 0.004 (0.51 ± 0.10)	3, 2, 1	straight lengths
0.430 (10.92)	0.278 (7.06)	0.020 ± 0.004 (0.51 ± 0.10)	3, 2, 1	straight lengths
0.450 (11.43)	0.311 (7.90)	0.020 ± 0.004 (0.51 ± 0.10)	3, 2, 1	straight lengths
0.470 (11.94)	0.329 (8.36)	0.020 ± 0.004 (0.51 ± 0.10)	3, 2, 1	straight lengths
0.470 (11.94)	0.347 (8.81)	0.020 ± 0.004 (0.51 ± 0.10)	3, 2, 1	straight lengths
0.470 (11.94)	0.334 (8.48)	0.025 ± 0.005 (0.64 ± 0.13)	3, 1, min	straight lengths
0.560 (14.22)	0.339 (8.61)	0.025 ± 0.005 (0.64 ± 0.13)	3, 1, min	straight lengths
0.655 (16.64)	0.462 (11.73)	0.025 ± 0.005 (0.64 ± 0.13)	3, 1, min	straight lengths
0.750 (19.05)	0.524 (13.31)	0.025 ± 0.005 (0.64 ± 0.13)	3, 1, min	straight lengths
0.930 (23.6)	0.655 (16.64)	0.030 ± 0.005 (0.76 ± 0.13)	3, 1, min	straight lengths
1.125 (28.6)	0.786 (20.0)	0.035 ± 0.006 (0.89 ± 0.15)	3, 1, min	straight lengths
1.310 (33.3)	0.911 (23.1)	0.035 ± 0.006 (0.89 ± 0.15)	3, 1, min	straight lengths
1.500 (38.1)	1.036 (26.3)	0.035 ± 0.006 (0.89 ± 0.15)	3, 1, min	straight lengths
Thin Wall				
0.034 (0.86)	0.015 (0.38)	0.009 ± 0.002 (0.23 ± 0.05)	3, min	spools
0.038 (0.97)	0.018 (0.46)	0.009 ± 0.002 (0.23 ± 0.05)	3, min	spools
0.046 (1.17)	0.022 (0.56)	0.009 ± 0.002 (0.23 ± 0.05)	3, min	spools
0.050 (1.27)	0.027 (0.69)	0.010 ± 0.002 (0.25 ± 0.05)	3, min	spools
0.055 (1.40)	0.032 (0.81)	0.010 ± 0.002 (0.25 ± 0.05)	3, min	spools
0.060 (1.52)	0.039 (0.99)	0.012 ± 0.003 (0.30 ± 0.08)	3, min	spools
0.065 (1.65)	0.043 (1.09)	0.012 ± 0.003 (0.30 ± 0.08)	3, min	spools
0.076 (1.93)	0.049 (1.24)	0.012 ± 0.003 (0.30 ± 0.08)	3, min	spools
0.085 (2.16)	0.054 (1.37)	0.012 ± 0.003 (0.30 ± 0.08)	3, min	spools
0.093 (2.36)	0.061 (1.55)	0.012 ± 0.003 (0.30 ± 0.08)	3, min	spools
0.110 (2.79)	0.067 (1.70)	0.012 ± 0.003 (0.30 ± 0.08)	3, min	spools
0.120 (3.05)	0.072 (1.83)	0.012 ± 0.003 (0.30 ± 0.08)	3, 2, 1	straight lengths
0.140 (3.56)	0.080 (2.03)	0.012 ± 0.003 (0.30 ± 0.08)	3, 2, 1	straight lengths
0.150 (3.81)	0.089 (2.26)	0.012 ± 0.003 (0.30 ± 0.08)	3, 2, 1	straight lengths
0.170 (4.32)	0.101 (2.56)	0.012 ± 0.003 (0.30 ± 0.08)	3, 2, 1	straight lengths
0.191 (4.85)	0.112 (2.84)	0.012 ± 0.003 (0.30 ± 0.08)	3, 2, 1	straight lengths
0.205 (5.21)	0.124 (3.15)	0.015 ± 0.004 (0.38 ± 0.10)	3, 2, 1	straight lengths
0.215 (5.46)	0.130 (3.30)	0.015 ± 0.004 (0.38 ± 0.10)	3, 2, 1	straight lengths
0.240 (6.10)	0.141 (3.58)	0.015 ± 0.004 (0.38 ± 0.10)	3, 2, 1	straight lengths
0.270 (6.86)	0.158 (4.01)	0.015 ± 0.004 (0.38 ± 0.10)	3, 2, 1	straight lengths
0.302 (7.67)	0.178 (4.53)	0.015 ± 0.004 (0.38 ± 0.10)	3, 2, 1	straight lengths
0.320 (8.13)	0.198 (5.03)	0.015 ± 0.004 (0.38 ± 0.10)	3, 2, 1	straight lengths
0.370 (9.40)	0.224 (5.69)	0.015 ± 0.004 (0.38 ± 0.10)	3, 2, 1	straight lengths

TABLE 3 *Continued*

As Supplied		After Unrestrictive Shrinkage	Stock Lengths, ft	Packaging
Inside Diameter, min, in. (mm)	Inside Diameter, max, in. (mm)	Wall Thickness, in. (mm)		
Thin Wall				
0.390 (9.91)	0.249 (6.32)	0.015 ± 0.004 (0.38 ± 0.10)	3, 2, 1	straight lengths
0.410 (10.41)	0.260 (6.60)	0.015 ± 0.004 (0.38 ± 0.10)	3, 2, 1	straight lengths
0.430 (10.92)	0.278 (7.06)	0.015 ± 0.004 (0.38 ± 0.10)	3, 2, 1	straight lengths
0.450 (11.43)	0.311 (7.90)	0.015 ± 0.004 (0.38 ± 0.10)	3, 2, 1	straight lengths
0.470 (11.94)	0.329 (8.36)	0.015 ± 0.004 (0.38 ± 0.10)	3, 2, 1	straight lengths
0.470 (11.94)	0.347 (8.81)	0.015 ± 0.004 (0.38 ± 0.10)	3, 2, 1	straight lengths
0.560 (14.22)	0.399 (10.13)	0.015 ± 0.004 (0.38 ± 0.10)	3, 2, 1	straight lengths
0.560 (14.22)	0.399 (10.13)	0.020 ± 0.005 (0.51 ± 0.13)	3, 2, 1	straight lengths
0.655 (16.64)	0.462 (11.73)	0.018 ± 0.005 (0.46 ± 0.13)	3, 2, 1	straight lengths
0.655 (16.64)	0.462 (11.73)	0.020 ± 0.005 (0.51 ± 0.13)	3, 2, 1	straight lengths
0.750 (19.05)	0.524 (13.31)	0.018 ± 0.005 (0.46 ± 0.13)	3, 2, 1	straight lengths
0.750 (19.05)	0.524 (13.31)	0.020 ± 0.005 (0.51 ± 0.13)	3, 2, 1	straight lengths
0.930 (23.6)	0.655 (16.64)	0.020 ± 0.005 (0.51 ± 0.13)	3, 2, 1	straight lengths
0.930 (23.6)	0.655 (16.64)	0.025 ± 0.005 (0.64 ± 0.13)	3, 2, 1	straight lengths
1.125 (28.6)	0.786 (20.0)	0.025 ± 0.005 (0.64 ± 0.13)	3, 2, 1	straight lengths
1.125 (28.6)	0.786 (20.0)	0.030 ± 0.006 (0.76 ± 0.15)	3, 2, 1	straight lengths
2.0:1 Shrink Factor				
0.039 (1)	0.020 (0.50)	0.010 ± 0.002 (0.25 ± 0.05)	4	straight lengths
0.059(1.5)	0.030 (0.75)	0.010 ± 0.002 (0.25 ± 0.05)	4	straight lengths
0.098 (2.5)	0.049 (1.25)	0.010 ± 0.002 (0.25 ± 0.05)	4	straight lengths
0.138 (3.5)	0.069 (1.75)	0.010 ± 0.002 (0.25 ± 0.05)	4	straight lengths
0.197 (5)	0.098 (2.5)	0.010 ± 0.002 (0.25 ± 0.05)	4	straight lengths
0.276 (7)	0.138 (3.5)	0.020 ± 0.004 (0.50 ± 0.10)	4	straight lengths
0.394 (10)	0.197 (5.0)	0.020 ± 0.004 (0.50 ± 0.10)	4	straight lengths
0.512 (13)	0.256 (6.5)	0.020 ± 0.004 (0.50 ± 0.10)	4	straight lengths
0.827 (20)	0.394 (10.0)	0.020 ± 0.004 (0.50 ± 0.10)	4	straight lengths
1.024 (26)	0.512 (13.0)	0.030 ± 0.004 (0.75 ± 0.10)	4	straight lengths
Very Thin Wall				
0.050 (1.27)	0.027 (0.69)	0.006 ± 0.002 (0.15 ± 0.05)	3	spools
0.055 (1.40)	0.032 (0.81)	0.006 ± 0.002 (0.15 ± 0.05)	3	spools
0.060 (1.52)	0.039 (0.99)	0.006 ± 0.002 (0.15 ± 0.05)	3	spools
0.065 (1.65)	0.043 (1.09)	0.006 ± 0.002 (0.15 ± 0.05)	3	spools
0.076 (1.93)	0.049 (1.24)	0.006 ± 0.002 (0.15 ± 0.05)	3	spools
0.085 (2.16)	0.054 (1.37)	0.006 ± 0.002 (0.15 ± 0.05)	3	spools
0.093 (2.36)	0.061 (1.55)	0.006 ± 0.002 (0.15 ± 0.05)	3, 2, 1	straight lengths
0.110 (2.79)	0.067 (1.70)	0.006 ± 0.002 (0.15 ± 0.05)	3, 2, 1	straight lengths
0.120 (3.05)	0.072 (1.83)	0.008 ± 0.002 (0.20 ± 0.05)	3, 2, 1	straight lengths
0.140 (3.56)	0.080 (2.03)	0.008 ± 0.002 (0.20 ± 0.05)	3, 2, 1	straight lengths
0.150 (3.81)	0.089 (2.26)	0.008 ± 0.002 (0.20 ± 0.05)	3, 2, 1	straight lengths
0.170 (4.32)	0.101 (2.56)	0.008 ± 0.002 (0.20 ± 0.05)	3, 2, 1	straight lengths
0.191 (4.85)	0.112 (2.84)	0.008 ± 0.002 (0.20 ± 0.05)	3, 2, 1	straight lengths
0.205 (5.21)	0.124 (3.15)	0.008 ± 0.002 (0.20 ± 0.05)	3, 2, 1	straight lengths
0.215 (5.46)	0.130 (3.30)	0.008 ± 0.002 (0.20 ± 0.05)	3, 2, 1	straight lengths
0.240 (6.10)	0.141 (3.58)	0.008 ± 0.002 (0.20 ± 0.05)	3, 2, 1	straight lengths
0.270 (6.86)	0.158 (4.01)	0.008 ± 0.002 (0.20 ± 0.05)	3, 2, 1	straight lengths
0.302 (7.67)	0.178 (4.52)	0.010 ± 0.003 (0.25 ± 0.08)	3, 2, 1	straight lengths
0.320 (8.13)	0.198 (5.03)	0.010 ± 0.003 (0.25 ± 0.08)	3, 2, 1	straight lengths
0.370 (9.40)	0.224 (5.69)	0.010 ± 0.003 (0.25 ± 0.08)	3, 2, 1	straight lengths
0.390 (9.91)	0.249 (6.32)	0.010 ± 0.003 (0.25 ± 0.08)	3, 2, 1	straight lengths
0.410 (10.41)	0.260 (6.60)	0.010 ± 0.003 (0.25 ± 0.08)	3, 2, 1	straight lengths
0.430 (10.92)	0.278 (7.06)	0.010 ± 0.003 (0.25 ± 0.08)	3, 2, 1	straight lengths
0.450 (11.43)	0.311 (7.90)	0.010 ± 0.003 (0.25 ± 0.08)	3, 2, 1	straight lengths
0.470 (11.94)	0.329 (8.36)	0.010 ± 0.003 (0.25 ± 0.08)	3, 2, 1	straight lengths
0.470 (11.94)	0.347 (8.81)	0.010 ± 0.003 (0.25 ± 0.08)	3, 2, 1	straight lengths
4:1 PTFE Shrinkable Tubing				
0.078 (1.98)	0.025 (0.64)	0.009 ± 0.002 (0.23 ± 0.05)	4	straight lengths
0.125 (3.18)	0.037 (0.94)	0.010 ± 0.002 (0.25 ± 0.05)	4	straight lengths
0.250 (6.35)	0.063 (1.60)	0.012 ± 0.003 (0.30 ± 0.08)	4	straight lengths
0.375 (9.53)	0.096 (2.44)	0.012 ± 0.003 (0.30 ± 0.08)	4	straight lengths
0.500 (12.70)	0.144 (3.66)	0.015 ± 0.004 (0.38 ± 0.10)	4	straight lengths
Over Expanded Tubing				
0.625 (15.88)	0.178 (4.52)	0.015 ± 0.004 (0.38 ± 0.10)	4	straight lengths
0.750 (19.05)	0.224 (5.69)	0.015 ± 0.004 (0.38 ± 0.10)	4	straight lengths
1.000 (25.4)	0.278 (7.06)	0.015 ± 0.004 (0.38 ± 0.10)	4	straight lengths
1.250 (31.8)	0.347 (8.81)	0.015 ± 0.004 (0.38 ± 0.10)	4	straight lengths
1.500 (38.1)	0.400 (10.16)	0.015 ± 0.004 (0.38 ± 0.10)	4	straight lengths
1.750 (44.4)	0.450 (11.43)	0.015 ± 0.004 (0.38 ± 0.10)	4	straight lengths
2.00 (50.8)	0.520 (13.21)	0.020 ± 0.004 (0.51 ± 0.10)	4	straight lengths
2.25 (57.2)	0.585 (14.86)	0.020 ± 0.004 (0.51 ± 0.10)	4	straight lengths
2.50 (63.5)	0.650 (16.51)	0.020 ± 0.004 (0.51 ± 0.10)	4	straight lengths
2.75 (69.8)	0.710 (18.03)	0.020 ± 0.004 (0.51 ± 0.10)	4	straight lengths
3.00 (76.2)	0.775 (19.68)	0.020 ± 0.004 (0.51 ± 0.10)	4	straight lengths
3.25 (82.6)	0.835 (21.2)	0.020 ± 0.004 (0.51 ± 0.10)	4	straight lengths