

# Standard Guide for Identification of Metals and Alloys in Computerized Material Property Databases<sup>1</sup>

This standard is issued under the fixed designation E1338; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\varepsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This guide covers the identification of metals and alloys in computerized material property databases. It establishes essential and desirable data elements that serve to uniquely identify and describe a particular metal or alloy sample as well as properties that identify a given metal or alloy in general.

1.1.1 This guide does not necessarily provide sufficient data elements to describe weld metal, metal matrix composites, or joined metals.

1.1.2 The data element identified herein are not all germane to every metal or alloy group.

1.1.3 Different sets of data elements may also be applied within a given metal or alloy group depending on conditions or applications specific to that metal or alloy group. Further, within a particular metal or alloy group, different sets of data elements may be used to identify specific material conditions.

1.1.4 Table 1 on Recommended Data Elements and Tables 2-17 on values for specific data elements appear at the end of this guide. ASTM E1338-09(2021)

1.2 Some of the data elements in this guide may be useful for other purposes. However, this guide does not attempt to document the essential and desirable data element for any purpose except for the identification of metals and alloys in computerized material property databases. Other purposes, such as material production, material procurement, and material processing, each may have different material data reporting requirements distinct from those covered in this guide. A specific example is the contractually required report for a material property testing series. Such a report may not contain all the data elements considered essential for a specific computerized database; conversely, this guide may not contain all the data elements considered essential for a contracted test report.

1.3 Results from material tests conducted as part of the procurement process are often used to determine adherence to a specification. While this guide includes a number of test result data elements, such data elements are included in this guide only for the purposes of material identification.

1.4 Reporting of contracted test results, such as certification test results, shall follow the requirements described in the material specification, or as agreed upon between the purchaser and the manufacturer.

1.5 This guide contains a limited number of data elements related to material test results. These data elements are for material

Copyright © ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959. United States

<sup>&</sup>lt;sup>1</sup> This guide is under the jurisdiction of ASTM Committee B08 on Metallic and Inorganic Coatings and is the direct responsibility of Subcommittee B08.01 on Ancillary Activities. This guide was developed in cooperation with Committee B07 on Light Metals and Alloys.

Current edition approved Nov. 1, 2015 April 1, 2021. Published December 2015 May 2021. Originally approved in 1990. Last previous edition approved in 20092015 as E1338 – 09:09(2015). DOI: 10.1520/E1338-09R15. 10.1520/E1338-09R21.

€1338 – 09 (2021)

TABLE 1 Recommended Data Elements for the Identification of Metals and Alloys

Number <sup>A</sup>	Data Element Descriptive Name	Data Type	Category Set, Value Set, or Units
	Primary Identifiers		
1	Material class	String	metal
2	Family name	String	Category set in Table 2
3	Family subclass	String	Value set in Table 3
4 <sup><i>B</i></sup>	Common name <sup>C</sup>	String	
5	Application group <sup><math>C</math></sup>	String	
6	Product group <sup>C</sup>	String	
	Material Specification		
7 <sup><i>B</i></sup>	UNS Number	String	Category set defined in Practice E527
8 <sup><i>B</i></sup>	Specification organization	String	
9 <sup>B</sup>	Specification number	String	
10 <sup>B</sup>	Specification version	String	
11 <sup>B</sup>	Designation keyword <sup><math>C</math></sup>	String	Category set in Table 4
12 <sup><i>B</i></sup>	Designation value <sup><math>C</math></sup>	String	
12	Composition Requirement		
13	Element symbol	String	IUPAC symbol(s)
14	Fraction type	String	mass, volume, or mole
15	Composition units	String	% or ppm
16	Minimum specified composition	Real	
17	Maximum specified composition	Real	
	Mechanical Properties Requi Tensile Test Requiremer		
10	Orientation of tensile specimen for certification		Value set in Table 5
18		String	
19	Location of tensile specimen for certification	String	Values set in Table 6
20	Tensile test temperature for certification	Real	°C (°F)
21	Minimum ultimate tensile strength	Real	MPa (ksi)
22	Maximum ultimate tensile strength	Real	MPa (ksi)
23	Minimum yield strength	Real	MPa (ksi)
24	Maximum yield strength	Real	MPa (ksi)
25	Yield strength determination method	String	Category set in Table 7
26	Yield strength offset or extension	Real	%
27	Minimum elongation	Real	%
28	Maximum elongation	Real	%
29	Original gage length	Real	mm (in.)
30	Minimum reduction of area	Real	%
31	Maximum reduction of area	Real	%
00	Hardness Requirement		Malua ant in Table 0
32	Location of hardness measurement for certification	String	Value set in Table 6
33	Minimum hardness	Real	
34	Maximum hardness	Real	
35	Hardness scale	String	Category set in Table 8
	Charpy Impact Energy to Fracture I	Poquiromonte <sup>C</sup>	
ttns://36andar	Location of Charpy specimen for certification	String 768_726	Value set in Table 6 1338-00202
		Real	
37	Temperature of Charpy test for certification		°C (°F)
38	Minimum Charpy impact energy	Real	J (ft-lbf)
39	Maximum Charpy impact energy	Real	J (ft-lbf)
	Maximum Charpy impact energy Primary Material Produc	cer	J (IT-IDI)
40	Maximum Charpy impact energy Primary Material Produce Original producer	cer String	J (IT-IDT)
40 41	Maximum Charpy impact energy Primary Material Produce Original producer Country of origin	cer String String	J (171-107)
40 41 42	Maximum Charpy impact energy Primary Material Produce Original producer Country of origin Producer's facility	cer String String String	J (101-117)
40 41	Maximum Charpy impact energy Primary Material Produce Original producer Country of origin	cer String String	J (101-117)
40 41 42	Maximum Charpy impact energy Primary Material Produce Original producer Country of origin Producer's facility	cer String String String	J (101-117)
40 41 42 43	Maximum Charpy impact energy Primary Material Produce Original producer Country of origin Producer's facility Production date	cer String String String Date	Value set in Table 9
40 41 42 43 44 45 46	Maximum Charpy impact energy Primary Material Produce Original producer Country of origin Producer's facility Production date Primary process type Melt practice	cer String String Date String String	
40 41 42 43 44 45 46	Maximum Charpy impact energy Primary Material Produce Country of origin Producer's facility Production date Primary process type Melt practice Cast practice	cer String String Date String String String	Value set in Table 9
40 41 42 43 44 45	Maximum Charpy impact energy Primary Material Produce Country of origin Producer's facility Production date Primary process type Melt practice Cast practice Heat number	cer String String Date String String String String	Value set in Table 9
40 41 42 43 44 45 46 46 47 <sup>B</sup>	Maximum Charpy impact energy Primary Material Produce Country of origin Producer's facility Production date Primary process type Melt practice Cast practice	cer String String Date String String String String	Value set in Table 9
40 41 42 43 44 45 46 47 <sup>B</sup> 48	Maximum Charpy impact energy Primary Material Produce Original producer Country of origin Producer's facility Production date Primary process type Melt practice Cast practice Heat number Material Processing <sup>C</sup> Processor's name	cer String String Date String String String String String	Value set in Table 9 Value set in Table 10
40 41 42 43 44 45 46 47 <sup>B</sup> 48 49	Maximum Charpy impact energy Primary Material Produce Original producer Country of origin Producer's facility Production date Primary process type Melt practice Cast practice Heat number Processor's name Processor's country	cer String String Date String String String String String String	Value set in Table 9
40 41 42 43 44 45 46 47 <sup>B</sup> 48 49 50	Maximum Charpy impact energy Primary Material Produce Original producer Country of origin Production date Primary process type Melt practice Cast practice Heat number Processor's name Processor's name Processor's facility name	cer String String Date String String String String String String String String String String	Value set in Table 9 Value set in Table 10
40 41 42 43 44 45 46 47 <sup>B</sup> 48 49 50 51	Maximum Charpy impact energy Primary Material Produce Original producer Country of origin Producer's facility Production date Primary process type Melt practice Cast practice Heat number Material Processing <sup>C</sup> Processor's name Processor's facility name Processor's assigned production date	cer String String Date String String String String String String String String String String String	Value set in Table 9 Value set in Table 10
$ \begin{array}{r}     40 \\     41 \\     42 \\     43 \\     44 \\     45 \\     46 \\     47^{\beta} \\ \end{array} $ $ \begin{array}{r}     48 \\     49 \\     50 \\     51 \\     52^{B} \\ \end{array} $	Maximum Charpy impact energy         Primary Material Produce         Country of origin         Producer's facility         Production date         Primary process type         Melt practice         Cast practice         Heat number         Material Processor's name         Processor's facility name         Processor's assigned production date         Process type	cer String String Date String String String String String String String String String String String String String String	Value set in Table 9 Value set in Table 10
40 41 42 43 44 45 46 47 <sup>B</sup> 48 49 50 51	Maximum Charpy impact energy         Primary Material Produce         Country of origin         Producer's facility         Production date         Primary process type         Melt practice         Cast practice         Heat number         Material Processor's name         Processor's country         Processor's facility name         Processor's assigned production date         Process type         Process type         Process type	cer String String Date String String String String String String String String String String String	Value set in Table 9 Value set in Table 10
$ \begin{array}{r} 40\\ 41\\ 42\\ 43\\ 44\\ 45\\ 46\\ 47^{B}\\ \hline 48\\ 49\\ 50\\ 51\\ 52^{B}\\ 53\\ \end{array} $	Maximum Charpy impact energy         Primary Material Producer         Country of origin         Producer's facility         Production date         Primary process type         Melt practice         Cast practice         Heat number         Material Processor's name         Processor's country         Processor's facility name         Processor's assigned production date         Process type         Process type <td>cer String String Date String String String String String String String Date String String String String String String String String String String String</td> <td>Value set in Table 9 Value set in Table 10</td>	cer String String Date String String String String String String String Date String String String String String String String String String String String	Value set in Table 9 Value set in Table 10
40 41 42 43 44 45 46 47 <sup>B</sup> 48 49 50 51 52 <sup>B</sup> 53	Maximum Charpy impact energy         Primary Material Produce         Country of origin         Producer's facility         Production date         Primary process type         Melt practice         Cast practice         Heat number         Processor's name         Processor's country         Processor's stilly name         Process type         Process type </td <td>cer String String Date String</td> <td>Value set in Table 9 Value set in Table 10 see ISO 3166</td>	cer String String Date String	Value set in Table 9 Value set in Table 10 see ISO 3166
$ \begin{array}{r} 40\\ 41\\ 42\\ 43\\ 44\\ 45\\ 46\\ 47^{B}\\ \hline 48\\ 49\\ 50\\ 51\\ 52^{B}\\ 53\\ \end{array} $	Maximum Charpy impact energy         Primary Material Producer         Country of origin         Producer's facility         Production date         Primary process type         Melt practice         Cast practice         Heat number         Material Processor's name         Processor's country         Processor's facility name         Processor's assigned production date         Process type         Process type <td>cer String String Date String String String String String String String Date String String String String String String String String String String String</td> <td>Value set in Table 9 Value set in Table 10 see ISO 3166</td>	cer String String Date String String String String String String String Date String String String String String String String String String String String	Value set in Table 9 Value set in Table 10 see ISO 3166
40 41 42 43 44 45 46 47 <sup>B</sup> 48 49 50 51 52 <sup>B</sup> 53	Maximum Charpy impact energy         Primary Material Produce         Country of origin         Producer's facility         Production date         Primary process type         Melt practice         Cast practice         Heat number         Processor's name         Processor's country         Processor's stilly name         Process type         Process type </td <td>cer String String Date String</td> <td>Value set in Table 9 Value set in Table 10 see ISO 3166</td>	cer String String Date String	Value set in Table 9 Value set in Table 10 see ISO 3166
$ \begin{array}{r}     40 \\     41 \\     42 \\     43 \\     44 \\     45 \\     46 \\     47^B \\     \hline       \hline     \hline       \hline     \hline     \hline         \hline     \hline            $	Maximum Charpy impact energy         Primary Material Produce         Country of origin         Producer's facility         Production date         Primary process type         Melt practice         Cast practice         Heat number         Material Processing <sup>C</sup> Processor's name         Processor's country         Processor's facility name         Process type         Procestype         Mate	cer String String Date String	Value set in Table 9 Value set in Table 10 see ISO 3166
$ \begin{array}{c} 40\\ 41\\ 42\\ 43\\ 44\\ 45\\ 46\\ 47^{B}\\ \hline 48\\ 49\\ 50\\ 51\\ 52^{B}\\ 53\\ \hline 54\\ 55\\ 56\\ 57\\ \hline 57\\ \hline $	Maximum Charpy impact energy         Primary Material Produce         Country of origin         Producer's facility         Production date         Primary process type         Melt practice         Cast practice         Heat number         Material Processor's name         Processor's name         Processor's country         Processor's facility name         Processor's assigned production date         Process type         Thermal step type         Time of thermal step         Thermal step temperature         Heating environment	cer String String Date String String String String String String String Date String	Value set in Table 9 Value set in Table 10 see ISO 3166 h °C (°F) Values set in Table 11
$ \begin{array}{r}     40 \\     41 \\     42 \\     43 \\     44 \\     45 \\     46 \\     47^{B} \\ \hline     48 \\     49 \\     50 \\     51 \\     52^{B} \\ \hline     53 \\ \hline     54 \\     55 \\     56 \\     57 \\     58 \\ \hline \end{array} $	Maximum Charpy impact energy         Primary Material Produce         Country of origin         Producer's facility         Production date         Primary process type         Melt practice         Cast practice         Heat number         Material Processing <sup>C</sup> Processor's name         Processor's country         Processor's facility name         Processor's sasigned production date         Process type         Process type         Process type         Thermal step type         Time of thermal step         Thermal step temperature         Heating environment         Heating rate	cer String String Date String String String String String String Date String Date String Date String String String Real String Real String Real	Value set in Table 9 Value set in Table 10 see ISO 3166 h °C (°F) Values set in Table 11 °C/h (°F/h)
$ \begin{array}{r}     40 \\     41 \\     42 \\     43 \\     44 \\     45 \\     46 \\     47^{B} \\ \end{array} $ $ \begin{array}{r}     48 \\     49 \\     50 \\     51 \\     52^{B} \\     53 \\ \end{array} $ $ \begin{array}{r}     54 \\     55 \\     56 \\     57 \\     58 \\     59 \\ \end{array} $	Maximum Charpy impact energy         Primary Material Produce         Country of origin         Producer's facility         Production date         Primary process type         Melt practice         Cast practice         Heat number         Processor's name         Processor's country         Processor's facility name         Processor's sasigned production date         Process type         Process lot number         Heat Treatment <sup>C</sup> Thermal step type         Time of thermal step         Thermal step temperature         Heating rate         Cooling environment	cer String String Date String String String String String String String String String String String String String String Real String Real String Real String S	Value set in Table 9 Value set in Table 10 see ISO 3166 h °C (°F) Values set in Table 11 °C/h (°F/h) Value set in Table 12
$ \begin{array}{r}     40 \\     41 \\     42 \\     43 \\     44 \\     45 \\     46 \\     47^{B} \\ \hline     48 \\     49 \\     50 \\     51 \\     52^{B} \\ \hline     53 \\ \hline     54 \\     55 \\     56 \\     57 \\     58 \\ \hline \end{array} $	Maximum Charpy impact energy         Primary Material Produce         Country of origin         Producer's facility         Production date         Primary process type         Melt practice         Cast practice         Heat number         Processor's name         Processor's country         Processor's facility name         Processor's assigned production date         Process type         Material Step         Thermal step type	cer String String Date String String String String String String Date String Date String Date String String String Real String Real String Real	Value set in Table 9 Value set in Table 10 see ISO 3166 h °C (°F) Values set in Table 11 °C/h (°F/h)
$ \begin{array}{r} 40\\ 41\\ 42\\ 43\\ 44\\ 45\\ 46\\ 47^B\\ \hline  \\  \\  \\  \\  \\  \\  \\  \\  \\  \\  \\  \\  \\ $	Maximum Charpy impact energy         Primary Material Producer         Country of origin         Producer's facility         Production date         Primary process type         Melt practice         Cast practice         Heat number         Material Processing <sup>C</sup> Processor's name         Processor's country         Processor's country         Processor's statility name         Processor's sasigned production date         Process type         Premail step type         Time of thermal step         Thermal step temperature         Heating ante         Cooling environment         Heating rate         Cooling rate	cer String String Date String String String String String String String String String String String String Real String Real String Real String Real String Real String Real String Real String Real String Real	Value set in Table 9 Value set in Table 10 see ISO 3166 h °C (°F) Values set in Table 11 °C/h (°F/h) Value set in Table 12 °C/h (°F/h)
$\begin{array}{c} 40\\ 41\\ 42\\ 43\\ 44\\ 45\\ 46\\ 47^B\\ \hline \\ \\ \\ \\ \\ \\ \\ \\ \\ \\ \\ \\ \\ \\ \\ \\ \\ \\$	Maximum Charpy impact energy         Primary Material Producer         Country of origin         Producer's facility         Production date         Primary process type         Melt practice         Cast practice         Heat number         Material Processing <sup>C</sup> Processor's name         Processor's country         Processor's country         Processor's statility name         Processor's sasigned production date         Process type         Process type         Process type         Process type         Process type         Thermal step type         Time of thermal step         Thermal step temperature         Heating environment         Heating rate         Cooling environment         Heating rate         Cooling rate         Product forming method	cer String String Date String String String String String String String String Date String String String Real Real String Real String Real String	Value set in Table 9 Value set in Table 10 see ISO 3166 h °C (°F) Values set in Table 11 °C/h (°F/h) Value set in Table 12
$ \begin{array}{r}     40 \\     41 \\     42 \\     43 \\     44 \\     45 \\     46 \\     47^{B} \\ \end{array} $ $ \begin{array}{r}     48 \\     49 \\     50 \\     51 \\     52^{B} \\     53 \\ \end{array} $ $ \begin{array}{r}     54 \\     55 \\     56 \\     57 \\     58 \\     59 \\     60 \\ \end{array} $	Maximum Charpy impact energy         Primary Material Producer         Country of origin         Producer's facility         Production date         Primary process type         Melt practice         Cast practice         Heat number         Material Processing <sup>C</sup> Processor's name         Processor's country         Processor's country         Processor's statility name         Processor's sasigned production date         Process type         Premail step type         Time of thermal step         Thermal step temperature         Heating ante         Cooling environment         Heating rate         Cooling rate	cer String String Date String String String String String String String String String String String String Real String Real String Real String Real String Real String Real String Real String Real String Real String Real String Real String Real	Value set in Table 9 Value set in Table 10 see ISO 3166 h °C (°F) Values set in Table 11 °C/h (°F/h) Value set in Table 12 °C/h (°F/h)

∰ E1338 – 09 (2021)

TABLE 1 Continued

TABLE 1     Continued				
Number <sup>A</sup>	Data Element Descriptive Name	Data Type	Category Set, Value Set, or Units	
64	Product form	String	Value set in Table 15	
65	Dimension type	String	nominal or actual	
66	Length	Real	cm (in.)	
67	Width	Real	cm (in.)	
68	Thickness	Real	cm (in.)	
69	Outside diameter	Real	cm (in.)	
70	Wall thickness	Real	cm (in.)	
71	Weight	Real	kg (lb)	
72	Fabrication history	String		
73	Service history	String		
	Measured Chemica			
74	Source of chemical composition data	String		
75	Element symbol	String	IUPAC symbol(s)	
76	Fraction type	String	mass, volume, or mole	
77	Composition units	String	% or ppm	
78	Measured composition	Real		
	Measured Mechan			
79	Measured Tensile Source or basis for tensile properties	String		
80	Orientation of test specimen	String	Value set in Table 5	
81	Location of tensile specimen	String	Value set in Table 6	
82	Tensile test temperature	Real	°C (°F)	
		Real		
83	Ultimate tensile strength		MPa (ksi)	
84	Number of tensile strength tests, if averaged	Integer		
85	Yield strength	Real	MPa (ksi)	
86	Yield strength method	String	Category set in Table 7	
87	Yield strength offset or extension	Real	%	
88	Number of yield strength tests, if averaged	Integer	24	
89	Total elongation	Real	%	
90	Original gage length	Real	mm (in.)	
91	Number of elongation tests, if averaged	Integer		
92	Type of elongation	String	Value set in Table 16	
93	Reduction of area	Real	%	
94	Number of reduction of area tests, if averaged Measured Ha	Integer		
95	Source or basis for hardness measurement	String	I.dl)	
96	Location of hardness measurement	String	Value set in Table 6	
97	Hardness value	- D Real		
98	Hardness scale	String	Category set in Table 8	
99	Number of hardness readings, if averaged	Integer		
00	Measured Charpy Impac			
100	Source or basis for Charpy measurements	String		
101	Location of Charpy specimen ASTIMET338	S-09(20String	Value set in Table 6	
102	Temperature of Charpy test	28-4 Real 2762-7	36c °C (°F) 874e/astm-e1338-092021	
103	Charpy specimen size	String	Category set in Table 17	
104	Charpy impact energy	Real	J (ft-lbf)	
105	Number of Charpy tests, if averaged	Integer		
	Measured Microstruct	ture Descriptions <sup>C</sup>		
106	Grain size measurement	Real		
107	Scale for grain size	String		
108	Basis for grain size	String		
109	Description of microstructure	String		

<sup>A</sup> Data element numbers are provided for information only.
 <sup>B</sup> Essential data element, as described in 4.6.
 <sup>C</sup> Provisions should be made in the database for repeated values of this data element, or for the set of data elements in this section.

E527		
Aluminum and aluminum alloys	Zinc and zinc alloys	
Copper and copper alloys	Cast irons	
Rare earth and rare earth-like metals	Cast steels	
and alloys	Carbon steels	
Low melting point metals and alloys	Alloy steels	
Nickel and nickel alloys	AISI H-steels	
Precious metals and alloys	Heat and corrosion-resistant	
Reactive and refractory metals and	(stainless) steels	
alloys	Tool steels	
	Cobalt alloys	

# TABLE 2 Category Set for Family Name as Listed in Practice

identification purposes and are not intended to replace the more detailed sets of data elements listed in guides such as Guide E1313 covering data recording formats for mechanical testing of metals. For material identification purposes, the data elements in this



#### TABLE 3 Example Value Sets for Family Subclass Name for Aluminum, Copper, Steel, and Other Metals and Alloys


······································			
Aluminum:	Copper:		
Commercially pure aluminum	Copper		
Aluminum-copper alloy	High copper alloy		
Aluminum-manganese alloy	Beryllium copper		
Aluminum-silicon alloy	Chromium copper		
Aluminum-manganese-silicon alloy	Copper-zinc alloy (brass)		
Aluminum-magnesium alloy	Copper-zinc-lead-alloy (leaded		
Aluminum-magnesium-silicon alloy	brass)		
Aluminum-zinc alloy	Copper-zinc-tin alloy (tin brass)		
Other aluminum alloy	Copper-tin-phosphorus alloy (phosphor bronze)		
Steel:	Copper-tin-lead-phosphorus alloy		
Chromium-molybdenum	(leaded phosphor bronze)		
Low carbon			
High carbon			
Austenitic			
Ferritic			
Martensitic			

#### **TABLE 4 Category Set for Designation Keyword**

Precipitation hardening



# TABLE 5 Value Set for Specimen Orientation



nttps://standards.iteh.ai/catal<del>og/standards/sist/c9a86c27-128c-46af-8768-736c225</del>7874e/astm-e1338-092021

# TABLE 6 Value Set for Location Within Product

Outer surface
Internal
Inside surface
Surface
Quarter thickness
Center of thickness
Leading edge
Trailing edge

### TABLE 7 Category Set for Yield Strength Method (as explained in Test Methods E8 or E8M)

Offset Extension under load Upper Lower


guide include typical, nominal, or summary properties normally derived from a population of individual specimen tests. If warranted by the scope of a particular database system, the system might provide links between the material identification data elements given in this guide, and the individual specimen test results recorded in accordance with other guides corresponding to particular test methods.

# E1338 – 09 (2021)

#### **TABLE 8 Category Set for Hardness Scale**

Brinell	
Knoop	
Rockwell A	
Rockwell B	
Rockwell C	
Rockwell E	
Rockwell F	
Shore	
Vickers	
Rockwell 15t	
Rockwell 30t	
Rockwell 45t	
Rockwell 15N	
Rockwell 30N	
Rockwell 45N	

#### **TABLE 9 Value Set for Melt Practice**



Powder metallurgy Spin

ASTM E1338-09(2021

https://standards.iteh.a/catalog/standards.stele92021 TABLE 11 Value Set for Heating Environment

> Air Vacuum Inert gas Hydrogen Other reducing gas Oxidizing gas atmosphere

#### **TABLE 12 Value Set for Cooling Environment**

Quenched in oil Air-cooled Inert gas-cooled Quenched in water Quenched in polymer Quenched in air and water

1.6 *Material Classes*—See ANSI/AWS A9.1-92 for arc welds, Guide E527 for Metal and Alloys in the Unified Numbering System (UNS), Guide E1308 for polymers, Guide E1309 for composite material, and Guide E1471 for fibers, fillers, and core materials.

<u>1.7 This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.</u>

# E1338 – 09 (2021)

#### **TABLE 13 Value Set for Forming Method**

Forging Casting Extrusion Hot rolling Cold rolling Powder compaction Drawing/coining Bending

# TABLE 14 Value Set for Product Shape Flat Round Hexagonal Square Structural Irregular Profile TABLE 15 Value Set for Product Form

TABLE 15 Value Set for Floduct Form		
Bar	Rod	
Block	Sheet	
Pipe	Shift	
Plate	Strip	
Powder	Tube	
Ring	Wire	
	Extruded profile	

# ileh Standards

TABLE 16 Value Set for Type of Elongation as Explained in Test Methods E8 and E8M



## TABLE 17 Category Set for Charpy Specimen Size

STME One half 09(2021

https://standards.iteh.ai/catalog/standards/sist/e9a86One quarter c-46af-8768-736c2257874e/astm-e1338-092021 One eighth

## 2. Referenced Documents

## 2.1 ASTM Standards:<sup>2</sup>

- E8 Test Methods for Tension Testing of Metallic Materials [Metric] E0008\_E0008M
- E8M Test Methods for Tension Testing of Metallic Materials [Metric] (Withdrawn 2008)<sup>3</sup>
- E527 Practice for Numbering Metals and Alloys in the Unified Numbering System (UNS)
- E616 Terminology Relating to Fracture Testing (Withdrawn 1996)<sup>3</sup>
- E1308 Guide for Identification of Polymers (Excludes Thermoset Elastomers) in Computerized Material Property Databases (Withdrawn 2000)<sup>3</sup>
- E1309 Guide for Identification of Fiber-Reinforced Polymer-Matrix Composite Materials in Databases (Withdrawn 2015)<sup>3</sup>
- E1313 Guide for Recommended Formats for Data Records Used in Computerization of Mechanical Test Data for Metals (Withdrawn 2000)<sup>3</sup>
- E1443 Terminology Relating to Building and Accessing Material and Chemical Databases (Withdrawn 2000)<sup>3</sup>
- E1471 Guide for Identification of Fibers, Fillers, and Core Materials in Computerized Material Property Databases (Withdrawn 2015)<sup>3</sup>
- IEEE/ASTM SI 10 American National Standard for Metric Practice

<sup>&</sup>lt;sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>&</sup>lt;sup>3</sup> The last approved version of this historical standard is referenced on www.astm.org.

# E1338 – 09 (2021)

2.2 Other Standards:

- ISO Standard: 3166 Codes for Representation of Names of Countries Quantities, Units and Symbols in Physical Chemistry— IUPAC<sup>4</sup>
- ANSI/AWS A9.1-92 Standard Guide for Describing Arc Welds in Computerized Material Property and Nondestructive Examination Databases<sup>5</sup>

## 3. Terminology

3.1 Computer-related technical terms in this guide are defined in Terminology E1443.

## 4. Significance and Use

4.1 This guide describes the types of information that are indispensable for uniquely identifying a metal or alloy in a computerized database. The purpose is to facilitate standardized storage and retrieval of the information with a computer, and allow meaningful comparison of data from different sources.

4.2 Many numbering systems for metals and alloys have been developed which are based on their chemical compositions. Separate systems have also evolved to describe the thermomechanical condition of metals and alloys in order to narrow their description. It is the separation into logical data elements from these complex, historically significant, and overlapping systems of identification that is the challenge in the identification of metals and alloys within computerized databases.

4.3 This guide is intended to provide a common starting point for designers and builders of materials property databases. This guide generally identifies the contents of the database in terms of data elements, but does not recommend any particular logical or physical database design. A database builder has considerable flexibility in designing a database schema, and it is intended that this guide support that flexibility.

4.4 It is recognized that material property databases will be designed for different levels of material information and for different purposes. For example, a database developed by an industry trade group might only identify typical properties generally representative of those for a particular metal or alloy, and not actual values measured on a specific sample. On the other hand, a business might desire to manage data on specific lots it procures, or even properties of a specific piece or sample from a lot. Consequently, some of the data elements identified in this guide might not be applicable in every database instance.

## ASTM E1338-09(2021)

4.5 The extent of material identification implemented in a particular database depends on its specific purpose. A single organization may include substantial detail in its database. Less detail may be included in a common database used by several organizations because of commercial and other considerations. Since metals and alloys are diverse and the technologies are always changing, recommendations should not be regarded as exclusive of additional data elements for material identification. The recommended data elements should be expanded if additional detailed information which serves to identify materials is to be recorded.

4.6 A number of data elements are considered essential to any database and need to exist in the database. Data elements are considered essential if they are required for users to have sufficient information to interpret the data and be confident of their ability to compare sets of data for materials from different sources. Failure to complete an essential data element may render the record unusable in a database or in data exchange. Essential refers to the quality or completeness of recorded data, and does not necessarily have direct meaning relative to database structure. In some cases, the identified data element might be accommodated within a particular database without explicitly including a field just for the essential data element. Additionally, a database schema may require additional data fields to be not null to maintain data record integrity or to implement a mandatory data relationship. These additional fields are beyond the scope of this guide. Finally, it is also noted that a data element identified as essential in this guide might not be relevant for a database created for a specific application of limited scope.

4.7 This guide presents a listing of the data elements and does not intend to define any single organization of the data elements to be used in either a logical or physical model for the database. The data element lists are divided by group headings for discussion purposes only. The group headings are not intended to identify normalization of the database model; this is left to the database designer.

<sup>&</sup>lt;sup>4</sup> Available from International Organization for Standardization (ISO), 1, ch. de la Voie-Creuse, Case postale 56, CH-1211, Geneva 20, Switzerland, http://www.iso.ch.

<sup>&</sup>lt;sup>5</sup> Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, http://www.ansi.org.