



Designation: D2582 – 21

# Standard Test Method for Puncture-Propagation Tear Resistance of Plastic Film and Thin Sheeting<sup>1</sup>

This standard is issued under the fixed designation D2582; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the U.S. Department of Defense.*

## 1. Scope\*

1.1 This test method covers the determination of the dynamic tear resistance of plastic film and thin sheeting subjected to end-use snagging-type hazards.

1.2 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

NOTE 1—Film has been arbitrarily defined as sheeting having nominal thickness not greater than 0.25 mm (0.010 in.).

NOTE 2—There is no known ISO equivalent to this standard.

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

## 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

[D618 Practice for Conditioning Plastics for Testing](#)

[D883 Terminology Relating to Plastics](#)

[D4000 Classification System for Specifying Plastic Materials](#)

[D5947 Test Methods for Physical Dimensions of Solid Plastics Specimens](#)

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee D20 on Plastics and is the direct responsibility of Subcommittee D20.19 on Film, Sheeting, and Molded Products.

Current edition approved May 1, 2021. Published May 2021. Originally approved in 1967. Last previous edition approved in 2016 as D2582 – 16. DOI: 10.1520/D2582-21.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

[D6988 Guide for Determination of Thickness of Plastic Film Test Specimens](#)

[E691 Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method](#)

## 3. Terminology

3.1 *Definitions of Terms Specific to This Standard:*

3.1.1 *slit tear*—a single tear parallel to the direction of the falling carriage.

3.1.2 *“V” tear*—a tear that has two individual tear legs (not necessarily of equal length) radiating approximately  $\pm 45^\circ$  from the point the tear was initiated.

## 4. Significance and Use

4.1 The puncture-propagation of tear test measures the resistance of a material to snagging, or more precisely, to dynamic puncture and propagation of that puncture resulting in a tear. Failures due to snagging occur in a variety of end uses, including industrial bags, liners, and tarpaulins. The units reported in this test method are Newtons (tear resistance).

4.2 Experience has shown that for many materials puncture does not contribute significantly to the force value determined, due to the sharpness of the propagating probe used. However, comparing the results of prepunctured test specimens with normal nonpunctured specimens will give an indication of the extent of any puncture resistance in the reported result.

4.3 For many materials, there may be a specification that requires the use of this test method, but with some procedural modifications that take precedence when adhering to the specification. Therefore, it is advisable to refer to that material specification before using this test method. Table 1 of Classification System [D4000](#) lists the current ASTM materials standards.

## 5. Apparatus<sup>3</sup>

5.1 As shown in [Fig. 1](#), the instrument consists of:

<sup>3</sup> The sole source of supply of the apparatus known to the committee at this time is Testing Machines, Inc., 2910 Expressway Drive, South, Islandia, NY 11749. If anyone is aware of alternative suppliers, please provide this information to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee<sup>1</sup>, which you may attend.

\*A Summary of Changes section appears at the end of this standard




FIG. 1 Puncture-Propagation of Tear Tester

5.1.1 Carriages of different weight, each with a pointed probe. Each carriage weight shall have a tolerance of  $\pm 1\%$  of the weight desired.

5.1.2 A test stand including:

5.1.2.1 Carriage release mechanism,

5.1.2.2 Scale marked in millimetres,

5.1.2.3 Curved specimen holder with a tear slot and five clamps,

5.1.2.4 Drop base with a guide channel to accommodate the carriage wheels, and

5.1.2.5 Bubble level to level the base.

5.2 The standard drop height is 508 mm (20.0 in.); however, it can be varied to suit the desired end-use-rate condition. See 10.3 for an alternative method for calculating tear resistance for heights other than 508 mm.

5.3 The probe is a 3.18-mm (0.125-in.) diameter drill rod having one end a truncated cone, the short base 0.40 mm (0.016 in.) in diameter, with a  $30^\circ$  included angle so that most of the tear is propagated against the body of the rod. See Fig. 2.

5.4 *Thickness Gauge*— a dead-weight micrometer as described in Test Method C of Test Method D5947, or an equivalent measuring device, reading to 0.0025 mm (0.0001 in.) or less.

## 6. Test Specimen

6.1 Specimens are typically cut in any rectangular shape so long as they are approximately 200 mm (8.0 in.) long in the direction of tear and can be held by all five clamps. Multiple




FIG. 2 Short Base Probe

tears can be made on a single sheet provided a minimum separation of 25 mm (1 in.) is maintained between tears.

6.2 Two sets of specimens shall be cut from each sample such that the direction of tear, during the test, will be parallel to (1) MD, the machine direction and (2) TD, the transverse direction, respectively, of the material being tested. Enough specimens shall be cut in each direction to provide for a minimum of five tears.

## 7. Preparation and Calibration of Apparatus

7.1 Level the base of the tester by centering the spirit level bubble by adjustment of the leveling legs.

7.2 Check “sharpness” of probes by visual observation under a magnifying glass. If the short base end is not 0.40 mm (0.016 in.) in diameter or any burrs, nicks, or distortions are noted, or both, replace the probe.

7.3 Check the length of the probes by inserting each carriage in turn in the guide channel and lowering to the alignment mark on the curved specimen holder. The point of the probe should be aligned with this mark.

7.4 Measure the vertical drop height from the specimen holder mark, located near the tear slot, to the horizontal mark on the carriage release mechanism. Adjust the selected height to the nearest 2 mm (0.078 in.). The standard drop height is  $508 \pm 2$  mm.

7.5 Check the alignment of the specimen holder receiving slot by lowering a carriage with its probe extending into the slot, up and down the slot length. The probe should be centered, that is, not touching either edge of the slot.

## 8. Conditioning

8.1 *Conditioning*—Condition the test specimens at  $23 \pm 2^\circ\text{C}$  ( $73.4 \pm 3.6^\circ\text{F}$ ) and  $50 \pm 10\%$  relative humidity for not less than 40 h prior to test in accordance with Procedure A of Practice D618 unless otherwise specified by agreement or the relevant ASTM material specification. In cases of disagreement, the tolerances shall be  $\pm 1^\circ\text{C}$  ( $\pm 1.8^\circ\text{F}$ ) and  $\pm 5\%$  relative humidity.

8.2 *Test Conditions*—Conduct the tests at the same temperature and humidity used for conditioning with tolerances in accordance with Section 7 of Practice D618, unless otherwise

specified by contract or the relevant ASTM material specification. In cases of disagreement, the tolerances shall be  $\pm 1^\circ\text{C}$  ( $\pm 1.8^\circ\text{F}$ ) and  $\pm 5\%$  relative humidity.

## 9. Procedure

9.1 Measure and record the thickness of each specimen tested in accordance with Test Methods **D5947** or Guide **D6988**, as appropriate for the specimen thickness.

9.2 Secure the specimen in the holder by placing it under the clamps and setting the clamp lever to the down position. The specimen should drape against the holder contour. Stiffer materials should be loosely held adjacent to the holder. Each clamp needs to apply sufficient pressure to prevent any specimen slippage.

9.3 By trial and error, select the carriage that produces a minimum tear length of 40 mm and does not bottom-out against the drop base. Lower selected carriage until the probe point touches but does not indent the specimen. Adjust the tear length indicating rod to “0” on the scale located on the guide channel.

9.4 Place the selected carriage in the release mechanism.

9.5 Cock the release mechanism on the left side and release the carriage by pushing the button on the front of the release mechanism.

9.6 Read the tear length to the nearest 0.5 mm.

9.7 Raise the carriage by pulling the handle on the left side of the guide channel.

9.8 After the carriage has stopped its upward movement, relocate it in the release mechanism by pushing the carriage up in the guide channel by hand. (When the handle is released, the carriage-raising mechanism should return to the bottom of the guide channel. However, check before releasing the carriage for the next test.)

9.9 Re-cock the release mechanism.

9.10 Release the clamps and relocate the specimen for the next tear test cycle. Take care not to relocate the specimen so that the tears are too close to one another, thereby influencing the tear results.

9.11 A minimum of five determinations in each direction for each sample is required.

## 10. Calculation

10.1 To determine the tear resistance employing a standard drop height of  $508 \pm 2$  mm, use **Table 1**. (See **X1.1.5** for an explanation of normalization.)

10.2 To determine the tear resistance employing a nonstandard drop height or carriage weight, other than those listed above, calculate the tear resistance,  $F$ , in Newtons, as follows:

$$F = [(W \times H)/L] + W \quad (9.8065) \quad (1)$$

where:

- $W$  = weight of carriage, kg,
- $H$  = height of carriage before release, mm,
- $L$  = length of tear, mm, and

**TABLE 1 Normalized Equations for Each Carriage Weight Using the Standard Drop Height**

Carriage No.	Carriage Weight		Equations
	kg $\pm 1\%$	lb $\pm 1\%$	
No. 1	0.1134	0.250	$F = (564.93/L) + 11.670$
No. 2	0.2268	0.500	$F = (1129.85/L) + 9.179$
No. 3	0.3402	0.750	$F = (1694.78/L) + 6.953$
No. 4	0.4536	1.00	$F = (2259.70/L) + 4.452$
No. 5	0.6804	1.50	$F = (3389.55/L) - 0.284$
No. 6	0.9072	2.00	$F = (4519.40/L) - 4.727$
No. 7	1.1340	2.50	$F = (5649.24/L) - 9.541$
No. 8	1.3608	3.00	$F = (6779.10/L) - 14.234$

9.8065 = conversion factor for Newtons.

10.3 For inter- and intralaboratory data comparisons, the same drop height and weight carriage must be used.

10.4 Calculate the average tear length,  $L$ , in both directions (MD and TD) to the nearest 0.1 mm.

10.5 Calculate the tear resistance,  $F$ , in each direction to the nearest 0.1 Newton.

10.6 Calculate the standard deviation (estimated) for each direction tested as follows:

$$s = \sqrt{(\sum X^2 - n\bar{X}^2)/(n - 1)} \quad (2)$$

where:

- $s$  = estimated standard deviation,
- $X$  = value of single observation,
- $n$  = number of observations, and
- $\bar{X}$  = arithmetic mean of the set of observations.

## 11. Report

11.1 Report the following information:

- 11.1.1 Complete identification of the sample tested,
- 11.1.2 Average tear resistance for the direction tested,
- 11.1.3 Drop height selected, if nonstandard,
- 11.1.4 Carriage used,
- 11.1.5 Number of specimens tested, if greater or less than five,
- 11.1.6 Average thickness, in mils,
- 11.1.7 Type of tears produced, for example, “V” or slit, and
- 11.1.8 Standard deviation for each direction tested, reported to two significant digits.

## 12. Precision and Bias<sup>4</sup>

12.1 **Table 2** is based on a round robin conducted in 1990 in accordance with Practice **E691** involving eight materials tested in both MD and TD directions by six laboratories. All the samples were prepared at one source. Each test result was the average of five individual determinations. Each laboratory obtained two test results for each material. **Warning**—The following explanations of  $r$  and  $R$  (**12.2 – 12.2.3**) are only intended to present a meaningful way of considering the approximate precision of this test method. The data in **Table 2** should not be rigorously applied to acceptance or rejection of

<sup>4</sup> Supporting data are available from ASTM Headquarters. Request RR:D20-1168.