



Designation: ~~F437--15~~ F437 – 21

An American National Standard

Standard Specification for Threaded Chlorinated Poly(Vinyl Chloride) (CPVC) Plastic Pipe Fittings, Schedule 80¹

This standard is issued under the fixed designation F437; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification covers chlorinated poly(vinyl chloride) (CPVC) threaded Schedule 80 pipe fittings. Included are requirements for materials, workmanship, dimensions, and burst pressure.

NOTE 1—The CPVC fittings covered by this specification were covered previously in Specification [D2464](#).

1.2 The products covered by this specification are intended for use with the distribution of pressurized liquids only, which are chemically compatible with the piping materials. Due to inherent hazards associated with testing components and systems with compressed air or other compressed gases some manufacturers do not allow pneumatic testing of their products. Consult with specific product/component manufacturers for their specific testing procedures prior to pneumatic testing.

NOTE 2—Pressurized (compressed) air or other compressed gases contain large amounts of stored energy which present serious ~~safety~~safety hazards should a system fail for any reason.

1.3 The text of this specification references notes, footnotes, and appendixes which provide explanatory material. These notes and footnotes (excluding those in tables and figures) shall not be considered as requirements of the specification.

<https://standards.iteh.ai/catalog/standards/sist/6daa4015-88b8-4aa0-ac57-875506ec4158/astm-f437-21>

1.4 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.5 The following safety hazards caveat pertains only to the test method portion, Section 8, of this specification: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.6 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:²

[D618 Practice for Conditioning Plastics for Testing](#)

¹ This specification is under the jurisdiction of ASTM Committee [F17](#) on Plastic Piping Systems and is the direct responsibility of Subcommittee [F17.10](#) on Fittings. Current edition approved ~~March 1, 2015~~April 1, 2021. Published ~~July 2015~~May 2021. Originally approved in 1974. Last previous edition approved in ~~2009~~2015 as ~~F437–09~~F437 – 15. DOI: ~~10.1520/F0437-15~~10.1520/F0437-21.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard

- D1599 Test Method for Resistance to Short-Time Hydraulic Pressure of Plastic Pipe, Tubing, and Fittings
- D1600 Terminology for Abbreviated Terms Relating to Plastics
- D1784 Classification System and Basis for Specification for Rigid Poly(Vinyl Chloride) (PVC) Compounds and Chlorinated Poly(Vinyl Chloride) (CPVC) Compounds
- D2122 Test Method for Determining Dimensions of Thermoplastic Pipe and Fittings
- D2464 Specification for Threaded Poly(Vinyl Chloride) (PVC) Plastic Pipe Fittings, Schedule 80
- D2749 Symbols for Dimensions of Plastic Pipe Fittings
- F412 Terminology Relating to Plastic Piping Systems
- F1498 Specification for Taper Pipe Threads 60° for Thermoplastic Pipe and Fittings

2.2 *Federal Standard:*

Fed Std. No. 123 Marking for Shipment (Civil Agencies)³

2.3 *Military Standard:*

MIL-STD-129 Marking for Shipment and Storage³

2.4 ~~NSF Standard:~~ NSF/ANSI Standards:

NSF/ANSI Standard No. 14 for Plastic Piping Components and Related Materials

NSF/ANSI Standard No. 61 Drinking Water System Components – Health Effects

3. Terminology

3.1 *Definitions:*

3.1.1 Definitions are in accordance with Terminology F412 and abbreviations are in accordance with Terminology D1600, unless otherwise indicated. The abbreviation for chlorinated poly(vinyl chloride) is CPVC.

4. Classification

4.1 *General*—This specification covers threaded Schedule 80 CPVC pipe fittings, intended for use with threaded Iron Pipe Size (IPS) outside-diameter plastic pipe.

4.1.1 Fittings covered by this specification are normally molded. In-line fittings, such as couplings, unions, bushings, caps, nipples, etc., shall be molded or machined from extruded stock.

4.1.2 Fittings fabricated by backwelding are not included in this specification.

NOTE 3—This specification does not include requirements for pipe and fittings intended to be used to vent combustion gases.

5. Materials and Manufacture

5.1 This specification covers CPVC pipe fittings made from compounds meeting the requirements of Class 23447 as defined in Specification D1784.

NOTE 4—Mechanical strength, heat resistance, flammability, and chemical resistance requirements are covered in Specification D1784.

5.2 *Rework Material*—The manufacturers shall use only their own clean rework fitting material and the fittings produced shall meet all the requirements of this specification.

6. Requirements


6.1 *Dimensions and Tolerances:*

6.1.1 The dimensions and tolerances of the fittings shall be as shown in Table 1 and Table 2 when measured in accordance with Test Method D2122. Minimum dimensions have zero negative tolerances. Bushings shall have thread lengths applicable to the corresponding sizes. Counterbore, which is optional, is not shown in Table 1, and is not included in the center-to-end or end-to-end dimensions.

³ DLA Document Services Building 4/D 700 Robbins Avenue Philadelphia, PA 19111-5094 <http://quicksearch.dla.mil/>

⁴ Available from NSF International, P.O. Box 130140, 789 N. Dixboro Rd., Ann Arbor, MI 48113-0140, <http://www.nsf.org>.

TABLE 1 Dimensions of 90° Ells, Tees, Crosses, 45° Elbows and Couplings (Straight Sizes), in. (mm)^{A,B}



| Nominal Pipe Size | Center to Thread End, 90° Elbows, Tees, Crosses, H , min | Length of Thread, T , min | Center to Thread End, 45° Elbow, K , min | Inside Diameter of Fitting, D , min | Nominal Wall Thickness, F , min | Outside Diameter of Hub, M , min | Thread End to Thread End of Coupling, L , min |
|-------------------|--|-----------------------------|--|---------------------------------------|-----------------------------------|------------------------------------|---|
| 1/4 | 0.812 (20.62) | 0.50 (12.70) | 0.688 (17.48) | 0.258 (6.55) | 0.135 (3.43) | 0.840 (21.34) | 1.063 (27.00) |
| 3/8 | 0.938 (23.83) | 0.50 (12.70) | 0.750 (19.05) | 0.379 (9.63) | 0.144 (3.66) | 1.000 (25.40) | 1.063 (27.00) |
| 1/2 | 1.125 (28.58) | 0.64 (16.26) | 0.750 (19.05) | 0.502 (12.75) | 0.198 (5.03) | 1.280 (32.51) | 1.344 (34.14) |
| 3/4 | 1.250 (31.75) | 0.65 (16.51) | 1.000 (25.40) | 0.698 (17.73) | 0.207 (5.25) | 1.500 (38.10) | 1.500 (38.10) |
| 1 | 1.500 (28.10) | 0.81 (20.51) | 1.125 (28.58) | 0.911 (23.14) | 0.225 (5.72) | 1.810 (45.97) | 1.688 (42.88) |
| 1 1/4 | 1.750 (44.45) | 0.85 (21.59) | 1.313 (23.35) | 1.227 (31.17) | 0.261 (6.63) | 2.200 (55.88) | 1.750 (44.45) |
| 1 1/2 | 1.938 (49.23) | 0.85 (21.59) | 1.438 (36.83) | 1.446 (36.73) | 0.270 (6.85) | 2.500 (63.50) | 2.000 (50.80) |
| 2 | 2.250 (57.15) | 0.90 (22.86) | 1.625 (41.28) | 1.881 (47.78) | 0.297 (7.54) | 3.000 (76.20) | 2.063 (52.40) |
| 2 1/2 | 2.688 (68.28) | 1.21 (30.73) | 1.938 (49.23) | 2.250 (57.15) | 0.315 (8.00) | 3.560 (90.42) | 2.625 (66.68) |
| 3 | 3.063 (77.80) | 1.30 (33.02) | 2.125 (53.98) | 2.820 (71.63) | 0.405 (10.29) | 4.300 (109.22) | 2.750 (69.85) |
| 4 | 3.625 (92.08) | 1.38 (35.05) | 2.625 (66.68) | 3.737 (94.92) | 0.450 (11.43) | 5.430 (137.92) | 3.000 (76.20) |
| 6 | 5.125 (130.18) | 1.50 (38.10) | 3.250 (82.55) | 5.646 (143.41) | 0.504 (12.80) | 7.625 (193.68) | 3.250 (82.55) |

^AThe sketches and designs of fittings shown are illustrative only.

^BSymbols for dimensions are per Symbols D2749.

^CThis dimension locates the end of the fitting.

TABLE 2 Dimensions of Plugs and Caps, in. ^{A,B}



| Nominal Pipe Size | Length of Male Thread, S , min | Length of Female Thread, T , min | Width of Flats, Q , min | Nominal Wall Thickness, F , min | Height of Head, R , min | Cap Height, W , min | Outside Diameter of Hub, M , min |
|-------------------|----------------------------------|------------------------------------|---------------------------|-----------------------------------|---------------------------|-----------------------|------------------------------------|
| 1/4 | 0.44 (11.18) | 0.50 (12.70) | 0.625 (15.88) | 0.135 (3.43) | 0.188 (4.78) | 0.688 (17.48) | 0.840 (21.34) |
| 3/8 | 0.44 (11.18) | 0.50 (12.70) | 0.750 (19.05) | 0.144 (3.66) | 0.188 (4.78) | 0.688 (17.48) | 1.000 (25.40) |
| 1/2 | 0.53 (13.46) | 0.64 (16.26) | 0.938 (23.83) | 0.198 (5.03) | 0.188 (4.73) | 0.875 (22.23) | 1.280 (32.51) |
| 3/4 | 0.55 (13.92) | 0.65 (16.51) | 1.125 (28.53) | 0.207 (5.26) | 0.219 (5.56) | 1.000 (25.40) | 1.450 (35.03) |
| 1 | 0.68 (17.27) | 0.81 (20.57) | 1.375 (34.93) | 0.225 (5.72) | 0.219 (5.56) | 1.188 (30.18) | 1.810 (45.97) |
| 1 1/4 | 0.71 (18.03) | 0.85 (21.59) | 1.750 (44.45) | 0.261 (6.63) | 0.281 (7.14) | 1.250 (31.75) | 2.200 (55.88) |
| 1 1/2 | 0.72 (18.29) | 0.85 (21.59) | 1.875 (47.63) | 0.270 (6.85) | 0.313 (7.95) | 1.250 (31.75) | 2.450 (62.23) |
| 2 | 0.76 (19.30) | 0.90 (22.86) | 1.875 (47.63) | 0.297 (7.54) | 0.313 (7.95) | 1.375 (34.93) | 3.000 (76.20) |
| 2 1/2 | 1.14 (28.96) | 1.21 (30.25) | 1.875 (47.63) | 0.369 (8.00) | 0.375 (9.53) | 1.625 (41.28) | 3.560 (90.42) |
| 3 | 1.20 (30.48) | 1.30 (33.02) | 2.000 (50.80) | 0.405 (10.29) | 0.375 (9.53) | 1.750 (49.45) | 4.250 (107.98) |
| 4 | 1.30 (33.02) | 1.38 (35.05) | 2.000 (50.80) | 0.450 (11.43) | 0.375 (9.53) | 2.000 (50.60) | 5.350 (125.87) |
| 6 | 1.44 (36.58) | 1.50 (38.10) | 2.000 (50.80) | 0.504 (12.80) | 0.500 (12.10) | 2.125 (53.98) | 7.625 (193.68) |

^AThe sketches and designs of fittings shown are illustrative only.

^BSymbols for dimensions are per Symbols D2749.

^CAt the manufacturer's option the head of the plug shall be hexagonal, octagonal, square, or round.

6.1.2 *Fittings Not Illustrated*—All fittings, whether illustrated in Table 1 and Table 2 or not, shall have wall thicknesses and thread dimensions conforming to 6.1 and 6.2.

6.2 *Threads*—For all fittings having taper pipe threads, threads shall conform to Specification F1498 and be gaged in accordance with 8.4.

6.3 *Burst Pressure*:

6.3.1 The minimum burst strength of the fittings shall be not less than that calculated for the size and wall thickness of the pipe with which it is to be used, when calculated from the following equation:

$$S = P(D_o - t)/2t \quad (1)$$

where:

- S = hoop stress, psi (or MPa),
- P = internal pressure, psi (or MPa),
- D_o = average outside diameter, in. (or mm), and
- t = minimum wall thickness, in. (or mm).

Fittings tested in accordance with 8.5 shall withstand the minimum burst pressure shown in **Table 3**.

6.3.2 Pressures shown are minimum burst pressures and do not imply rated working pressures. The burst pressure shall be used only as an indication of quality.

7. Workmanship, Finish, and Appearance

7.1 The fittings shall be homogeneous throughout and free of cracks, holes, foreign inclusions, or other defects. The fittings shall be as uniform as commercially practicable in color, opacity, density, and other physical properties.

8. Test Methods

8.1 *Conditioning*—Condition the test specimens at ~~73.473 °F ± 3.6°F (23.4 °C ± 2°C)~~ and ~~50 ± 10 % ± 2 °C~~ and ~~50 % ± 10 %~~ relative humidity for not less than 40 h prior to test in accordance with Procedure A of Practice **D618**, for those tests where conditioning is required.

8.2 *Test Conditions*—Conduct tests in the Standard Laboratory Atmosphere of ~~73.4 ± 3.6°F (23 ± 2°C)~~ and ~~5073 °F ± 4 °F (23 °C ± 2 °C)~~ and ~~50 % ± 10 %~~ relative humidity, unless otherwise specified in the test methods or in this specification.

8.3 *Sampling*—A sufficient quantity of fittings as agreed upon between the seller and the purchaser shall be selected at random from each lot or shipment and tested to determine that the basic design is in conformance with this specification.

NOTE 5—For individual orders or specifications where supplemental tests are required, only those tests and numbers of tests specifically agreed upon between the purchaser and seller need be conducted.

8.4 *Threads*—All taper pipe threads shall be gaged in accordance with Specification **F1498**.

TABLE 3 Burst Pressure Requirements for Water at 73°F (23°C) for CPVC Threaded Pipe Fittings, Schedule 80

| Nominal Size, in. | Min Burst Strength ^A | |
|-------------------|---------------------------------|---------|
| | Class 23447 | |
| | psi | (MPa) |
| 1/4 | 3620 | (24.96) |
| 3/8 | 2940 | (20.27) |
| 1/2 | 2720 | (18.75) |
| 3/4 | 2200 | (15.17) |
| 1 | 2020 | (13.93) |
| 1 1/4 | 1600 | (11.44) |
| 1 1/2 | 1510 | (10.41) |
| 2 | 1290 | (8.89) |
| 2 1/2 | 1360 | (9.38) |
| 3 | 1200 | (8.27) |
| 4 | 1040 | (7.17) |
| 6 | 890 | (6.14) |

^AThis table was calculated for Schedule 80 pipe using the ISO formula and a stress level as follows:

| | | |
|--------------------------------------|------|------|
| | psi | MPa |
| Class 23447 (Type IV Grade 1 (CPVC)) | 6400 | 44.1 |