



Designation: **A781/A781M—20a** A781/A781M – 21

Standard Specification for Castings, Steel and Alloy, Common Requirements, for General Industrial Use¹

This standard is issued under the fixed designation A781/A781M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

1. Scope*

1.1 This specification covers a group of requirements that are mandatory requirements of the following steel casting specifications issued by ASTM. If the product specification specifies different requirements, the product specification shall prevail.

ASTM Designation	Title of Specification
A27/A27M	Steel Castings, Carbon, for General Application
A128/A128M	Steel Castings, Austenitic Manganese
A148/A148M	Steel Castings, High Strength, for Structural Purposes
A297/A297M	Steel Castings, Iron-Chromium and Iron-Chromium-Nickel, Heat Resistant, for General Application
A447/A447M	Steel Castings, Chromium-Nickel-Iron Alloy (25-12 Class), for High-Temperature Service
A494/A494M	Castings, Nickel and Nickel Alloy
A560/A560M	Castings, Chromium-Nickel Alloy
A743/A743M	Castings, Iron-Chromium, Iron-Chromium-Nickel, Corrosion Resistant, for General Application
A744/A744M	Castings, Iron-Chromium-Nickel, Corrosion Resistant, for Severe Service
A747/A747M	Steel Castings, Stainless, Precipitation Hardening
A890/A890M	Castings, Iron-Chromium-Nickel-Molybdenum Corrosion-Resistant, Duplex (Austenitic/Ferritic) for General Application
A915/A915M	Steel Castings, Carbon and Alloy, Chemical Requirements Similar to Standard Wrought Grades
A958/A958M	Steel Castings, Carbon and Alloy, with Tensile Requirements, Chemical Requirements Similar to Standard Wrought Grades
A1002	Castings, Nickel-Aluminum Ordered Alloy

1.2 This specification also covers a group of supplementary requirements that may be applied to the above specifications as indicated therein. These are provided for use when additional testing or inspection is desired and apply only when specified individually by the purchaser in the order.

1.3 The requirements of the individual material specification and this general specification shall prevail in the sequence named.

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.18 on Castings.

Current edition approved Nov. 1, 2020 May 1, 2021. Published November 2020 May 2021. Originally approved in 1980. Last previous edition approved in 2020 as A781/A781M—20; A781/A781M – 20a. DOI: 10.1520/A0781_A0781M-20A; 10.1520/A0781_A0781M-21.

*A Summary of Changes section appears at the end of this standard

1.4 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in nonconformance with the standard.

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:²

- [A27/A27M Specification for Steel Castings, Carbon, for General Application](#)
- [A128/A128M Specification for Steel Castings, Austenitic Manganese](#)
- [A148/A148M Specification for Steel Castings, High Strength, for Structural Purposes](#)
- [A297/A297M Specification for Steel Castings, Iron-Chromium and Iron-Chromium-Nickel, Heat Resistant, for General Application](#)
- [A370 Test Methods and Definitions for Mechanical Testing of Steel Products](#)
- [A380/A380M Practice for Cleaning, Descaling, and Passivation of Stainless Steel Parts, Equipment, and Systems](#)
- [A447/A447M Specification for Steel Castings, Chromium-Nickel-Iron Alloy \(25-12 Class\), for High-Temperature Service](#)
- [A488/A488M Practice for Steel Castings, Welding, Qualifications of Procedures and Personnel](#)
- [A494/A494M Specification for Castings, Nickel and Nickel Alloy](#)
- [A560/A560M Specification for Castings, Chromium-Nickel Alloy](#)
- [A609/A609M Practice for Castings, Carbon, Low-Alloy, and Martensitic Stainless Steel, Ultrasonic Examination Thereof](#)
- [A743/A743M Specification for Castings, Iron-Chromium, Iron-Chromium-Nickel, Corrosion Resistant, for General Application](#)
- [A744/A744M Specification for Castings, Iron-Chromium-Nickel, Corrosion Resistant, for Severe Service](#)
- [A747/A747M Specification for Steel Castings, Stainless, Precipitation Hardening](#)
- [A751 Test Methods and Practices for Chemical Analysis of Steel Products](#)
- [A800/A800M Practice for Estimating Ferrite Content of Stainless Steel Castings Containing Both Ferrite and Austenite](#)
- [A802/A802M Practice for Steel Castings, Surface Acceptance Standards, Visual Examination](#)
- [A890/A890M Specification for Castings, Iron-Chromium-Nickel-Molybdenum Corrosion-Resistant, Duplex \(Austenitic/Ferritic\) for General Application](#)
- [A915/A915M Specification for Steel Castings, Carbon, and Alloy, Chemical Requirements Similar to Standard Wrought Grades](#)
- [A941 Terminology Relating to Steel, Stainless Steel, Related Alloys, and Ferroalloys](#)
- [A958/A958M Specification for Steel Castings, Carbon and Alloy, with Tensile Requirements, Chemical Requirements Similar to Standard Wrought Grades](#)
- [A967/A967M Specification for Chemical Passivation Treatments for Stainless Steel Parts](#)
- [A991/A991M Test Method for Conducting Temperature Uniformity Surveys of Furnaces Used to Heat Treat Steel Products](#)
- [A1002 Specification for Castings, Nickel-Aluminum Ordered Alloy](#)
- [A1058 Test Methods for Mechanical Testing of Steel Products—Metric](#)
- [A1067/A1067M Specification for Test Coupons for Steel Castings](#)
- [A1080/A1080M Practice for Hot Isostatic Pressing of Steel, Stainless Steel, and Related Alloy Castings](#)
- [E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications](#)
- [E94/E94M Guide for Radiographic Examination Using Industrial Radiographic Film](#)
- [E125 Reference Photographs for Magnetic Particle Indications on Ferrous Castings](#)
- [E165/E165M Practice for Liquid Penetrant Testing for General Industry](#)
- [E186 Reference Radiographs for Heavy-Walled \(2 to 4½ in. \(50.8 to 114 mm\)\) Steel Castings](#)
- [E280 Reference Radiographs for Heavy-Walled \(4½ to 12 in. \(114 to 305 mm\)\) Steel Castings](#)
- [E340 Practice for Macroetching Metals and Alloys](#)
- [E353 Test Methods for Chemical Analysis of Stainless, Heat-Resisting, Maraging, and Other Similar Chromium-Nickel-Iron Alloys](#)
- [E354 Test Methods for Chemical Analysis of High-Temperature, Electrical, Magnetic, and Other Similar Iron, Nickel, and Cobalt Alloys](#)
- [E446 Reference Radiographs for Steel Castings Up to 2 in. \(50.8 mm\) in Thickness](#)
- [E709 Guide for Magnetic Particle Testing](#)

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

2.2 SAE Standard:³
AMS 2750 Pyrometry

3. Terminology

3.1 Definitions:

3.1.1 The definitions in Test Methods and Definitions **A370**, Test Methods, Practices, and Terminology **A751**, Terminology **A941**, and Test Methods **A1058** are applicable to this specification and to those listed in **1.1**.

3.1.2 *test coupon, n*—the part from which the test specimen will be extracted.

3.1.3 *test specimen, n*—the part that will be acted upon in a test.

4. Materials and Manufacture

4.1 *Melting Process*—The steel shall be made by open-hearth or electric furnace process with or without separate refining, such as argon-oxygen-decarburization (AOD), unless otherwise specified in the individual specification.

4.2 Heat Treatment:

4.2.1 Castings shall be heat treated in the working zone of a furnace that has been surveyed in accordance with Test Method **A991/A991M** or AMS 2750.

4.2.2 When using furnaces surveyed in accordance with Test Method **A991/A991M**, the following requirements apply for heat treatments above 2000 °F [1100 °C]. When castings are heat treated at temperatures above 2000 °F [1100 °C], then the working zone shall have been established by a survey performed at not more than 25 °F [15 °C] below nor more than 200 °F [110 °C] above the minimum heat treatment temperature specified for the grade. If a minimum heat treatment temperature is not specified for the grade, then the survey temperature shall be not more than 50 °F [30 °C] below nor more than 175 °F [100 °C] above the furnace set point used.

4.2.3 When using furnaces surveyed in accordance with AMS 2750, there are no additional requirements beyond those stated in AMS 2750.

4.2.4 The maximum variation in measured temperature, as determined by the difference between the highest temperature and the lowest temperature, shall be as agreed between the purchaser and producer, except that during production heat treatment no portion of the furnace shall be below the minimum specified temperature nor above the maximum specified temperature for the grade being processed.

5. Chemical Composition

5.1 *Chemical Analysis*—Chemical analysis of materials covered by this specification shall be in accordance with Test Methods, Practices, and Terminology **A751**.

5.2 *Heat Analysis*—An analysis of each heat shall be made by the manufacturer to determine the percentages of the elements specified in the individual specification for the grade being poured. The analysis shall be made from a test sample, preferably taken during the pouring of the heat. When drillings are used, they shall be taken not less than ¼ in. [6.4 mm] beneath the surface. The chemical composition thus determined shall conform to the requirements in the individual specification for the grade being poured.

5.3 *Product Analysis*—A product analysis may be made by the purchaser from material representing each heat, lot, or casting. The analysis shall be made on representative material. Samples for carbon analysis shall be taken no closer than ¼ in. [6 mm] to a cast surface, except that castings too thin for this shall be analyzed on representative material. The chemical composition thus determined shall meet the requirements specified in the applicable specification for the grade involved, or shall be subject to rejection by the purchaser, except that the chemical composition determined for carbon and low-alloy steel and stainless steel steel, stainless steel, and nickel and cobalt based castings may vary from the specified limits by the amounts shown in **Table 1** and **Table 2**, and **Table 3**, respectively. The product analysis tolerances of **Tables 1 and 1-23** are not applicable as acceptance criteria for heat

³ Available from SAE International (SAE), 400 Commonwealth Dr., Warrendale, PA 15096, <http://www.sae.org>.

**TABLE 1 Product Analysis Tolerances – Carbon and Low-Alloy Steels**

Element	Range, % ^A	Tolerances ^{B,C} Over Maximum or Under Minimum Limit, %
C	up to 0.65 above 0.65	$0.03 \times \% C_L + 0.02$ 0.04
Mn	up to 1 above 1	$0.08 \times \% Mn_L + 0.01$ 0.09
Si	up to 0.60 above 0.60	$0.22 \times \% Si_L - 0.01$ 0.15
P	all	$0.13 \times \% P_L + 0.005$
S	all	$0.36 \times \% S_L + 0.001$
Ni	up to 2 above 2	$0.10 \times \% Ni_L + 0.03$ 0.25
Cr	up to 2 above 2	$0.07 \times \% Cr_L + 0.04$ 0.18
Mo	up to 0.6 above 0.6	$0.04 \times \% Mo_L + 0.03$ 0.06
V	up to 0.25 above 0.25	$0.23 \times \% V_L + 0.004$ 0.06
W	up to 0.10 above 0.10	$0.08 \times \% W_L + 0.02$ 0.02
Cu	up to 0.15 above 0.15	$0.18 \times \% Cu_L + 0.02$ 0.05
Al	up to 0.10 above 0.10	$0.08 \times \% Al_L + 0.02$ 0.03

^A The range denotes the composition limits up to which tolerances are computed by the equation, and above which the tolerances are given by a constant.

^B The subscript _L for the elements in each equation indicates that the limits of the element specified by the applicable specification are to be inserted into the equation to calculate the tolerance for the upper limit and the lower limit (if applicable), respectively. Examples of computing tolerances are presented in footnote C.

^C To illustrate the computation of the tolerance, consider the manganese maximum of 0.70 for a 0.30 carbon grade 65-35 in Specification A27/A27M. The maximum permissible deviation is $(0.08 \times 0.70 + 0.01) = 0.066$. Therefore, the highest acceptable product analysis is 0.766. Similarly, for a 0.20 carbon grade 70-40 in Specification A27/A27M, the maximum manganese content is 1.40; thus, the highest acceptable product analysis is $(1.40 + 0.09) = 1.49$.

analysis by the casting manufacturer. When comparing product and heat analysis for other than carbon and low-alloy steels and stainless steels, the reproducibility data R_2 , in Test Methods E353 or E354, as applicable, shall be taken into consideration.

5.4 Unspecified Elements—When chemical analysis for elements not specified for the grade ordered is desired, Supplementary Requirement S13 may be specified.

5.5 Grade Substitution—Grade substitution is not permitted. Grade substitution occurs when the material being supplied contains one or more elements that are not specified for the supplied material such that the material conforms to the requirements of a different grade.

6. Mechanical Test Requirements

NOTE 1—The tension testing requirements of this specification are intended only to characterize the tensile properties of the heat for determination of conformance to the requirements of the applicable product specification. Such testing procedures are not intended to define the upper or lower limits of tensile properties at all possible test locations within a heat. It is well known and documented that tensile properties will vary within a heat or individual casting as a function of chemical composition, processing, testing procedure, and other factors.⁴ It is, therefore, incumbent on designers and engineers to use sound engineering judgement when using tension test results.

6.1 The individual product specifications vary as to whether mechanical tests are required; for this reason, and to determine specific test requirements, the individual product specification should be reviewed.

6.2 Unless otherwise specified by the purchaser, when mechanical properties are required by the product specification, test coupons may be cast integrally with the castings, or as separate blocks, in accordance with Specification A1067/A1067M, Fig. 1,

⁴ Information on the relationship of mechanical properties determined on test coupons obtained as specified in 6.2 with those obtained from the casting may be found in *The Steel Casting Handbook*, Fifth Edition, Steel Founders' Society of America, pp.15–35 through 15–43, 1980.

TABLE 2 Product Analysis Tolerances – Stainless Steels

ElementsElement	Limit or Maximum of Specified Range, %	Tolerance Over the Maximum Limit or Under the Minimum Limit	ElementsElement	Limit or Maximum of Specified Range, %	Tolerance Over the Maximum Limit or Under the Minimum Limit		
Carbon	to 0.010, incl	0.002	Titanium	to 1.00, incl	0.05		
	over 0.010 to 0.030, incl	0.005		over 1.00 to 3.00, incl	0.07		
	over 0.030 to 0.20, incl	0.01		Cobalt	over 0.05 to 0.50, incl	0.01 ^A	
	over 0.20 to 0.60, incl	0.02			over 0.50 to 2.00, incl	0.02	
	over 0.60 to 1.20, incl	0.03			over 2.00 to 5.00, incl	0.05	
Manganese	to 1.00, incl	0.03	Columbium plus tantalum	to 1.50, incl	0.05		
	over 1.00 to 3.00, incl	0.04		Tantalum	to 0.10, incl	0.02	
	over 3.00 to 6.00, incl	0.05			Copper	to 0.50, incl	0.03
	over 6.00 to 10.00, incl	0.06				over 0.50 to 1.00, incl	0.05
	over 10.00 to 15.00, incl	0.10				over 1.00 to 3.00, incl	0.10
over 15.00 to 20.00, incl	0.15	over 3.00 to 5.00, incl	0.15				
Phosphorus	to 0.040, incl	0.005	over 5.00 to 10.00, incl	0.20			
	over 0.040 to 0.20, incl	0.010	Aluminum	to 0.15, incl	-0.005, +0.01		
Sulfur	to 0.040, incl	0.005		over 0.15 to 0.50, incl	0.05		
	over 0.040 to 0.20, incl	0.010		over 0.50 to 2.00, incl	0.10		
	over 0.20 to 0.50, incl	0.020	Aluminum	to 0.15, incl	-0.005, +0.01		
Silicon	to 1.00, incl	0.05		over 0.15 to 0.50, incl	0.05		
	over 1.00 to 3.00, incl	0.10		over 0.50 to 2.00, incl	0.10		
	over 3.00 to 6.00, incl	0.15	Silicon	to 1.00, incl	0.05		
Silicon	over 1.00 to 3.00, incl	0.10		over 1.00 to 3.00, incl	0.10		
	over 3.00 to 6.00, incl	0.15		over 3.00 to 6.00, incl	0.15		
	Chromium	over 4.00 to 10.00, incl		0.10	Nitrogen	to 0.02, incl	0.005
over 10.00 to 15.00, incl		0.15		to 0.02, incl		0.005	
over 15.00 to 20.00, incl		0.20		over 0.02 to 0.19, incl		0.01	
over 20.00 to 30.00, incl		0.25		over 0.02 to 0.19, incl		0.01	
over 30.00 to 40.00, incl		0.30		over 0.19 to 0.25, incl		0.02	
over 40.00 to 50.00, incl		0.35		over 0.19 to 0.25, incl		0.02	
over 50.00 to 60.00, incl		0.40		over 0.25 to 0.35, incl		0.03	
Nickel	to 1.00, incl	0.03	over 0.25 to 0.35, incl	0.03			
	over 1.00 to 5.00, incl	0.07	over 0.35 to 0.45, incl	0.04			
	over 5.00 to 10.00, incl	0.10	over 0.35 to 0.45, incl	0.04			
Nickel	over 10.00 to 20.00, incl	0.15	over 0.45 to 0.55, incl	0.05			
	over 20.00 to 30.00, incl	0.20	over 0.45 to 0.55, incl	0.05			
	Molybdenum	over 0.20 to 0.60, incl	0.03	Tungsten	to 1.00, incl	0.03	
		over 0.60 to 2.00, incl	0.05		over 1.00 to 2.00, incl	0.05	
over 2.00 to 8.00, incl		0.10	Vanadium		to 0.50, incl	0.03	
Molybdenum	over 0.60 to 2.00, incl	0.05		over 0.50 to 1.50, incl	0.05		
	over 2.00 to 8.00, incl	0.10	Selenium	all	0.03		

^A Product analysis limits for cobalt under 0.05 % have not been established, and the manufacturer should be consulted for those limits.

Fig. 2, or Fig. 4, except when Supplementary Requirement S15 is specified. The test coupon in Specification **A1067/A1067M**, Fig. 4 may be employed only for austenitic stainless steel and nickel-base alloy castings with cross sections less than 2½ in. [65 mm].

6.3 Test specimens may be cut from heat-treated castings, at the producer’s or the purchaser’s option, instead of from separately cast test coupons.

6.4 Choice of testing track from the options listed in Test Methods **A1058** when material is ordered to an M-suffix (SI units) product standard should be identified by the purchaser in the ordering information. If the choice of test track is not specified in the order, then the default ASTM track shall be used as noted in Test Methods **A1058**.

6.5 The coupon from which the test specimen is taken shall be heat treated in production furnaces to the same procedure as the castings it represents.



TABLE 3 Product Analysis Tolerances – Nickel and Cobalt Base Alloys

Element	Limit or Maximum of Specified Element, %	Variation Under Min or Over Max	Element	Limit or Maximum of Specified Element, %	Variation Under Min or Over Max		
Carbon	up to 0.02, incl	0.005	Aluminum	up to 0.10, incl	0.02		
	over 0.02 to 0.20, incl	0.01		over 0.10 to 0.50, incl	0.05		
	over 0.20 to 0.60, incl	0.02		over 0.50 to 2.00, incl	0.10		
	over 0.60 to 1.00, incl	0.03		over 2.00 to 5.00, incl	0.20		
Manganese	up to 1.00, incl	0.03	Boron	over 5.00 to 10.00, incl	0.25		
	over 1.00 to 3.00, incl	0.04		over 10.00 to 15.00, incl	0.30		
	over 3.00 to 6.00, incl	0.07		Iron	up to 0.01, incl	0.002	
	over 6.00 to 10.00, incl	0.10			over 0.01 to 0.05, incl	0.005	
Silicon	up to 0.05, incl	0.02	over 0.05 to 0.15, incl		0.010		
	over 0.05 to 0.25, incl	0.03	Copper		up to 0.20, incl	0.02	
	over 0.25 to 0.50, incl	0.04		over 0.20 to 0.50, incl	0.03		
	over 0.50 to 1.00, incl	0.05		over 0.50 to 5.00, incl	0.04		
over 1.00 to 4.50, incl	0.10	over 5.00 to 10.00, incl		0.05			
Phosphorus	all	0.005	over 10.00 to 20.00, incl	0.10			
Sulfur	up to 0.02, incl	0.003	over 20.00 to 30.00, incl	0.15			
	over 0.02 to 0.06, incl	0.005	over 30.00 to 50.00, incl	0.30			
Chromium	up to 5.00, incl	0.10	Zinc	over 30.00 to 50.00, incl	0.45		
	over 5.00 to 15.00, incl	0.15		Vanadium	up to 0.20, incl	0.02	
	over 15.00 to 25.00, incl	0.25			over 0.20 to 0.50, incl	0.03	
	over 25.00 to 35.00, incl	0.30			over 0.50 to 5.00, incl	0.04	
	over 35.00 to 45.00, incl	0.40			over 5.00 to 10.00, incl	0.05	
	over 45.00 to 50.00, incl	0.50		over 10.00 to 20.00, incl	0.10		
Nickel	up to 1.00, incl	0.05	over 20.00 to 30.00, incl	0.15			
	over 1.00 to 5.00, incl	0.10	over 30.00 to 40.00, incl	0.20			
	over 5.00 to 10.00, incl	0.15	over 40.00 to 60.00, incl	0.25			
	over 10.00 to 20.00, incl	0.20	over 60.00 to 80.00, incl	0.45			
	over 20.00 to 30.00, incl	0.25	over 80.00 to 99.00, incl	0.60			
	over 30.00 to 40.00, incl	0.30	Yttrium	up to 0.050, incl	0.005		
over 40.00 to 60.00, incl	0.35	over 0.050 to 0.10, incl		0.010			
over 60.00 to 80.00, incl	0.45	over 0.10 to 0.20, incl		0.015			
over 80.00 to 99.00, incl	0.60	Zirconium		up to 0.10, incl	0.01		
Cobalt	up to 0.10, incl		0.01	over 0.10 to 0.20, incl	0.02		
	over 0.10 to 0.20, incl	0.02	Lanthanum	up to 0.20, incl	0.01		
	over 0.20 to 1.00, incl	0.03		Cerium	up to 0.050, incl	0.005	
	over 1.00 to 5.00, incl	0.05			over 0.050 to 0.10, incl	0.010	
	over 5.00 to 10.00, incl	0.10			over 0.10 to 0.20, incl	0.015	
	over 10.00 to 15.00, incl	0.15	Hafnium		up to 1.50, incl	0.05	
	over 15.00 to 20.00, incl	0.20		over 1.50 to 3.00, incl	0.10		
	over 20.00 to 25.00, incl	0.25		Rhenium	up to 1.50, incl	0.05	
	over 25.00 to 30.00, incl	0.30			over 1.50 to 3.00, incl	0.10	
	over 30.00 to 35.00, incl	0.35	Platinum		up to 0.50, incl	0.03	
	over 35.00 to 50.00, incl	0.50			over 0.50, incl	0.03	
	Molybdenum	up to 1.00, incl		0.03	Oxygen	up to 0.010, incl	0.005
		over 1.00 to 3.00, incl		0.05		Nitrogen	up to 0.02, incl
		over 3.00 to 5.00, incl	0.10	over 0.02 to 0.19, incl			0.01
over 5.00 to 20.00, incl		0.15	over 0.19 to 0.25, incl	0.02			
over 20.00 to 30.00, incl	0.25	over 0.25 to 0.35, incl	0.03				
over 30.00 to 40.00, incl	0.35	over 0.35 to 0.45, incl	0.04				
Tungsten	up to 1.00, incl	0.04	over 0.45 to 0.60, incl	0.05			
	over 1.00 to 3.00, incl	0.10	Magnesium	up to 0.10, incl	0.01		
	over 3.00 to 5.00, incl	0.15		Lead	up to 0.01, incl	0.002	
	over 5.00 to 10.00, incl	0.20			Tin	up to 0.01, incl	0.002
over 10.00 to 20.00, incl	0.25	over 0.01 to 0.05, incl				0.005	
Niobium ^A and/or Tantalum	up to 1.50, incl	0.05	Zinc			up to 0.01, incl	0.002
	over 1.50 to 3.00, incl	0.10		over 0.01 to 0.05, incl		0.005	
	3.00 to 5.00, incl	0.15		Titanium	up to 0.10, incl	0.02	
	over 5.00 to 7.00, incl	0.20			over 0.10 to 0.50, incl	0.03	
over 7.00 to 10.00, incl	0.25	over 0.50 to 1.00, incl	0.04				
over 10.00 to 13.00, incl	0.30	over 1.00 to 2.00, incl	0.05				

TABLE 3 *Continued*

Element	Limit or Maximum of Specified Element, %	Variation Under Min or Over Max	Element	Limit or Maximum of Specified Element, %	Variation Under Min or Over Max
Titanium	over 2.00 to 3.50, incl	0.07			
	over 3.50 to 5.00, incl	0.10			
	over 5.00 to 10.00, incl	0.20			

^A Niobium (Nb) and columbium (Cb) both designate element 41.

6.6 The specimens may be cast to shape or machined from coupons to dimensions in accordance with Test Methods and Definitions [A370](#).

6.7 To determine conformance with the tension test requirements, an observed value or calculated value shall be rounded off in accordance with Practice [E29](#) to the nearest 0.5 ksi [5 MPa] for yield and tensile strength and to the nearest 1 % for elongation and reduction of area. In the special case of rounding the number “5” when no additional numbers other than “0” follow the “5,” rounding shall be done in the direction of the specification limits if following Practice [E29](#) would cause rejection of material.

7. Workmanship, Finish, and Appearance

7.1 All castings shall be made in a workmanlike manner and shall conform to the dimensions on drawings furnished by the purchaser before manufacture is started. If the pattern is supplied by the purchaser, the dimensions of the casting shall be as predicated by the pattern.

8. Quality

8.1 The surface of the casting shall be free of adhering sand, scale, cracks, and hot tears as determined by visual examination. Other surface discontinuities shall meet the visual acceptance standards specified in the order. Practice [A802/A802M](#) or other visual standards may be used to define acceptable surface discontinuities and finish. Unacceptable visual surface discontinuities shall be removed and their removal verified by visual examination of the resultant cavities.

8.2 When additional inspection is desired, Supplementary Requirement S1, S2, S3, S4, or S5 may be specified.

8.3 Rejectable indications shall not be peened, plugged, or impregnated.

9. Repair

9.1 Repair by welding shall be in accordance with the requirements of the individual specification, using procedures and welders qualified in accordance with Practice [A488/A488M](#).

10. Inspection

10.1 The manufacturer shall afford the purchaser’s inspector all reasonable facilities necessary to satisfy that the material is being produced and furnished in accordance with the applicable specification. Foundry inspection by the purchaser shall not interfere unnecessarily with the manufacturer’s operations. All tests and inspections, with the exception of product analysis ([5.3](#)), shall be made at the place of manufacture unless otherwise agreed.

11. Rejection

11.1 Subsequent to acceptance at the manufacturer’s works, material that is found to be unacceptable as determined by requirements specified in the order may be rejected by the purchaser. The manufacturer should be notified of such rejection. If the manufacturer is dissatisfied with the results of any tests performed by the purchaser, they may make claim for a rehearing.

12. Retesting

12.1 If a specimen is machined improperly, or if flaws are revealed by machining or during testing, the specimen may be discarded and another substituted from the same heat.