



Designation: ~~D955—08 (Reapproved 2014)~~ D955 – 21

Standard Test Method of Measuring Shrinkage from Mold Dimensions of Thermoplastics¹

This standard is issued under the fixed designation D955; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. ~~Scope~~ Scope*

1.1 This test method is intended to measure shrinkage from mold cavity to molded dimensions of thermoplastics when molded by compression or injection processes with specified process conditions.

1.2 This test method covers shrinkage measurements at 24 and 48 hours.

1.3 This method will give comparable data based on standard specimens and can not predict absolute values in actual molded parts with varying flow paths, wall thicknesses, pressure and temperature gradients and process conditions. Differences in mold shrinkage may also be observed among the three specimen geometries described in this test method.

1.4 The values stated in SI units are to be regarded as the standard. The values given in parentheses are given for information only.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate ~~safety~~ safety, health, and health ~~environmental~~ environmental practices and determine the applicability of regulatory limitations prior to use.*

<https://standards.iteh.ai/catalog/standards/sist/3ecb9857-050a-4817-a1aa-4c23cb042bd7/astm-d955-21>

NOTE 1—This standard and ISO 294-3 are equivalent in the design of specimen D2. This test method is equivalent to ISO 294-4 where Type D2 specimens and the procedure in **Appendix X2** are used.

NOTE 1—This standard and ISO 294-3 are equivalent in the design of specimen D2. This test method is equivalent to ISO 294-4 where Type D2 specimens and the procedure in **Appendix X2** are used.

1.6 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

[D618 Practice for Conditioning Plastics for Testing](#)

[D788 Classification System for Poly\(Methyl Methacrylate\) \(PMMA\) Molding and Extrusion Compounds](#)

[D883 Terminology Relating to Plastics](#)

¹ This test method is under the jurisdiction of ASTM Committee [D20](#) on Plastics and is the direct responsibility of Subcommittee [D20.09](#) on Specimen Preparation. Current edition approved ~~Aug. 1, 2014~~ April 1, 2021. Published ~~August 2014~~ April 2021. Originally approved in 1948. Last previous edition approved in ~~2008~~ 2014 as ~~D955—08~~ D955 – 08(2014). DOI: ~~10.1520/D0955-08R14~~ 10.1520/D0955-21.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

***A Summary of Changes section appears at the end of this standard**

- D3641 Practice for Injection Molding Test Specimens of Thermoplastic Molding and Extrusion Materials
- D4066 Classification System for Nylon Injection and Extrusion Materials (PA)
- D4549 Classification System and Basis for Specification for Polystyrene and Rubber-Modified Polystyrene Molding and Extrusion Materials (PS)
- D4703 Practice for Compression Molding Thermoplastic Materials into Test Specimens, Plaques, or Sheets
- D4976 Specification for Polyethylene Plastics Molding and Extrusion Materials
- D5947 Test Methods for Physical Dimensions of Solid Plastics Specimens
- D6778 Classification System and Basis for Specification for Polyoxymethylene Molding and Extrusion Materials (POM)
- D6779 Classification System for and Basis of Specification for Polyamide Molding and Extrusion Materials (PA)
- E456 Terminology Relating to Quality and Statistics
- E691 Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method
- E2935 Practice for Conducting Equivalence Tests for Comparing Testing Processes

2.2 ISO Standards:³

- ISO 293 Plastics—Compression Moulding Test Specimens of Thermoplastic Materials
- ISO 294-1 Plastics—Injection Moulding of Test Specimens of Thermoplastic Materials—Part 1: General Principles, and Moulding of Multipurpose and Bar Test specimens
- ISO 294-3 Plastics—Injection Moulding of Test Specimens of Thermoplastic Materials—Part 3: Small Plates
- ISO 294-4 Plastics—Injection Moulding of Test Specimens—Part 4: Determination of Moulding Shrinkage

3. Terminology

3.1 *Definitions*—General definitions of terms applying to this test method appear in Terms used in this standard are defined in accordance with Terminology D883, unless otherwise specified. For terms relating to precision and bias and associated issues, the terms used in this standard are defined in accordance with Terminology E456.

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *jetting, n*—non-uniform multi-directional flow front apparent on the surface of the mold due to rapid filling of the mold cavity.

4. Summary of Test Method

4.1 The principle of this test method is to compare mold cavity dimensions with specimen dimensions and report the differences in percent.

5. Significance and Use

5.1 *Injection Molding*—In injection molding, the difference between the dimensions of a mold cavity and of the molded specimen may vary according to the design of the mold and operation of the molding process. Factors such as mold and melt temperature, fill times, and packing conditions are known to affect shrinkage significantly. Adherence to the specified mold design (see 7.1) and specifications outlined in Practice D3641 or ISO 294-4 or the appropriate material specification will improve the reproducibility of the test.

5.2 *Compression Molding*—In compression molding, the difference between the dimensions of a mold cavity and of the molded specimen may vary according to the design of the mold and operation of the molding process. Factors, such as the amount of material in charge, cooling time, and pressure application are known to affect shrinkage significantly. Adherence to the specified mold design (see 7.2) and specifications outlined in Practice D4703 or ISO 293 or the appropriate material specifications will improve the reproducibility of the test.

6. Sample Preparation

6.1 Some materials require special treatment before they are molded. For example, thermoplastics, which absorb moisture must be dried before molding. For required conditions for sample preparation, refer to the appropriate material specification or the manufacturer's recommendations if no specification is available. The preparation given to the material prior to molding shall be recorded and reported.

³ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

7. Apparatus

7.1 *Injection Mold*—Specimens shall be molded in a two cavity mold conforming with dimensions as shown in Figs. 1 and 2 for the 60 × 60-mm plaque specimen (Type D2), Fig. 3 for the 12.7 by 127-mm bar specimen (Type A) and Fig. 4 for the 100 mm by 3.2-mm disk specimen (Type B). Pressure transducers for monitoring the pressure in at least one cavity are mandatory for Type D2. Mold shrinkage measurements shall be made on specimens that have been molded at one of the following cavity pressures ± 3 % from the selected pressure: 20 MPa, 40 MPa, 60 MPa, 80 MPa, 100 MPa, or as specified in the appropriate material specification. Pressure transducers are recommended, but not mandatory for specimens Type A and Type B.

7.2 *Compression Mold*—A single cavity positive mold having cavity dimensions conforming to the dimensions of Fig. 2 for the 60 × 60-mm plaque (Type D2) Fig. 3 for the 12.7 × 127-mm bar specimen (Type A) and Fig. 4 for the 100-mm × 3.2-mm disk specimen (Type B), not including the sprue, runner or gate.


NOTE 2—Although scribe marks are not required, if they are used for injection or compression molded specimens for the measurement of shrinkage, the scribe marks shall be 1.0 mm long by 0.1 mm wide located 4.0 mm from each edge on one side of the mold.

7.2.1 Although scribe marks are not required, if they are used for injection or compression molded specimens for the measurement of shrinkage, the scribe marks shall be 1.0 mm long by 0.1 mm wide located 4.0 mm from each edge on one side of the mold.

7.3 *Injection Press*—A suitable injection molding machine that shall fill the test molds when it is operated in the range from 20 to 80 % of its rated shot capacity at the molding parameters specified in Practice D3641, ISO 294-3 or the appropriate material specification.


NOTE 2—If the injection machines of appropriate capacity are not available, the requirements of 7.3 may be met in machines of larger capacities by providing test molds with multiple cavities (maximum of four) to be filled from a common sprue and having a balanced filling pattern, so that the total weight of the shot, including sprue and runner will fall within the specified limits.

7.4 *Compression Press*—A suitable hydraulic press that shall deliver a pressure of 20 to 35 MPa (3000 to 5000 psi) to the material in the mold.



Sp sprue
G gate
L _c = distance between the lines along which the test specimens are cut from the runners
Molding volume = 20 000 mm ³
Projected area = 11 000 mm ²

FIG. 1 Type D2 (Mold Layout)



Sp	sprue	
G	gate	
R	runner	
P	pressure sensor	
l	length of plate	60 ± 2 mm
b	width of plate	60 ± 2 mm
h	thickness of plate	2.0 ± 0.1 mm
l _G	length of gate	4.0 ± 0.1 mm
h _G	height of gate	(0.75 ± 0.05) × h
l _R	length of runner	25 to 40 mm
b _R	width of runner	≥ (b + 6) mm
h _g	depth of runner at gate	
l*	unspecified distance	...
l _p	distance of pressure sensor from gate	5 ± 2 mm

FIG. 2 Type D2 (Cavity Details)




FIG. 3 Bar Specimen

7.5 *Measuring Tools*—Measuring tools (micrometers, vernier calipers, etc.) accurate to 0.025 mm (0.001 in.) for measuring the molds and test specimens conforming to the measuring tool requirements in Test Methods D5947.




FIG. 4 Disk Specimen

iteh Standards
 (https://standards.iteh.ai)
 Document Preview

8. Test Specimen

8.1 The following specimen dimensions are applicable for both compression and injection molding. Orientation effects due to flow direction do not generally pertain to compression molding.

8.1.1 *Specimen Type D2*—For mold shrinkage in both flow and cross flow the preferred specimen shall be 60 by 60 by 2 mm depth conforming to the dimensions of Fig. 2.

8.1.2 *Specimen Type A*—For shrinkage parallel to flow, a bar mold having a cavity of 12.7 by 127 mm shall be used as shown in Fig. 3. The thickness shall be 3.2 mm unless otherwise agreed upon by the seller and the purchaser. The mold shall have at one end a gate 6.4 mm in width by 3.2 mm in depth.

8.1.3 *Specimen Type B*—A disc shaped specimen, as shown in Fig. 4, having a cavity 100 mm in diameter by 3.2 mm in thickness with a gate 12.7 mm in width by 3.2 mm in depth, placed radially at the edge, shall be used.

NOTE 3—Although this specimen may be used to determine mold shrinkage in both the flow and cross flow directions, the filling pattern does not produce uniform flow lengths and orientation. Consequently, there may be significant differences when measuring the specimen at different points around the circumference. Values would not be expected to be in agreement with those obtained using the specimens described in 8.1.1 and 8.1.2.

9. Conditioning

9.1 *Conditioning*—Conditioning of molded specimens shall be done in the Standard Laboratory Atmosphere, Unless otherwise specified by relevant material standard, condition molded specimens at $23 \pm 2^\circ\text{C}$ and $50\% \pm 10\text{ RH}$, if not otherwise specified in the appropriate materials 10% relative humidity in accordance with Practice D618 standard.

9.2 *Test Conditions*—Conduct measurement in the standard laboratory atmosphere of Unless otherwise specified by relevant material standard, conduct measurement at $23 \pm 2^\circ\text{C}$ and $50\% \pm 10\text{ RH}$, if not otherwise specified in the appropriate materials 10% relative humidity in accordance with Practice D618 standard.

10. Procedure

10.1 Measure the length and width of the mold cavity at the center of each edge or at the molded scribe marks, to the nearest 0.025 mm at $23 \pm 2^\circ\text{C}$ and $50\% \pm 10\text{RH}$. 10 % relative humidity. Record these values as l and w , respectively.

10.2 Mold at least five flat test specimens from the sample to be tested.

NOTE 4—Flat is represented by a specimen with less than 3 % warp. Three percent warp is defined as 3 mm depth deflection, positive or negative, per 100 mm in length.

10.2.1 *Thermoplastics Molded by Injection*—Molding of thermoplastic materials shall be conducted in accordance with the appropriate material standard, Practice **D3641** or **ISO 294-3**. The temperature of the heating cylinder and the mold shall be maintained at a point which, on a cycle selected, will produce temperature within the range recommended by the material molding standard. Begin with a short shot to ensure the flow front is straight and not radial and that the flow is laminar and does not exhibit melt fracture (jetting). Collect samples after the machine is at equilibrium.

10.2.2 *Thermoplastics Molded by Compression*—For thermoplastics, molding shall be conducted in accordance with the appropriate material standard or **D4703**.

10.3 *Treatment of Specimens after Removal from the Mold:*

10.3.1 In order to minimize warpage, separate the test specimens from the runners in the gate area immediately after removal from the mold. Do not modify or alter the edges used for the measurement of dimensions. It is recommended to cool specimens in a horizontal position at room temperature by placing them on a material of low thermal conductivity to minimize warpage. After the first hour, condition the specimens at $23 \pm 2^\circ\text{C}$ and $50\% \pm 5\text{RH}$, unless otherwise specified in the material standard.

10.3.2 *Specification of Measurement Time:*

10.3.2.1 Twenty four hour shrinkage measurements shall be made $24 \pm 0.5\text{ h}$ after the specimen has been removed from the mold.

10.3.2.2 Forty eight hour shrinkage measurements shall be made $48 \pm 0.5\text{ h}$ after the specimen has been removed from the mold.

11. Calculation and Report

11.1

$$S_w = (W_m - W_s) \times 100/W_m \quad (1)$$

where:

S_w = the shrinkage perpendicular to flow, %,
 W_m = the mold dimension perpendicular to flow,
 W_s = the specimen dimension perpendicular to flow, and

$$S_l = (L_m - L_s) \times 100/L_m \quad (2)$$

where:

S_l = the shrinkage parallel to flow, %,
 L_m = the mold dimension parallel to flow, and,
 L_s = the specimen dimension parallel to flow.

Report mold shrinkage in both flow and cross direction to two significant figures.

11.2 The report shall include the following:

11.2.1 Details of any special material preparation, such as drying, which the material received before molding;

11.2.2 The molding procedure used, following the report as outlined in Practice **D3641** for injection molding and Practice **D4703** for compression molding.

11.2.3 The 24-hour shrinkage and the 48-hour shrinkage shall be expressed in percent (mm/mm) with each value representing the mean of determinations obtained on five or more specimens.

12. Precision and Bias

12.1 Precision:

12.1.1 **Tables 1-3** summarize data from a round robin⁴ conducted in 1988, using specimens Type A and Type B, involving five thermoplastics materials tested by eight laboratories. Each material was supplied in granular form to each of the testing laboratories by a single supplier. The resins were handled in accordance with the supplier's instructions and were molded in accordance with Practice **D3641**. Each test result is the average of five individual determinations from successive injection molding cycles. Each laboratory obtained one test result for each material.⁸

~~NOTE 6—A repeatability study was conducted in Europe using specimen Type D2. The results, including suggested cavity hold pressure for various materials, are shown in Appendix X1.~~

12.1.2 Warning—The data in **Tables 1-3** shall not be rigorously applied to acceptance or rejection of a material, as those data are specific to the interlaboratory study and are not necessarily representative of other lots, conditions, materials, or laboratories. Users of this test method shall apply the principles outlined in Practice **E691** to generate data specific to their laboratory and materials or between specific laboratories.

~~NOTE 5—A repeatability study was conducted in Europe using specimen Type D2. The results, including suggested cavity hold pressure for various materials, are shown in **Appendix X1**.~~

12.1.3 Repeatability estimates S_r and r were made by treating the five individual determinations from successive injection molding cycles as test results. Poorer precision (larger values of S_r and r) would be expected if the same operator were to shutdown and then restart the injection molding machine on the same day with the same mold, material and operating set points. Repeatability under such circumstances was not evaluated.

~~12.1.4 Repeatability Limit (r)—The following explanations of value below which r and R only are intended to present a meaningful way of considering the approximate precision of this test method. The data in the absolute difference between two individual test results obtained under repeatability **Tables 1-3** should not be rigorously applied to acceptance or rejection of material, as those data are specific to the round robin and may not be representative of other lots, conditions, materials, or laboratories. Users of this test method should apply the principles outlined in Practice **E691** to generate data specific to their laboratory and materials, or between specific laboratories. The principles of 11.1.3 through 11.3.3 then would be valid for such data occur with a probability of approximately 0.95 (95 %).~~

12.1.5 **Reproducibility Limit (R)—The value below which the absolute difference between two individual test results obtained under reproducibility conditions may be expected to occur with a probability of approximately 0.95 (95 %).**

TABLE 1 Shrinkage from Mold Dimensions of I.M. Bars^A

Material ^B	Average	S_r	S_R	r	R
1	0.00513	0.00008	0.00124	0.00022	0.00347
2	0.04108	0.00022	0.00754	0.00062	0.02111
3	0.00474	0.00021	0.00127	0.00059	0.00356
4	0.02107	0.00013	0.00280	0.00036	0.00784
5	0.01731	0.00017	0.00389	0.00048	0.01089

^A Values expressed in mm/mm (in./in.).

^B 1 = Polystyrene	Specification D4549	PS110B56152
2 = Polyethylene	Specification D4976	PE235
3 = PMMA	Specification D788	PMMA0131V0
4 = Acetal	Specification D6778	POM0213
5 = Nylon (Polyamide)	Specification D6779	PA0111

⁴ Supporting data are available from ASTM Headquarters. Request RR: D-20-1158 have been filed at ASTM International Headquarters and may be obtained by requesting Research Report RR:D20-1158. Contact ASTM Customer Service at service@astm.org.