



SLOVENSKI STANDARD
SIST EN 14844:2006

01-december-2006

Montažni betonski izdelki - Škatlasti nosilci

Precast concrete products - Box culverts

Betonfertigeteile - Hohlkastenelemente

Produits préfabriqués en béton - Cadres enterrés

Ta slovenski standard je istoveten z: EN 14844:2006

<https://standards.iteh.ai/catalog/standards/sist/613e54d2-01af-4ac4-b5b0-05143ccd7c51/sist-en-14844-2006>

ICS:

91.100.30 Beton in betonski izdelki Concrete and concrete products

SIST EN 14844:2006

en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 14844:2006

<https://standards.iteh.ai/catalog/standards/sist/613e54d2-01af-4ac4-b5b0-05143ccd7c51/sist-en-14844-2006>

ICS 91.100.30

English Version

Precast concrete products - Box culverts

Produits préfabriqués en béton - Cadres enterrés

Betonfertigteile - Hohlkastenelemente

This European Standard was approved by CEN on 17 April 2006.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

(standards.iteh.ai)

SIST EN 14844:2006

<https://standards.iteh.ai/catalog/standards/sist/613e54d2-01af-4ac4-b5b0-05143ccd7c51/sist-en-14844-2006>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

Page

Foreword.....	4
Introduction	6
1 Scope	7
2 Normative references	7
3 Terms and definitions, symbols and abbreviated terms	7
3.1 Terms and definitions	7
3.2 Symbols and abbreviations	7
4 Requirements	8
4.1 Material requirements	8
4.1.1 General.....	8
4.2 Production requirements	8
4.2.1 Concrete production	8
4.2.2 Hardened concrete	9
4.3 Finished product requirements.....	9
4.3.1 Geometrical properties	9
4.3.2 Surface characteristics	11
4.3.3 Mechanical resistance.....	11
4.3.7 Durability	12
4.3.8 Other requirements.....	12
5 Test methods.....	12
5.1 Tests on concrete	12
5.2 Measuring of dimensions and surface characteristics	12
5.3 Weight of the products.....	13
6 Evaluation of conformity.....	13
6.2.2 Initial Type Testing	13
7 Marking	14
8 Technical documentation	14
Annex A (informative) Additional information for the design of box culverts	15
A.1 Characteristic horizontal load	15
A.2 Reinforcement of inner wall faces	15
A.3 Stability	15
A.4 Horizontal surface loads	15
A.5 Deflection of roof slab	15
A.6 Differential settlement	16
Annex B (normative) Verification by calculation aided by physical testing.....	17
B.1 Introduction	17
B.2 Limit of use of this test	17
B.3 Test arrangements.....	17
B.4 Test criteria.....	18
B.5 Definition of the dimensional parameters	18
B.6 Definition of the main sections	19
B.7 Determination of the test parameters (w_p , w_a , F)	19
B.8 Test method	21
B.9 Interpretation of the test results.....	21
Annex C (informative) Installation	22

ITeC STANDARD PREVIEW
(standards.itec.ai)

SIST EN 14844:2006

https://standards.itec.ai/catalog/standards/sist/613e54d2-01af-4ac4-b560-

03145cc07c91/sist-en-14844-2006

C.1	Products/Units	22
C.2	Preparing the site	22
C.3	Bedding	22
C.4	Laying	22
C.5	Backfilling.....	23
Annex Y (informative)	Choice of CE marking method.....	24
Y.1	General	24
Y.2	Method 1	24
Y.3	Method 2	24
Y.4	Method 3	24
Annex ZA (informative)	Clauses of this European Standard addressing the provisions of the EU Construction Products Directive	25
ZA.1	Scope and relevant characteristics	25
ZA.2	Procedure(s) for the attestation of conformity of box culvert units	26
ZA.2.1	Systems of attestation of conformity	26
ZA.2.2	EC Certificate and Declaration of conformity	28
ZA.3	CE marking and labelling.....	29
ZA.3.1	General	29
ZA.3.2	Declaration of geometrical data and material properties.....	30
ZA.3.3	Declaration of product properties	33
ZA.3.4	Declaration of compliance with a given design specification	36
Bibliography	38

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN 14844:2006

<https://standards.iteh.ai/catalog/standards/sist/613e54d2-01af-4ac4-b5b0-05143ccd7c51/sist-en-14844-2006>

Foreword

This European Standard (EN 14844:2006) has been prepared by Technical Committee CEN/TC 229 "Precast concrete products", the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by January 2007, and conflicting national standards shall be withdrawn at the latest by April 2009.

This European Standard has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of EU Directive(s).

This European Standard was examined by and agreed with a joint working party appointed by the Liaison Group CEN/TC 229 – TC 250, particularly for its compatibility with structural Eurocodes.

This standard is one of a series of product standards for precast concrete products.

For common aspects reference is made to EN 13369, *Common rules for precast concrete products*, from which also the relevant requirements of the EN 206-1, *Concrete – Part 1: Specification, performance, production and conformity* are taken.

The references to EN 13369:2004 by CEN/TC 229 product standards are intended to make them homogeneous and to avoid repetitions of similar requirements.

Eurocodes are taken as a common reference for design aspects. The installation of some structural precast concrete products is dealt with by ENV 13670-1: *Execution of concrete structures – Part 1: Common rules*, which has at the moment the status of a European Prestandard. In all countries it can be accompanied by alternatives for national application and it should not be treated as a European Standard.

The programme of standards for structural precast concrete products comprises the following standards, in some cases consisting of several parts:

- EN 1168, *Precast concrete products – Hollow core slabs*
- EN 12794, *Precast concrete products – Foundation piles*
- EN 12843, *Precast concrete products – Masts and poles*
- EN 13225, *Precast concrete products – Linear structural elements*
- EN 13693, *Precast concrete products – Special roof elements*
- EN 13747, *Precast concrete products – Floor plates for floor systems*
- EN 13978, *Precast concrete products – Precast concrete garages*
- EN 13224, *Precast concrete products – Ribbed floor elements*
- prEN 14843, *Precast concrete products – Stairs*
- EN 14844, *Precast concrete products – Box culverts*
- prEN 14991, *Precast concrete products – Foundation elements*

- prEN 14992, *Precast concrete products - Wall elements : Products properties and performances*
- prEN 15037-1, *Precast concrete products - Beam-and-block floor systems - Part 1: Beams*
- prEN 15037-2, *Precast concrete products - Beam-and-block floor systems - Part 2: Concrete blocks*
- prEN 15037-3, *Precast concrete products - Beam and block floor system - Part 3: Clay blocks*
- prEN 15037-4, *Precast concrete products - Beam and blocks floor system - Part 4: Polystyrene blocks*
- prEN 15037-5, *Precast concrete products - Beam and blocks floor system - Part 5: Lightweight blocks*
- prEN 15050, *Precast concrete bridge elements*
- prEN 15258, *Precast concrete products – Retaining wall elements*

This standard defines in Annex ZA the application methods of CE marking to products designed using the relevant EN Eurocodes (EN 1992). Where, in default of applicability conditions of EN Eurocodes to the works of destination, design provisions other than EN Eurocodes are used for mechanical strength, the conditions to affix CE marking to the product are described in ZA.3.4.

For relationship with EU Directive(s), see informative Annex ZA, which is an integral part of this European Standard.

According to the CEN/GENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

[SIST EN 14844:2006](https://standards.iteh.ai/catalog/standards/sist/613e54d2-01af-4ac4-b5b0-05143ccd7c51/sist-en-14844-2006)

<https://standards.iteh.ai/catalog/standards/sist/613e54d2-01af-4ac4-b5b0-05143ccd7c51/sist-en-14844-2006>

Introduction

The Construction Products Directive sets out Essential Requirements to be considered, depending upon the use made of the product. For box culverts it was mandated that the requirements for mechanical resistance and stability should be considered. For these requirements this standard will mainly refer to clauses of EN 1992-1-1, *Eurocode 2, Design of concrete structures, Part 1-1 : General rules and rules for buildings*.

The mandate also requires consideration of durability, from the point of view of freeze thaw action and corrosion, which is also addressed by the Eurocodes referred to above.

The numbering of clauses is strictly related to EN 13369:2004: *Common rules for precast concrete products*, at least for the first three digits. When a clause of EN 13369:2004 is not relevant or included in a more general reference of this standard, its number is omitted and this may result in a gap on numbering.

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN 14844:2006

<https://standards.iteh.ai/catalog/standards/sist/613e54d2-01af-4ac4-b5b0-05143ccd7c51/sist-en-14844-2006>

1 Scope

This standard deals with both large (structural) and small (non-structural or light structural) box culverts of rectangular cross-section formed monolithically and designed as continuous elements with a joint detail shaped to allow the possible incorporation of sealing materials. Box culverts can be used for creation of voids below ground for conveyance and storage of materials. e.g. conveyance and storage of wastewater, cable tunnels and subways

For the purposes of this standard, box culverts having internal cross-sectional dimensions (W and H in Figure 1) less than or equal to 1 250 mm should be considered as small (non-structural or light structural). All other units should be defined as large. The elements are generally manufactured in factories using either normal weight or lightweight concrete and usually require reinforcing steel. This standard does not include units manufactured from autoclaved aerated concrete, nor prefabricated reinforced box culverts of lightweight concrete with open structure.

Each unit is structurally complete. They are used in combination to form a total structure of appropriate length (including joints) and capacity.

2 Normative references

The following referenced documents are indispensable for the application of this European Standard. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 1992-2, *Eurocode 2: Design of concrete structures - Concrete bridges - Design and detailing rules*

EN 13369:2004, *Common rules for precast concrete products*

[SIST EN 14844:2006](https://standards.iteh.ai/catalog/standards/sist/613e54d2-01af-4ac4-b5b0-05143ca17c51/sist-en-14844-2006)

[https://standards.iteh.ai/catalog/standards/sist/613e54d2-01af-4ac4-b5b0-](https://standards.iteh.ai/catalog/standards/sist/613e54d2-01af-4ac4-b5b0-05143ca17c51/sist-en-14844-2006)

[05143ca17c51/sist-en-14844-2006](https://standards.iteh.ai/catalog/standards/sist/613e54d2-01af-4ac4-b5b0-05143ca17c51/sist-en-14844-2006)

3 Terms and definitions, symbols and abbreviated terms

3.1 Terms and definitions

For the purposes of this European Standard, the terms and definitions given in EN 13369:2004 and the following apply.

3.1.1

corner splay

internal chamfering of the corners

3.2 Symbols and abbreviations

Principal and other dimensions and their symbols are given in Figure 1.

The symbols comply with EN 1992-1-1 as far as possible and are listed:

W internal width

H internal height

L unit length (measured from end of spigot to base of socket for rebated joint— see Figure 1a)

t_r roof/floor slab thickness



t_w wall thickness

e, f - geometry of the splay, see Figure 1b below

Effective roof span (W_e) = $W + t_w$

Effective wall span (H_e) = $H + t_r$

Spigot and Socket inner and outer overlapping nibs of a rebated joint profile (see Figure 2a)



SIST EN 14844:2006
<https://standards.itih.ai/catalog/standards/sist/613e54d2-01af-4ac4-b5b0-05143ccd7c51/sist-en-14844-2006>

Figure 1a — Unit Length

Figure 1b — Explanation of symbols

Figure 1 — Principal dimensions and symbols

See Figure 2 for alternative joint configurations.

4 Requirements

4.1 Material requirements

4.1.1 General

Subclause 4.1 of EN 13369:2004 shall apply.

4.2 Production requirements

4.2.1 Concrete production

Subclause 4.2.1 of EN 13369:2004 shall apply.

4.2.2 Hardened concrete

4.2.2.1 Strength classes

Subclause 4.2.2.1 of EN 13369:2004 shall apply. The minimum concrete strength class shall be C30/37.

4.2.2.2 Compressive strength

The compressive strength of hardened concrete shall be declared by the manufacturer. Subclause 4.2.2.2 of EN 13369:2004 shall apply.

The design values of strength properties should be based on partial safety factors for material properties, according to Annex C of EN 13369:2004.

4.2.2.3 Drying shrinkage of lightweight aggregate concrete

For lightweight concrete, the drying shrinkage shall be declared by the manufacturer.

4.2.2.4 Density of lightweight aggregate concrete

The manufacturer shall declare the density of lightweight concrete and it shall be in accordance with EN 206-1:2000, 4.3.2.

4.2.3 Structural reinforcement

4.2.3.1 Processing of reinforcing steel

Subclauses 4.2.3 and 4.2.3.1 of EN 13369:2004 shall apply.

4.3 Finished product requirements

4.3.1 Geometrical properties

4.3.1.1 Production tolerances

Units shall have an appropriate joint detail capable of providing sealing and location integrity. Typical arrangements are shown in Figure 2 below.

Types of joints (see Figure 2):

- rebated joint (A);
- nib joint (B);
- butt joint (C).

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 14844:2006](https://standards.iteh.ai/catalog/standards/sist/613e54d2-01af-4ac4-b5b0-05143ccd7c51/sist-en-14844-2006)

<https://standards.iteh.ai/catalog/standards/sist/613e54d2-01af-4ac4-b5b0-05143ccd7c51/sist-en-14844-2006>




Figure 2 — Examples of box culvert joints

For the types of rebated joint illustrated, the spigot and socket shall have a thickness of not less than 45 mm at the root ($a + b$) and a nib length (d) of not less than 45 mm. The length of the nib should normally be in the range from 1.3 to 2 times the nib root dimension. Early casts from each mould shall be checked to ensure that joints mate satisfactorily.

The maximum permissible tolerance from the manufacturer's declared dimensions, measured in accordance with 5.2, shall be as follows:

- thickness of roof/floor slab and wall : ± 10 mm;
- internal width and height of the opening : ± 1 % (max 15 mm);
- length of units : ± 1 %; <https://standards.iteh.ai/catalog/standards/sist/613e54d2-01af-4ac4-b5b0-05143ccd7c51/sist-en-14844-2006>
- joints: (see Figure 2) ; a, b, c, d, e, f, g : ± 6 mm.

4.3.1.2 Minimum dimensions

The nominal thickness for roof, floor and wall shall be not less than 100 mm.

NOTE The length of unit is determined by the maximum weight and overall dimensions which can conveniently be lifted, transported and placed into the works but is not likely to be less than 1 000 mm except where handling or special considerations apply.

4.3.1.3 Nominal size

Box culverts shall be described by their principal dimensions according to 3.2, expressed in sequence:

- WxHxL

The manufacturer shall declare the box culvert nominal dimensions.

The opening may be provided with corner splays, which shall not reduce the rectangular area by more than 10 %.

4.3.1.4 Shape tolerance

Squareness: the difference between the diagonal dimensions of any face or end shall not exceed the following values :

- for any internal dimensions up to 2 000 mm: 10 mm;
- for any internal dimensions greater than 2 000 mm up to 4 000 mm: 15 mm;
- for any internal dimensions greater than 4 000 mm: 20 mm.

NOTE Tolerances might influence the watertightness characteristic of the joints.

4.3.1.5 Cumulative effect

Deviations can be cumulative and the overall effect may need to be considered.

For initial production from a new mould, where required with regard to fit, overlap and stepping shall be determined by placing at least three units onto a common level support, with the units just touching each other. Measured inside the units, the joint width between successive units shall not vary by more than 10 mm and the maximum step between adjacent units should not be more than 15 mm.

4.3.2 Surface characteristics

4.3.2.1 General

Subclause 4.3.2 of EN 13369:2004 shall apply.

Flatness : the deviation from a 1 500 mm straight edge placed in any position on an internal surface shall not exceed 10 mm.

<https://standards.iteh.ai/catalog/standards/sist/613e54d2-01af-4ac4-b5b0-05143ccd7c51/sist-en-14844-2006>

4.3.2.2 Cracking

Crazing within the cement rich layer, shrinkage or temperature hairline cracks with a surface width not exceeding 0,15 mm and residual cracks caused by testing, having the same limiting surface width are permissible.

4.3.3 Mechanical resistance

4.3.3.1 General

Subclause 4.3.3.1 of EN 13369:2004 shall apply.

4.3.3.2 Verification by calculation

Subclause 4.3.3.2 of EN 13369:2004 shall apply, see also EN 1992-2. For the design of box culverts, additional specific information is given in Annex A.

Different calculation methods may be applied provided they are confirmed by testing (see 4.3.3.3 below).

4.3.3.3 Verification by calculation aided by physical testing

In the case of testing 4.3.3.3 of EN 13369 shall apply and the appropriate design parameters shall be simulated in the test arrangement. The testing rig shall have the capability to apply load in varying positions and intensities to simulate the critical bending, shear and cracking conditions.