



Designation: ~~E1800 – 13~~ E1800 – 21

Standard Specification for Adhesive for Bonding Foam Cored Sandwich Panels (~~160°F~~ 160 °F Elevated Humidity Service), Type I Panels¹

This standard is issued under the fixed designation E1800; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope

1.1 This specification covers two-part paste adhesives for bonding foam core sandwich panels. The adhesive may be used for new production or depot maintenance. The adhesive should be suitable for forming bonds that can withstand long term exposure to temperatures ~~from –55~~ from –55 °C to 71°C (–67°F to 160 °F) and also withstand combinations of stress, temperature, and humidity expected to be encountered in service. The adhesives shall be used for bonding aluminum alloy facing to foam core, inserts, internal aluminum framing members, and other components of a foam cored sandwich panel.

1.2 The values stated in SI units are to be regarded as the standard where only SI units are given or where SI units are given first followed by inch-pound units; where inch-pound units are given first followed by SI units, the inch-pound units are to be regarded as the standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate ~~safety~~ safety, health, and health environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:²

- ~~B209~~ B209/B209M Specification for Aluminum and Aluminum-Alloy Sheet and Plate (Metric) ~~B0209–B0209M~~
- D1002 Test Method for Apparent Shear Strength of Single-Lap-Joint Adhesively Bonded Metal Specimens by Tension Loading (Metal-to-Metal)
- E631 Terminology of Building Constructions
- E864 Practice for Surface Preparation of Aluminum Alloys to Be Adhesively Bonded in Honeycomb Shelter Panels
- E1749 Terminology Relating to Rigid Wall Relocatable Shelters

2.2 Military Standard:³

- MIL-STD-202F Test Methods for Electronic and Electrical Component Parts

¹ This specification is under the jurisdiction of ASTM Committee E06 on Performance of Buildings and is the direct responsibility of Subcommittee E06.53 on Materials and Processes for Durable Rigidwall Relocatable Structures.

Current edition approved Oct. 1, 2013 June 15, 2021. Published February 2014 July 2021. Originally approved in 1996. Last previous edition approved in 2008 2013 as E1800 – 08-E1800 – 13. DOI: 10.1520/E1800-13.10.1520/E1800-21.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from DLA Document Services, Building 4D-4-D, 700 Robbins Avenue, Philadelphia, PA 19111-5094, 19111, http://quicksearch.dla.mil/.

2.3 *Federal Specification:*³

QQ-A-250/11d Aluminum Alloy 6061 T6 Plate and Sheet

3. Terminology

3.1 ~~Definitions~~Definitions:—See

3.1.1 For definitions of general terms related to building construction used in this specification, refer to Terminology [E631](#), and for general terms related to rigid wall relocatable shelters, refer to Terminology [E1749](#). ~~Terminologies [E631](#) and [E1749](#) for definitions of terms used in this specification.~~

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *adhesive life*—the maximum time that an adhesive, when mixed in a prescribed quantity, can set at a designated temperature, after which the adhesive, when used to prepare specimens, will deliver the required properties.

4. Requirements

4.1 *Material*—The adhesive shall be a two-part thermosetting epoxy paste containing no asbestos and, when tested using the test methods described in Section 6, shall meet the requirements of Section 4. The adhesive shall not have a detrimental effect on the components being bonded over the range of temperatures at which the adhesive will be used.

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[ASTM E1800-21](#)

<https://standards.iteh.ai/catalog/standards/sist/c4a153eb-50ba-4306-a686-f1c98b48dac/astm-e1800-21>

4.2 Working Characteristics:

4.2.1 *Application*—The adhesive shall be suitable for application to facings and foam core materials. The adhesive shall be suitable for spray application to faying surfaces.

4.2.2 *Curing*—The time, temperature, and pressure used to cure the adhesive shall be within the range specified herein.

4.2.2.1 *Curing Time and Temperature*—The adhesive, when mixed in accordance with the manufacturer’s instruction, shall meet the requirements of this specification when cured at a temperature of not less than ~~52°C (125°F)~~ 52 °C (125 °F) for 4 h, or ~~63°C (145°F)~~ 63 °C (145 °F) for 60 min. The timing of the cure shall start when the panel skins have reached the specified temperature. The temperature for the cure shall be fully attained within 2 h after the first application of the adhesive to the faying surface.

4.2.2.2 *Curing Pressure*—Specimens for testing under this specification shall be cured under a normal load of ~~0.050 MPa ± 0.007 MPa (8.0 psi ± 0.5 psi)~~ 0.050 MPa ± 0.007 MPa (8.0 psi ± 0.5 psi). No more than 75 min at ~~25°C (77°F)~~ 25 °C (77 °F) shall elapse between the application of the adhesive to the faying surface and the application of the pressure.

4.2.3 *Mix Ratio*—The mix ratio for the two parts of the adhesive shall be as defined by the manufacturer.

4.3 *Storage Life*—The storage life shall not exceed one year from the date of manufacture, when the components of the adhesive shall be stored at a temperature between ~~10°C (50°F) and 42°C (90°F)~~ 10 °C (50 °F) and 42 °C (90 °F). The storage life of the two parts of the adhesive, from the date of shipment, when stored in airtight containers at ~~23.3°C ± 3°C (73.4°F ± 5.4°F)~~ 23.3 °C ± 3 °C (73.4 °F ± 5.4 °F), shall be at least 12 months. The adhesive shall be considered to have met this storage life requirement if all the characteristics described in 4.1 and 4.5 are met by the adhesive after the 12-month storage period described above.

4.4 *Adhesive Life*—The adhesive life of one quart of the mixed adhesive at ~~25°C (77°F)~~ 25 °C (77 °F) shall not be less than 160 min, at which time the adhesive shall meet the requirements of 4.5.

4.5 *Mechanical Properties*—The minimum mechanical properties of the adhesives, when cured as specified, shall meet the requirements of **Table 1**.

5. Significance and Use

5.1 This specification is intended to provide information on the properties of adhesives, and the test methods required to evaluate adhesives to be used in the production bonding of aluminum alloys to foam core materials for the manufacture of tactical shelters.

6. Test Methods

6.1 *Qualification Tests*—For qualification, the adhesive shall be tested using the tests described in this section. Shear tests shall be performed in accordance with Test Method **D1002** except that the length of the test coupon shall be 103.7 mm (4¼ in.) and the thickness shall be 2.196 mm (0.090 in.).

6.2 *Preparation of Test Specimens*—Prepare at least ten specimens for each separate test. The metal to be bonded shall be 6061 T6 (Federal Specification QQ-A-250/11d or Specification **B209B209/B209M**) cleaned as specified in Practice **E864**. Time, temperature, and pressure for curing the adhesive shall be as specified in 4.2.2.1 and 4.2.2.2.

6.3 *Room Temperature Shear*—Subject specimens to a tensile shear test at a room temperature of ~~27.27°C ± 6°C (80.6°C (80 °F ± 10°F))~~ 27.27 °C ± 6 °C (80.6 °C (80 °F ± 10 °F)).

TABLE 1 Physical Property Requirements

Test	Requirement
Room temperature, shear	1500 psi, min, 10.4 MPa
Low temperature, shear	1500 psi, min, 10.4 MPa
High temperature, shear	400 psi, min, 2.8 MPa
Humidity exposure, shear, hot	500 psi, min, 3.4 MPa
Salt spray exposure, shear, RT	1500 psi, min, 10.4 MPa