



Designation: D1836 – 07 (Reapproved 2021)

Standard Specification for Commercial Hexanes¹

This standard is issued under the fixed designation D1836; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers the range of products commonly referred to as hexanes, which find uses in the preparation of adhesives, coatings, and printing inks, as raw materials in chemical synthesis operations, and as solvents in various kinds of extraction operations.

1.2 The following applies to all specified limits in this standard; for purposes of determining conformance with this standard, an observed value or a calculated value shall be rounded off “to the nearest unit” in the last right-hand digit used in expressing the specification limit, in accordance with the rounding-off method of Practice E29.

1.3 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.5 For specific hazard information and guidance consult supplier’s Material Safety Data Sheet.

1.6 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:²

D156 Test Method for Saybolt Color of Petroleum Products (Saybolt Chromometer Method)

¹ This specification is under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.35 on Solvents, Plasticizers, and Chemical Intermediates.

Current edition approved July 1, 2021. Published August 2021. Originally approved in 1961. Last previous edition approved in 2013 as D1836 – 07 (2013). DOI: 10.1520/D1836-07R21.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.

- D268 Guide for Sampling and Testing Volatile Solvents and Chemical Intermediates for Use in Paint and Related Coatings and Material (Withdrawn 2021)³
- D611 Test Methods for Aniline Point and Mixed Aniline Point of Petroleum Products and Hydrocarbon Solvents
- D1078 Test Method for Distillation Range of Volatile Organic Liquids
- D1133 Test Method for Kauri-Butanol Value of Hydrocarbon Solvents
- D1209 Test Method for Color of Clear Liquids (Platinum-Cobalt Scale)
- D1296 Test Method for Odor of Volatile Solvents and Diluents (Withdrawn 2021)³
- D1353 Test Method for Nonvolatile Matter in Volatile Solvents for Use in Paint, Varnish, Lacquer, and Related Products
- D2710 Test Method for Bromine Index of Petroleum Hydrocarbons by Electrometric Titration
- D3120 Test Method for Trace Quantities of Sulfur in Light Liquid Petroleum Hydrocarbons by Oxidative Microcoulometry
- D4367 Test Method for Benzene in Hydrocarbon Solvents by Gas Chromatography (Withdrawn 2021)³
- D5386 Test Method for Color of Liquids Using Tristimulus Colorimetry
- E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications
- E300 Practice for Sampling Industrial Chemicals
- 2.2 U.S. Federal Specification:⁴
- PPP-C-2020 Chemicals, Liquid, Dry, and Paste: Packaging of

3. Properties

3.1 Commercial hexanes shall conform to the following requirements:

Aniline point, min	57 °C
Apparent specific gravity 15.6/15.6 °C	0.660–0.686
Bromine index, max	100

³ The last approved version of this historical standard is referenced on www.astm.org.

⁴ Available from Standardization Documents Order Desk, DODSSP, Bldg. 4, Section D, 700 Robbins Ave., Philadelphia, PA 19111-5098, <http://www.dodssp.daps.mil>.

Color Pt-Co max (Note 1)	not darker than + 28 on the Saybolt Scale or 10 on the Pt-Co Scale
Distillation range:	
Initial boiling point, min	63 °C
Dry point, max	71 °C
Kauri-butanol value, max	33
Nonvolatile matter, mg/100 mL, max	1
Odor	nonresidual
Sulfur, ppm, max	5
Benzene content, weight %, max	0.1

NOTE 1—Instrumental Pt-Co color determined by Test Method **D5386** has been shown to have no statistically significant difference from Pt-Co color determined by Test Method **D1209**. However, it is not known whether commercial hexanes was part of the sample set included in the interlaboratory study.

4. Sampling

4.1 The material shall be sampled in accordance with Practice **E300**.

5. Test Methods

5.1 The properties enumerated in this specification shall be determined in accordance with the following ASTM test methods:

5.1.1 *Aniline Point*—Test Methods **D611**.

5.1.2 *Apparent Specific Gravity*—Determine apparent specific gravity by any method that is accurate to the third decimal place, the temperature of both specimen and water being 15.6 °C. See Guide **D268**. If measurement is by hydrometer, the instrument must be calibrated at the test temperature.

5.1.3 *Benzene Content*—Test Method **D4367**.

5.1.4 *Bromine Index*—Test Method **D2710**. Bromine index is defined as the number of milligrams of bromine which will react with a 100 g sample under test conditions.

5.1.5 *Color*—Test Method **D156** or **D1209** (see **Note 1**). In case of dispute, Test Method **D156** shall be the referee method.

5.1.6 *Distillation*—Test Method **D1078**, using a temperature measuring device having a range of 98 °C to 152 °C and a resolution of 0.1 °C.

5.1.7 *Kauri-Butanol Value*—Test Method **D1133**.

5.1.8 *Nonvolatile Matter*—Test Method **D1353**.

5.1.9 *Odor*—Test Method **D1296**. Samples of particular types of products being tested, having odor characteristics satisfactory to consumer and producer, are to be used as reference standards for comparison.

5.1.10 *Sulfur*—Test Method **D3120**.

6. Packaging and Package Marking

6.1 Package size shall be agreed upon by the purchaser and the supplier.

6.2 Packaging shall conform to applicable carrier rules and regulations or when specified shall conform to Fed. Spec. PPP-C-2020.

7. Keywords

7.1 commercial hexanes; hexanes; solvents

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/