



Designation: B 465 – 00^{ε1}

Standard Specification for Copper-Iron Alloy Plate, Sheet, Strip, and Rolled Bar¹

This standard is issued under the fixed designation B 465; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

^{ε1} NOTE—Section 1.1, Summary of Changes, Table 1, and Table 4 were editorially corrected in October 2001.

1. Scope *

1.1 This specification establishes Copper Alloy UNS Nos. C19200, C19400, C19500, and C19700² plate, sheet, strip, and rolled bar.

1.2 The values stated in inch-pound units are to be regarded as the standard.

2. Referenced Documents

2.1 ASTM Standards:

B 193 Test Method for Resistivity of Electrical Conductor Materials²

B 248 Specification for General Requirements for Wrought Copper and Copper-Alloy Plate, Sheet, Strip, and Rolled Bar³

B 601 Practice for Temper Designations for Copper and Copper Alloys—Wrought and Cast³

B 846 Terminology for Copper and Copper Alloys³

E 8 Test Methods for Tension Testing of Metallic Materials⁴

E 54 Test Methods for Chemical Analysis of Special Brasses and Bronzes⁵

E 62 Test Methods for Chemical Analysis of Copper and Copper Alloys (Photometric Methods)⁵

E 75 Test Methods for Chemical Analysis of Copper-Nickel and Copper-Nickel-Zinc Alloys⁵

E 76 Test Methods for Chemical Analysis of Nickel-Copper Alloys⁵

E 112 Test Methods for Determining Average Grain Size⁴

E 478 Test Methods for Chemical Analysis of Copper Alloys⁶

E 527 Practice for Numbering Metals and Alloys (UNS)⁴

3. Terminology

3.1 *Definitions*—For definitions of terms related to copper and copper alloys, refer to Terminology B 846.

4. General Requirements

4.1 The following sections of Specification B 248 constitutes a part of this specification:

4.1.1 Terminology,

4.1.2 Materials and Manufacture,

4.1.3 Workmanship, Finish, and Appearance,

4.1.4 Sampling,

4.1.5 Number of Tests and Retests,

4.1.6 Specimen Preparation,

4.1.7 Test Methods (except chemical analysis),

4.1.8 Significance of Numerical Limits,

4.1.9 Inspection,

4.1.10 Rejection and Rehearing,

4.1.11 Certification,

4.1.12 Test Reports (Mill),

4.1.13 Packaging and Package Marking, and

4.1.14 Supplementary Requirements.

4.2 In addition, when a section with a title identical to that referenced in 4.1 appears in this specification, it contains additional requirements which supplement those appearing in Specification B 248.

5. Ordering Information

5.1 Contracts or purchase orders for product under this specification should include the following information:

5.1.1 ASTM designation and year of issue (for example B 465–XX),

5.1.2 Copper Alloy UNS No. designation (for example, C19200),

5.1.3 Temper (Section 8),

5.1.4 *Dimensions*—Thickness, width, length, and so forth (Section 11),

5.1.5 *Form*—Plate, sheet, strip, or rolled bar,

5.1.6 *How Furnished*—Coils (rolls), specific lengths or stock lengths, with or without ends,

¹ This specification is under the jurisdiction of ASTM Committee B05 on Copper and Copper Alloys and is the direct responsibility of Subcommittee B05.1 on Plate, Sheet, and Strip.

Current edition approved May 10, 2000. Published July 2000. Originally published as B 465 – 68. Last previous edition B 465 – 93.

² *Annual Book of ASTM Standards*, Vol 02.03.

³ *Annual Book of ASTM Standards*, Vol 02.01.

⁴ *Annual Book of ASTM Standards*, Vol 03.01.

⁵ *Annual Book of ASTM Standards*, Vol 03.05.

⁶ *Annual Book of ASTM Standards*, Vol 03.06.

*A Summary of Changes section appears at the end of this standard.



5.1.7 *Quantity*—total weight each form, temper, and size, and

5.1.8 When material is purchased for agencies of the U.S. Government (Section 11).

5.2 The following options are available under this specification and should be specified in the contract or purchase order when required:

5.2.1 *Type of Edge*—Slit, sheared, sawed, square corners, round corners, rounded edges, or full rounded edges,

5.2.2 Width and straightness tolerances (appropriate table in Specification B 248),

5.2.3 Heat identification or traceability details,

5.2.4 Certification, and

5.2.5 Mill test report.

6. Materials and Manufacture

6.1 *Material*:

6.1.1 The material of manufacture shall be a cast bar, cake, slab, and so forth of Copper Alloy UNS No. C19200, C19400, C19500, or C19700, as specified in the ordering information, and of such purity and soundness as to be suitable for processing into the products prescribed herein.

6.1.2 In the event heat identification or traceability is required, the purchaser shall specify the details desired.

NOTE 1—Because of the discontinuous nature of the processing of castings into wrought products, it is not practical to identify a specific casting analysis with a specific quantity of finished product.

6.2 *Manufacture*:

6.2.1 The product shall be manufactured by such hot-working, cold-working, and annealing processes as to produce a uniform wrought structure in the finished product.

6.2.2 The product shall be hot- or cold-worked to the finished size, and subsequently annealed, when required, to meet the temper properties specified.

6.2.3 *Edges*—Slit edges shall be furnished unless otherwise specified in the contract or purchase order.

7. Chemical Composition

7.1 The material shall conform to the requirements prescribed in Table 1 for the Copper Alloy UNS No. designation specified in the ordering information.

7.1.1 These composition limits do not preclude the presence of other elements. Limits may be established and analysis

required for unnamed elements by agreement between the manufacturer and the purchaser.

7.2 Copper, when specified as the remainder, may be taken as the difference between the sum of results for specified elements and 100 %.

7.3 When all elements listed in Table 1 for the designated alloy are determined, the sum of results shall be 99.8 % minimum.

8. Temper

8.1 As defined in Practice B 601, products shall be produced in tempers O60 (soft annealed), O61 (annealed), O50 (light annealed), O82 (annealed to temper - 1/2 hard), H01 (1/4 hard), H02 (1/2 hard), H03 (3/4 hard), H04 (hard), H06 (extra hard), H08 (spring), H10 (extra spring), and H14 (super spring).

NOTE 2—The purchaser should confer with the manufacturer or supplier for the availability of product in a specific alloy, temper, and form, since all tempers are subject to manufacturing limitations.

NOTE 3—Properties of special tempers not listed in this specification are subject to agreement between the manufacturer and purchaser.

9. Grain Size for Annealed Tempers

9.1 *Grain Size*—No grain size requirements have been established for tempers O50, O60, and O61; however, the product material shall be fully recrystallized when examined in accordance with Test Methods E 112.

10. Physical Property Requirements

10.1 *Electrical Resistivity Requirement*:

10.1.1 The product furnished shall conform to the requirements of Table 2 for the Copper UNS No. designation and temper specified in the ordering information when determined in accordance with Test Method B 193.

10.1.1.1 Products produced in temper O60 from Copper Alloy UNS No. C19400 are not required to conform with the resistivity requirement of Table 2.

11. Mechanical Property Requirements

11.1 *Tensile Requirements*:

11.1.1 The product furnished shall conform to the requirements prescribed in Table 3 for the Copper Alloy UNS No. designation and temper specified in the ordering information when subjected to test in accordance with Test Methods E 8.

TABLE 1 Chemical Requirements

| Element | Composition, % | | | |
|----------------|----------------------|---------------|--------------|-----------|
| | Copper Alloy UNS No. | | | |
| | C19200 | C19400 | C19500 | C19700 |
| Copper | 98.5 min | 97.0 min | 96.0 min | remainder |
| Iron | 0.8 to 1.2 | 2.1 to 2.6 | 1.0 to 2.0 | 0.30–1.2 |
| Phosphorus | 0.01 to 0.04 | 0.015 to 0.15 | 0.01 to 0.35 | 0.10–0.40 |
| Zinc | 0.20 max | 0.05 to 0.20 | 0.20 max | 0.20 max |
| Lead, max | 0.03 | 0.03 | 0.02 | 0.05 |
| Tin | ... | ... | 0.10 to 1.0 | 0.20 max |
| Cobalt | ... | ... | 0.3 to 1.3 | 0.05 max |
| Aluminum | ... | ... | 0.02 max | ... |
| Magnesium | ... | ... | ... | 0.01–0.20 |
| Nickel, max | ... | ... | ... | 0.05 |
| Manganese, max | ... | ... | ... | 0.05 |