



Designation: D7715 – 12 (Reapproved 2021)

Standard Specification for Fully-Formulated Glycerin Base Engine Coolant for Heavy-Duty Engines¹

This standard is issued under the fixed designation D7715; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers the requirements for fully-formulated glycerin base coolants for cooling systems of heavy-duty engines. When concentrates are used at 40 % to 60 % glycerin concentration by volume in water of suitable quality (see [Appendix X1](#)), or when prediluted glycerin base engine coolants (50 volume % min) are used without further dilution, they will function effectively during both winter and summer to provide protection against corrosion, cavitation, freezing, and boiling.

1.2 This specification is intended to cover the requirements for engine coolants prepared from virgin glycerin.

NOTE 1—This specification is based on the knowledge of the performance of engine coolants prepared from new or virgin ingredients that comply with Specification [D7714](#).

1.3 The coolants governed by this specification are categorized as follows:

Coolant Type	Description
V-FF	Glycerin base concentrate
VI-FF	Glycerin predilute (50 vol %)

1.4 Coolant concentrates meeting this specification do not require addition of supplemental coolant additive (SCA) until the first maintenance interval when a maintenance dose of SCA is required to continue protection in certain heavy duty engine cooling systems, particularly those of the wet cylinder liner-in-block design. The SCA additions are defined by and are the primary responsibility of the engine manufacturer or vehicle manufacturer. If they provide no instructions, follow the SCA supplier's instructions.

1.5 The values stated in SI units are to be regarded as standard. The values given in parentheses after SI units are provided for information only and are not considered standard.

1.6 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appro-*

priate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.

1.7 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:²

- [D1126 Test Method for Hardness in Water](#)
- [D1293 Test Methods for pH of Water](#)
- [D3306 Specification for Glycol Base Engine Coolant for Automobile and Light-Duty Service](#)
- [D3321 Test Method for Use of the Refractometer for Field Test Determination of the Freezing Point of Aqueous Engine Coolants](#)
- [D4327 Test Method for Anions in Water by Suppressed Ion Chromatography](#)
- [D4725 Terminology for Engine Coolants and Related Fluids](#)
- [D5828 Test Method for Compatibility of Supplemental Coolant Additives \(SCAs\) and Engine Coolant Concentrates](#)
- [D6130 Test Method for Determination of Silicon and Other Elements in Engine Coolant by Inductively Coupled Plasma-Atomic Emission Spectroscopy](#)
- [D7583 Test Method for John Deere Coolant Cavitation Test](#)
- [D7714 Specification for Glycerin Base Engine Coolant for Automobile and Light-Duty Service](#)
- [E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications](#)

2.2 Other Standards:³

- [Federal Method 2540B Total Dissolved Solids Dried at 103-105°C](#)

¹ This specification is under the jurisdiction of ASTM Committee [D15](#) on Engine Coolants and Related Fluids and is the direct responsibility of Subcommittee [D15.07](#) on Specifications.

Current edition approved Sept. 1, 2021. Published September 2021. Originally approved in 2011. Last previous edition approved in 2016 as D7715 – 12 (2016) ^{ϵ 1}. DOI: 10.1520/D7715-12R21.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ *Standard Method for the Examination of Water and Wastewater*, American Public Health Association, et al, 801 I Street, NW, Washington, DC 20001, <http://www.apha.org>.

3. Terminology

3.1 Definitions:

3.1.1 *glycerin base engine coolant, n*—engine coolant in which the freeze point depressant is 1,2,3 propane triol, with inhibitors to minimize foaming and corrosion.

3.1.2 *supplemental coolant additive (SCA), n*—additive used in conventionally inhibited heavy duty engine coolants required to maintain protection against general corrosion, cylinder liner pitting, and scaling in heavy duty engines.

3.1.3 For other definitions and terms used in this specification, refer to Terminology **D4725**.

4. General Requirements

4.1 Concentrated and prediluted coolants shall meet all of the physical, chemical and performance requirements of Specification **D7714**, Tables 1, 2, and 3.

4.2 The coolant concentrate mixed with water or the prediluted coolant, when maintained with maintenance doses of SCA in accordance with the engine manufacturer’s recommendations, and those on the product label, shall be suitable for use in a properly maintained cooling system in normal service for a minimum of two years (see **Appendix X1**).

5. Additional Requirements

5.1 The coolant concentrate or prediluted coolant additionally shall provide protection in operating engines against cavitation corrosion (also termed liner pitting) and against scaling of internal engine hot surfaces. Hot surfaces typically are within the engine head, head spacer, upper cylinder liner, or liquid cooled exhaust manifold (Test Method **D7583**).

5.2 Lack of compatibility between the coolant and SCA product’s chemistry may cause the solute to precipitate out of solution, with potential adverse effects in the vehicle or engine cooling system. A test procedure for compatibility (Test Method **D5828**) has been developed and approved. The compatibility of SCA and coolant concentrate solutions meeting this specification shall be determined using (Test Method **D5828**) and the results reported.

5.3 Both the concentrated and prediluted coolants shall contain less than 50 µg/g sulfate ion.

6. Keywords

6.1 cavitation; fully-formulated heavy-duty engine coolant; glycerin; supplemental coolant additive maintenance dose

iTeh Standards
ANNEX
(Mandatory Information)

A1. REQUIREMENTS FOR FULLY FORMULATED HEAVY DUTY ENGINE COOLANT

A1.1 Laboratory data or in-service experience demonstrating a positive influence on reducing cavitation corrosion in an operating engine is required (see **Table A1.1**).

A1.1.1 In-service qualification tests may consist of single- or multiple-cylinder engine tests. At the option of the engine or vehicle manufacturer, such testing may be conducted in “loose

TABLE A1.1 Cavitation Protection Options Meeting the Requirements of Annex A1

Utilize One of the Following	Predilute or Concentrate	Acceptance Criteria
In-service test	In accordance with agreement	Agreement between engine manufacturer and coolant supplier for test criteria
Laboratory test (Test Method D7583)	In accordance with tested formulation	200 pit count measured in accordance with Test Method D7583 , max
Chemical composition nitrite formulation	Predilute	Nnitrite (as NO ₂ ⁻) of 1200 µg/g (ppm), min
Nitrite formulation	Concentrate	Nitrite (as NO ₂ ⁻) of 2400 µg/g (ppm), min
Combined nitrite and molybdate formulation	Predilute	Combined concentration of nitrite (as NO ₂ ⁻) plus molybdate (as MoO ₄ ⁻²) of 780 µg/g (ppm), min (at least 300 µg/g (ppm) each of NO ₂ ⁻ and MoO ₄ ⁻² must be present)
Combined nitrite and molybdate formulation	Concentrate	Combined concentration of nitrite (as NO ₂ ⁻) plus molybdate (as MoO ₄ ⁻²) of 1560 µg/g (ppm), min (at least 600 µg/g (ppm) each of NO ₂ ⁻ and MoO ₄ ⁻² must be present)

engines” or in engines fully integrated into an application, such as a vehicle, a power boat, or a stationary power source. One such test has been developed.⁴

A1.1.2 Coolants that have completed Test Method **D7583** with a maximum pit count of 200 are regarded as passing the requirements of **Annex A1**.

A1.1.3 Several chemical compositions have been tested extensively by producers and users and satisfactorily minimize cylinder liner cavitation in actual test engines. Coolants meeting either of the following compositions are regarded as passing the requirements of **Annex A1**:

A1.1.3.1 A minimum concentration of nitrite (as NO₂⁻) of 1200 µg/g (ppm) in the 50 volume % predilute coolant, or

⁴ “A Comparison of Engine Coolant in an Accelerated Heavy-Duty Engine Cavitation Test,” SAE Technical Paper 960883, SAE International, 400 Commonwealth Dr., Warrendale, PA 15096, <http://www.sae.org>.

A1.1.3.2 A minimum combined concentration of nitrite (as NO₂⁻) plus molybdate (as MoO₄⁻² in the 50 volume % predilute coolant of 780 µg/g (ppm). At least 300 µg/g (ppm) each of NO₂⁻ and MoO₄⁻² must be present.

A1.1.3.3 The above concentrations are doubled for coolant concentrates.

A1.2 Both concentrated and prediluted coolants under this specification shall contain additives to minimize hot surface scaling deposits. Certain additives (polyacrylate and other types) minimize the deposition of calcium and magnesium compounds on heat rejecting surfaces. No specific chemical requirements for hot surface scaling and deposits resistance have been established at this time. A test procedure is under development by ASTM Committee D15 and will be incorporated into the specification when approved.

APPENDIXES

(Nonmandatory Information)

X1. COOLANT MAINTENANCE FOR HEAVY DUTY ENGINES

X1.1 Engine Coolant—Cooling system fill for a heavy duty engine consists of water and fully formulated heavy duty coolant concentrate or fully formulated prediluted heavy duty coolant.

X1.1.1 Water:

X1.1.1.1 Water quality affects the efficiency of coolant additives. When untreated, all water is corrosive. Water having a high mineral content or corrosive materials is unfit for cooling system use.

X1.1.1.2 When preparing coolant mixtures, the water should be of such quality that it does not contain excessive solids, hardness salts, sulfates, or chlorides. In the absence of specific recommendations from the engine or vehicle manufacturer, see **Table X1.1**. Contact your local water department, the responsible government agency, or submit a water sample for analysis if there is a question on water quality.

X1.1.2 Coolant Concentrates:

X1.1.2.1 The coolant concentration should be maintained between 50 and 60 % glycerin by volume, depending on the

engine operating environment. Freeze protection shall be provided in accordance with **Table X1.2**.

X1.1.3 Prediluted Engine Coolants:

X1.1.3.1 Prediluted glycerin base engine coolants (50 volume % minimum) should be used without further dilution. If additional freeze protection is required, coolant concentrate may be added to the prediluted engine coolant to increase the total glycerin content in the cooling system (see **Table X1.2**).

X1.1.4 Supplemental Coolant Additive:

X1.1.4.1 SCAs extend the life of the coolant by replenishing the additives that deplete during normal operation. SCAs, however, do not extend the freeze protection provided by the coolant concentrate.

X1.1.4.2 Heavy-duty engine users experience has shown that coolants not meeting the criteria specified in **Annex A1** may not provide long term protection against cavitation corrosion (liner pitting). User experience and published information shows the presence of nitrite in an SCA or fully-formulated heavy-duty coolant is particularly effective in providing maximum protection.

X1.1.4.3 New technology consisting of other chemistries may provide satisfactory protection. Such chemistries can be established by agreement between producers and users upon

TABLE X1.1 Suggested Water Quality Limits^A

Property	Specific Values	Test Method
Total solids, µg/g (ppm (grains/gal))	340 (20) max	Fed Method 2540B
Total hardness, µg/g (ppm (grains/gal))	170 (10) max	D1126
Chloride (Cl), µg/g (ppm (grains/gal))	40 (2.4) max	D4327
Sulfate (SO ₄), µg/g (ppm (grains/gal))	100 (5.9) max	D4327
pH	5.5 to 9.0	D1293

^A Adopted from a survey by the D15 Water Quality Task Force.

TABLE X1.2 Freeze Protection

Glycerin Content, % ^A	Approximate Freeze Protection Temperature, °C (°F)	
	Coolant Type V-FF	
40	-18.0 (-0.0)	
50	-27.0 (-16.6)	
60	-44.0 (-42.0)	

^A Adopted from a survey by the D15 Water Quality Task Force.