



Designation: C822 – 21

Standard Terminology Relating to Concrete Pipe and Related Products¹

This standard is issued under the fixed designation C822; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Referenced Documents

1.1 *ASTM Standards*:²

C497 Test Methods for Concrete Pipe, Concrete Box Sections, Manhole Sections, or Tile

2. Terminology

absorption, *n*—the increase in weight of concrete resulting from the penetration of water into the concrete.

absorption test, *n*—a test made to determine the absorption of concrete.

admixture, *n*—a material other than water, aggregates, cement and fibre reinforcing used as an ingredient of concrete and added to the batch immediately before or during its mixture.

ambient conditions, *n*—common, prevailing, and uncontrolled atmospheric and weather conditions in a room or place.

annular space, *n*—the space between the inner surface of the female end and the outer surface of the male end of an assembled pipe joint.

bell—see **female end of pipe**.

blend, *n*—a combining of various cementitious materials.

box section, *n*—a concrete pipe with a rectangular cross section.

box section bottom slab, *n*—lower horizontal portion of a box section in the installed condition.

box section top slab, *n*—upper horizontal portion of a box section in the installed condition.

box section wall, *n*—vertical sides of a box section in the installed condition.

¹ This terminology is under the jurisdiction of ASTM Committee C13 on Concrete Pipe and are the direct responsibility of Subcommittee C13.10 on Correlation and Editorial.

Current edition approved Sept. 1, 2021. Published September 2021. Originally approved in 1975. Last previous edition approved in 2020 as C822 – 20. DOI: 10.1520/C0822-21.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

cage, *n*—an assembled unit of steel reinforcement consisting of circumferential and longitudinal bars or wires.

circular reinforcement, *n*—a circular-shaped line of reinforcement.

circumferential reinforcement, *n*—reinforcement that is approximately perpendicular to the longitudinal axis of the concrete pipe, box, or structure.

combined sewer, *n*—a pipeline intended to convey sewage and storm water.

compression test, *n*—a test made on a concrete specimen to determine the compressive strength.

compressive strength, *n*—the maximum resistance of a concrete specimen to axial compressive loading; or the specified resistance used in design calculations.

concrete, *n*—a mixture of portland cement, fine aggregate, coarse aggregate, and water; the mixture may also contain admixtures, or other cementitious materials, or both.

core, *n*—a cylinder of concrete obtained from concrete by means of a core drill.

crown, *n*—the top or highest point of the internal surface of the transverse cross section of a pipe.

culvert, *n*—a pipeline intended to convey water under a highway, railroad, canal, or similar facility.

cylinder (test), *n*—a cast cylindrical specimen of concrete.

design strength, *n*—the minimum acceptable 0.01-in. (0.3-mm) crack D-load.

designated size, *n*—the dimensional name for a particular size that may or may not be equal to or related to the dimensions used for design purposes or of the manufactured product.

distribution reinforcement, *n*—reinforcement, typically running 90° to the main or circumferential reinforcement, intended to disperse concentrated loads to larger areas of a structural member.

D-load, *n*—the supporting strength of a pipe loaded under three-edge-bearing test conditions expressed in pounds per

linear foot per foot of inside diameter or horizontal span, or expressed in newtons per linear metre per millimetre of inside diameter or horizontal span.

D-load, 0.01-in. (0.3-mm) crack, *n*—the maximum three-edge-bearing test load supported by a concrete pipe before a crack having a width of 0.01 in. (0.3 mm) occurs, measured at close intervals, throughout a continuous length of 1 ft (300 mm) or more measured parallel to the longitudinal axis of pipe barrel expressed as D-load.

D-load ultimate (*D_u*), *n*—the maximum three-edge-bearing test load supported by a pipe, expressed as D-load.

drain tile, *n*—pipe for collecting and conveying surface and subsurface water from an area.

elliptical reinforcement, *n*—a line of reinforcement in the approximate shape of an ellipse.

exfiltration, *n*—the volume of pipeline flow leaving a sewer and its connections into the soil from pipe, joints, connections, and appurtenances.

external load-crushing strength test, *n*—a test of the pipe in which external crushing forces are exerted in specified directions and locations on a specified length of pipe.

external sealing bands, *n*—flexible wrappings that are applied to the outside of a concrete pipe, box section, or manhole section joint intended to control the movement of fluids or solids through the joint.

female end of pipe (bell, socket, groove, modified groove), *n*—that portion of the end of the pipe, regardless of its shape or dimensions, which overlaps a portion of the end of the adjoining pipe.

flow line, *n*—a line formed by the inverts of pipe.

gradation, *n*—the distribution of particles of granular material among standard sizes usually expressed in terms of cumulative percentages larger or smaller than each of a series of sieve openings.

grade rings, *n*—precast concrete rings used for vertical adjustment at the top of a manhole to set manhole casting to proper grade.

groove—see **female end of pipe**.

handling reinforcement, *n*—reinforcement intended to reduce the risk of collapse of the pipe or section during handling or storage prior to and during final placement.

hydrostatic pressure, *n*—the pressure exerted by water at rest.

hydrostatic test, *n*—a test of the ability of a pipe or its joint to withstand internal hydrostatic pressure.

infiltration, *n*—the volume of groundwater entering a sewer and its connections from the soil through pipe, joints, connections, or appurtenances.

inflow, *n*—the volume of any kind of water entering a sewer and its connections from outside sources not including those sources described under “infiltration.”

installed length, *n*—final length, along the centerline, of a pipe or box section in place including the longitudinal joint separation between the section and the last section placed.

invert, *n*—the bottom or lowest point of the internal surface of the transverse cross section of a pipe.

irrigation pipe, *n*—pipe intended for the distribution of irrigation water by pumping or gravity.

joint, *n*—a connection of two pipe, manhole, or box section ends, made either with or without the use of additional parts and/or materials.

joint angular deflection, *n*—change in alignment commencing in the joint caused by opening or closing one side of the joint.

joint at normal (design) closure, *n*—position of the joint when closed to the manufacturer’s recommended inside longitudinal separation without joint angular deflection.

joint in off-center position, *n*—with the joint at normal or design closure, without joint angular deflection, when the spigot or bell has been moved in a radial direction.

DISCUSSION—The maximum off-center position occurs when the outer surface of the spigot and the inner surface of the bell are in contact.

joint leakage test, *n*—test procedure, utilizing water pressure, air pressure or a vacuum, intended to determine the acceptability of an individual joint relative to leakage.

joint leakage test apparatus, *n*—sealing device used to isolate a single joint so that the joint can be tested for leakage. See **joint leakage test**.

joint reinforcement, *n*—reinforcement, in or near the joint, intended to enhance the structural characteristics of the joint area of a concrete pipe or box section.

joint shear test, *n*—a proof-of-design test procedure to determine minimum shear strength of a joint.

layer of reinforcement—circumferential reinforcement that is one bar or wire in thickness.

laying length, *n*—pipe section center-line dimension used for preparing pipeline layout plans; or the length as measured from a point on a pipe to an identical point of an adjacent pipe of an installed pipeline.

lift hole, *n*—a small hole cast or drilled in the wall of the pipe or section for inserting a bolt, loop of cable or other device used in handling the pipe or section.

line of reinforcement, *n*—circumferential reinforcement comprised of one or more layers.

longitudinal reinforcement, *n*—reinforcement, in a concrete pipe or box section, running parallel to the intended flow.

lot, *n*—an assemblage of concrete products, all being of like size, material, and strength designation, manufactured by the same process.

DISCUSSION—The lot size may differ from the quantity designated in the contract or order.

low-pressure air test, *n*—testing procedure, utilizing compressed air, intended to determine the acceptability of a pipe section, joint, or pipeline.

male end of pipe (spigot, tongue, modified tongue), *n*—that portion of the end of the pipe, regardless of its shape or dimensions, which is overlapped by a portion of the end of the adjoining pipe.

manhole, *n*—a precast concrete structure for vertical access to a pipeline or other closed structure.

manhole base, *n*—a concrete slab foundation and the bottom manhole riser section or a bottom manhole riser section with a connected concrete slab.

manhole base section, *n*—precast concrete slab foundation and the bottom manhole riser section, or the bottom riser section with precast monolithic or integral slab.

DISCUSSION—A monolithic base section is cast as a single unit. An integral base section is made into a single unit by interconnecting precast manhole components such as a riser section and base slab.

manhole reducer section, *n*—a concrete section used as a transition between different diameter manhole riser sections.

manhole riser section, *n*—a concrete section used to construct a manhole exclusive of the base, reducers, and top section.

manhole top—the concrete slab top or conical top used to reduce the manhole riser diameter to that of the desired access hole.

manufactured length, *n*—the length from spigot/tongue end face to bell/groove inside shoulder; or the length from the spigot/tongue outside shoulder to bell/groove end face.

manufacturer, *n*—the group, corporation, partnership, or individual that manufactures or supplies a product.

mat reinforcement—see **quadrant mat**.

material tests, *n*—the quality and property tests of component materials.

modified design, *n*—a concrete pipe design changed from a standard design.

modified groove—see **female end of pipe**.

modified tongue—see **male end of pipe**.

monolithic, *n*—cast as one complete piece by a continuous placement of concrete.

negative air pressure (vacuum) test, *n*—test procedure utilizing air at a pressure less than atmospheric pressure, intended to determine the acceptability of a pipe section or multiple pipe sections, or an installed pipeline or manhole before or after backfill.

nonreinforced pipe, *n*—concrete pipe designed without reinforcement.

O-ring gasket, *n*—a solid gasket of circular cross section.

overall length, *n*—the length from the spigot/tongue end face to bell/groove end face.

owner, *n*—the public agency or authority, group, corporation, partnership, individual, or representative that specifies, accepts, or approves products or services for use on a project that it presently or eventually will own or administrate.

permeability, *n*—that property which permits movement of a liquid through the pores and interstices of the concrete.

permeability test, *n*—a test to determine the movement of a liquid through concrete under a hydraulic or pressure gradient.

pipe, *n*—a tube or elongated hollow concrete structure intended to transmit flow between locations.

pipe diameter, *n*—the inside diameter of a concrete pipe.

pipe section, *n*—a single pipe.

pipeline, *n*—pipe sections joined together.

plant tests, *n*—the quality assurance tests performed prior to delivery as a basis of acceptance.

preformed flexible joint sealant, *n*—pliable bitumen or elastomeric polymer (butyl) material, formed into a defined cross section, that is applied to the section joint surface of a pipe, box section, or manhole.

production run, *n*—quantity of concrete products of like size, material, and strength designation produced uninterrupted by a change in the size, material, production method, or strength designation of the product.

quadrant mat, *n*—additional tension zone circumferential reinforcement secured to a layer of reinforcement in the concrete pipe wall.

reinforced concrete pipe, *n*—a pipe structure comprised of concrete and steel reinforcement.

DISCUSSION—Steel reinforcement is comprised of steel wire, welded wire reinforcement, or bars, of known strength, formed into a cage and positioned in the concrete wall in a specific location in such a manner that the two materials act together to resist stresses.

reinforcement, *n*—steel in the form of continuous wire, welded wire reinforcement, or bars embedded in concrete in such a manner that the above referenced concrete and steel act together to resist stresses.

resilient connector, *n*—a flexible connection for joining pipe to structures capable of being deformed and deflected without rupture or leakage.

rubber gasket, *n*—rubber formed and used as a seal in concrete pipe joints.

sample, *n*—the number of specimens drawn from a lot.

sewage (wastewater), *n*—the spent water of a community which is a combination of liquid and water-carried wastes.

sewer, *n*—a pipeline intended to convey sewage.

special design, *n*—a concrete pipe design for sizes, loads, or service conditions not covered by a standard design.

specimen, *n*—an individual unit on which a test can be made.

spigot—see **male end of pipe**.

splice (reinforcement), *n*—junction of two sections of parallel reinforcement intended to provide continuity and to transfer forces between the two sections.

springline, *n*—the points on the internal surface of the transverse cross section of a pipe intersected by the line of maximum horizontal dimension; or in box sections, the mid-height of the internal vertical wall.

standard design, *n*—a published and proven concrete pipe design.

storm drain, *n*—a pipeline intended to convey storm water.

storm sewer, *n*—a pipeline intended to convey storm water.

storm water, *n*—precipitation run-off.

three-edge-bearing method, *n*—a method for applying the load to a pipe in an external load-crushing strength test.

tongue—see **male end of pipe**.

ultimate strength, *n*—the maximum three edge bearing test load supported by a pipe.

wall (pipe), *n*—the structural element composed of concrete or concrete and steel between the inside and outside surfaces of a concrete pipe.

watertight, *n*—will restrain the passage of water to not exceed a specified limit.

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[ASTM C822-21](#)

<https://standards.iteh.ai/catalog/standards/sist/de045876-fb65-4cdf-9fc4-03813ceae40d/astm-c822-21>