



Designation: C886 – 21

Standard Test Method for Scleroscope Hardness Testing of Carbon and Graphite Materials¹

This standard is issued under the fixed designation C886; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This test method covers the apparatus and procedure for determining the hardness of carbon and graphite materials using the Model C-2 scleroscope² with the hammer calibrated for use on carbon and graphite materials with particles smaller than 0.8 mm.³

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*⁴

[D4175 Terminology Relating to Petroleum Products, Liquid Fuels, and Lubricants](#)

[E171 Practice for Conditioning and Testing Flexible Barrier Packaging](#)

[E448 Practice for Scleroscope Hardness Testing of Metallic Materials \(Withdrawn 2017\)](#)⁵

2.2 *ANSI Standard:*⁶

[ANSI C 64.1 Brushes for Electrical Machines](#)

3. Terminology

3.1 For definitions of terms used in this test method, refer to Terminology [D4175](#).

4. Summary of Test Method

4.1 The specimen is held in position, and the height of rebound of a diamond-tipped hammer is observed and recorded as the hardness number.

5. Significance and Use

5.1 The scleroscope is a rebound hardness tester with a scale divided into 140 equal parts. For carbon and graphite materials, there is no established correlation between the Scleroscope hardness scale and other hardness scales. The test is useful in the evaluation and the manufacturing control of carbon and graphite materials.

6. Interferences

6.1 Lack of alignment of the instrument, as specified in Section 11, will cause low readings.

6.2 The specimen must be held firmly in position and must have adequate support from the anvil on which the sample rests. Neglect of alignment, positioning, or support will result in low readings.

6.3 Rough surface finish, above 3.2 μm AA, may cause low readings.

6.4 Indentations that are superimposed or spaced too closely together (approximately 3 mm) will cause incorrect readings.

¹ This test method is under the jurisdiction of ASTM Committee D02 on Petroleum Products, Liquid Fuels, and Lubricants and is the direct responsibility of Subcommittee D02.F0 on Manufactured Carbon and Graphite Products.

Current edition approved Oct. 1, 2021. Published October 2021. Originally approved in 1988. Last previous edition approved in 2015 as C886 – 98 (2015). DOI: 10.1520/C0886-21.

² Registered trademark of the Shore Instrument and Manufacturing Co., Inc., 80-A Commercial St., Freeport, NY 11520, and available from Instron Worldwide Headquarters, 825 University Ave., Norwood, MA 02062, www.instron.com.

³ This test method may be more readily understood by referring to the following documents: Practice E448, ANSI C 64.1, Brushes for Electrical Machines, available from American National Standards Institute, 1430 Broadway, New York, NY 10017, and Lysaght and DeBellis, *Indentation Hardness Testing*, American Chain and Cable Corp., Reinhold Publishing Co., 1969.

⁴ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

⁵ The last approved version of this historical standard is referenced on www.astm.org.

⁶ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

*A Summary of Changes section appears at the end of this standard

7. Apparatus

7.1 *Table*, or equivalent, firm, for support.

7.2 *Scleroscope*, Model C-2, equipped with a hammer calibrated by the manufacturer for use on carbon and graphite materials.

8. Test Specimen

8.1 The specimen may be of any convenient size, but test surfaces smaller than 5 mm by 5 mm are not recommended.

8.2 The recommended specimen shall have a minimum thickness of 5 mm.

8.3 The test surface shall not exceed 3175 nm AA in surface finish.

8.4 The test surface-to-opposite side parallelism shall be within 1 %. For all specimens, the test surfaces must be maintained normal to the axis of the scleroscope tube.

9. Calibration and Standardization

9.1 Check the calibration of the scleroscope with carbon test blocks obtained from the instrument manufacturer.

9.2 Make a series of tests on carbon test blocks that cover the range of hardness to be tested.

9.3 Make at least five tests on each carbon test block. Do not make any tests closer than 6 mm from the sides of the test blocks.

9.4 Consider the instrument calibrated if 90 % of the readings deviate no more than ± 4 %, or ± 3 points, whichever is larger, from the mean of the hardness numbers stamped on the carbon test blocks.

10. Conditioning

10.1 Allow the specimen to reach equilibrium with room temperature air, and test under the same conditions in accordance with Specification E171.

10.2 Keep specimens free of contamination.

11. Procedure

11.1 Place the instrument on a firm support.

11.2 Level the instrument using the plumb bob or bubble level.

11.3 Check the calibration in accordance with Section 9.

11.4 Place the specimen on the anvil.

11.5 Be certain that the hammer is in the “UP” (locked) position.

11.6 Lower the tube against the specimen, and hold firmly.

11.7 Release the hammer and read the height of the rebound.

11.8 Return the hammer to the “UP” (locked) position.

11.9 Repeat 11.6 through 11.8 four or more times, using a different impact point each time in accordance with 9.4.

11.10 Record the average reading to the nearest whole number.

11.11 A single reading substantially different from the other shall be reported, but not included in the average or standard deviation calculations.

12. Report

12.1 Report the following information:

12.1.1 Material identification,

12.1.2 Specimen dimensions,

12.1.3 Surface conditions, that is, as formed or machined, wet or dry,

12.1.4 Orientation of the test surface with respect to anisotropy of material (parallel or perpendicular),

12.1.5 Number of readings taken,

12.1.6 Average hardness reading to the nearest whole number,

12.1.7 Standard deviation where applicable,

12.1.8 Testing conditions, including test date, serial number of test machine, and operator’s name, and

12.1.9 Special environmental conditions, if any.

13. Precision and Bias⁷

13.1 Six laboratories participated in the interlaboratory study.

13.2 *Precision*—The repeatability standard deviation has been determined to be 3 points and the 95 % repeatability limit is 8.4 points. The reproducibility standard deviation has been determined to be 3 points and the 95 % reproducibility limit is 8.4 points.

13.3 Bias of a properly calibrated instrument is ± 4 %, or ± 3 points, whichever is larger.

14. Keywords

14.1 carbon; graphite; hardness; scleroscope

⁷ Supporting data have been filed at ASTM International Headquarters and may be obtained by requesting Research Report RR:C05-1005. Contact ASTM Customer Service at service@astm.org.