



Designation: E246 – 21

Standard Test Methods for Determination of Iron in Iron Ores and Related Materials by Dichromate Titrimetry¹

This standard is issued under the fixed designation E246; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 These test methods cover the determination of total iron in iron ores, concentrates, and agglomerates in the concentration range 30 % to 95 % iron.

1.2 The test methods in this standard are contained in the sections indicated as follows:

Test Method A—Iron by the Hydrogen Sulfide Reduction Dichromate Titration Method (30 % to 75 % Fe)

Test Method B—Iron by the Stannous Chloride Reduction Dichromate Titration Method (35 % to 95 % Fe)

Test Method C—Iron by the Silver Reduction Dichromate Titration Method (35 % to 95 % Fe)

1.3 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.* Specific hazards statements are given in Section 5 and in special “Warning” paragraphs throughout these test methods.

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

D1193 Specification for Reagent Water

¹ These test methods are under the jurisdiction of ASTM Committee E01 on Analytical Chemistry for Metals, Ores, and Related Materials and are the direct responsibility of Subcommittee E01.02 on Ores, Concentrates, and Related Metallurgical Materials.

Current edition approved Oct. 1, 2021. Published October 2021. Originally approved in 1964. Last previous edition approved in 2015 as E246 – 10(2015). DOI: 10.1520/E0246-21.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.

E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

E50 Practices for Apparatus, Reagents, and Safety Considerations for Chemical Analysis of Metals, Ores, and Related Materials

E276 Test Method for Particle Size or Screen Analysis at No. 4 (4.75-mm) Sieve and Finer for Metal-Bearing Ores and Related Materials

E691 Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method

E877 Practice for Sampling and Sample Preparation of Iron Ores and Related Materials for Determination of Chemical Composition and Physical Properties

E882 Guide for Accountability and Quality Control in the Chemical Analysis Laboratory

E1028 Test Method for Total Iron in Iron Ores and Related Materials by Dichromate Titrimetry (Withdrawn 2003)³

3. Significance and Use

3.1 The determination of the total iron content is the primary means for establishing the commercial value of iron ores used in international trade.

3.2 These test methods are intended as referee methods for the determination of iron in iron ores. It is assumed that all who use these test methods will be trained analysts capable of performing common laboratory procedures skillfully and safely. It is expected that work will be performed in a properly equipped laboratory and that proper waste disposal procedures will be followed. Appropriate quality control practices must be followed, such as those described in Guide E882.

4. Apparatus, Reagents, and Instrumental Practices

4.1 *Apparatus*—Specialized apparatus requirements are listed in the “Apparatus” Section in each test method.

4.2 *Reagents*:

4.2.1 *Purity of Reagents*—Reagent grade chemicals shall be used in all tests. Unless otherwise indicated, it is intended that all reagents conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society where

³ The last approved version of this historical standard is referenced on www.astm.org.

such specifications are available.⁴ Other grades may be used, provided it is first ascertained that the reagent is of sufficiently high purity to permit its use without lessening the accuracy of the determination.

4.2.2 *Purity of Water*—Unless otherwise indicated, references to water shall be understood to mean reagent water conforming to Type I or Type II of Specification **D1193**. Type III or Type IV may be used if they effect no measurable change in the blank or sample.

5. Hazards

5.1 For precautions to be observed in the use of certain reagents and equipment in this test method refer to Practices **E50**.

6. Sampling and Sample Preparation

6.1 Collect and prepare the test sample in accordance with Practice **E877**.

6.2 The test sample shall be pulverized to pass a No. 100 (150- μ m) sieve in accordance with Test Method **E276**. To facilitate decomposition some ores, such as specular hematite, require grinding to pass a No. 200 (75- μ m) sieve.

TEST METHOD A—IRON BY THE HYDROGEN SULFIDE REDUCTION DICHROMATE TITRATION METHOD

7. Scope

7.1 This test method covers the determination of total iron in iron ores, concentrates, and agglomerates in the range from 30 % to 75 % by mass.

7.2 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

8. Summary of Test Method

8.1 The sample is dissolved in HCl. The insoluble residue is removed by filtration, ignited, treated for the recovery of iron, and added to the main solution. To this solution containing all of the iron, H_2SO_4 is added and the solution evaporated to fumes to expel chlorides. The salts are dissolved in water, the solution heated to boiling, and the iron reduced by a rapid stream of hydrogen sulfide (H_2S). The precipitated sulfides are filtered and washed with an acid-sulfide wash solution until free of iron. The filtrate is then boiled to expel the H_2S , cooled, and titrated with $K_2Cr_2O_7$ solution, using sodium diphenylamine sulfonate as the indicator.

9. Interferences

9.1 None of the elements normally found in iron ores interfere with this test method. These include vanadium,

copper, and small amounts of molybdenum, which occasionally occur in iron ores.

10. Apparatus

10.1 *Hydrogen Sulfide Generator*— H_2S shall be obtained from a cylinder of the compressed gas or from a Kipp generator. A consistent flow of 1 L/min shall be maintained and the gas passed through a water trap to remove any salts.

10.1.1 **Warning**— H_2S is extremely toxic. All procedures involving its use must be performed in an efficient fume hood. Refer to Hazards section in Practices **E50**.

10.2 *Crucibles*, platinum, 25-milliliter (mL) capacity.

11. Reagents and Materials

11.1 *Ferrous Ammonium Sulfate Solution* (approximately 0.10 *N*)—Dissolve 40 g of ferrous ammonium sulfate ($FeSO_4 \cdot (NH_4)_2SO_4 \cdot 6H_2O$) in H_2SO_4 (1 + 19). Transfer to a 1-L flask and dilute to volume with the same acid. When the sample solution is ready for titration, standardize the $FeSO_4 \cdot (NH_4)_2SO_4 \cdot 6H_2O$ solution against the standard $K_2Cr_2O_7$ (0.1000 *N*), as described in **12.5**. Calculate the milliliters of standard $K_2Cr_2O_7$ equivalent to 1 mL of the $FeSO_4 \cdot (NH_4)_2SO_4 \cdot 6H_2O$ solution.

11.2 *Potassium Dichromate, Standard Solution* (0.1000 *N*)—Transfer 4.9031 g of primary standard grade potassium dichromate ($K_2Cr_2O_7$); previously ground in an agate mortar, and dried at 105 °C to 110 °C, to a 1-L volumetric flask. Dissolve in water and dilute to 1 L. If preferred, this solution may be prepared from reagent grade $K_2Cr_2O_7$, by purifying the salt twice by recrystallizing from water, drying at 110 °C, pulverizing in an agate mortar, and drying at 180 °C to constant weight. The titer of this solution shall be confirmed by means of standard sample similar in type and composition to the test sample.

11.3 *Potassium Permanganate Solution* (25 g/L)—Dissolve 25 g of potassium permanganate ($KMnO_4$) in water and dilute to 1 L.

11.4 *Sodium Diphenylamine Sulfonate Indicator Solution*—Dissolve 0.3 g of sodium diphenylamine sulfonate in 100 mL of water. Store in a dark-colored bottle.

11.5 *Sodium Pyrosulfate* ($Na_2S_2O_7$).

11.6 *Sulfuric Acid-Hydrogen Sulfide Wash Solution*—Add 20 mL of concentrated H_2SO_4 (H_2SO_4 , sp gr 1.84) to 900 mL water, cool, dilute to 1 L, and pass a rapid stream of H_2S through it for at least 10 min.

12. Procedure

12.1 Transfer approximately 0.50 g of the test specimen to a small weighing bottle previously dried at about 105 °C. Dry the bottle and contents for 1 h at 105 °C to 110 °C (**Note 1**). Cap the bottle and cool to room temperature in a desiccator. Momentarily release the cap to equalize the pressure and weigh the capped bottle and sample to the nearest 0.1 mg. Repeat the drying and weighing until there is no further mass loss. Transfer the test specimen to a 250-mL beaker and reweigh the capped bottle to the nearest 0.1 mg. The difference between the two masses is the mass of the sample taken for analysis.

⁴ *Reagent Chemicals, American Chemical Society Specifications*, American Chemical Society, Washington, DC. For suggestions on the testing of reagents not listed by the American Chemical Society, see the *United States Pharmacopeia and National Formulary*, U.S. Pharmacopeial Convention, Inc. (USPC), Rockville, MD.

NOTE 1—Most ores yield their hygroscopic moisture at this temperature. If a drying temperature other than that specified is required, this shall be determined by mutual agreement between manufacturer and purchaser.

12.2 *Decomposition of the Sample*—Moisten the sample with a few (mL) of water and add 25 mL of HCl. Cover the beaker and heat, maintaining a temperature below boiling until most of the dark particles are dissolved and no further attack is apparent. Add 5 mL of HNO₃ and digest for another 15 min. Remove from the source of heat, wash the sides and cover of the beaker, and dilute to 50 mL with warm water. Filter the insoluble residue on a fine-texture paper. Wash the residue with warm HCl (1 + 50) until the yellow color of ferric chloride is no longer observed and then with warm water six times to eight times. Collect the filtrate and washings in a 600-mL beaker and reserve as the main solution (Note 2). Place the paper and residue in a platinum crucible. Char the paper at a low

5). Remove from the source of heat, cover the flask with a small watch glass, and cool in running water to 20 °C.

NOTE 4—If the sample contains much calcium, prolonged fuming with H₂SO₄ may lead to the formation of salts that are difficult to dissolve. Therefore, in the presence of considerable calcium, fume just long enough to expel the chlorides and nitrates. Cool, wash the sides of the beaker with water, and again evaporate to light fumes.

NOTE 5—If the sample contains an appreciable amount of molybdenum, further precipitation may occur in the filtrate when boiling out the H₂S. The effect of residual molybdenum is not significant and may be neglected.

12.4 *Titration*—Add to the cooled solution 5 mL of phosphoric acid (H₃PO₄) and five drops of the sodium diphenylamine sulfonate indicator solution. Dilute to 350 mL and titrate with the standard K₂Cr₂O₇ solution to a distinct purple endpoint.

TABLE 1 Precision Data

Sample	Number of Laboratories	Iron Found %	Repeatability		Reproducibility	
			<i>s_r</i>	<i>R_I</i> (2.8 <i>s_r</i>)	<i>s_R</i>	<i>R₂</i> (2.8 <i>s_R</i>)
Seine River Ore	9	57.52	0.125	0.35	0.126	0.35
Knob Lake Ore	9	58.45	0.097	0.27	0.136	0.38
NBS 27d (64.96 % Fe)	6	65.01	0.057	0.16	0.085	0.24
Chilean Iron Ore	9	66.11	0.102	0.29	0.172	0.48
Pooled standard deviations ^A			0.101		0.137	

^A Weighted by degrees of freedom, *n* for *s_r* and (*n* – 1) for *s_R* where *n* = number of laboratories.

temperature, then ignite at 950 °C. Allow the crucible to cool, moisten the residue with H₂SO₄ (1 + 1), add about 5 mL of HF, and heat gently to remove silica and H₂SO₄ (Note 3). Cool the crucible, add 3 g of Na₂S₂O₇, and heat until a clear melt is obtained. Cool, place the crucible in a 250-mL beaker, add about 25 mL of water and 5 mL of HCl, and warm to dissolve the melt. Rinse and remove the crucible. Add the solution and washings to the main solution.

NOTE 2—If the residue is small in amount and perfectly white, the filtration, and treatment of the residue may be omitted without causing significant error.

NOTE 3—The treatment of the residue depends upon the nature of the minerals present. Many ores require only an H₂SO₄–HF treatment to decompose the residue.

12.3 *Reduction*—To the combined solution add 10 mL of H₂SO₄ (1 + 1) and evaporate to copious fumes of sulfur trioxide (SO₃) (Note 4). Cool, dilute to approximately 100 mL with water, and heat to boiling. Add dropwise KMnO₄ solution until the permanganate color persists. Dilute the solution to 250 mL and again heat to boiling for several minutes. Remove from the source of heat and pass a rapid stream of H₂S through the solution for 15 min. (**Warning**—Hydrogen sulfide is extremely toxic. All procedures involving its use must be performed in an efficient fume hood. Refer to Hazards section in Practices E50.) Digest at 60 °C for 15 min and filter through a medium-texture paper, collecting the filtrate in a 500-mL Erlenmeyer flask. Wash the precipitated sulfides thoroughly with the H₂SO₄–H₂S wash solution. Add 10 mL of H₂SO₄ (1 + 1) to the solution in the flask and add glass beads to prevent bumping. Boil for 10 min to expel H₂S (lead acetate test paper) and continue boiling for an additional 10 min (Note

12.5 *Determination of Blank*—Determine the blank value of the reagents concurrently with the test determination, using the same amount of all reagents and following all the steps of the procedure. Immediately before titrating with the K₂Cr₂O₇ solution, add 1.0 mL, accurately measured, of the FeSO₄·(NH₄)₂SO₄·6H₂O solution. In another beaker place 350 mL of cold H₂SO₄ (1 + 9) and add an accurately measured 1 mL of the FeSO₄·(NH₄)₂SO₄·6H₂O solution. Add 5 mL of H₃PO₄ and five drops of the sodium diphenylamine sulfonate indicator solution and titrate with the K₂Cr₂O₇ solution. Record this titration and subtract from the titration of the blank solution to obtain the corrected blank.

NOTE 6—In the absence of iron, the diphenylamine sulfonate indicator does not react with the K₂Cr₂O₇ solution. The addition of the FeSO₄·(NH₄)₂SO₄·6H₂O is, therefore, necessary to promote indicator response in the blank solution. A correction must be made in terms of its equivalent in mL of K₂Cr₂O₇ solution.

13. Calculation

13.1 Calculate the percentage of iron as follows:

$$\text{iron, \%} = [(A - B) \times C/D] \times 100 \quad (1)$$

where:

- A = mL of K₂Cr₂O₇ required for titration of the sample,
- B = mL of K₂Cr₂O₇ required for titration of the blank,
- C = iron equivalent of the K₂Cr₂O₇, g/mL, and
- D = grams of sample used.

13.2 Rounding of test results obtained using this test method shall be performed as directed in Practice E29, Rounding Method, unless an alternative rounding method is specified by the customer or applicable material specification.

14. Precision and Bias

14.1 *Precision*—From six to nine laboratories analyzed four iron ore samples to determine iron. The replication made by the different laboratories ranged from two to four, averaging three replicates. The data was studied by the interlaboratory test procedure of Practice E691 – 87 modified by weighting certain sums to accommodate the unequal replication.⁵ Table 1 shows a summary of these results. From pooled standard deviations, the overall between-laboratory reproducibility coefficient, R , was calculated as being 0.38.

14.2 The agreement of the determination of iron in the NBS Standard Reference Material with the certified value shows no evidence of bias, well within a 95 % confidence level:

$$(R_2 = 0.24)$$

TEST METHOD B—IRON BY THE STANNOUS CHLORIDE REDUCTION DICHROMATE TITRATION METHOD

15. Scope

15.1 This test method covers the determination of total iron in iron ores, concentrates, and agglomerates in the range from 35 % to 95 % by mass.

15.2 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

16. Summary of Test Method

16.1 This test method provides two alternative dissolution procedures.

16.2 *Acid Decomposition*—The sample is dissolved in HCl. The insoluble residue is removed by filtration, ignited, treated for the recovery of iron, and added to the main solution.

16.3 *Decomposition by Fusion*—The sample is fused with a mixture of sodium carbonate and sodium peroxide (Na_2O_2). The melt is leached with water. For samples containing more than 0.1 % of vanadium or molybdenum, or both, the solution is filtered and the insoluble residue is dissolved in HCl. For other samples the leachate is acidified with HCl.

16.4 *Reduction of the Iron*—Most of the iron is reduced with stannous chloride, followed by the addition of a slight excess of titanium (III) chloride solution. The excess titanium (III) is then oxidized in the hot solution with HClO_4 . The solution is cooled and the reduced iron is titrated with a standard $\text{K}_2\text{Cr}_2\text{O}_7$ solution using sodium diphenylamine sulfonate as the visual endpoint indicator.

17. Interferences

17.1 This test method covers the analysis of iron ores containing less than 0.1 % copper. In the case of iron ores

containing molybdenum or vanadium, or both, these elements are removed by water leach and filtration of the cooled sodium carbonate/sodium peroxide fusion melt. Other elements normally found in iron ores do not interfere.

18. Apparatus

18.1 *Crucibles*, platinum, 25-mL to 30-mL capacity.

18.2 *Crucibles*, zirconium, 25-mL to 30-mL capacity.

18.3 *Weighing Spatula*, of a nonmagnetic material or demagnetized stainless steel.

19. Reagents

19.1 *Iron (III) Ammonium Sulfate (approximately 0.1 N)*—Dissolve 40 g of iron (II) ammonium sulfate [$\text{FeSO}_4 \cdot (\text{NH}_4)_2\text{SO}_4 \cdot 6\text{H}_2\text{O}$] in H_2SO_4 (1 + 19). Transfer to a 1-L volumetric flask, dilute to volume with the same acid, and mix. Standardize against standard $\text{K}_2\text{Cr}_2\text{O}_7$ solution using diphenylamine sulfonate as indicator.

19.2 *Potassium Dichromate, Standard Solution (0.1 N)*—Pulverize about 6 g of $\text{K}_2\text{Cr}_2\text{O}_7$ reagent in an agate mortar, dry in an air-bath at 140 °C for 3 h to 4 h, and cool to room temperature in a desiccator. Dissolve 4.9031 g of the dry reagent in water and dilute the solution with water to exactly 1 L in a volumetric flask. Record the temperature at which this dilution was made.

19.3 *Potassium Permanganate Solution (KMnO_4)*, 25 g/L.

19.4 *Potassium Pyrosulfate Fine Powder ($\text{K}_2\text{S}_2\text{O}_7$)*.

19.5 *Sodium Carbonate Anhydrous Powder (Na_2CO_3)*.

19.6 *Sodium Diphenylaminesulfonate Solution*—Dissolve 0.2 g of the reagent ($\text{C}_6\text{H}_5\text{NC}_6\text{H}_4 \cdot \text{SO}_3\text{Na}$) in water and dilute to 100 mL. Store the solution in a brown glass bottle.

19.7 *Sodium Hydroxide Solution (NaOH)*, 20 g/L.

19.8 *Sodium Peroxide (Na_2O_2)*, dry powder. (**Warning**—Use proper safety practices and equipment when performing Na_2O_2 fusions.)

19.9 *Sulfuric Acid-Phosphoric Acid Mixture*—Pour 150 mL of H_3PO_4 (6.12) into about 400 mL of water. While stirring, add 150 mL of H_2SO_4 (6.20). Cool in a water bath and dilute with water to 1 L.

19.10 *Tin (II) Chloride Solution (100 g/L)*—Dissolve 100 g of crystalline tin (II) chloride ($\text{SnCl}_2 \cdot 2\text{H}_2\text{O}$) in 200 mL of HCl by heating the solution in a water bath. Cool the solution and dilute the water to 1 L. This solution should be stored in a brown glass bottle with the addition of a small quantity of granular or mossy tin metal.

19.11 *Titanium (III) Chloride Solution (2 %)*—Dissolve 1 g of titanium sponge (99.5 % minimum purity) in about 30 mL of HCl in a covered beaker by heating on a steam bath. Cool the solution and dilute with water to 50 mL. Prepare fresh as needed. (If preferred, dilute one volume of commercial titanium (III) chloride solution (about 15 % w/v) with seven volumes of HCl (1 + 1).)

⁵ Supporting data giving the results of cooperative testing have been filed at ASTM International Headquarters and may be obtained by requesting Research Report RR:E16-63, dated April 23, 1968, with an amendment, dated July 27, 1993. Contact ASTM Customer Service at service@astm.org.

20. Procedure

NOTE 7—If the procedure is based on acid decomposition, use 20.1. If the procedure is based on an alkaline fusion followed by the filtration of the leached melt, (samples containing more than 0.1 % by mass vanadium or molybdenum, or both), use 20.2. If the procedure is based on an alkaline fusion, followed by acidification of the leached melt (samples containing less than 0.1 % of molybdenum or vanadium, or both), use 20.3. (**Warning**—Use proper safety practices and equipment when performing Na_2O_2 fusions.)

20.1 Acid Decomposition:

20.1.1 Weigh approximately 0.40 g of sample into a small weighing bottle previously dried at about 105 °C (Note 8). Dry the bottle and contents for 1 h at 105 °C to 110 °C. Cap the bottle and cool to room temperature in a desiccator. Momentarily release the cap to equalize the pressure and weigh the capped bottle and sample to the nearest 0.1 mg. Repeat the drying and weighing until there is no further mass loss. Transfer the samples to a 250-mL beaker and reweigh the capped bottle to the nearest 0.1 mg. The difference between the two masses is the mass of the sample taken for analysis.

NOTE 8—For samples of iron content greater than 68 % by mass, weigh approximately 0.38 g.

20.1.2 Carry a reagent blank through all steps of the procedure.

20.1.3 Add 30 mL of HCl, cover the beaker with a watch glass, and heat the solution gently without boiling until no further attack is apparent. Wash the watch glass and dilute to 50 mL with warm water. Filter the insoluble residue on a close-texture paper. Wash the residue with warm HCl (1 + 50), until the yellow color or iron (III) chloride is no longer observed, then wash with warm water six times to eight times. Collect the filtrate and washings in a 400-mL beaker. Start to evaporate this solution.

20.1.4 Place the filter paper and residue in a platinum crucible, dry, and ignite at 750 °C to 800 °C. Allow the crucible to cool, moisten the residue with H_2SO_4 (1 + 1), add about 5 mL of HF, and heat gently to remove silica and H_2SO_4 . Add to the cold crucible 2 g of potassium pyrosulfate, heat gently at first, then strongly until a clear melt is obtained. Cool, place the crucible in a 250-mL beaker, add about 25 mL of water and about 5 mL of HCl, and warm to dissolve the melt. Remove and wash the crucible.

20.1.5 Adjust the solution to slight alkalinity with ammonia solution. Heat to coagulate the precipitate, filter on a coarse-texture paper, and wash several times with hot water. Discard the filtrate.

20.1.6 Place the beaker containing the main solution under the funnel and dissolve the precipitate on the filter paper by pouring over it 10 mL of hot HCl (1 + 2), wash the filter, first six times to eight times with warm HCl (1 + 50), then twice with hot water. Evaporate the combined filtrates at low heat to a volume of about 30 mL and continue with 20.4.

20.2 *Fusion Decomposition and Filtration of Leached Melt* (Note 7):

NOTE 9—For blank determination, see 20.1.2.

20.2.1 Dry the sample in accordance with 20.1.1 and transfer to a zirconium crucible, add about 4 g of a (1 + 2) mixture of sodium carbonate and Na_2O_2 . Mix thoroughly and

place in a muffle furnace at 500 °C \pm 10 °C for 30 min. Remove from the furnace and heat over a burner until melted. Continue heating just above the melting point for approximately 1.5 min. Allow the melt to cool, place the crucible in a 400-mL beaker, add about 100 mL of warm water, and heat to leach the melt. Remove the crucible and wash. Reserve the crucible. Cool the solution and filter through a filter paper of dense texture. Wash the paper six times to eight times with NaOH solution (20 g/L) and discard the filtrate and washings.

20.2.2 Wash the precipitate into the original beaker with water, add 10 mL of HCl, and warm to dissolve the precipitate. Dissolve the iron in the reserved crucible in hot HCl (1 + 1). Wash the crucible with hot HCl (1 + 10) and add to the main solution. Wash the filter paper three times with warm HCl (1 + 2), several times with warm HCl (1 + 50), and finally with warm water until the washings are no longer acid, adding the washings to the main solution. Evaporate with low heat to a volume of about 30 mL and continue with 20.4.

20.3 *Fusion-Decomposition and Acidification of Leached Melt* (Note 7) :

NOTE 10—For blank determination, see 20.1.2.

20.3.1 Dry the sample in accordance with 20.1.1 and transfer to a zirconium crucible. Add 3 g of Na_2O_2 and mix thoroughly. Place the crucible in a muffle furnace at 400 °C. After 10 min to 15 min remove from the furnace and heat over a burner to the melting point. Fuse, swirling the crucible, until the melt is cherry red and clear.

20.3.2 Allow the melt to cool and place in a 400-mL beaker. Add about 10 mL of water to the crucible and cover the beaker immediately with a watch glass. After the reaction has ceased, empty the contents of the crucible into the beaker, and wash the crucible with about 20 mL of water. Add 20 mL of HCl to the crucible, transfer to the beaker, and rinse the crucible with water. Boil the solution for 2 min to 3 min. Rinse the watch glass and the sides of the beaker with water. The volume of the solution should be between 40 mL and 50 mL. Continue with 20.4.

20.4 Reduction:

20.4.1 Heat the solution to just below the boiling point and add three drops to five drops of KMnO_4 solution (25 g/L). Maintain at this temperature for 5 min to oxidize any arsenic and organic matter. Wash the cover and inside wall of the beaker with a small amount of hot HCl (1 + 10). Immediately add tin (II) chloride solution (100 g/L), drop by drop, while swirling the liquid in the beaker, until only a light yellow color remains (Note 11).

20.4.2 Reduce the remaining iron (III) by adding titanium (III) chloride solution (2 %) until the yellow color has disappeared, then add an additional three drops to five drops. Wash the inside wall of the beaker with a small amount of water and heat to an incipient boil. Remove from the source of heat and without delay, add all at once 5 mL, dilute HClO_4 (35 %). Mix well by swirling for 5 s. Dilute immediately with ice cold water to 200 mL. Cool rapidly to below 15 °C and proceed immediately to 20.5.1.

NOTE 11—It is essential that some iron (III) is left unreduced by the stannous chloride. If all the iron is inadvertently reduced, reoxidize a little