



Designation: E2294 – 21

# Standard Practice for Proof Silver Corrections in Metal Bearing Ores, Concentrates, and Related Materials by Fire Assay Gravimetry<sup>1</sup>

This standard is issued under the fixed designation E2294; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This practice covers the determination of fire assay correction for silver, utilizing proof silver, ores, concentrates, and related metallurgical materials.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.* (See Test Methods E1335, Practices E50, Guide E882, and ISO Guide 35: 2017.)

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

## 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

E50 Practices for Apparatus, Reagents, and Safety Considerations for Chemical Analysis of Metals, Ores, and Related Materials

E135 Terminology Relating to Analytical Chemistry for Metals, Ores, and Related Materials

<sup>1</sup> This practice is under the jurisdiction of ASTM Committee E01 on Analytical Chemistry for Metals, Ores, and Related Materials and is the direct responsibility of Subcommittee E01.02 on Ores, Concentrates, and Related Metallurgical Materials.

Current edition approved Oct. 1, 2021. Published October 2021. Originally approved in 2003. Last previous edition approved in 2013 as E2294 – 03(2013). DOI: 10.1520/E2294-21

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

E882 Guide for Accountability and Quality Control in the Chemical Analysis Laboratory

E1335 Test Methods for Determination of Gold in Bullion by Fire Assay Cupellation Analysis

2.2 *Other Documents:*<sup>3</sup>

ISO Guide 35: 2017 Reference Materials — Guidance for Characterization and Assessment of Homogeneity and Stability

ISO 10378: 2016 Copper, Lead and Zinc Sulfide Concentrates — Determination of Gold and Silver — Fire Assay Gravimetric and Flame Atomic Absorption Spectrometric Method

## 3. Terminology

3.1 *Definitions*—For definitions of terms used in this practice, refer to Terminology E135.

## 4. Summary of Practice

4.1 In the process of fire assay, silver losses occur. Proof silver is carried through the assay fusion and cupellation procedures to determine losses that can provide the fire assay silver correction values (see Test Methods E1335, ISO 10378: 2016, Bugbee,<sup>4</sup> and Smith<sup>5</sup>).

## 5. Significance and Use

5.1 This practice is primarily intended to be used for the correction of silver loss in the fire assay process. Silver assays are determined by fire assay for the purpose of metallurgical exchange between seller and buyer.

5.2 It is assumed that all who use this practice will be trained analysts capable of performing skillfully and safely. It is expected that work will be performed in a properly equipped laboratory under appropriate quality control practices such as those described in Guide E882.

<sup>3</sup> Available from International Organization for Standardization (ISO), 1, ch. de la Voie-Creuse, Case postale 56, CH-1211, Geneva 20, Switzerland, http://www.iso.ch.

<sup>4</sup> Bugbee, E. E., *A Textbook of Fire Assaying*, Third Ed., John Wiley and Sons, Inc., Hoboken, NJ, 1946.

<sup>5</sup> Smith, E. A., *The Sampling and Assay of the Precious Metals*, Second Ed., Charles Griffin and Co., Ltd., 1947.

## 6. Apparatus

- 6.1 *Analytical Balance*—Capable of weighing to 0.001 mg.
- 6.2 *Assay Furnace*—Capable of temperatures up to 1100 °C, accurate to  $\pm 5$  °C.
- 6.3 *Hammer*—Blacksmith type.
- 6.4 *Hammering Block*—Flat Steel plate.

## 7. Reagents and Materials

7.1 *Purity of Reagents*—Reagent grade chemicals shall be used in all tests. Unless otherwise indicated, it is intended that all reagents conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society where such specifications are available.<sup>6</sup> Other grades may be used, provided it is first ascertained that the reagent is of sufficiently high purity to permit its use without lessening the accuracy of the determination.

7.2 *Borax*—Sodium tetraborate—( $\text{Na}_2\text{B}_4\text{O}_7$ )—technical grade.

7.3 *Cupels*—Magnesite ( $\text{MgCO}_3$ ) or bone ash.

7.4 *Crucibles*—Standard Fire Assay clay.

7.5 *Flour*—Common baking grade.

7.6 *Lead Foil*, 99.99 % purity, min (1 ug/g silver max).

7.7 *Litharge (PbO)*—Technical grade—precious metal free.

7.8 *Potassium Carbonate ( $\text{K}_2\text{CO}_3$ )*—Technical grade.

7.9 *Silica Sand ( $\text{SiO}_2$ )*—Technical grade.

7.10 *Silver Metal*, 99.99 % purity.

7.11 *Sodium Carbonate ( $\text{Na}_2\text{CO}_3$ )*—Technical grade.

## 8. Hazards

8.1 For precautions to be observed in this practice, refer to Practices **E50**.

<sup>6</sup> *Reagent Chemicals, American Chemical Society Specifications*, American Chemical Society, Washington, DC, <http://www.chemistry.org>. For suggestions on the testing of reagents not listed by the American Chemical Society, see *Annual Standards for Laboratory Chemicals*, BDH Ltd., Poole, Dorset, U.K., <http://uk.vwr.com>, and the *United States Pharmacopeia and National Formulary*, U.S. Pharmacopeial Convention, Inc. (USPC), Rockville, MD, <http://www.usp.org>.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or [service@astm.org](mailto:service@astm.org) (e-mail); or through the ASTM website ([www.astm.org](http://www.astm.org)). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>

## 9. Procedure

9.1 Prepare samples according to normal fire assay procedures (Bugbee<sup>4</sup> or Smith<sup>5</sup>).

9.2 Weigh two proof silver samples (99.99 % pure silver foil), to match the typical weight of the expected doré bead. If the weight of the doré bead is unknown, weigh two proof silver samples, approximately 75 mg to 150 mg and 250 mg to 350 mg.

9.3 Fill an assay clay crucible with the same flux used in the test samples. A typical flux is:

### Typical Fire Assay Flux

- 30.5 g of sodium carbonate
- 14.5 g potassium carbonate
- 6.5 g silica sand
- 4 g to 5 g flour
- 60 g litharge
- flux cap (15 g litharge and 3 g borax)

9.4 Mix the flux mixture first. For the best consistent results, transfer the weighed silver samples and lead foil packet on the top of the mixture, then cover with the flux cap mixture.

9.5 Place crucibles in fire assay furnace and proceed with fusion and cupellation steps required for test samples.

9.6 After cupellation, the silver proof is weighed on the microbalance. The weight after the fire assay is compared to the original silver proof weight.

## 10. Calculation

10.1 Calculate the silver ratio as follows:

$$\text{Silver Ratio} = B/A \quad (1)$$

Where:

A = Initial Weight of Proof Silver, mg, and  
B = Final Weight of Proof Silver, mg.

10.2 Rounding of test results obtained using this test method shall be performed as directed in Practice **E29**, Rounding Method, unless an alternative rounding method is specified by the customer or applicable material specification.

10.3 To correct a silver fire assay result for test samples, divide the weight of the silver in the test sample, determined by the difference in weight before and after parting, by the average silver ratio for the two proofs to obtain the corrected silver weight.

## 11. Keywords

11.1 cupellation; fire assay; silver; silver correction