



Designation: D3141/D3141M – 21

Standard Specification for Asphalt for Undersealing Portland-Cement Concrete Pavements¹

This standard is issued under the fixed designation D3141/D3141M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers asphalt suitable for undersealing portland-cement concrete and overlaid concrete pavements by pumping hot asphalt under the slabs.

1.2 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in nonconformance with the standard.

1.3 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

[D5/D5M Test Method for Penetration of Bituminous Materials](#)

[D6/D6M Test Method for Loss on Heating of Oil and Asphaltic Compounds](#)

[D36/D36M Test Method for Softening Point of Bitumen \(Ring-and-Ball Apparatus\)](#)

[D92 Test Method for Flash and Fire Points by Cleveland Open Cup Tester](#)

¹ This specification is under the jurisdiction of ASTM Committee D04 on Road and Paving Materials and is the direct responsibility of Subcommittee D04.40 on Asphalt Specifications.

Current edition approved Nov. 1, 2021. Published November 2021. Originally approved in 1972. Last previous edition approved in 2015 as D3141/D3141M – 15. DOI: 10.1520/D3141_D3141M-21.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

[D113 Test Method for Ductility of Asphalt Materials](#)
[D140/D140M Practice for Sampling Asphalt Materials](#)
[D312/D312M Specification for Asphalt Used in Roofing](#)
[D2042 Test Method for Solubility of Asphalt Materials in Trichloroethylene](#)
[D7553 Test Method for Solubility of Asphalt Materials in N-Propyl Bromide](#)

3. Material

3.1 An asphalt of suitable consistency for pumping when heated to a temperature from 204 to 232 °C [400 to 450 °F] and for resistance to displacement in the pavement when cooled; for sealing the underside of the slabs and joints, to fill cavities, and to correct vertical alignment by raising the slab.

4. Properties

4.1 The asphalt shall be homogeneous and free of water and shall conform to the requirements in [Table 1](#).

5. Methods of Sampling and Testing

5.1 The asphalt shall be sampled and the properties enumerated in this specification shall be determined in accordance with the following ASTM methods:

5.1.1 *Sampling*—Practice [D140/D140M](#).

5.1.2 *Softening Point*—Test Method [D36/D36M](#).

5.1.3 *Flash Point*—Test Method [D92](#).

5.1.4 *Penetration*—Test Method [D5/D5M](#).

5.1.5 *Ductility*—Test Method [D113](#).

5.1.6 *Loss on Heating*—Test Method [D6/D6M](#).

5.1.7 *Asphalt Soluble in Trichloroethylene*—Test Method [D2042](#).

5.1.8 *Asphalt Soluble in N-Propyl Bromide*—Test Method [D7553](#).

6. Keywords

6.1 asphalt; portland-cement concrete; undersealing



TABLE 1 Requirements for Asphalt for Undersealing Portland-Cement Concrete Pavements

NOTE 1—These requirements are the same as for Type III asphalt in Specification D312/D312M.

	min	max
Softening point, °C [°F]	85 [185]	96 [205]
Flash point, °C [°F]	260 [500]	...
Penetration, units:		
at 0 °C [32 °F]	6	...
at 25 °C [77 °F]	15	35
at 46 °C [115 °F]	...	90
Ductility at 25 °C [77 °F], cm	2.5	...
Solubility, % ^A	99	...

^A Use Test Method D2042 or Test Method D7553.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/

(https://standards.iteh.ai)
Document Preview

[ASTM D3141/D3141M-21](https://standards.iteh.ai/catalog/standards/sist/8510d260-10bf-4b31-8a47-0ec9da83607e/astm-d3141-d3141m-21)

<https://standards.iteh.ai/catalog/standards/sist/8510d260-10bf-4b31-8a47-0ec9da83607e/astm-d3141-d3141m-21>