



Designation: ~~A582/A582M—12 (Reapproved 2017)~~ A582/A582M – 21

Standard Specification for Free-Machining Stainless Steel Bars¹

This standard is issued under the fixed designation A582/A582M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope^{*}

1.1 This specification covers hot-finished or cold-finished bars, except bars for forging (**Note 1**), suitable for machining processes. It includes rounds, squares, and hexagons in the more commonly used types of stainless free-machining steels designed especially for optimum machinability and for general corrosion and high-temperature service. Stainless steel bars other than the free-machining types are covered in a separate specification (**Note 2**).

1.2 This specification is expressed in both inch-pound units and in SI units; however, unless the purchase order or contract specifies the applicable *M* specification designation (SI units), the inch-pound units shall apply. The values stated in either inch-pound units or SI (metric) units are to be regarded separately as standard: within the text and tables, the SI units are shown in [brackets]. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in nonconformance with the specification.

NOTE 1—For bars for reforging, see Specification [A314](#).

NOTE 2—For non-free machining stainless bars, see Specification [A276](#).

1.3 This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.

2. Referenced Documents

2.1 *ASTM Standards*:²

[A276](#) Specification for Stainless Steel Bars and Shapes

[A314](#) Specification for Stainless Steel Billets and Bars for Forging

[A370](#) Test Methods and Definitions for Mechanical Testing of Steel Products

[A484/A484M](#) Specification for General Requirements for Stainless Steel Bars, Billets, and Forgings

[A751](#) Test Methods and Practices for Chemical Analysis of Steel Products

[A959](#) Guide for Specifying Harmonized Standard Grade Compositions for Wrought Stainless Steels

[E527](#) Practice for Numbering Metals and Alloys in the Unified Numbering System (UNS)

2.2 *SAE Document*:³

[SAE J 1086](#) Recommended Practice for Numbering Metals and Alloys³

¹ This specification is under the jurisdiction of ASTM Committee [A01](#) on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee [A01.17](#) on Flat-Rolled and Wrought Stainless Steel.

Current edition approved March 15, 2017; Nov. 1, 2021. Published March 2017; November 2021. Originally approved in 1967. Last previous edition approved in 2014; 2017 as A582/A582M – 12 (2017)². DOI: [10.1520/A0582-A0582M-12R17.10.1520/A0582_A0582M-21](#).

² For referenced ASTM standards, visit the ASTM website, [www.astm.org](#), or contact ASTM Customer Service at [service@astm.org](#). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from Society of Automotive Engineers (SAE), 400 Commonwealth Dr., Warrendale, PA 15096-0001.

***A Summary of Changes section appears at the end of this standard**

3. Ordering Information

3.1 It is the responsibility of the purchaser to specify all requirements that are necessary for product ordered under this specification. Such requirements to be considered include, but are not limited to, the following:

3.1.1 Quantity (weight or number of pieces),

3.1.2 Type (alloy) or UNS designation ([Table 1](#)),

3.1.3 Form (bars, angles, and so forth),

3.1.4 Condition ([Table 2](#)),

3.1.5 Finish ([5.1](#)),

TABLE 1 Chemical Requirements

UNS Designation ^A	Type ^B	Chemical Composition, %									
		Carbon ^C	Manganese ^C	Phosphorus, ^C	Sulfur ^C	Silicon, max	Chromium	Nickel	Molybdenum	Selenium	Other Elements
Austenitic											
S20300	XM-1 ^D	0.08	5.0–6.5	0.04	0.18–0.35	1.00	16.00–18.0	5.0–6.5	Cu 1.75–2.25
S30300	303	0.15	2.00	0.20	0.15 min	1.00	17.0–19.0	8.0–10.0
S30310	XM-5 ^D	0.15	2.5–4.5	0.20	0.25 min	1.00	17.0–19.0	7.0–10.0
S30323	303Se	0.15	2.00	0.20	0.06	1.00	17.0–19.0	8.0–10.0	...	0.15 min	...
S30345	XM-2 ^D	0.15	2.00	0.05	0.11–0.16	1.00	17.0–19.0	8.0–10.0	0.40–0.60	...	Al 0.60–1.00
Martensitic											
S41600	416	0.15	1.25	0.06	0.15 min	1.00	12.0–14.0
S41610	XM-6 ^D	0.15	1.50–2.50	0.06	0.15 min	1.00	12.0–14.0
S41623	416Se	0.15	1.25	0.06	0.06	1.00	12.0–14.0	0.15 min	...
S42020	420F	0.30–0.40	1.25	0.06	0.15 min	1.00	12.0–14.0	0.50 ^E	Cu 0.60 ^E
S42023	420FSe	0.20–0.40	1.25	0.06	0.06	1.00	12.0–14.0	0.50 ^E	...	0.15 min	Cu 0.60 ^E
S44020	440F	0.95–1.20	1.25	0.06	0.15 min	1.00	16.0–18.0	0.50 ^E	Cu 0.60 ^E
S44023	440FSe	0.95–1.20	1.25	0.06	0.06	1.00	16.0–18.0	0.50 ^E	...	0.15 min	Cu 0.60 ^E
Ferritic											
S18200	XM-34 ^D	0.08	2.50	0.04	0.15 min	1.00	17.5–19.5	...	1.50–2.50
S18235	...	0.025	0.50	0.030	0.15–0.35	1.00	17.5–18.5	1.00	2.00–2.50	...	Ti 0.30–1.00 N 0.025 C+N 0.035
S41603	...	0.08	1.25	0.06	0.15 min	1.00	12.0–14.0
S43020	430F	0.12	1.25	0.06	0.15 min	1.00	16.0–18.0
S43023	430FSe	0.12	1.25	0.06	0.06	1.00	16.0–18.0	0.15 min	...

^A Designation established in accordance with Practice [E527](#) and SAE J 1086, Recommended Practice for Numbering Metals and Alloys (UNS).

^B Unless otherwise indicated, a grade designation originally assigned by the American Iron and Steel Institute (AISI).

^C Maximum unless otherwise noted.

^D Naming system originated by ASTM.

^E At manufacturer's option, reported only when intentionally added.



TABLE 2 Condition

Type	Condition A (Annealed)	Condition T (Intermediate Temper)	Condition H (Hard Temper)
XM-1	A
303	A
XM-5	A
303Se	A
XM-2	A
416	A	T	H
XM-6	A	T	H
416Se	A	T	H
420F	A
420FSe	A
440F	A
440FSe	A
XM-34	A
S18235	A
S41603	A
430F	A
430FSe	A

3.1.6 Applicable dimensions, including size, thickness, width, and length,

3.1.7 Cross section (round, square, and so forth),

3.1.8 ASTM designation (Specification A582/A582M) and approval date,

3.1.9 Preparation for delivery, and

3.1.10 Marking requirements.

NOTE 3—A typical ordering description is as follows: 5000 lb [2000 kg] Type 416 bars, annealed and centerless ground, 1½ in. [40 mm] round, 10 to 12 ft [3 to 4 m] in length, ASTM Specification A582/A582Mdated.

4. General Requirements

4.1 Product furnished to this specification shall conform to the requirements of Specification A484/A484M, including any supplementary requirements indicated in the purchase order or contract. Failure to comply with the general requirements of Specification A484/A484M constitutes nonconformance with this specification.

5. Materials and Manufacture

5.1 Bars may be furnished either hot finished or cold finished, suitable for machining processes, in one of the conditions listed in Table 2.

6. Chemical Requirements

6.1 The chemical composition shall conform to the requirements specified in Table 1.

6.2 Methods and practices relating to chemical analysis required by this specification shall be in accordance with Test Methods, Practices, and Terminology A751.

7. Hardness Requirement

7.1 The product shall conform to the hardness requirements listed in Table 3 for Brinell Hardness Number (HBW).

7.2 At least one hardness test shall be made midway between surface and center on each lot to determine that the material conforms to Table 3.