



Designation: ~~C232/C232M—20a~~ C232/C232M – 21

Standard Test Method for Bleeding of Concrete¹

This standard is issued under the fixed designation C232/C232M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscripted epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This test method covers the determination of the relative quantity of mixing water that will bleed from a sample of freshly mixed concrete.

1.2 When various concretes are to be compared, if the batches are of similar unit weight, the sample masses shall not differ by more than 1 kg [2 lb].

1.3 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system are not necessarily exact equivalents; therefore, to ensure conformance with the standard, each system shall be used independently of the other, and values from the two systems shall not be combined.

NOTE 1—Sieve size is identified by its standard designation in Specification E11. The alternative designation given in parentheses is for information only and does not represent a different standard sieve size.

1.4 The text of this standard refers to notes and footnotes that provide explanatory material. These notes and footnotes (excluding those in tables and figures) shall not be considered as requirements of the standard.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use. (Warning—Fresh hydraulic cementitious mixtures are caustic and may cause chemical burns to skin and tissue upon prolonged exposure.²)*

1.6 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:³

[C29/C29M Test Method for Bulk Density \(“Unit Weight”\) and Voids in Aggregate](#)

[C125 Terminology Relating to Concrete and Concrete Aggregates](#)

[C138/C138M Test Method for Density \(Unit Weight\), Yield, and Air Content \(Gravimetric\) of Concrete](#)

¹ These test methods are under the jurisdiction of ASTM Committee C09 on Concrete and Concrete Aggregates and are the direct responsibility of Subcommittee C09.60 on Testing Fresh Concrete.

Current edition approved Nov. 1, 2020/Sept. 1, 2021. Published July 2021/November 2021. Originally approved in 1949. Last previous edition approved in 2020 as ~~C232/C232M – 20~~ C232/C232M – 20a. DOI: 10.1520/C0232-C0232M-20A-10.1520/C0232_C0232M-21.

² Section on Safety Precautions, Manual of Aggregate and Concrete Testing, *Annual Book of ASTM Standards*, Vol 04.02.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard

[C172/C172M Practice for Sampling Freshly Mixed Concrete](#)
[C192/C192M Practice for Making and Curing Concrete Test Specimens in the Laboratory](#)
[C670 Practice for Preparing Precision and Bias Statements for Test Methods for Construction Materials](#)
[E11 Specification for Woven Wire Test Sieve Cloth and Test Sieves](#)

3. Terminology

3.1 Definitions:

3.1.1 For definitions of terms used in this test method, refer to Terminology [C125](#).

4. Significance and Use

4.1 This test method provides procedures to be used for determining the effect of variables of composition, treatment, environment, or other factors in the bleeding of concrete. It is also permitted to be used to determine the conformance of a product or treatment with a requirement relating to its effect on bleeding of concrete.

4.2 A specimen consolidated by rodding and tested without further disturbance simulates conditions in which the concrete is not subjected to intermittent vibration after placement.

5. Apparatus

5.1 *Container*—A cylindrical container of approximately 14 L [$\frac{1}{2}$ ft³] capacity, having an inside diameter of 255 mm \pm 5 mm [10 in. \pm $\frac{1}{4}$ in.] and an inside height of 280 mm \pm 5 mm [11 in. \pm $\frac{1}{4}$ in.]. The container shall conform to the requirements for a measure in Test Method [C29/C29M](#). The inside shall be free of corrosion, coatings, or lubricants. A cover shall be provided to prevent evaporation of bleed water during the test.

5.2 *Scale*, of sufficient capacity to determine the mass of the load required with an accuracy of 0.5 %. Balances or scales shall be calibrated at least annually or whenever there is reason to question the accuracy of the equipment.

5.3 *Pipet*, or similar instrument, for drawing off free water from the surface of the test specimen.

5.4 *Glass Graduate*, 100-mL capacity for collecting and measuring the quantity of water withdrawn.

5.5 *Tamping Rod*—A round, straight steel rod, 16 mm [$\frac{5}{8}$ in.] in diameter and approximately 610 mm [24 in.] in length, having the tamping end rounded to a hemispherical tip, the diameter of which is 16 mm [$\frac{5}{8}$ in.].

6. Test Specimen

6.1 For concrete made in the laboratory, prepare as described in Practice [C192/C192M](#). For concrete made in the field, sample the concrete as described in Practice [C172/C172M](#). The apparatus described in this test method is permitted to be used with samples of concrete containing any size of aggregate graded up to and including a nominal maximum size of 50 mm [2 in.]. Concrete containing aggregate larger than 50 mm [2 in.] in nominal maximum size shall be wet sieved over a 37.5 mm [1½ in.] sieve and the test performed on a portion of the sample that passes through the sieve.

6.2 Determine the proportion of net mixing water (total water minus water absorbed by the aggregates) in the batch of concrete being tested from the batch weights data.

6.3 Determine the mass of the empty container. Fill the container with the concrete in accordance with Test Method [C138/C138M](#) except that the container shall be filled to a height of 255 mm \pm 3 mm [10 \pm $\frac{1}{8}$ in.]. Level the top surface of the concrete using no more than three passes of a trowel. Determine the mass of the container and concrete.

7. Procedure

7.1 During the test, maintain the ambient temperature ~~between 18 and 24 °C [65 and 75 °F]. Immediately after~~ at 23°C \pm 2 °C [73.5 °F \pm 3.5 °F]. When finished troweling the surface of the specimen, record the time. Place the specimen and container on a

level platform or floor free of noticeable ~~vibration and cover vibration~~. Cover the container to prevent evaporation of the bleed water. Keep the cover in place throughout the test, except when drawing off the water. Draw off (with pipet or similar instrument) the water that has accumulated on the surface at 10 min intervals during the first 40 min and at 30 min intervals thereafter until cessation of ~~bleeding, recording~~ ~~bleeding~~. Record the time of last observation. To facilitate the collection of bleed water, tilt the specimen ~~carefully~~ by placing a block approximately 50 mm [2 in.] thick under one side of the container 2 min ~~prior~~ ~~before~~ to each time the water is withdrawn.

7.2 After water is removed, return the container to a level position without jarring. After each withdrawal, transfer the water to a 100 mL graduated cylinder. Record the accumulated quantity of water after each transfer.

8. Calculation

8.1 Calculate the total accumulated bleed water, expressed as a percentage of the net mixing water contained within the test specimen, as follows:

$$C = (w/W) \times S \quad (1)$$

$$\text{Bleeding, \%} = (D/C) \times 100$$

where:

C = mass of net mixing water in the test specimen, g [lb],

W = total mass of the batch, kg [lb],

w = mass of net mixing water in the batch (the total amount of water minus the water absorbed by the aggregates), kg [lb],

S = mass of the specimen, g [lb], and

D = accumulated mass of the bleed water, g [lb], (total volume withdrawn from the test specimen in mL multiplied by 1 g/mL [0.0022 lb/mL]).

8.2 If specified, the comparative rate of bleeding can be demonstrated by plotting the accumulated volume of bleed water versus the elapsed time.

9. Report

9.1 Concrete mixture proportions,

<https://standards.iteh.ai/catalog/standards/sist/6528ec5d-a33e-49b9-9635-f62b684c9082/astm-c232-c232m-21>

9.2 Source and identification of each material used,

9.3 The total accumulated bleed water, expressed as a percentage of the net mixing water contained within the test specimen, and

9.4 Elapsed time required for cessation of bleeding.

9.5 If specified, plot of accumulated volume of bleed water versus elapsed time.

10. Precision and Bias

10.1 *Precision:*

10.1.1 Data are available to evaluate the precision of the test method for concrete consolidated by vibration. The values given shall be used as maximum precision limits for concrete consolidated by rodding.

NOTE 2—In earlier versions of this test method, there were two consolidation procedures: Method A by rodding and Method B by using a vibrating platform. Precision data had been obtained for Method B and because both methods used the same procedures for determining the amount of bleed water the precision for Method B is applicable to Method A. In 2013, Method B was deleted from the test method. The precision statement is based on consolidation using a vibrating platform and is provided to give the user information on the magnitude of the variation that is expected for concrete consolidated by rodding.

10.1.2 The single operator-day-multibatch standard deviation has been found to be 0.71 % for a bleeding range from 0 to 10 %,