



Designation: D4610 – 98 (Reapproved 2021)

Standard Guide for Determining the Presence of and Removing Microbial (Fungal or Algal) Growth on Paint and Related Coatings¹

This standard is issued under the fixed designation D4610; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This guide describes techniques used for determining the presence of fungal or algal growth on paint and related coatings and methods for removal of such growth prior to recoating.

1.2 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

- 2.1 *ASTM Standards:*²
- D2022 Test Methods of Sampling and Chemical Analysis of Chlorine-Containing Bleaches
 - D3274 Test Method for Evaluating Degree of Surface Disfigurement of Paint Films by Fungal or Algal Growth, or Soil and Dirt Accumulation

3. Significance and Use

3.1 Microbial growth is a major cause of discoloration and deterioration of paint films. This guide describes techniques used to distinguish fungi and algae from other surface contaminants.

¹ This guide is under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.28 on Biodeterioration.

Current edition approved Nov. 1, 2021. Published November 2021. Originally approved in 1986. Last previous edition approved in 2017 as D4610 – 98 (2017). DOI: 10.1520/D4610-98R21.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

3.2 Repainting a surface contaminated with fungi or algae generally causes more rapid infestation of the new paint than repainting a surface from which fungal or algal growth has been removed. In addition, poor adhesion, staining/bleeding, and many other problems may result. This guide describes methods for removing fungal or algal growth prior to repainting.

NOTE 1—It is extremely important that all steps and notes be read and followed. In particular the washing steps outlined in 5.2.2 and 5.2.4 must be fully carried out, since residual sodium hypochlorite (bleach) can cause many of the same problems, or even loss of coloration after repainting, and residual phosphate detergents can encourage further fungal and algal growth.

NOTE 2—This procedure is intended for use when recoating the surface. Reports of using this procedure to remove fungi and algae without recoating necessitate inclusion of a warning about the adverse effects of bleach on a coating film. The oxidative effects of bleach can degrade film properties, including particularly the “bleaching” (loss of color) in films containing organic coloring pigments (such as quinacridones, etc.), loss of gloss, chalking, etc. A small patch must be tested prior to use of this procedure for that purpose.

4. Reagents

4.1 *Sodium Hypochlorite*, approximately 5 % aqueous (NaOCl) as commercial household bleach. Because sodium hypochlorite decomposes on exposure to heat and sunlight and becomes ineffective, use only fresh material. See Test Methods D2022 for methods of sampling and chemical analysis.

4.2 *Phosphate-Free*, non-ammonia-containing detergent or commercial cleaner recommended for washing paint.

5. Procedures

5.1 *Determining the Presence of Fungal or Algal Growth on Paint:*

5.1.1 *Chemical*—Apply a drop of 5 % aqueous sodium hypochlorite solution (common household bleach) to the area suspected of being contaminated with fungal or algal growth. Fungal or algal discoloration will normally bleach within 60 s. Discoloration that does not bleach is probably dirt. For further confirmation do visual and subculture tests.

5.1.2 The following procedures should preferably be used by persons who have had basic microbiological training:

5.1.2.1 *Visual*—Examine the surface using magnification from 10 to 100 \times to distinguish among fungal, algal, or dirt disfigurement in accordance with Test Method D3274.

5.1.2.2 *Subculture*—Apply a prepared petri dish containing a raised convex surface of nutrient agar culture medium³ directly to the surface to be sampled and exert moderate pressure. Replace the cover and incubate for at least 72 h at 35 °C (95 °F). Examine the agar surface visually as in 5.1.2.1.

NOTE 3—The culture medium must contain the nutrients necessary for growth of algae and fungi.

5.2 *Removal of Fungal and Algal Growth on Paint:*

5.2.1 Wash the surface with a solution of approximately 2 % phosphate-free detergent in water.

NOTE 4—The term wash as it is used in 5.2.1 and 5.2.3 is defined as firmly scrubbing the surface with a fully wet sponge or other suitable applicator. Care should be taken to ensure the surface is thoroughly wet with cleaning solution.

5.2.2 Thoroughly rinse the surface with water to remove residual detergent.

5.2.3 Wash the surface with a solution of 1 part by volume of sodium hypochlorite 5 % aqueous solution and 3 parts by volume of water.

NOTE 5—See warnings in Note 1 and Note 2. Also be warned that overspray of bleach can be detrimental to ornamental shrubs, plants, or lawn, and can “bleach,” discolor, or otherwise degrade adjacent areas if not adequately protected from exposure. Adequate personal protective equipment should always be used.

NOTE 6—The solution should be allowed to remain on the surface from 10 to 15 min.

NOTE 7—The sodium hypochlorite solution and the 2 % detergent solution may be combined 1:1 by volume in one treatment if desired.

5.2.4 Thoroughly rinse the surface with water to remove residual sodium hypochlorite (see Note 1).

5.2.5 If agreed upon by the parties involved, reinspect the surface in accordance with 5.1 to ensure that there has been adequate removal. Refer to the coating manufacturer’s literature for recommended drying time before recoating.

6. Keywords

6.1 algal; bleaches; fungals; microbials; washes

³ Agar available from various microbiological supply companies.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/

[ASTM D4610-98\(2021\)](https://standards.iteh.ai/ASTM-D4610-98(2021))

<https://standards.iteh.ai/catalog/standards/sist/7ad68500-5ee4-476e-92af-3062c68d7b94/astm-d4610-982021>