



Designation: **E1652—15 E1652 – 21**

An American National Standard

Standard Specification for Magnesium Oxide and Aluminum Oxide Powder and Crushable Insulators Used in the Manufacture of Base Metal Thermocouples, Metal-Sheathed Platinum Resistance Thermometers, and Noble Metal Thermocouples¹

This standard is issued under the fixed designation E1652; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers the requirements for magnesium oxide (MgO) and aluminum oxide (Al_2O_3) powders and crushable insulators used to manufacture base metal thermocouples, metal-sheathed platinum resistance thermometers (PRTs), noble metal thermocouples, and their respective cables.

1.2 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only after SI units are provided for information only and are not considered standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

<https://standards.iteh.ai/catalog/standards/sist/cc9a5b0c-7dc7-44a9-8994-5133e24e2c39/astm-e1652-21>

2. Referenced Documents

2.1 ASTM Standards:²

- B329 Test Method for Apparent Density of Metal Powders and Compounds Using the Scott Volumeter
- C809 Test Methods for Chemical, Mass Spectrometric, and Spectrochemical Analysis of Nuclear-Grade Aluminum Oxide and Aluminum Oxide-Boron Carbide Composite Pellets
- C832 Test Method for Measuring Thermal Expansion and Creep of Refractories Under Load
- D2766 Test Method for Specific Heat of Liquids and Solids (Withdrawn 2018)³
- E228 Test Method for Linear Thermal Expansion of Solid Materials With a Push-Rod Dilatometer
- E235 Specification for Type K and Type N Mineral-Insulated, Metal-Sheathed Thermocouples for Nuclear or for Other High-Reliability Applications
- E344 Terminology Relating to Thermometry and Hydrometry
- E585/E585M Specification for Compacted Mineral-Insulated, Metal-Sheathed, Base Metal Thermocouple Cable

¹ This specification is under the jurisdiction of ASTM Committee E20 on Temperature Measurement and is the direct responsibility of Subcommittee E20.13 on Thermocouples - Materials and Accessories Specifications.

Current edition approved Nov. 1, 2015. Published November 2015. Originally approved in 1995. Last previous edition approved in 2014 as E1652 – 14a. E1652 – 15. DOI: 10.1520/E1652-15.10.1520/E1652-21.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.

[E1137/E1137M](#) Specification for Industrial Platinum Resistance Thermometers

[E1225](#) Test Method for Thermal Conductivity of Solids Using the Guarded-Comparative-Longitudinal Heat Flow Technique

[E2181/E2181M](#) Specification for Compacted Mineral-Insulated, Metal-Sheathed, Noble Metal Thermocouples and Thermocouple Cable

3. Terminology

3.1 The definitions given in Terminology [E344](#) shall apply to this specification.

4. Significance and Use

4.1 Magnesium oxide and aluminum oxide are used to electrically isolate and mechanically support the thermoelements of a thermocouple (see Specifications [E235](#), [E585/E585M](#), and [E2181/E2181M](#)) and the connecting wires of a PRT (see Specification [E1137/E1137M](#)) within a metal sheath. The metal sheath is typically reduced in diameter to compact the oxide powder or crushable oxide insulators around the thermoelements or wires.

4.2 In order to be suitable for this purpose, the materials shall meet certain criteria for purity and for mechanical and dimensional characteristics. Material that does not meet the purity criteria may cause premature failure of the sensor.

4.3 Use of this specification for the procurement of powder and crushable insulators will help to ensure that the product obtained is suitable for the intended purpose.

4.4 Useful information about alumina and magnesia is given in the appendixes.

5. Classification

5.1 The purchaser shall specify the appropriate Material and Type from [5.2](#) through [5.6](#) below.

5.2 MgO Type 1 in accordance with [Table 1](#).

5.3 Al₂O₃ Type 1 in accordance with [Table 1](#).

5.4 MgO Type 1P in accordance with [Table 2](#).

5.5 Al₂O₃ Type 1P in accordance with [Table 2](#).

TABLE 1 Chemical Requirements for Al₂O₃ Type 1 and MgO Type 1^{A, B}

Aluminum Oxide (Al ₂ O ₃) 99.65 % (mass) min		Magnesium Oxide (MgO) 99.40 % (mass) min	
Impurity	Concentration, % (mass)	Impurity	Concentration, % (mass)
Al ₂ O ₃	99.65 % min	MgO	99.40 % min
CaO	0.08 max	CaO	0.35 max
SiO ₂	0.08 max ^B	SiO ₂	0.35 max ^B
SiO ₂	0.08 max	SiO ₂	0.35 max
MgO	0.08 max	Al ₂ O ₃	0.15 max
Fe ₂ O ₃	0.04 max	Fe ₂ O ₃	0.07 max
ZrO ₂	0.08 max		
Na ₂ O	0.06 max		
C	0.01 max	C	0.02 max
S	0.005 max	S	0.0025 max
B	0.001 max	B	0.0035 max
Cd	0.001 max	Cd	0.001 max
		B+Cd	0.004 max

^A Platinum thermoelements and Noble Metal thermocouples for use above 650°C shall specify Type 1P composition according to [Table 2](#).

^B Base metal thermocouples for nuclear environments in accordance with Specification [E235](#) shall specify Type 1P composition according to [Table 2](#).

TABLE 2 Chemical Requirements for Al₂O₃ Type 1P and MgO Type 1P^A

Aluminum Oxide (Al ₂ O ₃) 99.65 % (mass) min		Magnesium Oxide (MgO) 99.40 % (mass) min	
Impurity	Concentration, % (mass)	Impurity	Concentration, % (mass)
Al ₂ O ₃	99.65 % min	MgO	99.40 % min
CaO	0.08 max	CaO	0.35 max
SiO ₂	0.08 max	SiO ₂	0.13 max
MgO	0.08 max	Al ₂ O ₃	0.15 max
Fe ₂ O ₃	0.04 max	Fe ₂ O ₃	0.04 max
ZrO ₂	0.08 max		
Na ₂ O	0.06 max		
C	0.01 max	C	0.02 max
S	0.005 max	S	0.0025 max
B	0.005 max	B	0.0035 max
B	0.001 max	B	0.0035 max
Cd	0.001 max	Cd	0.001 max
Cd	0.001 max	Cd	0.001 max
		B+Cd	0.004 max

^APlatinum thermoelements and noble Metal thermocouples for use below 650°C/650 °C may optionally specify Type 1 composition according to Table 1.

5.6 MgO Type 2 in accordance with **Table 3**.

NOTE 1—There is no corresponding Al₂O₃ Type 2 designation at this time.

5.7 The final product shall be chemically analyzed using appropriate methods listed in **9.1**. Major impurities shall not exceed the limits indicated in **Table 1** through **Table 3** for the appropriate grade. Any detected impurity with a concentration greater than 0.001 % (mass) shall be reported to the purchaser.

6. Ordering Information

6.1 The purchaser shall specify the following when ordering:

6.1.1 *Material and Type in accordance with Section 5.*

6.1.2 *Insulator Outside Diameter.*

6.1.3 *Hole Diameter.*

6.1.4 *Number of Holes.*

6.1.5 *Hole Pattern.*

6.1.6 *Length.*

TABLE 3 Chemical Requirements for MgO Type 2

Magnesium Oxide (MgO) 97.00 % (mass) min	
Impurity	Concentration, % (mass)
MgO	97.00 % min
CaO	1.50 max
Al ₂ O ₃	1.00 max
SiO ₂	3.00 max
Fe ₂ O ₃	0.15 max
C	0.02 max
S	0.0025 max
B	0.0050 max
Cd	0.001 max
B + Cd	0.0050 max
MgO + CaO + Al ₂ O ₃ + SiO ₂	99.50 min

6.1.7 *Particle Size* (if supplied as powder).

6.2 The purchaser may specify the following additional information when ordering:

6.2.1 *Minimum Inside Diameter (at Maximum Material Condition (MMC)) of the Tubing*, (into which insulators will be inserted, see 8.3).

6.2.2 *Maximum Outside Diameter of Wire which will be inserted into the insulators*, (see 8.3).

6.3 Consult the insulator manufacturer for limitations of relationships between outside diameter, hole diameters, hole patterns, and length.

7. Physical Properties

7.1 *Density*—The density of crushable magnesium oxide and aluminum oxide insulators typically ranges from 2060 kg/m³ (0.074 lbm/in.³) to 3060 kg/m³ (0.111 lbm/in.³). Specific density requirements, as well as the test method to be used to determine density, shall be negotiated between the purchaser and manufacturer. See [Appendix X3](#) for suggested test methods.

7.2 *Modulus of Rupture (MOR)*—In the past, a breaking force test that is based on a relative modulus of rupture and is related to crushability has been used. However, with variations in modulus from 21 to 83 MPa (3000 to 12 000 lb/in.²) influenced by insulator configuration, number of holes, and cross-sectional dimensions, specific modulus requirements cannot be listed for each configuration. The modulus of rupture is best used for lot-to-lot comparison of a given insulator size and configuration. See [Appendix X4](#) for a suggested test method and [X2.4](#) for recommended tolerances.

8. Dimensional Requirements

8.1 Outside diameter and hole diameter tolerances for insulators shall be as specified in [Table 4](#) and [Table 5](#), respectively, unless otherwise agreed to between the purchaser and manufacturer.

8.2 The wall and web thicknesses (see [Fig. 1](#)) shall be equal within outside the total allowable outside diameter tolerance as specified in [Table 5](#) and the minimum measured web or wall shall be no smaller than 75 % of the maximum measured web or wall, unless otherwise agreed to between the purchaser and manufacturer.

8.3 The camber shall not exceed 0.3 % of the length. The insulator shall be capable of passing through a rigid straight tube longer than the insulator and with an inside diameter as specified in [6.2.1](#). Local camber defects caused by "knees" or "doglegs" shall not impede the insertion of wire.

8.4 The helical twist of holes shall not exceed 2° per cm (5° per in.) of the length.

8.5 The length shall be as specified in [6.1.6](#) with a tolerance of +6/−0.00 mm (+0.25/−0.00 in.).

8.6 The ends of each insulator should be cut square and shall be essentially chip-free as agreed upon between the supplier and purchaser.


TABLE 4 Outside Diameter (O.D.) Tolerances

Nominal Insulator O.D.	O.D. Tolerance
Over 0.25 to 1.00 mm (0.010 to 0.039 in.), inclusive	±0.05 mm (±0.002 in.)
Over 1.00 to 1.50 mm (0.039 to 0.059 in.), inclusive	±0.08 mm (±0.003 in.)
Over 1.50 to 5.00 mm (0.059 to 0.197 in.), inclusive	±0.10 mm (±0.004 in.)
Over 5.00 to 8.00 mm (0.197 to 0.315 in.), inclusive	±0.13 mm (±0.005 in.)
Over 8.00 to 10.00 mm (0.315 to 0.394 in.), inclusive	±0.15 mm (±0.006 in.)
Over 10.0 mm (0.394 in.)	±1.75%

TABLE 5 Hole Diameter Tolerance^A

Nominal Insulator Hole Diameter	Hole Diameter Tolerance
Over 0.18 to 1.00 mm (0.007 to 0.039 in.), inclusive	±0.05 mm (±0.002 in.)
Over 1.00 to 2.00 mm (0.040 to 0.079 in.), inclusive	±0.08 mm (±0.003 in.)
Over 2.00 to 2.50 mm (0.079 to 0.098 in.), inclusive	±0.10 mm (±0.004 in.)
Over 2.50 mm (0.098 in.) and larger, inclusive	±05 %

^A See X2.3 for recommended inspection procedure.



4 hole insulator shown.
Other hole patterns are available—
consult manufacturer.

FIG. 1 Wall and Web Thicknesses

9. Test Methods

9.1 Chemical Composition:

9.1.1 Wet chemical analysis, or fusion calorimetric analysis, or both, X-ray fluorescence, inductively coupled plasma spectrometry (ICP), or a combination of test methods, can be used for quantitative determination of silicon dioxide (SiO₂), iron oxide (Fe₂O₃), and zirconium oxide (ZrO₂) with gravimetric determination for SiO₂ and Fe₂O₃. The SiO₂ filtrate can be used for further calcium oxide (CaO) determination. Boron and cadmium can be measured using ICP and other minor components. Sulfur and carbon can be measured using infrared spectrometry.

9.1.2 Test Method C809 can be used for quantitative analysis of elemental impurities.

9.1.3 Any method used for quantitative determination of MgO, Al₂O₃, CaO, SiO₂, and ZrO₂ should have a detection sensitivity of at least 0.001 % (mass)-0.01 % (mass). Test methods used for the quantitative analysis of boron, cadmium, sulfur, carbon and iron oxide should have a detection sensitivity of 0.0001 % (mass).

9.2 Density (Powder)—Test Method B329 can be used for determining the density of Al₂O₃ and MgO powders.

9.3 Appendix X5 lists other optional test methods.

10. Handling and Storage Precautions

10.1 Powders and crushable insulators shall be shipped and stored in containers that prevent contamination and breakage. Powders and crushable insulators should be stored in sealed containers to prevent contamination by moisture absorption. (See Appendix X2.)

11. Keywords

11.1 aluminum oxide; crushable; insulator; magnesium oxide; mineral-insulated, metal-sheathed cable; platinum resistance thermometer; thermocouple, base metal; thermocouple, noble metal

APPENDIXES
(Nonmandatory Information)
X1. MATERIALS AND MANUFACTURE
X1.1 Alumina (Al₂O₃)
X1.1.1 Sources:

X1.1.1.1 Bauxite is the principal source of alumina. Gibbsite, Al(OH)₃, is the most stable phase. Boehmite, AlO(OH), also occurs in nature. High grade bauxite is low in iron and silica content. The major use of purified alumina is in the production of aluminum metal.

X1.1.1.2 Depending upon the application, the economics, and the purity of the bauxite, the purification process could be wet alkaline, wet acid, alkaline furnace, carbothermic furnace, or electrolytic processes.

X1.1.1.3 The wet alkaline processes are the most economical. Gibbsite bauxite is easier to dissolve. It is digested in sodium hydroxide (NaOH) solution at about ~~150°C (302°F)~~ at 345 kPa 150 °C (302 °F) at 345 kPa (50 lb/in.²). Boehmitic bauxite, AlO(OH), is more difficult to dissolve. It requires a higher concentration of NaOH solution, a pressure of 1930 to 4826 kPa (280 to 700 lb/in.²), and a temperature of about ~~238°C (545°F)~~ 238 °C (545 °F).

X1.1.1.4 When digested, the slurry is cooled to about ~~100°C (212°F)~~ 100 °C (212 °F) by releasing pressure to atmospheric, and the undissolved “mud” is sedimented or filtered off. When cooled to about ~~50°C (122°F)~~ 50 °C (122 °F) and seeded with alumina-trihydrate, precipitation occurs. The precipitated trihydrate is washed and then calcinated. The trihydrate dehydrates slowly. At atmospheric pressures, the dehydration process involves two steps.

X1.1.1.5 The trihydrate dehydrates first to a composition close to boehmite (Al₂O₃·H₂O). Even at ~~200°C (392°F)~~ 200 °C (392 °F) the rate of dehydration is very slow. Dehydration is essentially complete at ~~400°C (752°F)~~ 400 °C (752 °F) in an oven at below atmospheric pressure or at ~~500°C (932°F)~~ 500 °C (932 °F) at atmospheric pressure. In one study, the heating at ~~538°C (1000°F)~~ 538 °C (1000 °F) for 7 h still resulted in 0.1 moles of H₂O per mole Al₂O₃, that is, about 2 %. Differential thermal analysis (DTA) studies show endothermic effects at 225, 300, and ~~550°C (1022°F)~~ 550 °C (437, 572, and 1022 °F), respectively). The peak at ~~550°C (1022°F)~~ 550 °C (1022 °F) represents the dehydration of boehmite.

X1.1.1.6 Activated alumina is a desiccant and is more easily rehydrated when activated in vacuum. Alumina activated in vacuum at 180 to ~~200°C (392°F)~~ 200 °C (356 to 392°F) 392 °F) and then heated in air at about 350 to ~~450°C (842°F)~~ 450 °C (662 to 842°F) 842 °F) does not rehydrate as easily. No rehydration was found with alpha alumina of low surface area. To achieve low surface area the alumina should be heated to at least ~~1700°C (3092°F)~~ 1700 °C (3092 °F). Alumina is sintered at about 1700 to ~~2000°C (3632°F)~~ 2000 °C (3092 to 3632°F) 3632 °F). It melts around ~~2050°C (3722°F)~~ 2050 °C (3722 °F). The maximum temperature is impacted by the presence of certain metals and atmospheres where the phase change diagram can be lower than predicted by pure metal materials.

X1.1.2 Typical Crystal Properties—~~Properties~~:

X1.1.2.1 *Coefficient of Thermal Expansion*—~~6 to 9 × 10⁻⁶/K (3.3 to 5 × 10⁻⁶/°F)~~ between 20 and ~~1000°C (1832°F)~~ 1000 °C (68 and 1832°F) 1832 °F).

X1.1.2.2 *Crystal Shape*— Hexagonal.

X1.1.2.3 *Maximum Theoretical Density*— $3.98 \times 10^3 \text{ kg/m}^3$ (0.144 lbm/in³).

X1.1.2.4 *Dielectric Strength*—5600 kV/m (142 000 V/in).

X1.1.2.5 *Hardness (MOHS)*—9.

X1.1.2.6 *Softening Temperature*—1750°C (3182°F); 1750 °C (3182 °F).

X1.1.2.7 *Melting Temperature*—2050°C (3722°F); 2050 °C (3722 °F).

X1.1.2.8 *Molecular Weight*—101.94.

X1.1.2.9 *Typical Electrical Resistivity*—See **Table X1.1**.

X1.1.2.10 *Specific Heat*— $8.8 \times 10^2 \text{ J/kg}\cdot\text{K}$ @ 20°C (20 °C) (0.21 Btu/lbm °F @ 68°F (68 °F)); $1.2 \times 10^3 \text{ J/kg}\cdot\text{K}$ @ 1000°C (1000 °C) (0.28 Btu/lbm °F @ 1832°F (1832 °F)).

X1.1.2.11 *Typical Thermal Conductivity*—Conductivity—See **Table X1.2**.

X1.1.2.12 *Macroscopic Thermal Neutron Absorption Cross Section*— 1.0 m^{-1} (0.03 in⁻¹).

X1.2 Magnesia (MgO)

X1.2.1 Sources:

X1.2.1.1 Magnesia can be made by the oxidation of magnesium metal or by heating easily decomposed oxy-compounds of magnesium, such as the hydroxide, Mg(OH)₂, the oxalate, MgC₂O₄, or the naturally occurring carbonate (magnesite), MgCO₃. Mg(OH)₂ exists as the mineral brucite in small amounts; however the principal commercial source of magnesia is magnesite, which occurs in a relatively pure state in many parts of the world. Another source of magnesia is dolomite (a more abundant substance), a double carbonate of magnesium and calcium. With dolomite, the calcium must be removed.

**TABLE X1.1 Typical Electrical Resistivity of Alumina
(Theoretical, 100 % Density)**

Temperature		Typical Resistivity	
°C	°F	ohm-cm	ohm-in.
20	68	$>1 \times 10^{14}$	$>4 \times 10^{13}$
400	752	1×10^{11}	4×10^{10}
800	1472	1×10^9	4×10^8
1300	2372	1×10^6	4×10^5