



Designation: **B240–17** **B240 – 21**

Standard Specification for Zinc and Zinc-Aluminum (ZA) Alloys in Ingot Form for Foundry and Die Castings¹

This standard is issued under the fixed designation B240; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope*

1.1 This specification covers commercial zinc and zinc-aluminum (ZA) alloys in ingot form for remelting for the manufacture of pressure die castings, foundry castings and continuous cast bar stock as designated and specified in **Table 1**. Seven alloy compositions are specified, designated as follows:

Common	Traditional	ASTM ^A	UNS ^A
Alloy 3	Zamak 3	AG 40A	Z33524
Alloy 7	Zamak 7	AG 40B	Z33526
Alloy 5	Zamak 5	AC 41A	Z35532
Alloy 2	Zamak 2	AC 43A	Z35544
ZA-8	ZA-8	...	Z35637
ZA-12	ZA-12	...	Z35632
ZA-27	ZA-27	...	Z35842
ACuZinc ⁵	ACuZinc5	...	Z46540

^A See **Table 1**, footnote B.

<https://standards.iteh.ai/catalog/standards/sist/09d2f576-7650-42b5-bf6c-a96145706844/astm-b240-21>

1.2 Zinc alloys Z33524, Z33526, Z35532, Z46540, and Z35544 are used primarily for remelting in the manufacture of pressure die castings. Zinc-aluminum alloys Z35637, Z35632, and Z35842 are used for remelting in the manufacture of both foundry and pressure die castings. Castings made from these ingots are specified in Specification **B86**, Standard Specification for Zinc and Zinc-Aluminum Alloys for Foundry and Die Castings.

1.3 The values stated in inch-pound units are to be regarded as standard. No other units of measurement are included in this standard.

1.4 Systems of nomenclature used to designate zinc and zinc-aluminum (ZA) alloys used for casting are described in **Appendix X1**.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to become familiar with all hazards including those identified in the appropriate Safety Data Sheet*

¹ This specification is under the jurisdiction of ASTM Committee **B02** on Nonferrous Metals and Alloys and is the direct responsibility of Subcommittee **B02.04** on Zinc and Cadmium.

Current edition approved Nov. 1, 2017; Nov. 1, 2021. Published November 2017/December 2021. Originally approved in 1949. Last previous edition approved in 2013/2017 as **B240B240 – 17**, – 13. DOI: 10.1520/B0240-17.10.1520/B0240-21.

² ACuZinc and ACuZinc5 are registered trade names of the General Motors Corporation.

***A Summary of Changes section appears at the end of this standard**

TABLE 1 Chemical and North American Color Code Requirements

	Alloy 3 ^{A,B,C,D,G}	Alloy 7 ^{A,B,C,D,G}	Alloy 5 ^{A,B,C,D,G}	Alloy 2 ^{A,B,C,D,G}	ZA-8 ^{B,C,E,G}	ZA-12 ^{B,C,E,G}	ZA-27 ^{B,C,E,G}	ACuZinc5 ^{B,C,G}
	Zamak 3 (AG40A) (Z33524)	Zamak 7 (AG40B) (Z33526)	Zamak 5 (AC41A) (Z35532)	Zamak 2 (AC43A) (Z35544)	ZA-8 (Z35637)	ZA-12 (Z35632)	ZA-27 (Z35842)	ACuZinc5 (Z46540)
Color Code ^F	None	Brown	Black	Green	Blue	Orange	Purple	Red
Element								
Aluminum	3.9-4.3	3.9-4.3	3.9-4.3	3.9-4.3	8.2-8.8	10.8-11.5	25.5-28.0	2.8-3.3
Magnesium	0.03-0.06	0.010-0.020	0.03-0.06	0.025-0.05	0.02-0.03	0.02-0.03	0.012-0.020	0.035-0.050
Copper	0.10 max	0.10 max	0.7-1.1	2.7-3.3	0.9-1.3	0.5-1.2	2.0-2.5	5.2-6.0
Iron, Max	0.035	0.035	0.035	0.035	0.035	0.05	0.07	0.05
Lead, Max	0.0040	0.0030	0.0040	0.0040	0.005	0.005	0.005	0.004
Cadmium, Max	0.0030	0.0020	0.0030	0.0030	0.005	0.005	0.005	0.003
Tin, Max	0.0015	0.0010	0.0015	0.0015	0.002	0.002	0.002	0.002
Nickel	- - -	0.005-0.020	- - -	- - -	- - -	- - -	- - -	- - -
Zinc ^G	Remainder	Remainder	Remainder	Remainder	Remainder	Remainder	Remainder	Remainder

^A Zinc alloy ingot for die casting may contain nickel, chromium, silicon, and manganese in amounts of up to 0.02, 0.02, 0.035 and 0.05 %, respectively. No harmful effects detrimental effects on alloy performance have ever been noted due to the presence of these elements in up to these concentrations and, therefore, analyses are not required for these elements, except that nickel analysis is required for Z33526.

^B ASTM alloy designations were established in accordance with Practice B275. UNS assignments were established in accordance with Practice E527. The last digit of a UNS number differentiates between alloys of similar composition. UNS designations for ingot and casting versions of an alloy were not assigned in the same sequence for all alloys.

^C For purposes of acceptance and rejection, the observed value or calculated value obtained from analysis should be rounded to the nearest unit in the last right-hand place of figures, used in expressing the specified limit, in accordance with the rounding procedure prescribed in Practice E29.

^D When this material is required to conform to ISO Standard 301, the chemical limits for thallium and indium each shall not exceed 0.001 %.

^E Zinc-aluminum ingot for foundry and pressure die casting may contain nickel, chromium, and manganese in amounts of up to 0.01 % each or 0.03 % total. No harmful effects detrimental effects on alloy performance have ever been noted due to the presence of these elements in up to these concentrations and, therefore, analyses are not required for these elements.

^F Refer to Practice B908. (Note: Colors indicated are for North American applications.)

^G Determined arithmetically by difference.

iTeh Standards

(SDS) for this product/material as provided by the manufacturer, to establish appropriate safety, health, and environmental practices, and determine the applicability of regulatory limitations prior to use.

1.6 This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.

2. Referenced Documents

2.1 The following documents of the issue in effect on data of order acceptance form a part of this specification to the extent referenced herein:

2.2 ASTM Standards:³

- B86 Specification for Zinc and Zinc-Aluminum (ZA) Alloy Foundry and Die Castings
- B275 Practice for Codification of Certain Zinc, Tin and Lead Die Castings (Withdrawn 2020)⁴
- B897 Specification for Configuration of Zinc and Zinc Alloy Jumbo, Block, Half Block, and Slab Ingot
- B899 Terminology Relating to Non-ferrous Metals and Alloys
- B908 Practice for the Use of Color Codes for Zinc Casting Alloy Ingot
- B949 Specification for General Requirements for Zinc and Zinc Alloy Products
- E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications
- E527 Practice for Numbering Metals and Alloys in the Unified Numbering System (UNS)
- E536 Test Methods for Chemical Analysis of Zinc and Zinc Alloys

2.3 Other ASTM Document:

—Methods for Emission Spectrochemical Analysis⁵

2.3 ISO Standards:⁵

- ISO 301 Zinc Alloy Ingots Intended for Casting
- ISO 3815-1 Zinc and zinc alloys — Part 1: Analysis of solid samples by optical emission spectrometry.
- ISO 3815-2 Zinc and zinc alloys — Part 2: Analysis by inductively coupled plasma optical emission spectrometry.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard's Document Summary page on the ASTM website.

⁴ The last approved version of this historical standard is referenced on www.astm.org.

⁵ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, http://www.ansi.org.

3. Terminology

3.1 Terms shall be defined in accordance with Terminology B899.

3.2 Definitions of Terms Specific to This Standard:

3.2.1 *continuous casting, n*—a casting technique in which a cast is continuously withdrawn through the bottom of the mold as it solidifies, so that its length is not determined by mold dimensions; used chiefly to produce semifinished mill products such as billets, blooms, ingots, slabs and tubes; also known as concast.

3.2.2 *die casting, n*—a casting process in which molten metal is injected under high velocity and pressure into a metal die and solidified, also a product produced by such a process. ~~Alternately~~ process; alternately known as pressure die casting.

4. Ordering Information

4.1 Orders for ingot under this specification shall include information as specified in Specification B949.

5. Materials and Manufacturer

5.1 The material covered by this specification shall be of uniform quality and reasonably free from dross, adhering foreign matter, and surface oxide.

6. Chemical Requirements

6.1 The ingots shall conform to the requirements as to chemical composition prescribed in Table 1. Conformance shall be determined in accordance with Specification B949.

7. Ingot Sizes and Shapes

7.1 Zinc casting alloy ingots are typically supplied in ingot bundles weighing 1700 to 2400 lb.

7.2 Ingot and bundles vary in size and weight depending on the alloy and supplier.

7.2.1 Standard ingots have a nominal weight in the range of 17 to 24 ~~lb~~ and are generally 24 to 26 in. long.

7.2.2 Margash bars or ingots come in two sizes with a nominal weight in the range of either 12 to 14 ~~lb~~ or 20 to 24 lb.

7.3 Zinc casting alloy ingot may be ordered in jumbos or blocks, as specified in Specification B897.

7.4 Zinc casting alloy ingot may also be ordered in other shapes.

8. Sampling for Determination of Chemical Composition

8.1 Sampling procedures shall be in accordance with appropriate provisions of Specification B949.

9. Methods for Chemical Analysis

9.1 ~~The~~ At the discretion of the producer, the determination of chemical composition shall be made in accordance with Specifications suitable B949. spectrochemical or chemical methods.

9.2 In case of dispute, the results secured by an approved method (or combination of approved methods), or by a method agreed upon by both parties, shall be the basis of acceptance.

9.2.1 Approved methods include: Test Methods E536, ISO 3815–1, or ISO 3815–2.

NOTE 1—Test Methods E536 is directly applicable, in an unmodified form, only to alloys 3, 5 and 7. ISO 3815–1 and ISO 3815–2 are generic spectrochemical methods applied to zinc and zinc alloys. Each of the methods may be modified and formatted for the alloy to be assayed. An experienced