



Designation: C510 – 16 (Reapproved 2022)

Standard Test Method for Staining and Color Change of Single- or Multicomponent Joint Sealants¹

This standard is issued under the fixed designation C510; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers an accelerated laboratory procedure to determine if a sample of a joint sealant will stain the substrate when in contact with masonry, concrete, or stone (such as marble, limestone, sandstone, and granite). This test method also is intended to determine whether the sealant itself will change in color when exposed to the weather.

1.2 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

[C109/C109M Test Method for Compressive Strength of Hydraulic Cement Mortars \(Using 2-in. or \[50 mm\] Cube Specimens\)](#)

[C150 Specification for Portland Cement](#)

[C207 Specification for Hydrated Lime for Masonry Purposes](#)

[C717 Terminology of Building Seals and Sealants](#)

[C1442 Practice for Conducting Tests on Sealants Using](#)

¹ This test method is under the jurisdiction of ASTM Committee C24 on Building Seals and Sealants and is the direct responsibility of Subcommittee C24.40 on Weathering.

Current edition approved Jan. 1, 2022. Published January 2022. Originally approved in 1963. Last previous edition approved in 2016 as C510 – 16. DOI: 10.1520/C0510-16R22.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

[Artificial Weathering Apparatus](#)

[D2203 Test Method for Staining from Sealants](#)

[G113 Terminology Relating to Natural and Artificial Weathering Tests of Nonmetallic Materials](#)

3. Terminology

3.1 *Definitions*—For definitions of terms used in this test method, see Terminology C717 for terms relating to building seals and sealants, and Terminology G113 for terms relating to natural and artificial weathering tests.

4. Significance and Use

4.1 Staining of a building is an aesthetically undesirable occurrence. This test method evaluates the likelihood of a sealant causing early stain on a porous substrate due to certain chemical exudations from the sealant.

4.1.1 This test method may not predict staining caused by such factors as residue run-down or dirt pick-up by a sealant exudate.

4.2 This test method is useful to predict potential color changes in the sealant itself after weathering.

4.3 This test method measures color change in a sealant and staining of substrate by the sealant under conditions of artificial weathering. See also Test Method D2203, which measures staining by a sealant due to gross exudations from the sealant; it does not subject the sealant to artificial weathering.

5. Apparatus

5.1 The exposure apparatus shall be one of the three types of laboratory accelerated weathering devices described in Practice C1442 that use either xenon arc, fluorescent UV, or open flame carbon arc radiation. Consult Practice C1442 for the differences in test parameters among the devices. Because of differences in test conditions, test results may differ with the type of device used. The choice of device shall be by mutual agreement among the interested parties.

6. Materials

6.1 *Portland Cement*, white, nonstaining, conforming to Type I of Specification C150.

6.2 *Hydrated Lime*, conforming to Type S of Specification C207.

6.3 *Ottawa Sand*, graded, white, conforming to the requirements of Section 4 of Test Method **C109/C109M**.

6.4 *Aluminum Plates*, eight 152 mm by 70 mm (6-in. by 2¾-in.), No. 16 gauge.

6.5 *Metal Frames*, two rectangular noncorrosive, designated as A and B; frame A shall be 6 mm (¼ in.) thick with the inside opening slightly larger than an aluminum plate described in **6.4**; frame B shall have inside dimensions of 127 mm by 38 mm by 6 mm (5 in. by 1½ in. by ¼ in.) thick.

7. Test Specimens

7.1 The test specimen shall consist of a slab of mortar mix upon which is placed a layer of sealant. Prepare a minimum of eight specimens, four of which are then covered with sealant.

7.2 The mortar mix shall be prepared by combining, by weight, 1 part white portland cement, 0.25 part hydrated lime, and 4 parts graded Ottawa sand, with sufficient water to make a smooth, workable paste (water-cement ratio = 0.8).

7.3 The mortar mix shall be spread, with the aid of frame A, over the entire surface of each of the aluminum plates to a depth approximately 6 mm (¼ in.) and struck off flat with a spatula. After carefully removing the frame, allow the specimens to cure for 4 h at standard conditions.

8. Conditioning

8.1 Store the unopened sample of one- or two-part sealant at standard conditions for 16 h to 24 h immediately before testing.

9. Procedure

9.1 At the end of the 4-h curing period described in **7.3**, spread a 6 mm (¼-in.) thick layer of sealant, with the aid of frame B, over the surface of four specimens, leaving a margin of approximately 13 mm (½ in.) of mortar free of sealant. Leave the other four specimens without sealant.

9.1.1 Where a primer is submitted with a sample, apply the primer in accordance with the manufacturer's directions to half the surface of the cured mortar specimens before application of the sealant. For two-part sealants, mix approximately 200 g.

9.2 Then expose the specimens for 16 h to 24 h at standard conditions.

9.3 After the 16-h to 24-h curing period, place four specimens, (two with sealant and two without sealant), on the inside of the accelerated weathering machine. The exposure duration shall be a minimum of 100 h for the fluorescent

UV/condensation and open flame carbon arc tests. The exposure duration for the xenon arc test shall be a minimum of 184 kJ/(m² · nm) at 340 nm. This is based on a minimum of a 100-h exposure at an irradiance level of 0.51 W/(m² · nm) at 340 nm. See Annex A1 in Practice **C1442** for determining the exposure time required to obtain the same radiant exposure at other irradiance levels.

NOTE 1—The minimum exposure duration may not be sufficient to identify an unacceptable material.

9.3.1 Specimen temperature shall be 60 °C ± 2.8 °C (140 °F ± 5 °F) and water temperature 24 °C ± 2.2 °C (75 °F ± 4 °F).

9.4 Expose the third pair of specimens (one with sealant) in the laboratory at standard conditions for 14 consecutive days. During this exposure period immerse these specimens in distilled water for 1 min once a day (5 days per week).

9.5 The fourth pair of specimens with and without sealant will be used as the controls. Expose these to standard conditions for 14 consecutive days.

9.6 At the end of the exposure periods, examine the specimens containing the sealant for stains in the mortar and color changes in the sealant.

10. Report

10.1 Report a stain if there is any discoloration in the mortar color of the sealant test specimens when compared with the mortar color of the control specimen.

10.2 Report the name and description of the accelerated weathering machine and its test conditions.

10.3 Record a color change if there is any variation in color of the sealant specimen that has been placed in the weathering machine and the sealant specimen exposed under laboratory conditions.

11. Precision

11.1 In a round-robin test series eight producers tested nine sealants for stain and color-change properties. Excellent agreement was obtained by the testing laboratories among the 432 determinations that were completed in the test series.

12. Keywords

12.1 color change; sealant; stain; standard conditions

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/