



Designation: G29 – 21

Standard Practice for Determining Cyanobacterial Resistance of Polymeric Films¹

This standard is issued under the fixed designation G29; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope

1.1 This practice covers the determination of the susceptibility of polymeric films to the attachment and proliferation of surface-growing cyanobacteria.

1.2 *Units*—The values stated in SI units are to be regarded as standard. The values given in parentheses after SI units are provided for information only and are not considered standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Summary of Practice

2.1 In this practice, test strips of polymeric film are suspended in glass jars maintained at room temperature. The test strips are exposed to fluorescent light and in direct contact with a standardized inoculum of the filamentous blue-green cyanobacterium *Oscillatoria* in culture medium. The sample test jars are re-inoculated with fresh cyanobacteria every second or third day. A control using untreated polymeric film is used as a basis of comparison. The inoculum is prepared with the help of a propagation apparatus made from a small fish tank. The test is terminated at the end of two weeks, or whenever the untreated control shows dense cyanobacterial growth.

3. Significance and Use

3.1 Bodies of water, such as swimming pools, artificial ponds, and irrigation ditches often are lined with polymeric

films. Cyanobacteria tend to grow in such bodies of water under the proper atmospheric conditions, and they can produce slimy and unsightly deposits on the film. The method described herein is useful in evaluating the degree and permanency of protection against surface growth of cyanobacteria afforded by various additives incorporated in the film.

4. Apparatus

4.1 Propagation Tank:

4.1.1 A small fish tank (10 gal) is used to contain a cyanobacteria propagation system where culture medium is recirculated through a polymeric tube with holes punched in the bottom over the top of a polymeric mesh screen inside of the tank. This design was developed in order to provide ideal conditions for propagation of the cyanobacteria that serve as inocula for each test. The polymeric mesh is supported in such a way that water cascades over the top from a distributor tube above. A small, fully immersed recirculating pump rests on the bottom of the tank and operates continuously to deliver the tank contents to the distributor tube. The light required for cyanobacterial propagation is provided by a 100 W bulb placed 300 mm (12 in.) away from the polymeric mesh. A timing device turns the light on for the desired light cycle each day.

4.1.2 The propagation tank that is used as the permanent source of inoculum is filled to approximately one-third capacity with the culture medium. Heavy growth of *Oscillatoria* rapidly develops on the polymeric mesh screen and, at different phases, this growth appears light green, dark green, or black.

NOTE 1—Culture medium in the propagation tank is discarded monthly and replaced with fresh media.

4.2 Test Chambers:

4.2.1 One litre (1 qt) wide-mouth glass jars, 170 mm (6³/₄ in.) high by 76 mm (3 in.) in inside diameter, or equivalent, serve as test chambers wherein water containing an inoculum of the cyanobacterial organisms and strips of the polymeric film are maintained in contact.

4.2.2 The jars in 4.2.1 are placed in a suitable glass container, such as a 38 L (10 gal) fish tank that is illuminated by four 20 W “cool white” fluorescent bulbs, arranged two on each long side of the tank, at the level of the growing cyanobacteria in the jars. The lamps are mounted on a bracket that holds the outer surface of the bulbs 25 mm (1 in.) from the

¹ This practice is under the jurisdiction of ASTM Committee G03 on Weathering and Durability and is the direct responsibility of Subcommittee G03.04 on Biological Deterioration.

Current edition approved Dec. 1, 2021. Published January 2022. Originally approved in 1971. Last previous edition approved in 2016 as G29 – 16. DOI: 10.1520/G0029-21.

wall of the tank. The tank is filled with water to within 25 mm (1 in.) of the top of the exposure jars in order to create uniform temperature conditions for all jars.

4.3 *Homogenizer*—Any suitable commercial homogenizer for preparing the cyanobacterial inocula.

5. Reagents and Materials

5.1 *Purity of Reagents*—Reagent grade chemicals shall be used in all tests. Unless otherwise indicated, it is intended that all reagents shall conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society, where such specifications are available.² Other grades may be used, provided it is first ascertained that the reagent is of sufficiently high purity to permit its use without lessening the accuracy of the determination.

5.2 *Purity of Water*—Unless otherwise indicated, references to water shall be understood to mean distilled water or water of equal purity.

5.3 *Culture Medium for Propagation Apparatus*—Prepare this medium by dissolving in 15 L of water the designated amounts of the following reagents:

Aron's trace metal solution (see Note 2)	15 mL
Ethylenediamine tetraacetic acid disodium salt	0.04 g
Ferric ammonium citrate	0.85 g
Magnesium sulfate (MgSO ₄ ·7H ₂ O)	10.0 g
Potassium acid phosphate (K ₂ HPO ₄)	12.3 g
Potassium nitrate (KNO ₃)	12.1 g
Sodium citrate	2.0 g
Sulfuric acid, 10 %	10 mL

NOTE 2—Prepare this solution by combining the following reagents in the order given in the amounts designated in 1 L of water:

Boric acid	2.86 g
Copper sulfate (CuSO ₄ ·5H ₂ O)	0.079 g
Manganese chloride (MnCl ₂ ·4H ₂ O)	1.18 g
Molybdc oxide (MoO ₃)	0.018 g
Zinc sulfate (ZnSO ₄ ·7H ₂ O)	0.22 g

5.3.1 BG 11 Medium for Cyanobacteria:

	stock solution [g/100 ml]	nutrient solution [ml]
NaNO ₃	15	10
K ₂ HPO ₄ · 3H ₂ O	0.4	10
MgSO ₄ · 7H ₂ O	0.75	10
CaCl ₂ · 2H ₂ O	0.36	10
citric acid	0.06	10
ferric ammonium citrate	0.06	10
EDTA (dinatrium-salt)	0.01	10
Na ₂ CO ₃	0.2	10
Trace mineral solution ^A		1
de-ionized or distilled water		919

^AComposition of the Trace minerals solution (from Kuhl and Lorenzen 1964):

² *Reagent Chemicals, American Chemical Society Specifications* American Chemical Society, Washington, DC. For suggestions on the testing of reagents not listed by the American Chemical Society, see *Analar Standards for Laboratory Chemicals*, BDH Ltd., Poole, Dorset, U.K., and the *United States Pharmacopeia and National Formulary*, U.S. Pharmacopeial Convention, Inc. (USPC), Rockville, MD.

Trace Minerals Solution:

H ₃ BO ₃	61.0 mg
MnSO ₄ · H ₂ O	169.0 mg
ZnSO ₄ ·7H ₂ O	287.0 mg
CuSO ₄ ·5 H ₂ O	2.5 mg
(NH ₄) ₆ Mo ₇ O ₂₄ · 4H ₂ O	12.5 mg

Note—Add the above minerals to 1000 mL of de-ionized or distilled water.

5.3.2 BG 11 Medium without sodium nitrate (BG 11–NaNO₃):

Prepare BG 11 medium without sodium nitrate (NaNO₃) and add 929 mL instead of 919 mL of water.

5.3.3 Adjust to 7.2 to 7.5 pH range if necessary. Filter sterilization is recommended.

5.4 *Culture Medium for Test Vessels*—Dilute 50 mL of the culture medium in 5.3 with 950 mL of deionized or distilled water and place this medium in the test vessels.

6. Test Specimens

6.1 Select at random from the sample sufficient film to prepare the required number of test specimens 25 mm by 65 mm (1 in. by 2½ in.).

6.2 When possible, use untreated film, similar in all other respects to the treated film, for testing in the same manner as the test specimens, in order to verify the viability of the test organism. If this untreated viability control material fails to show any abundant growth of the test organisms, consider the test inconclusive and repeat it.

7. Procedure

7.1 *Attachment of Specimens*—Samples are suspended in each test vessel by means of polymeric clips hooked over a polymeric or fiberglass rod extending over the test chambers. Additional means of suspension may be used as long as no biologically active materials (for example, adhesives, cements) come in contact with the test specimens during submersion.

7.2 *Inoculation of Test Vessels*—Remove an area of growth about 4 cm² (1 in.²) in area from the propagation tank and place in 500 mL of test chamber culture medium (see 5.4). Homogenize until no discrete large particles can be seen. Then add 100 mL of this inoculum to each test vessel containing either a test specimen or an untreated control, and fill the vessel with the culture medium.

7.3 *Incubation*—Store the inoculated test chambers under light/dark exposure, such as 12 h light, then under darkness for 12 h, continually repeating this cycle. Every second or third day remove each test vessel, place in a sink, and re-inoculate with 100 mL of the fully homogenized cyanobacteria. Introduce the inoculum into the bottom of each test vessel, allowing the same volume of old vessel water to flow over the top of the vessel. This is done in order to simulate the addition of new water and the continuous re-inoculation that occurs under natural conditions.